



Designation: **E94 – 04 (Reapproved 2010) E94/E94M – 17**

Standard Guide for Radiographic Examination Using Industrial Radiographic Film¹

This standard is issued under the fixed designation **E94/E94M**; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This guide² covers satisfactory X-ray and gamma-ray radiographic examination as applied to industrial radiographic film recording. It includes statements about preferred practice without discussing the technical background which justifies the preference. A bibliography of several textbooks and standard documents of other societies is included for additional information on the subject.

1.2 This guide covers types of materials to be examined; radiographic examination techniques and production methods; radiographic film selection, processing, viewing, and storage; maintenance of inspection records; and a list of available reference radiograph documents.

NOTE 1—Further information is contained in Guide **E999**, Practice **E1025**, Test Methods **E1030**, and **E1032**.

1.3 The use of digital radiography has expanded and follows many of the same general principles of film based radiography but with many important differences. The user is referred to standards for digital radiography [**E2597**, **E2698**, **E2736**, and **E2737** for digital detector array (DDA) radiography and **E2007**, **E2033**, **E2445/E2445M**, and **E2446** for computed radiography(CR)] if considering the use of digital radiography.

1.4 *Interpretation and Acceptance Standards*—Interpretation and acceptance standards are not covered by this guide, beyond listing the available reference radiograph documents for castings and welds. Designation of accept - reject standards is recognized to be within the cognizance of product specifications and generally a matter of contractual agreement between producer and purchaser.

1.5 *Safety Practices*—Problems of personnel protection against X rays and gamma rays are not covered by this document. For information on this important aspect of radiography, reference should be made to the current document of the National Committee on Radiation Protection and Measurement, Federal Register, U.S. Energy Research and Development Administration, National Bureau of Standards, and to state and local regulations, if such exist. For specific radiation safety information refer to NIST Handbook ANSI 43.3, 21 CFR 1020.40, and 29 CFR 1910.1096 or state regulations for agreement states.

1.6 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system should be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.7 If an NDT agency is used, the agency should be qualified in accordance with Specification **E543**.

1.8 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* (See **1.4.1.5**.)

~~1.6 If an NDT agency is used, the agency shall be qualified in accordance with Practice **E543**.~~

1.9 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This guide is under the jurisdiction of ASTM Committee **E07** on Nondestructive Testing and is the direct responsibility of Subcommittee **E07.01** on Radiology (X and Gamma) Method.

Current edition approved June 1, 2010/June 1, 2017. Published November 2010/August 2017. Originally approved in 1952. Last previous edition approved in 2004/2010 as **E94 – 04**/**E94 – 04(2010)**. DOI: ~~10.1520/E0094-04R10~~10.1520/E0094_E0094M-17.

² For ASME Boiler and Pressure Vessel Code applications see related Guide SE-94 in Section V of that Code.

2. Referenced Documents

2.1 *ASTM Standards:*³

- [E543 Specification for Agencies Performing Nondestructive Testing](#)
- [E746 Practice for Determining Relative Image Quality Response of Industrial Radiographic Imaging Systems](#)
- [E747 Practice for Design, Manufacture and Material Grouping Classification of Wire Image Quality Indicators \(IQI\) Used for Radiology](#)
- [E801 Practice for Controlling Quality of Radiographic Examination of Electronic Devices](#)
- [E999 Guide for Controlling the Quality of Industrial Radiographic Film Processing](#)
- [E1000 Guide for Radioscopy](#)
- [E1025 Practice for Design, Manufacture, and Material Grouping Classification of Hole-Type Image Quality Indicators \(IQI\) Used for Radiology](#)
- [E1030 Practice for Radiographic Examination of Metallic Castings](#)
- [E1032 Test Method for Radiographic Examination of Weldments](#)
- [E1079 Practice for Calibration of Transmission Densitometers](#)
- [E1254 Guide for Storage of Radiographs and Unexposed Industrial Radiographic Films](#)
- [E1316 Terminology for Nondestructive Examinations](#)
- [E1390 Specification for Illuminators Used for Viewing Industrial Radiographs](#)
- [E1735 Test Method for Determining Relative Image Quality of Industrial Radiographic Film Exposed to X-Radiation from 4 to 25 MeV](#)
- [E1742 Practice for Radiographic Examination](#)
- [E1815 Test Method for Classification of Film Systems for Industrial Radiography](#)
- [E1817 Practice for Controlling Quality of Radiological Examination by Using Representative Quality Indicators \(RQIs\)](#)
- [E2007 Guide for Computed Radiography](#)
- [E2033 Practice for Computed Radiology \(Photostimulable Luminescence Method\)](#)
- [E2445/E2445M Practice for Performance Evaluation and Long-Term Stability of Computed Radiography Systems](#)
- [E2446 Practice for Manufacturing Characterization of Computed Radiography Systems](#)
- [E2597 Practice for Manufacturing Characterization of Digital Detector Arrays](#)
- [E2698 Practice for Radiological Examination Using Digital Detector Arrays](#)
- [E2736 Guide for Digital Detector Array Radiology](#)
- [E2737 Practice for Digital Detector Array Performance Evaluation and Long-Term Stability](#)

2.2 *ANSI Standards:*

- [PH1.41 Specifications for Photographic Film for Archival Records, Silver-Gelatin Type, on Polyester Base Silver Type⁴](#)
- [PH2.22 Methods for Determining Safety Times of Photographic Darkroom Illumination Photography \(Sensitometry\)—Determination of Safelight Conditions⁴](#)
- [PH4.8 Methylene Blue Method for Measuring Thiosulfate and Silver Densitometric Method for Measuring Residual Chemicals in Films, Plates, and Papers⁴](#)
- [T9.1 Imaging Media \(Film\)—Silver-Gelatin Type Specifications for Stability⁴](#)
- [T9.2 Imaging Media—Photographic Process Film Plate Processed Films, Plates, and Paper Filing Enclosures and Storage Containers⁴](#)

2.3 *Federal Standards:*

- [Title 21, Code of Federal Regulations \(CFR\) 1020.40, Safety Requirements of Cabinet X-Ray Systems⁵](#)
- [Title 29, Code of Federal Regulations \(CFR\) 1910.96, Ionizing Radiation \(X-Rays, RF, etc.\)⁵](#)

2.4 *Other Document:*

- [ISO 18917 Photography—Determination of residual thiosulphate and other related chemicals in processed photographic materials—Methods using iodine-amylose, methylene blue and silver sulfide](#)
- [NBS Handbook ANSI N43.3 General Radiation Safety Installations Using NonMedical X-Ray and Sealed Gamma-Ray Sources up to 10 MeV⁶](#)

3. Terminology

- 3.1 *Definitions*—For definitions of terms used in this guide, refer to Terminology [E1316](#).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁵ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401.

⁶ Available from National Technical Information Service (NTIS), U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161-5301 Shawnee Rd, Alexandria, VA 22312.

4. Significance and Use

4.1 Within the present state of the radiographic art, this guide is generally applicable to available materials, processes, and techniques where industrial radiographic films are used as the recording media.

4.2 *Limitations*—This guide does not take into consideration the benefits and limitations of nonfilm radiography such as fluoroscopy, digital detector arrays, or computed radiography. Refer to Guides [E1000](#), [E2736](#), and [E2007](#).

4.3 *Limitations*—This guide does not take into consideration special benefits and limitations resulting from the use of nonfilm recording media or readouts such as paper, tapes, xeroradiography, fluoroscopy, and electronic image intensification devices. Although reference is made to documents that may be used in the identification and grading, where applicable, of representative discontinuities in common metal castings and welds, no attempt has been made to set standards of acceptance for any material or production process. Radiography will be consistent in sensitivity and resolution only if the effect of all details of techniques, such as geometry, film, filtration, viewing, etc., is obtained and maintained.

4.4 Radiography will be consistent in image quality (contrast sensitivity and definition) only if all details of techniques, such as geometry, film, filtration, viewing, etc., are obtained and maintained.

5. Quality of Radiographs Equipment and Configuration

5.1 To obtain quality radiographs, it is necessary to consider as a minimum the following list of items. Detailed information on each item is further described in this guide.

- 5.1.1 Radiation source (X-ray or gamma),
- 5.1.2 Voltage selection (X-ray); Energy selection,
- 5.1.3 Source size (X-ray or gamma); focal spot dimension or gamma source size),
- 5.1.4 Ways and means to eliminate scattered radiation,
- 5.1.5 Film system class,
- 5.1.6 Source to film Source-to-film and object-to-film distance,
- 5.1.7 Image quality indicators (IQIs); (IQIs),
- 5.1.8 Screens and filters,
- 5.1.9 Geometry of part or component configuration,
- 5.1.10 Identification and location markers, and
- 5.1.11 Radiographic quality level.

6. Radiographic Quality Level

6.1 Image Quality Indicators (IQIs) are devices placed within a radiographic set-up to indicate that a certain contrast sensitivity and definition has been achieved. IQIs demonstrating the required sensitivity level do not guarantee that a similar size flaw in a part will be detected but indicate that the radiographic quality has been met. Information on the design and manufacture of image quality indicators (IQIs) can be found in Practices [E747](#), [E801](#), [E1025](#), and [E1742](#).

6.2 Radiographic quality level is usually expressed in percent of part thickness and diameter of feature to be detected. If a single percent number is given, the feature diameter is assumed to be twice the given percent thickness of the part. For example, if 2% is given for one inch [25.4 mm] thick part, the feature diameter is $2 \times 0.02 \times 1$ in. [25.4 mm] or 0.04 in. [1.016 mm]. Image quality levels using hole-type IQIs (see Practice [E1025](#)) are designated by a two part expression $X-YT$. The first part of the expression X refers to the IQI thickness expressed as a percentage of the specimen thickness. The second part of the expression YT refers to the diameter of the hole and is expressed as a multiple of the IQI thickness, T . The image quality level usually $2-2T$ required for radiography is 2 % means that the IQI thickness ($2-2T$ when using hole type IQI) unless a higher or lower quality is agreed upon between the purchaser and the supplier. At the 2 % subject contrast level, three quality levels of inspection, $2-1T$, $2-2T$, and $2-4T$, are available through the design and application of is 2% of the specimen thickness and that the diameter of the IQI imaged hole is 2 times the IQI thickness. If using wire IQIs, the wire set and wire number are designated. Correspondence between hole-type and wire-type IQIs is given in Practice [E747](#) the IQI (Practice, Hole- and [E1025](#), Table 1). Other levels of inspection are available in Practice wire-type IQIs are the major types used for industrial radiography. Other [E1025](#) Table 1- types may also be used (for example, see Practice [E1817](#)). The quality level usually required for radiography is 2 % ($2-2T$ when using hole type IQI) unless a higher or lower quality is agreed upon between the purchaser and the supplier. The level of inspection specified should be based on the service requirements of the product. Great care should be taken in specifying quality levels $2-1T$, $2-1T$, $1-1T$, $1-1T$, and $1-2T$ $1-2T$ by first determining that these quality levels can be maintained in production radiography.

NOTE 2—The first number of the quality level designation refers to IQI thickness expressed as a percentage of specimen thickness; the second number refers to the diameter of the IQI hole that must be visible on the radiograph, expressed as a multiple of penetrometer thickness, T .

6.3 If IQIs of material radiographically similar to that being examined are not available, IQIs of the required dimensions but of a lower-absorption material may be used.

6.4 The quality level required using wire IQIs should be equivalent to the $2-2T$ level of Practice [E1025](#) unless a higher or lower quality level is agreed upon between purchaser and supplier. Table 4 of Practice [E747](#) gives provides a list of

various hole-type IQI's-IQIs and the corresponding diameter of the wires of corresponding EPS to achieve the Equivalent Penetrator Sensitivity (EPS) with the applicable 1T, 2T, and 4T holes in the plaque IQI. Appendix X1 of Practice E747 gives the equation for calculating other equivalencies, if needed.

7. Energy Selection

7.1 X-ray energy affects image quality. In general, the lower the energy of the source utilized the higher the achievable radiographic contrast, however, other variables such as excessive dose geometry and scatter conditions may override the potential advantage of higher contrast. For a particular energy, a range of thicknesses which are a multiple of the half value layer, may be radiographed to an acceptable quality level utilizing a particular X-ray machine or gamma ray source. In all cases the specified IQI (penetrator) quality level must be shown on the radiograph. In general, satisfactory results can normally be obtained for X-ray energies between 100 kV to 500 kV in a range between 2.5 to 10 half value layers (HVL) of material thickness (see Table 1). This range may be extended by as much as a factor of 2 in some situations for X-ray energies in the 1 to 25 MV range primarily because of reduced scatter.

8. Radiographic Equivalence Factors

8.1 The radiographic equivalence factor of a material is that factor by which the thickness of the material must be multiplied to give the thickness of a "standard" material (often steel) which has the same absorption. Radiographic equivalence factors of several of the more common metals are given in Table 2, with steel arbitrarily assigned a factor of 1.0.

Example: To radiograph 1.0 in. [25.4 mm] of aluminum at 220 kV, multiply 1.0 by the 0.18 (equivalence factor for aluminum at 220 kV) and this indicates that 1.0 in. [25.4 mm] of aluminum is equivalent to 0.18 in. [4.57 mm] of steel when using 220 kV. The factors may be used:

- 8.1.1 To determine the practical thickness limits for radiation sources for materials other than steel, and
- 8.1.2 To determine exposure factors for one metal from exposure techniques for other metals.

9. Film

9.1 Various industrial radiographic films are available to meet the needs of production radiographic work. However, definite rules on the selection of film are difficult to formulate because the choice depends on individual user requirements. Some user requirements are as follows: radiographic quality levels, exposure times, and various cost factors. Several methods are available for assessing image quality levels (see Test Method Practices E746, and Practices E747, and E801). Information about specific products can be obtained from the manufacturers.

TABLE 1 Typical Steel HVL Thickness in Inches (mm) for Common Energies

Energy	Thickness, Inches (mm)
120 kV	0.10 (2.5)
150 kV	0.14 (3.6)
200 kV	0.20 (5.1)
250 kV	0.25 (6.4)
400 kV (Ir 192)	0.35 (8.9)
1 MV	0.57 (14.5)
2 MV (Co-60)	0.80 (20.3)
4 MV	1.00 (25.4)
6 MV	1.15 (29.2)
10 MV	1.25 (31.8)
16 MV and higher	1.30 (33.0)

TABLE 1 Typical Steel HVL Thickness in Inches [mm] for Common Energies

kV/MV	Thickness, Inches [mm]
120 kV	0.10 [2.5]
150 kV	0.14 [3.6]
200 kV	0.20 [5.1]
250 kV	0.25 [6.4]
400 kV (Ir 192)	0.35 [8.9]
1 MV	0.57 [14.5]
2 MV (Co 60)	0.80 [20.3]
4 MV	1.00 [25.4]
6 MV	1.15 [29.2]
10 MV	1.25 [31.8]
16 MV and higher	1.30 [33.0]

TABLE 2 Approximate Radiographic Equivalence Factors for Several Metals (Relative to Steel)

Metal	Energy Level kVMV									¹⁹² Ir	⁶⁰ Co	⁷⁵ Se
	100 kV	150 kV	220 kV	250 kV	400 kV	1 MV	2 MV	4 to 25 MV				
Magnesium	0.05	0.05	0.08									
Aluminum	0.08	0.12	0.18						0.35	0.35	0.5	
Aluminum alloy	0.10	0.14	0.18						0.35	0.35	0.5	
Titanium		0.54	0.54		0.71	0.9	0.9	0.9	0.9	0.9	0.9	0.6
Iron/all steels	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Copper	1.5	1.6	1.4	1.4	1.4	1.1	1.1	1.2	1.1	1.1	1.1	1.4
Zinc		1.4	1.3		1.3	1.3	1.2	1.2	1.1	1.1	1.0	1.2
Brass		1.4	1.3		1.3	1.2	1.1	1.0	1.1	1.0	1.0	1.3
Inconel X		1.4	1.3		1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
Monel	1.7		1.2									1.1
Zirconium	2.4	2.3	2.0	1.7	1.5	1.0	1.0	1.0	1.2	1.0	1.0	1.6
Lead	14.0	14.0	12.0			5.0	2.5	2.7	4.0	2.3		8.0
Hafnium			14.0	12.0	9.0	3.0						11.0
Uranium			20.0	16.0	12.0	4.0		3.9	12.6	3.4		14.0

9.2 Various industrial radiographic films are manufactured to meet quality level and production needs. Test Method E1815 provides a method for film manufacturer classification of film systems. A film system consist of the film and associated film processing system. Users may obtain a classification table from the film manufacturer for the film system used in production radiography. A choice of film class can be made as provided in Test Method E1815. Additional specific details regarding classification of film systems is provided in Test Method E1815. ANSI Standards PH1.41, PH4.8, ISO 417, T9.1, and T9.2 provide specific details and requirements for film manufacturing.

10. Filters

10.1 *Definition*—Filters are uniform layers of material placed between the radiation source and the film.

10.2 *Purpose*—The purpose of filters is to absorb the softer components of the primary radiation, thus resulting in one or several of the following practical advantages:

10.2.1 Decreasing scattered radiation, thus increasing contrast.

10.2.2 Decreasing undercutting, thus increasing contrast.

10.2.3 Decreasing contrast of parts of varying thickness-thickness, thereby increasing radiographic latitude.

10.3 *Location*—Usually the filter will be placed in one of the following two locations:

10.3.1 As close as possible to the radiation source, which minimizes the size of the filter and also the contribution of the filter itself to scattered radiation to the film.

10.3.2 Between the specimen and the film in order to absorb preferentially the scattered radiation from the specimen. It should be noted that lead foil and other metallic screens (see 13.1) fulfill this function.

10.4 *Thickness and Filter Material*— The thickness and material of the filter will vary depending upon the following:

10.4.1 The material radiographed.

10.4.2 Thickness of the material radiographed.

10.4.3 Variation of thickness of the material radiographed.

10.4.4 Energy spectrum of the radiation used.

10.4.5 The improvement desired (increasing or decreasing contrast). Filter thickness and material can be calculated or determined empirically.

11. Masking and Collimation

11.1 Masking or blocking (surrounding specimens or covering thin sections with an absorptive material) is helpful in reducing scattered radiation. Such a material can also be used to equalize the absorption of different sections, but the loss of detail may be high in the thinner sections.

11.2 Collimating the beam by restricting its size with heavy metal beam blockers to only that area needed to expose the area of interest is helpful in restricting scatter from areas in the part outside the area of interest and the surrounding environment, including air scatter. Collimators are usually placed close to the source to minimize size and weight; however, collimators may be placed anywhere in the beam to help with scatter control.

12. Back-Scatter Protection

12.1 Effects of back-scattered radiation can be reduced by confining the radiation beam to the smallest practical cross section and by placing lead behind the film. In some cases either or both the back lead screen and the lead contained in the back of the cassette or film holder will furnish adequate protection against back-scattered radiation. In other instances, this ~~must~~ shall be supplemented by additional lead shielding behind the cassette or film holder.

12.2 If there is any question about the adequacy of protection from back-scattered radiation, a characteristic symbol (frequently a $\frac{1}{8}$ -in. (~~3.2-mm~~)[3.2-mm] thick letter *B*) should be attached to the back of the cassette or film holder, and a radiograph made in the normal manner. If the image of this symbol appears on the radiograph as a lighter density than background, it is an indication that protection against back-scattered radiation is insufficient and that additional precautions ~~must~~shall be taken.

13. Screens

13.1 *Metallic Foil Screens:*

13.1.1 Lead foil screens are commonly used in direct contact with the films, and, depending upon their thickness, and composition of the specimen material, will exhibit an intensifying action at as low as 90 kV. In addition, any screen used in front of the film acts as a filter (Section 10) to preferentially absorb scattered radiation arising from the specimen, thus improving radiographic quality. The selection of lead screen thickness, or for that matter, any metallic screen thickness, is subject to the same considerations as outlined in 10.4. Lead screens lessen the scatter reaching the film regardless of whether the screens permit a decrease or necessitate an increase in the radiographic exposure. To avoid image unsharpness due to screens, there should be intimate contact between the lead screen and the film during exposure.

13.1.2 Lead foil screens of appropriate thickness should be used whenever they improve radiographic quality or penetrometer sensitivity or both. The thickness of the front lead screens should be selected with care to avoid excessive filtration in the radiography of thin or light alloy materials, particularly at the lower kilovoltages. In general, there is no exposure advantage to the use of 0.005 in. [0.13 mm] in front and back lead screens below 125 kV in the radiography of $\frac{1}{4}$ -in. (~~6.35-mm~~)[6.35-mm] or lesser thickness steel. As the kilovoltage is increased to penetrate thicker sections of steel, however, there is a significant exposure advantage. In addition to intensifying action, the back lead screens are used as protection against back-scattered radiation (see Section 12) and their thickness is only important for this function. As exposure energy is increased to penetrate greater thicknesses of a given subject material, it is customary to increase lead screen thickness. For radiography using radioactive sources, the minimum thickness of the front lead screen should be 0.005 in. (~~0.13 mm~~)[0.13 mm] for iridium-192, and 0.010 in. (~~0.25 mm~~)[0.25 mm] for cobalt-60.

13.2 *Other Metallic Screen Materials:*

13.2.1 Lead oxide screens perform in a similar manner to lead foil screens except that their equivalence in lead foil thickness approximates 0.0005 in. (0.013 mm).

13.2.2 Copper screens have somewhat less absorption and intensification than lead screens, but may provide somewhat better radiographic sensitivity with higher energy above 1 MV.

13.2.3 Gold, tantalum, or other heavy metal screens may be used in cases where lead cannot be used.

13.3 *Fluorescent Screens*—Fluorescent screens may be used as required providing the required image quality is achieved. Proper selection of the fluorescent screen is required to minimize image unsharpness. Technical information about specific fluorescent screen products can be obtained from the manufacturers. Good film-screen contact and screen cleanliness are required for successful use of fluorescent screens. Additional information on the use of fluorescent screens is provided in Appendix X1.

13.4 *Screen Care*—All screens should be handled carefully to avoid dents and scratches, dirt, or grease on active surfaces. Grease and lint may be removed from lead screens with a solvent. Fluorescent screens should be cleaned in accordance with the recommendations of the manufacturer. Screens showing evidence of physical damage should be discarded.

14. Radiographic Image Quality

14.1 *Radiographic image quality* is a qualitative term used to describe the capability of a radiograph to show flaws in the area under examination. There are three fundamental components of radiographic image quality as shown in Fig. 1. Each component is an important attribute when considering a specific radiographic technique or application and will be briefly discussed below.

14.2 *Radiographic contrast* between two areas of a radiograph is the difference between the film densities of those areas. The degree of radiographic contrast is dependent upon both subject contrast and film contrast as illustrated in Fig. 1.

14.2.1 *Subject contrast* is the ratio of X-ray or gamma-ray intensities transmitted by two selected portions of a specimen. Subject contrast is dependent upon the nature of the specimen (material type and thickness), the energy (spectral composition, hardness or wavelengths) of the radiation used and the intensity and distribution of scattered radiation. It is independent of time, milliamperage or source strength (curies), source distance and the characteristics of the film system.

14.2.2 *Film contrast* refers to the slope (steepness) of the film system characteristic curve. Film contrast is dependent upon the type of film, the processing it receives and the amount of ~~film~~optical density. It also depends upon whether the film was exposed with lead screens (or without) or with fluorescent screens. Film contrast is independent, for most practical purposes, of the wavelength and distribution of the radiation reaching the film and, hence is independent of subject contrast. For further information, consult Test Method E1815.

14.3 *Film system granularity* is the objective measurement of the local density variations that produce the sensation of graininess on the radiographic film (for example, measured with a densitometer with a small aperture of ≤ 0.0039 in. (~~0.1 mm~~)). [0.1 mm]). Graininess is the subjective perception of a mottled ~~random~~ pattern apparent to a viewer who sees small local density variations in an area of overall uniform density (that is, the visual impression of irregularity of silver deposit in a processed