



Designation: **C1372—16 C1372 – 17**

## Standard Specification for Dry-Cast Segmental Retaining Wall Units<sup>1</sup>

This standard is issued under the fixed designation C1372; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers dry-cast segmental retaining wall units of concrete, machine-made from hydraulic cement, water, and suitable mineral aggregates with or without the inclusion of other materials. The units are intended for use in the construction of mortarless segmental retaining walls.

NOTE 1—When particular features are desired, such as density classification, higher compressive strength, surface texture, finish, color, or other special features, such properties should be specified separately by the purchaser. Suppliers should be consulted as to availability of units having the desired features.

1.2 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C33 Specification for Concrete Aggregates

C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units

C150 Specification for Portland Cement

C331 Specification for Lightweight Aggregates for Concrete Masonry Units

C595 Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C989 Specification for Slag Cement for Use in Concrete and Mortars

C1157 Performance Specification for Hydraulic Cement

C1232 Terminology for Masonry

C1262 Test Method for Evaluating the Freeze-Thaw Durability of Dry-Cast Segmental Retaining Wall Units and Related Concrete Units

### 3. Terminology

3.1 Terminology defined in Terminology C1232 shall apply for this specification.

3.2 *Definitions:*

3.2.1 *Dry-cast, adj*—manufacturing concrete products using low frequency, high amplitude vibration to consolidate concrete of stiff or extremely dry consistency in a form.

3.2.2 *segmental retaining wall unit, n*—unit manufactured of concrete for the construction of dry-stacked earth retaining walls.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of C15.03 on Concrete Masonry Units and Related Units.

Current edition approved June 1, 2016/Aug. 1, 2017. Published July 2016/August 2017. Originally approved in 1997. Last previous edition approved in 2014/2016 as C1372—14a/C1372 – 16. DOI: 10.1520/C1372-16.10.1520/C1372-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

3.2.3 *segmental retaining wall unit, dry-cast, n*—a segmental retaining wall unit manufactured of concrete using a dry-cast process.

#### 4. Materials

4.1 *Cementitious Materials*—Materials shall conform to the following applicable specifications:

4.1.1 *Portland Cements*—Specification **C150**.

4.1.2 *Modified Portland Cement*—Portland cement conforming to Specification **C150**, modified as follows:

4.1.2.1 *Limestone*—Limestone, with a minimum 85 % Calcium Carbonate (CaCO<sub>3</sub>) content, shall be permitted to be added to the cement, provided these requirements of Specification **C150** as modified are met:

(1) Limitation on Insoluble Residue—1.5 %.

(2) Limitation on Air Content of Mortar—Volume percent, 22 % max.

(3) Limitation on Loss of Ignition—7 %.

4.1.3 *Blended Hydraulic Cements*—Specification **C595**.

4.1.4 *Hydraulic Cement*—Specification **C1157**.

4.1.5 *Pozzolans*—Specification **C618**.

4.1.6 *Blast Furnace Slag Cement*—Specification **C989**.

4.2 *Aggregates*—Aggregates shall conform to the following specifications, except that grading requirements shall not necessarily apply:

4.2.1 *Normal Weight Aggregates*—Specification **C33**.

4.2.2 *Lightweight Aggregates*—Specification **C331**.

4.3 *Other Constituents*—Air-entraining agents, coloring pigments, integral water repellents, finely ground silica, and other constituents shall be previously established as suitable for use in segmental retaining wall units and shall conform to applicable ASTM standards or shall be shown by test or experience to be not detrimental to the durability of the segmental retaining wall units or any material customarily used in segmental retaining wall construction.

#### 5. Physical Requirements

5.1 At the time of delivery to the work site, the units shall conform to the physical requirements of **Table 1** when tested in accordance with **8.2**. All units shall be sound and free of cracks or other defects that interfere with the proper placement of the units or significantly impair the strength or permanence of the construction. Minor cracks incidental to the usual method of manufacture or minor chipping resulting from customary methods of handling in shipment and delivery are not grounds for rejection.

5.1.1 When higher compressive strengths than those listed in **Table 1** are specified, the tested average net area compressive strength of three units shall equal or exceed the specified compressive strength, and the following single unit strength requirements shall apply.

5.1.1.1 When the specified compressive strength is less than 5000 psi, no single unit net area compressive strength test result shall be less than the specified compressive strength minus 500 psi.

5.1.1.2 When the specified compressive strength is 5000 psi or greater, no single unit net area compressive strength test result shall be less than 90 % of the specified compressive strength.

5.2 *Freeze-Thaw Durability*—In areas where repeated freezing and thawing under saturated conditions occur, freeze-thaw durability shall be demonstrated by test or by proven field performance that the segmental retaining wall units have adequate durability for the intended use. When testing is required by the specifier to demonstrate freeze-thaw durability, the units shall be tested in accordance with **8.3**.

5.2.1 Specimens shall comply with either of the following: (1) the weight loss of each of five test specimens at the conclusion of 100 cycles shall not exceed 1 % of its initial weight; or (2) the weight loss of each of four of the five test specimens at the conclusion of 150 cycles shall not exceed 1.5 % of its initial weight.

**TABLE 1 Strength, Absorption, and Density Classification Requirements<sup>A</sup>**

Density Classification	Oven-Dry Density of Concrete lb/ft <sup>3</sup> (kg/m <sup>3</sup> )	Maximum Water Absorption lb/ft <sup>3</sup> (kg/m <sup>3</sup> )		Minimum Net Area Compressive Strength lb/in. <sup>2</sup> (MPa)	
	Average of Three Units	Average of Three Units	Individual Units	Average of Three Units	Individual Units
Lightweight	Less than 105 (1680)	18 (288)	20 (320)	3000 (20.7)	2500 (17.2)
Medium Weight	105 to less than 125 (1680 to 2000)	15 (240)	17 (272)	3000 (20.7)	2500 (17.2)
Normal Weight	125 (2000) or more	13 (208)	15 (240)	3000 (20.7)	2500 (17.2)

<sup>A</sup> Consult manufacturers for available densities.