



Designation: E708 – 79 (Reapproved 2017)

Standard Specification for Waste Glass as a Raw Material for the Manufacture of Glass Containers¹

This standard is issued under the fixed designation E708; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers particulate glass (cullet material, recovered from waste destined for disposal, smaller than 6 mm intended for reuse as a raw material in the manufacture of glass containers.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 *Exception*—The values given in parentheses are for information only.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C162 Terminology of Glass and Glass Products](#)

[C169 Test Methods for Chemical Analysis of Soda-Lime and Borosilicate Glass](#)

[E688 Test Methods for Waste Glass as a Raw Material for Glass Manufacturing](#)

3. Terminology

3.1 *Definitions:*

3.1.1 *flint glass cullet*—a particulate glass material that contains no more than 0.1 weight % Fe_2O_3 , or 0.0015 weight % Cr_2O_3 , as determined by chemical analysis.

3.1.2 For definitions of other terms used in this specification, refer to Terminology [C162](#).

¹ This specification is under the jurisdiction of ASTM Committee [D34](#) on Waste Management and is the direct responsibility of Subcommittee [D34.03](#) on Treatment, Recovery and Reuse.

Current edition approved Sept. 1, 2017. Published September 2017. Originally approved in 1979. Last previous edition approved in 2011 as E708 – 79 (2011). DOI: 10.1520/E0708-79R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Representative Sample

4.1 The following requirements qualify the glass lot to be used for direct use in soda-lime glass container manufacturing. Sample should be prepared and examined in accordance with Test Methods [E688](#).

NOTE 1—A preponderant proportion of glass cullet will be soda-lime bottle glass, the glass cullet having a composition as follows, as determined by Test Methods [C169](#).

Oxide	Composition, Weight %
SiO_2	66 to 75
Al_2O_3	1 to 7
CaO + MgO	9 to 13
Na_2O	12 to 16

NOTE 2—All percents referred to in this specification are weight percents.

5. General Requirements

5.1 The sample shall show no drainage of liquid and be noncaking and free flowing. A moisture content of less than 0.5 weight % is required to meet the free-flowing characteristics of a cullet that is predominantly of smaller particle size, 1.18-mm (No. 16) sieve or smaller.

5.2 *Screen Size*—No material shall be retained on a 6-mm ($\frac{1}{4}$ -in.) screen. Material not exceeding 15 weight % shall pass through a 106- μm (No. 140) screen.

5.3 *Organic Materials*—The total content of organic materials, as measured in accordance with Section [6](#), shall not exceed 0.2 weight % of dry sample, except for color-mixed glass where the content of organic material may exceed 0.2 weight %. However, a content of organic material greater than 0.2 weight % must be held within a tolerance of ± 0.05 weight %, with a maximum organic limit of 0.4 weight %.

5.4 *Magnetic Materials*—The total magnetic materials shall not exceed 0.05 weight % of dry sample weight for flint glass and 0.14 weight % for colored glass of dry sample weight in accordance with Section [6](#).

5.5 *Permissible Color Mix for Color-Sorted Glass Cullet by Weight:*

5.5.1 *Amber Glass Cullet:*

90 to 100 % amber
0 to 10 % flint
0 to 10 % green
0 to 5 % other colors