

Designation: F720 – 17

# Standard Practice for Testing Guinea Pigs for Contact Allergens: Guinea Pig Maximization Test<sup>1</sup>

This standard is issued under the fixed designation F720; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice is intended to determine the potential for a substance, or material extract, to elicit contact dermal allergenicity.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health and environmental practices and determine the applicability of regulatory limitations prior to use.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

# 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

F619 Practice for Extraction of Medical Plastics

2.2 ISO Standards:<sup>3</sup>

ISO 10993–10 Biological evaluation of medical devices— Part 10: Tests for irritation and skin sensitization

# 3. Summary of Practice

3.1 After a two-stage induction employing Freund's complete adjuvant and sodium lauryl sulfate, the substance or extract is placed on patches and then placed on the skin of guinea pigs. After 24 h, the patches are removed and the skin examined for allergic reaction, and the intensity of the reaction scored at the time of removal and 24 and 48 h subsequent to removal.

### 4. Significance and Use

4.1 In selecting a new material for human contact in medical applications, it is important to ensure that the material will not stimulate the immune system to produce an allergic reaction. The reaction would be due to substances which could leach out of a material. Therefore, this practice provides for using material extracts. The rationale for this practice is based on the fact that the guinea pig has been shown to be the best animal model for human allergic contact dermatitis. The use of Freund's complete adjuvant and sodium lauryl sulfate tends to enhance the potential of a material to cause an allergy. Therefore, this test, while not guaranteeing that a material is nonallergenic, is the most severe animal test in common use today.

# 5. Materials and Manufacturer

5.1 *Hartley Strain Guinea Pigs*, male, 300 to 500 g. 5.1.1 Ten animals are used for each test material.

- 5.2 Freund's Complete Adjuvant.
- 5.3 Occlusive Surgical Tape, 3.75 cm in width.
- 5.4 Elastic Bandage.

5.5 Sodium Lauryl Sulfate (10 weight %) in USP petroleum jelly.

5.6 Positive Control Substance.

5.6.1 5 % formaldehyde for water-soluble test substances.

#### 6. Preparation of Test Samples

6.1 Samples for Intradermal Injection:

6.1.1 Water-Soluble Constituents or Water Extract Liquids:

6.1.1.1 Dissolve the water-soluble constituent up to its maximum solubility, not to exceed a concentration of 10 weight %, or obtain a water extraction liquid as described in Practice F619.

6.1.1.2 Combine equal volumes of the liquid described in 6.1.1.1 and Freund's complete adjuvant. Homogenize by continuous and vigorous vortex mixing for a minimum of 5 min.

<sup>&</sup>lt;sup>1</sup> This practice is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.16 on Biocompatibility Test Methods.

Current edition approved Sept. 1, 2017. Published September 2017. Originally approved in 1981. Last previous edition approved in 2013 as F720 – 13. DOI: 10.1520/F0720-17.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, CP 56, CH-1211 Geneva 20, Switzerland, http://www.iso.org.