



Designation: D3758 – 95 (Reapproved 2017)

## Standard Practice for Evaluation of Spray-Buff Products on Test Floors<sup>1</sup>

This standard is issued under the fixed designation D3758; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice covers the comparison of the performance of spray-buff products on test floors against a reference material. Spray-buff products are to be used to maintain base floor-polish films. This technique is intended to be used on water-emulsion floor polishes with a floor machine not exceeding 95 lb (43 kg) in weight and with a rate of rotation of 350 rpm or less.

1.2 Gloss, heel marking, soil resistance, and slip resistance of the spray-buffed test panels are rated in comparison to test panels similarly maintained with a reference spray-buff product.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D523 Test Method for Specular Gloss

D1455 Test Method for 60° Specular Gloss of Emulsion Floor Polish

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D21 on Polishes and is the direct responsibility of Subcommittee D21.04 on Performance Tests.

Current edition approved Sept. 1, 2017. Published October 2017. Originally approved in 1979. Last previous edition approved in 2010 as D3758 – 95 (2010). DOI: 10.1520/D3758-95R17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *Chemical Specialties Manufacturers Association Test Methods:*

245-70 Comparative Determination Slip Resistance of Floor Polishes<sup>3</sup>

### 3. Terminology

3.1 *Definitions:*

3.1.1 *water emulsion floor polish*—an emulsion-based polish in which water is the continuous or external phase.

3.1.2 *wax emulsion*—a water emulsion polish containing a predominance of natural or synthetic waxes, or both.

### 4. Significance and Use

4.1 Spray buff products are utilized for the maintenance of polished floors. This practice is for the evaluation of a spray buff product against a reference product. The procedure is a floor test utilizing a rotary-disc floor machine. This practice as currently written may or may not be applicable for machines in excess of 350 R.P.M.

### 5. Apparatus

5.1 *Floor Machine* of the single-disk type, fitted with a pad driver and a spray-buffing floor maintenance pad.

5.2 *Glossmeter*—The instrument and the reference standards shall conform to the requirements prescribed in Test Method D523, using an angle of reflection of 60°.

### 6. Description of Test Area

6.1 The preferred area is a corridor in normal traffic service exposed to nearly uniform traffic over the test area.

6.2 The preferred substrate is vinyl tile.

6.3 Divide the area into test sections at least 4 ft (1.2 m) in length and the full width of the corridor. Use one section for each test material in addition to the control section.

### 7. Preparation of Test Area

7.1 Completely strip the test area of dirt and old floor polish. Thoroughly rinse and dry before applying the base polishes.

<sup>3</sup> Available from Chemical Specialties Manufacturers Assn., Inc., 1913 Eye Street, N. W., Washington, DC 20006. Test Methods and General Information, Waxes, Polishes, and Floor Finishes Div.