



Designation: E815 – 17a

Standard Test Method for Determination of Calcium Fluoride in Fluorspar by EDTA Complexometric Titrimetry¹

This standard is issued under the fixed designation E815; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of calcium fluoride in acid-grade fluorspar and other types of fluorspar that can be rendered soluble by the procedure described in the test method.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This test method has been evaluated in accordance with Practice E1601 and Guide E1763. Unless otherwise noted in the precision and bias section, the lower limit in the scope of each method specifies the lowest analyte content that may be analyzed with acceptable error (defined as a nominal 5 % risk of obtaining a 50 % or larger relative difference in results on the same test sample in two laboratories).

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1193 Specification for Reagent Water

E29 Practice for Using Significant Digits in Test Data to

¹ This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.02 on Ores, Concentrates, and Related Metallurgical Materials.

Current edition approved Sept. 15, 2017. Published October 2017. Originally approved in 1981. Last previous edition approved in 2017 as E815 – 17. DOI: 10.1520/E0815-17A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Determine Conformance with Specifications
E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials
E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials
E276 Test Method for Particle Size or Screen Analysis at No. 4 (4.75-mm) Sieve and Finer for Metal-Bearing Ores and Related Materials
E882 Guide for Accountability and Quality Control in the Chemical Analysis Laboratory
E1601 Practice for Conducting an Interlaboratory Study to Evaluate the Performance of an Analytical Method
E1763 Guide for Interpretation and Use of Results from Interlaboratory Testing of Chemical Analysis Methods (Withdrawn 2015)³

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology E135.

4. Summary of Test Method

4.1 The sample is decomposed by digesting with HNO₃ and HClO₄ and the fluorine is expelled by fuming. The residue is dissolved in dilute HCl, the solution made alkaline, and the calcium titrated with standard EDTA solution. Calcium present as carbonate is determined in a separate sample with EDTA solution, after extracting the former with dilute acetic acid. A correction for calcium fluoride, solubilized by dilute acetic acid digestion, is applied by determining the fluoride in the acetic acid extract by fluoride ion-selective electrode. The CaF₂ content is then calculated.

5. Significance and Use

5.1 Fluorspar is used as a flux in the steelmaking and glass industries, and in the manufacture of HF.

5.2 This test method is intended to be used for compliance with compositional specifications for calcium fluoride content. It is assumed that all who use these procedures will be trained

³ The last approved version of this historical standard is referenced on www.astm.org.

analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory and that proper waste disposal procedures will be followed. Appropriate quality control practices must be followed such as those described in Guide E882.

6. Interferences

6.1 None of the elements normally found in fluor spar interferes with this test method.

7. Apparatus

7.1 *Fluoride Ion-Selective Electrode*.⁴

7.2 *Magnetic Stirrer and TFE-Fluorocarbon-Coated Spin Bar*.

7.3 *pH Meter with High Impedance*—Suitable for ion-selective electrode.

7.4 *Polyethylene Beakers, 100-mL*.

7.5 *Single Junction Ag/AgCl Reference Electrode*.⁵

8. Reagents and Materials

8.1 *Purity of Reagents*—Reagent-grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁶ Other grades may be used, provided it is first ascertained that the reagent is of sufficient high purity to permit its use without lessening the accuracy of the determination.

8.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water conforming to Type I or II of Specification D1193. Type III or IV may be used if they effect no measurable change in the blank or sample.

8.3 *Acetic Acid Solution (1 + 10)*—Mix 1 volume of glacial acetic acid (CH₃COOH) with 10 volumes of water.

8.4 *Calcium Carbonate, high purity (minimum 99.95 % CaCO₃)*.

8.5 *Ethylenediaminetetraacetic Acid Disodium Salt (EDTA)—Na₂C₁₀H₁₄O₈N₂·2H₂O Solution (0.025 mol/L)*—Dissolve 9.3062 g of EDTA in water, transfer to a 1-L volumetric flask, dilute to volume, and mix.

8.6 *Hydroxynaphthol Blue Indicator*—Grind 0.2 g of the salt with 50 g sodium chloride (NaCl).

8.7 *Potassium Acetate Buffer*—Dilute 283 mL of glacial acetic acid (CH₃COOH) to 1200 mL with water. While cooling and stirring, add KOH solution B (8.9) to adjust the pH to 5.0 (approximately 350 mL of KOH solution B are required).

8.8 *Potassium Hydroxide Solution A*—Dissolve 225 g of KOH in water and dilute to 1 L with water. Store in a plastic bottle.

8.9 *Potassium Hydroxide Solution B*—Dissolve 500 g of KOH in water and dilute to 1 L. Store in a plastic bottle.

8.10 *Sodium Fluoride Solution*—Dissolve 0.2210 g sodium fluoride (NaF) in water in a polyethylene beaker and dilute to 1 L in a volumetric flask. Store in a stoppered polyethylene bottle. This solution has a concentration of 1 mL = 0.10 mg F⁻ and is stable for six months.

8.11 *Triethanolamine Solution (1 + 1)*—Mix 50 mL of triethanolamine (NC₆H₁₅O₃) with 50 mL of water.

9. Hazards

9.1 For precautions to be observed in this method, refer to Practices E50.

10. Sampling, Test Specimens, and Test Units

10.1 Pulverize the test units so that 95 % passes a No. 100 mesh sieve (150-μm) as directed in Test Method E276.

11. Calibration and Standardization

11.1 *Standardization*—Weigh and transfer 2.4970 g of CaCO₃ (dried at 110 °C for 1 h and cooled in a desiccator) to a 600-mL beaker. Using a hood and appropriate personal protective equipment, cautiously add 75 mL of HCl and warm. Cool, transfer to a 1-L volumetric flask, dilute to volume with water, and mix. This solution has a concentration of 1 mL = 1.0000 mg of calcium.

11.1.1 Titration:

11.1.1.1 Transfer a 50.00-mL aliquot of this solution to a 400-mL beaker, add 5 mL of triethanolamine (8.11), dilute to 200 mL, make just alkaline with KOH solution A (8.8), using a strip of litmus paper, and then add an additional 15 mL of KOH solution A (8.8).

11.1.1.2 Add 0.2 g of hydroxynaphthol blue indicator and titrate immediately with 0.025 M EDTA solution (8.5). At the equivalence point, the color changes from pink to blue. Determine the calcium equivalent of the EDTA solution as follows:

$$1 \text{ mL of EDTA solution} = (50.0/V) = C \text{ mg of calcium} \quad (1)$$

where:

V = milliliters of EDTA used.

NOTE 1—If a sample with a known CaF₂ content is available, the standardization with CaCO₃ can be omitted. The “standard” CaF₂ sample should then be carried through all steps of the procedure.

11.2 *Calibration*—Transfer 10 mL of acetic acid (1 + 10) (8.3) into a series of seven 100-mL polyethylene beakers and add 20 mL of potassium acetate buffer (8.7). Potential measurements in calibration standards and sample should be carried out concurrently. Add standard fluoride solution (8.10) and water as follows:

⁴ Thermo Scientific Orion model 94-91 has been found suitable for this purpose.

⁵ Thermo Scientific Orion model 90-01-00 Single Junction Reference Electrode has been found suitable for this purpose.

⁶ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.