



## Designation: ~~D3897 – 91 (Reapproved 2012)~~ **D3897 – 17**

# Standard Practice for Calculation of Basicity of Chrome Tanning Liquors<sup>1</sup>

This standard is issued under the fixed designation D3897; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice is intended to show how the results of the chromium analysis (Test Method ~~Methods~~ **D3898** or **D6019**) and the acidity determination (Test Method **D3913**) can be combined to permit calculation of the basicity of a chrome tanning liquor.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and ~~health~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D3898** Test Method for Chromic Oxide in Basic Chromium Tanning Liquors

**D3913** Test Method for Acidity in Basic Chromium Tanning Liquors

**D6019** Test Method for Determination of Chromic Oxide in Basic Chromium Tanning Liquors (Ammonium Persulfate Oxidation)

## 3. Significance and Use

3.1 Basicity is a ratio. In any chromic salt solution, the electrovalence of the chromium (+3) is satisfied by the hydroxyl ions and by acid ions. The extent to which this electrovalence is satisfied by the hydroxyl ions, expressed as a percentage, is the basicity. The basicity of a chrome tanning liquid is closely related to the tanning behavior of the solution.

## 4. Procedure

4.1 Determine the chromic oxide as described in Test Method **D3898** or **D6019**. Determine the acid as described in Test Method **D3913**.

## 5. Results

5.1 The basicity of the liquor shall be expressed according to the Schorlemmer system. In this system, the basicity is the per cent of the total chromic oxide that is combined with hydroxyl and is calculated as follows:

$$\text{Basicity, \%} = \frac{A - B}{A} \times 100 \quad (1)$$

where:

$A$  = the amount of thiosulfate, as mL of 0.1 N solution required to titrate the 25 mL aliquot as the specimen in Test Method **D3898**;

$B$  = the amount of sodium hydroxide, as mL of 0.1 N solution required to titrate the 25 mL aliquot of the specimen in Test Method **D3913**.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee **D31** on Leather and is the direct responsibility of Subcommittee **D31.06** on Chemical Analysis.

Current edition approved April 1, 2012; Sept. 1, 2017. Published April 2012; October 2017. Originally approved in 1991. Last previous edition approved in 2006; 2012 as D3897 - 91(2006); (2012). DOI: 10.1520/D3897-91R12; 10.1520/D3897-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.