



Designation: C1064/C1064M – 17

Standard Test Method for Temperature of Freshly Mixed Hydraulic-Cement Concrete¹

This standard is issued under the fixed designation C1064/C1064M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This test method covers the determination of temperature of freshly mixed hydraulic-cement concrete.

1.2 The values stated in either SI or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The text of this standard references notes and footnotes that provide explanatory information. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.60 on Testing Fresh Concrete.

Current edition approved Oct. 1, 2017. Published October 2017. Originally approved in 1986. Last previous edition approved in 2012 as C1064/C1064M-12. DOI: 10.1520/C1064_C1064M-17.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[C125 Terminology Relating to Concrete and Concrete Aggregates](#)

[C172/C172M Practice for Sampling Freshly Mixed Concrete](#)

[C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials](#)

3. Terminology

3.1 For definitions of the terms used in this test method, refer to Terminology C125.

4. Significance and Use

4.1 This test method provides a means for measuring the temperature of freshly mixed concrete. The measured temperature represents the temperature at the time of testing and may not be an indication of the temperature of the freshly mixed concrete at a later time. It may be used to verify conformance to a specified requirement for temperature of concrete.

4.2 Concrete containing aggregate of a nominal maximum size greater than 75 mm [3 in.] may require up to 20 min for the transfer of heat from aggregate to mortar. (See ACI Committee 207.1R Report.⁴)

5. Apparatus

5.1 *Container*, shall be large enough to provide at least 75 mm [3 in.] of concrete in all directions around the sensor of the temperature measuring device; concrete cover must also be at least three times the nominal maximum size of the coarse aggregate.

5.2 *Temperature Measuring Device*, shall be capable of accurately measuring the temperature of the freshly mixed concrete to ± 0.5 °C [± 1 °F] throughout a range of 0° to 50 °C [30° to 120 °F]. The design of the temperature measuring device shall be such that it allows 75 mm [3 in.] or more immersion during operation.

5.3 Partial immersion liquid-in-glass thermometers (and possibly other types) shall have a permanent mark to which the device must be immersed without applying a correction factor.

⁴ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

*A Summary of Changes section appears at the end of this standard