



Designation: D3775 – 17

Standard Test Method for End (Warp) and Pick (Filling) Count of Woven Fabrics¹

This standard is issued under the fixed designation D3775; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the measurement of end (warp) and pick (filling) count and is applicable to all types of woven fabrics.

NOTE 1—Historically, the term fabric count has been used to describe the end and pick count of woven fabrics. The terms end count and pick count are replacing the term fabric count, to provide clarity.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.2.1 Throughout this document, there will be some instances in which the units do not convert 1:1. This is to acknowledge that this is a global document and that different parts of the world use different units of measurement. Organizations using the metric system will report the count per 1 cm. Organizations using the English system will report the count per 1 in.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—For a current test method for the wale and course count of weft knitted fabrics, refer to Test Method **D8007**.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D123 Terminology Relating to Textiles

D1776 Practice for Conditioning and Testing Textiles

D4850 Terminology Relating to Fabrics and Fabric Test Methods

D7023 Terminology Relating to Home Furnishings

D8007 Test Method for Wale and Course Count of Weft Knitted Fabrics

2.2 *Other Standard:*

ANSI/ASQC Z1.4—Inspection by Attributes³

3. Terminology

3.1 For all terminology related to D13.59, Fabric Test Methods, General, refer to Terminology **D4850**

3.1.1 The following terms are relevant to this standard: count, end, end count, filling, pick, pick count, thread count.

3.2 For all terminology related to Home Furnishings, refer to Terminology **D7023**.

3.3 For all other terms related to textiles, refer to Terminology **D123**.

4. Summary of Test Method

4.1 The number of ends per unit distance and picks per unit distance are determined using suitable magnifying and counting devices or by raveling yarns from fabrics. See ANSI Z1.4.

5. Significance and Use

5.1 This test method is considered satisfactory for acceptance testing of commercial shipments because it has been used extensively in the trade for that purpose.

5.1.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative test should be performed to determine if there is a

¹ This test method is under the jurisdiction of ASTM Committee **D13** on Fabric Test Methods, Specific

Current edition approved Sept. 1, 2017. Published September 2017. Replaces Sections 28 to 34 of Methods D1910 – 64 (1975). Originally approved in 1979. Last previous edition approved in 2012 as D3775 – 12. DOI: 10.1520/D3775-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

statistical bias between them, using competent statistical assistance. As a minimum, use the samples for such a comparative test that are as homogeneous as possible, drawn from the same lot of material as the samples that resulted in disparate results during initial testing and randomly assigned in equal numbers to each laboratory. The test results from the laboratories involved should be compared using a statistical test for unpaired data, a probability level chosen prior to the testing series. If bias is found, either its cause must be found and corrected, or future test results for that material must be adjusted in consideration of the known bias.

5.1.2 This test method is suitable for use with narrow fabrics when the count across the total width is measured in the narrow direction and extrapolated to the number of yarns per centimeter (inch).

6. Apparatus

6.1 Use any suitable device, such as pick glass, rule and pointer, microfilm reader, or projection equipment. The use of optical sensing equipment may be used as agreed upon by the purchaser and supplier.

6.2 Use a scale graduated in mm ($\frac{1}{16}$ -in.) to measure the distance over which thread counts were taken.

7. Sampling

7.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls of fabric as directed in an applicable material specification or other agreement between the purchaser and the supplier. Consider rolls of fabric to be the primary sampling units.

7.2 *Laboratory Sample*—As a laboratory sample, take a full width swatch at least 2 m (2 yd) long from each roll of fabric in the lot sample. Consider each designated place at which end counts and pick counts are made as a test specimen.

NOTE 3—For specimens not obtained as directed in Section 7, the results should not be used for acceptance testing of a lot.

8. Conditioning

8.1 Condition specimens as directed in Practice **D1776**.

8.2 Fabrics woven from yarns having a relatively low moisture regain in the standard atmosphere for testing textiles, which is 21 ± 2 °C (70 ± 4 °F) and 65 ± 5 % relative humidity, and which are not significantly affected by minor variations in different atmospheric conditions, for example, nylons, acrylics, and polyesters, may be tested without preconditioning. Fabrics woven from yarns composed wholly or in part from wool, rayon, cotton, or acetate are more sensitive to atmospheric changes and must be conditioned prior to testing, except by agreement of all parties interested in the test results.

8.3 When full rolls or bolts of fabric cannot be properly conditioned in a reasonable time with available facilities, perform the test without conditioning and report the actual conditions prevailing at the time of the test. Such results may not correspond with the results obtained after testing in the standard atmosphere for testing textiles.

9. Procedure

9.1 General:

9.1.1 Count the number of ends and picks in five randomly spaced places diagonally across the width of the laboratory sampling unit. For specific distances to count, see **9.3**.

9.1.2 Round all counts to the nearest whole yarn contained in the distance counted.

9.1.3 When two yarns are laid-in together and parallel, count each yarn separately, as a single unit, regardless of whether it is comprised of single or plied components.

9.2 Specific Fabric Widths:

9.2.1 For fabric widths of 100 cm (40 in.) or more, make no count closer than 15 cm (6 in.) from the selvage edge, or within 50 cm (20 in.) from the end of the roll or piece.

9.2.2 For fabric widths of less than 100 cm (40 in.) but greater than 12.5 cm (5 in.), make no count closer than one tenth of the width of the fabric from the selvage edge, or within 50 cm (20 in.) from the end of the roll or piece.

9.2.3 For narrow fabrics constructed with widths of 12.5 cm (5 in.) or less, use the full width of the fabric, but make no count within 50 cm (20 in.) from the end of the roll or piece.

9.3 Specific Fabric Counts:

9.3.1 For fabrics containing 10 yarns per cm (25 yarns per in.) or more, count the ends over 2.5 cm (1 in.) of width in five different, randomly selected places across the width of the laboratory sampling unit, and count the picks over a 2.5 cm (1 in.) length in five different, randomly selected places along the length of the laboratory sampling unit.

9.3.1.1 When the coefficient of variation for five counts is higher than 5 %, make five additional counts and average the results of the ten readings.

9.3.2 For fabrics containing less than 10 yarns per cm (25 yarns per in.), count the number of ends over a 7.5 cm (3 in.) width, in five randomly selected places across the width of the laboratory sampling unit, and count the number of picks over a 7.5 cm (3 in.) length in five randomly selected places along the length of the laboratory sampling unit.

9.3.2.1 When the coefficient of variation for five counts in a 7.5 cm (3 in.) width is higher than 5 %, discard those readings and make five fresh counts over a 12.5 cm (5 in.) width.

9.3.3 In fancy weaves, where one or more yarns do not appear at regular, short intervals, make count measurements over at least one full pattern repeat of each design in the weave. Count the number of ends over each design repeat in five different, randomly selected places across the width of the laboratory sampling unit, and count the number of picks over each design repeat in five different, randomly selected places along the length of the laboratory sampling unit. The repeat width and length shall be recorded to the nearest 0.1 cm ($\frac{1}{16}$ in.).

9.3.4 For narrow fabrics constructed with widths of 12.5 cm (5 in.) or less, count the number of ends in the full width of the fabric, and count the number of picks over a 2.5 cm (1 in.) length in five different, randomly selected places along the length of the laboratory sampling unit.