



Designation: D3265 – 17a

Standard Test Method for Carbon Black—Tint Strength¹

This standard is issued under the fixed designation D3265; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the tint strength of carbon black relative to an industry tint reference black (ITRB).

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D1799 Practice for Carbon Black—Sampling Packaged Shipments](#)

[D1900 Practice for Carbon Black—Sampling Bulk Shipments](#)

[D4483 Practice for Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries](#)

[D4821 Guide for Carbon Black—Validation of Test Method Precision and Bias](#)

3. Summary of Test Method

3.1 A carbon black sample is mixed with a white powder (zinc oxide) and a liquid vehicle (epoxidized soybean oil, ESO)

¹ This test method is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.21 on Carbon Black Surface Area and Related Properties.

Current edition approved Sept. 1, 2017. Published October 2017. Originally approved in 1973. Last previous edition approved in 2017 as D3265 – 17^{e1}. DOI: 10.1520/D3265-17A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

to produce a black or gray paste. This paste is then spread to produce a surface suitable for measuring the reflectance of the mixture by means of a photo-electric reflectance meter. The reflectance of the tested sample is then compared to the reflectance of the ITRB prepared in the same manner. The tint strength of the tested sample is expressed as units of the reflectance of the ITRB divided by the reflectance of the sample and multiplied by 100.

3.2 Correction Factor:

3.2.1 When ITRB-2, Paraplex G-62 (made before June 2012) and ZnO lot#8 are used, apply a correction factor of 1.0134 for the calibration and standardization in Section 8.

3.2.2 There should be no correction applied when ITRB is used with Paraplex G-62 and ZnO Lot#8 or earlier, that is, the correction factor is "1".

3.2.3 There should be no correction applied in the calculation in Section 10 when using the currently available tint raw materials (see Section 6) for pastes prepared with either ITRB or ITRB2, that is, the correction factor is "1".³

4. Significance and Use

4.1 For the broad range of commercial rubber grade carbon blacks, tint strength is highly dependent upon particle size. Tint strength can be used as an indication of particle size; however, tint strength is also dependent on structure and aggregate size distribution. Therefore, differences in tint strength within grades of carbon black may reflect differences other than particle size.

NOTE 1—This test method was developed primarily for the characterization of N100, N200, and N300 series carbon blacks.

³ In 2013 issues were reported when using Paraplex G-62 purchased after June 2012 and ZnO Lot#10. An ASTM task group investigated the issues and found the following raw materials acceptable for Tint testing:

1) ESO: Paraplex G-62 purchased before June 2012 or currently available GreenChem Greenflex 7170, lot 590911X24, and

2) zinc oxide Lot#8 or earlier, and currently available ZnO lot#11.

It is highly recommended to only use these raw materials identified as acceptable as other sources may lead to unacceptable differences in the test results. The tint task group has determined that Paraplex G-62 with lot numbers that begin with the digit 5 and zinc oxide lots 9 and 10 are suspect and may not give acceptable results.

When using the new raw materials for tint testing some differences may be observed with various grades of carbon black compared with historical data. For this reason it is the responsibility of the manufacturer to identify any such differences, and if necessary, revise any specifications between producer and user.

4.2 Tint strength values within the carbon black industry have been developed using a Automatic Muller apparatus which is used to prepare carbon black-zinc oxide pastes. A new mixing apparatus, SpeedMixer⁴ (DAC 150 FVZ), and a corresponding procedure have been extensively studied within D24 and shown to provide equivalent tint strength for all carcass or soft blacks and most tread blacks with the exception of higher surface area N100 types and specialty blacks. Therefore, it is the responsibility of the user of this alternate apparatus to ensure their products will adequately disperse. Disputes arising between a user and producer should be resolved using the Automatic Muller apparatus until ASTM develops adequate precision statements.

4.3 The term ITRB is used in the entire text for both, the original ITRB, used as the first reference material for tint testing, but which is now used up, and the successor reference material, ITRB2. Wherever required, like in calculations where it is crucial to differentiate between the original ITRB and ITRB2, this will be clearly mentioned in the text of the test procedure.

5. Apparatus

5.1 *Analytical Balance*, with a sensitivity of ± 0.1 mg.

5.2 *Automatic Muller*.^{5,6}

5.3 *Photometric Instrument*, capable of detecting differences in the amount of light reflectance between shades of gray.^{7,6} The instrument is to be operated following the manufacturer's instructions for optimum performance.

5.4 *Oven, Gravity-Convection Type*, capable of temperature regulation within $\pm 1^\circ\text{C}$ at 125°C ($\pm 2^\circ\text{F}$ at 257°F) and temperature uniformity within $\pm 5^\circ\text{C}$ ($\pm 9^\circ\text{F}$).

5.5 *Reflectance Standards*, as required for each reflectance instrument for checking calibration.

5.6 *Spatulas*, 100 to 150 mm (4 to 6 in.), two, flexible, tapered.

5.7 *Syringe*, 5-cm³, automatic refilling, reproducible to ± 0.02 cm³.

5.8 *Wiping Tissue*, absorbent and lint free.

⁴ SpeedMixer is a registered trademark of FlackTek Inc., 1708 Highway 11, Bldg. G, Landrum, SC 29356. <http://www.speedmixer.com>

⁵ The following instruments have been found satisfactory for this test method: Hoover Automatic Muller, Model M5, Hoover Color Corp., P.O. Box 218, State Highway 693, Hiwassee, VA 24347. Automatic Pigment Muller JEL 25/53-II, J. Engelsmann AG, Frankenthaler Str. 137 – 141, 67059 Ludwigshafen, Germany, www.engelsmann.de.

⁶ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

⁷ The following instruments have been found satisfactory for this test method: Erichsen Tint Tester 527, available from T. J. Bell, Inc., 1340 Home Ave., Akron, OH 44310, and Hunter MiniScan EZ, available from Hunter Associates Laboratory, Inc., 11491 Sunset Hills Road, Reston, Virginia 20190-5280.

The Hunter MiniScan XE or XE Plus may still be used for the test, but are no longer commercially available. Instructions are the same for all Hunter Miniscan types.

The Densicon reflectometer, though no longer commercially available, may be used for the test. For instructions, see Test Method D3265 – 01.

5.9 *Paste Application Apparatus*—Any one of the following groups of equipment may be used:

5.9.1 *Apparatus for Film Drawdown Method*:

5.9.1.1 *Film Applicator*,^{8,6} 0.076 mm (0.003 in.) in depth.

5.9.1.2 *Polished Glass Plate*, approximately 760 by 500 by 10 mm (30 by 20 by 0.375 in.).

5.9.2 *Apparatus for Roller Spreader Method*:

5.9.2.1 *Tint Roller Spreader*.^{9,6}

5.10 *Desiccator*.

5.11 *SpeedMixer (DAC 150 FVZ)*, PP15 cups and holder.^{10,6}

5.12 *IKA A-10 Analytical Mill*, A-14 SS cutter, A-18 chamber reducer.^{11,6}

5.13 *5 mm Glass Grinding Beads*.^{12,6}

6. Reagents and Materials

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.¹³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Industry Tint Reference Black*.¹⁴

6.3 *Plasticizer*, soybean oil epoxide.^{15,16}

6.4 *Denatured Alcohol*, for cleaning purposes.

6.5 *Zinc Oxide*, Industry Tint Zinc Oxide.¹⁷

⁸ The sole source of supply of the Film Applicator, Catalog No. AR-5257, known to the committee at this time is Byk-Gardner, 9104 Guilford Rd., Columbia, MD 21046. <http://www.bykgardner.com>.

⁹ The sole source of supply of the Tint Roller Spreader, Model 1A, known to the committee at this time is Titan Specialties, Inc., P.O. Box 2316, Pampa, TX 79066-2316.

¹⁰ The sole source of supply of the SpeedMixer known to the committee at this time is FlackTek Inc., 1708 Highway 11, Bldg. G, Landrum, SC 29356. <http://www.speedmixer.com>

¹¹ The sole source of supply of the apparatus (Part #EW-04301-00) known to the committee at this time is Cole-Parmer Instrument Company, 625 East Bunker Court, Vernon Hills, IL 60061. <http://www.coleparmer.com>

¹² The sole source of supply of glass grinding beads known to the committee at this time is Quackenbush Co., Inc., 6711 Sands Rd., Crystal Lake, IL 60014. <http://www.quackco.com>

¹³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

¹⁴ The original ITRB is depleted and therefore no longer commercially available. However, any available stocks of original ITRB may still be used. The successor of the original ITRB is ITRB2. ITRB2 was commercialized in 2012.

¹⁵ The sole source of supply of the epoxidized soybean oil (Greenflex 7170) known to the committee at this time is Balentine Enterprises, Inc., dba Laboratory Standards and Technologies, 227 Somerset St., Borger, TX 79007, www.carbonstandard.com.

¹⁶ Supporting data (on the shelf life of this material) have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D24-1004.

¹⁷ The sole source of supply of Industry Tint Zinc Oxide known to the committee at this time is Balentine Enterprises, Inc., dba Laboratory Standards and Technologies, 227 Somerset St., Borger, TX 79007, www.carbonstandard.com.

6.6 *ASTM D24 Standard Reference Blacks*.¹⁸

7. Sampling

7.1 Samples of shipments shall be taken in accordance with Practices **D1799** and **D1900**.

8. Calibration and Standardization

8.1 *Standard Pastes*—Prepare pastes of the ITRB, following **9.2 – 9.3.2** for the following masses, prepare the 0.1000-g Automatic Muller paste or the 0.1200-g SpeedMixer paste in duplicate:

Industry Tint Reference Black		Calibration Tint Units
Automatic Muller Pastes	SpeedMixer Pastes	
0.0900 g	0.1080 g	90.0
0.1000 g	0.1200 g	100.0
0.1100 g	0.1320 g	110.0
0.1200 g	0.1440 g	120.0
0.1300 g	0.1560 g	130.0

NOTE 2—Optionally, 0.1400 and 0.1500 g of Automatic Muller paste or 0.1680 and 0.1800 g of SpeedMixer paste may be added in the standardization step when samples with tint results above 130 tint units are tested. The modified standardization should only be used for samples exceeding 130 tint units.

8.2 *Erichsen Tint Tester 527:*

8.2.1 Turn on the power switch and allow for 30 min warm-up.

8.2.2 Place the reflectance head on the black calibration panel and adjust the digital readout to 0.00 using the “zero” control potentiometer.

8.2.3 Following Section 9, prepare the paste drawdown for reflectance measurement.

8.2.4 Use one of the 0.1000-g Automatic Muller or 0.1200-g SpeedMixer ITRB pastes of 8.1 to set the instrument to read 3.00 using the calibration control potentiometer.

8.2.5 Determine the reflectivity on the remaining 0.1000-g Automatic Muller or 0.1200-g SpeedMixer ITRB paste. This reflectance reading must be from 2.99 through 3.01 for the duplicate pastes to be considered acceptable.

8.2.6 If the duplicate 0.1000-g Automatic Muller or 0.1200-g SpeedMixer pastes are acceptable, the two duplicate pastes are blended together using a spatula, and the instrument is set to read 3.00 using the calibration control potentiometer.

8.2.7 If the duplicate pastes are unacceptable, prepare another 0.1000-g Automatic Muller or 0.1200-g SpeedMixer paste following **9.2 – 9.3.2**, and follow **8.2.5**.

8.2.8 Determine the reflectance value for all of the remaining ITRB pastes of 8.1.

8.2.9 Calculate the tint strength of the standard pastes as follows:

$$\text{Tint Units} = 3.00/S \times 100 \quad (1)$$

where:

S = reflectance value of sample.

8.2.10 Calculate a regression of the standard values (y value) on the measured values (x value) by using the least squares method.

8.2.11 The measured tint strength of all subsequent samples is corrected by substituting each measured value into this linear equation and calculating the corrected value for the tint strength.

8.2.12 New regression coefficients are determined periodically, typically on a monthly basis.

NOTE 3—Proper paste preparation and regression may be validated by analyzing at least one SRB tread grade (SRB A-C). After applying the normalization to the tint pastes and calculation as described in Section 10 the tested SRB samples should be within the accuracy limits given in Guide **D4821**.

8.2.13 Proper calibration and standardization of the equipment, reagents, materials, and method shall be checked on a periodic basis using ASTM D24 Standard Reference Blacks. The standard tint strength values and the acceptable test limit of the standard reference blacks may be found in Guide **D4821**.

8.3 *Hunter MiniScan:*

8.3.1 Calibrate the instrument using the black and white tiles.

8.3.2 Place the instrument in Setup Mode. Set up instrument with XYZ color scale, D65 illuminant, 10° observer, average a minimum of three readings. (Note that Y corresponds to the lightness/darkness function, and thus represents the information of interest).

8.3.3 Read each of the ITRB pastes at least three times and record only the average Y value of the three readings. The Y value for the 0.1000-g Automatic Muller or 0.1200-g SpeedMixer paste should read approximately 2.60. Calculate the tint strength of the ITRB pastes as follows:

$$\text{Tint} = I/Y \times 100 \quad (2)$$

where:

I = reflectance of 0.1000-g Automatic Muller or 0.1200-g SpeedMixer ITRB paste.

Y = reflectance value of sample.

8.3.4 Follow **8.2.10 – 8.2.13** to complete the calibration of the Hunter MiniScan.

9. Procedure

9.1 *Paste Preparation:*

9.1.1 *Automatic Muller Paste Preparation:*

9.1.1.1 Dry the zinc oxide, ITRB, and the carbon black sample(s) for 1 h in the specified oven set at $125 \pm 1^\circ\text{C}$ ($257 \pm 2^\circ\text{F}$). Remove to a desiccator and allow to cool to room temperature.

NOTE 4—The ITRB must be dried each day a test is performed, preferably at the same time as the tested sample. Dry only the required amount, as the ITRB should not be dried repeatedly.

NOTE 5—As an optional step in the procedure a carbon black sample may be homogenized prior to drying and weighing using either a mortar and pestle or by low-intensity grinding, for example, in a coffee mill.

9.1.1.2 Weigh a sample of exactly 0.1000 g of carbon black into a weighing dish and then weigh onto the carbon black

¹⁸ The sole source of supply of ASTM D24 Standard Reference Blacks known to the committee at this time is Laboratory Standards and Technologies, 227 Somerset St., Borger, TX 79007.