



Designation: ~~D5004 – 11~~ **D5004 – 11 (Reapproved 2017)**

Standard Test Method for Real Density of Calcined Petroleum Coke by Xylene Displacement¹

This standard is issued under the fixed designation D5004; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope^{*}

1.1 This test method covers the determination of the real density (RD) of calcined petroleum coke. Real density, by definition, is obtained when the particle size of the test specimen is smaller than ~~75 μm~~ **75 μm** (No. 200 sieve).

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ **safety, health, and health** environmental practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements, see Sections 10 and 11.1.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis

D1193 Specification for Reagent Water

D2013 Practice for Preparing Coal Samples for Analysis

D2234/D2234M Practice for Collection of a Gross Sample of Coal

D4057 Practice for Manual Sampling of Petroleum and Petroleum Products

D4292 Test Method for Determination of Vibrated Bulk Density of Calcined Petroleum Coke

D4930 Test Method for Dust Control Material on Calcined Petroleum Coke

D6969 Practice for Preparation of Calcined Petroleum Coke Samples for Analysis

D6970 Practice for Collection of Calcined Petroleum Coke Samples for Analysis <https://standards.iteh.ai/standards/astm-d5004-11/2017>

D7454 Test Method for Determination of Vibrated Bulk Density of Calcined Petroleum Coke using a Semi-Automated Apparatus

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Terminology

3.1 Definitions:

3.1.1 *calcined petroleum coke, n*—petroleum coke that has been thermally treated to drive off the volatile matter and to develop crystalline structure.

3.1.2 *petroleum coke, n*—solid, carbonaceous residue produced by thermal decomposition of heavy petroleum fractions or cracked stocks, or both.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *bulk density, n*—mass of the particles divided by the volume they occupy that includes the space between the particles. Refer to Test Methods D4292 and D7454 for bulk density procedures.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products—Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.05 on Properties of Fuels, Petroleum Coke and Carbon Material.

Current edition approved June 1, 2011; Oct. 1, 2017. Published July 2011; November 2017. Originally approved in 1989. Last previous edition approved in 2009 as D5004 – 89(2009); D5004 – 11. DOI: 10.1520/D5004-11; 10.1520/D5004-11R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

3.2.2 *dedusting material, n*—see Test Method **D4930**.

3.2.3 *real density, n*—(also referred to as true specific gravity), the mass divided by the volume occupied by the material excluding pores and voids. It is required, therefore, that voids in the coke be eliminated and that pores in the material be filled by the fluid being displaced. This requirement is met for the purposes of this test method by reducing the coke particles to a size smaller than ~~75 μm~~ 75 μm .

3.2.3.1 *Discussion*—

The density of particles larger than ~~75 μm~~ 75 μm up to the largest that can be put into the helium pycnometer can also be determined, but must be designated as particle density (PD). The precision data obtained for RD may not be applicable to PD.

4. Summary of Test Method

4.1 The mass of the sample is determined directly and the volume derived by determining the mass of liquid displaced when the sample is introduced into a pycnometer.

$$RD = M \times D/L \quad (1)$$

where:

- M = mass of sample,
- D = density of displaced liquid, and
- L = mass of displaced liquid.

5. Significance and Use

5.1 The density of petroleum coke directly influences the physical and chemical properties of the manufactured carbon and graphite artifacts for which it is used. Density, therefore, is a major quality specification of calcined petroleum coke and is used as a control in coke calcination.

6. Interferences

6.1 Oil or other material sprayed on calcined petroleum coke to control dust will interfere with the determination of real density so the oil must be removed before reducing the sample to ~~75 μm~~ 75 μm .

6.1.1 When a petroleum oil was used, it can be removed by flushing with a solvent such as methylene chloride, dichloroethane, or toluene. The solvent must be completely removed before proceeding with the RD determination. Heating to ~~+10°C~~ +10°C above the boiling point of the solvent used or application of vacuum is satisfactory for the removal of the dedusting oil.

NOTE 1—Consult the Material Safety Data Sheet (MSDS) for the selected solvent.

6.1.2 An alternative method of oil removal is by heating the calcined petroleum coke sample in an oven at ~~700°C~~ 700°C for 1 h.

7. Apparatus

7.1 *Pycnometer*, or specific gravity bottle, ~~50 mL~~, 50 mL, with a ground glass stopper with a capillary hole.³ Bottles with a large neck (~~+2(12 mm to 13 mm)~~ 13 mm outside diameter) are preferred.

7.2 *Water Bath*, controlled to a temperature of ~~25°C~~ 25°C \pm ~~0.1°C~~ 0.1°C.

NOTE 2—This test method is written to be performed at ~~25°C~~ 25°C \pm ~~0.1°C~~ 0.1°C; however, some laboratories may not have the provisions to perform the test at this temperature. It is permissible to perform the test procedure at any temperature between ~~20°C~~ 20°C and ~~40°C~~ 40°C providing that the water bath is controlled at \pm ~~0.1°C~~ 0.1°C of the chosen temperature and the pycnometers are calibrated at the same temperature that is used to determine the real density of the petroleum coke sample. This is possible due to the fact that the real density of calcined petroleum coke is not affected by temperature changes over a limited temperature range.

7.3 *Analytical Balance*, accurate to ~~\pm 0.1 mg~~, \pm 0.1 mg.

7.4 *Vacuum Desiccator*, with guard, connected to a vacuum source capable of lowering pressure to ~~75 mm~~ 75 mm of Hg (~~10 kPa~~); (10 kPa).

7.5 *Desiccator*, with drying agent. Anhydrous calcium sulphate is satisfactory.

7.6 *Drying Oven*, preferably a vacuum oven, for temperature to ~~+20°C~~ 120°C.

7.7 *Lead Weights*, for the pycnometers, to prevent tipping over in the water bath. These can be made by coiling solid wire solder.

7.8 *Wire Sieve*, ~~75 μm~~ 75 μm (No. 200 mesh), meeting Specification **E11**.

³ A Gay-Lussac pycnometer has been found suitable for this purpose.