



Designation: D2739 – 97 (Reapproved 2017)

## Standard Test Method for Volume Resistivity of Conductive Adhesives<sup>1</sup>

This standard is issued under the fixed designation D2739; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the volume resistivity of resin-based conductive adhesives in the cured condition. The test is made on a thin adhesive layer as prepared in a bonded specimen. This test method is used for conductive adhesives that are cured either at room temperature or at elevated temperatures.

1.2 The values stated in either SI or other units shall be regarded separately as standard. SI equivalents to screw threads are shown in the figures.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D618 Practice for Conditioning Plastics for Testing

D907 Terminology of Adhesives

2.2 *Federal Specification:*

QQ-B-626 Composition 22<sup>3</sup>

2.3 *ASTM Adjuncts:*

Assembly Jig<sup>4</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.80 on Metal Bonding Adhesives.

Current edition approved Nov. 1, 2017. Published November 2017. Originally approved in 1968. Last previous edition approved in 2010 as D2739 – 97 (2010). DOI: 10.1520/D2739-97R17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

<sup>4</sup> Detailed drawings of the assembly jig are available from ASTM International Headquarters. Order Adjunct No. ADJD2739. Original adjunct produced in 1987.

### 3. Terminology

3.1 *Definitions:*

3.1.1 Many terms in this test method are defined in Terminology D907.

3.1.2 *conductivity, n*—the ratio of the current density carried through a specimen to the potential gradient paralleling the current. This is numerically equal to the conductance between opposite faces of a unit cube of liquid. It is the reciprocal of resistivity. **D2864, D27**

3.1.3 *resistivity, volume, n*—the ratio of the electric potential gradient to the current density when the gradient is parallel to the current in the material. **D1566, D11**

### 4. Summary of Test Method

4.1 The volume resistivity of adhesive layers cured between metal adherends is measured on a resistance bridge. Tensile adhesion plugs (Fig. 1)<sup>5</sup> are described in this test method. Any other test specimens and materials can be used as long as similar precautions (see Section 7) are observed regarding preparation and tolerances.

### 5. Significance and Use

5.1 Accurate measurement of the volume resistivity of conductive adhesives is important, particularly with respect to applications in electronic packaging techniques. This method measures the resistance of conductive adhesives used in thin films as part of a bonded assembly. This does not imply that the measured results are applicable to different configurations with different metals. This method may be used for acceptance testing and for screening materials.

### 6. Apparatus

6.1 *Kelvin (Resistance) Bridge*, calibrated to 1 % accuracy.<sup>6</sup>

6.2 With the agreement of the interested parties, any metal tensile adhesion plugs (Fig. 1) can be used to prepare the tensile adhesion specimens.

NOTE 1—Different metals will inherently provide different resistance

<sup>5</sup> Plugs to accommodate banana plug—No. 192, Herman H. Smith, Inc., or equivalent.

<sup>6</sup> Satisfactory resistance bridges are made by: Leads and Northrup Co. Bridge Catalog No. 4306, Minneapolis Honeywell Division Catalog No. 1622, and Biddle Instruments Catalog No. 603282.