This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: F560 - 13<sup>E1</sup> F560 - 17

# Standard Specification for Unalloyed Tantalum for Surgical Implant Applications (UNS R05200, UNS R05400)<sup>1</sup>

This standard is issued under the fixed designation F560; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

 $\varepsilon^1$  NOTE—The designation was corrected editorially in December 2013.

## 1. Scope\*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for unalloyed tantalum plate, sheet, strip, bar, and wire used in the manufacture of surgical implants.

1.2 *The*<u>Units</u>—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values of the two systems may result in non-conformance with this standard.

<u>1.3</u> This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

E8/E8M Test Methods for Tension Testing of Metallic Materials

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

F981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Insertion into Bone

IEEE/ASTM SI 10 American National Standard for Use of the International System of Units (SI): The Modern Metric System 2.2 *ISO Standards*:<sup>3</sup>

ISO 6892 Metallic Materials Materials Tensile Testing at Ambient Temperature

ISO 9001 Quality Management Systems—Requirements

ISO 13782 Implants for Surgery—Metallic Materials—Unalloyed Tantalum for Surgical Implant Applications 560-17

#### 3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot*—all material produced from the same ingot or a single powder blend with the same cross section under the same conditions at essentially the same time.

3.1.2 plate—a flat product more than 4.75 mm [0.1875 in.] in thickness.

3.1.3 *bar*—material 3.15 to 63.5 mm [0.125 to 2.5 in.] in diameter in round, hexagonal, or octagonal cross section supplied in straight lengths.

3.1.4 sheet—a flat product 150 mm [6 in.] or more in width and from 0.13 to 4.75 mm [0.005 to 0.1875 in.] in thickness.

3.1.5 *strip*—a flat product less than 150 mm [6 in.] in width and from 0.13 to 4.75 mm [0.005 to 0.1875 in.] in thickness, which may be supplied in coil.

3.1.6 wire—material up to 3.15 mm [0.124 in.] in diameter furnished in coils or on spools or reels.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Oct. 1, 2013Nov. 1, 2017. Published November 2013November 2017. Originally approved in 1978. Last previous edition approved in 20082013 as F560 – 08.F560 – 13<sup>e1</sup>. DOI: 10.1520/F0560-13E01.10.1520/F0560-17.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

#### **€ F**560 – 17

# 4. Ordering Information

4.1 Inquiries and orders under this specification shall include the following information:

- 4.1.1 Quantity (weight or number of pieces); pieces);
- 4.1.2 ASTM designation, alloy number, and date of issue; issue;
- 4.1.3 Units to be used for certification—SI certification (SI or inch-pound.inch-pound);
- 4.1.4 Composition designation (see 5.1));

4.1.5 Form (strip, sheet, plate, bar, wire) (see 3.1););

4.1.6 Condition (see 5.4),);

4.1.7 Applicable dimensions, including size, thickness, width, and length (random, exact, multiples), or drawing number;

- 4.1.8 Special tests; tests;
- 4.1.9 Special requirements, requirements; and
- 4.1.10 Mechanical properties (if applicable for special conditions) (see 7.1).

## 5. Materials and Manufacture

5.1 Material covered by this specification shall be made from vacuum-arc melted or electron-beam melted ingots (R05200) or powder-metallurgy consolidated (R05400) unalloyed tantalum.

5.2 The various tantalum mill products covered by this specification are formed with the conventional extrusion, forming, swaging, rolling, and drawing equipment normally available in metalworking plants.

5.3 *Finish*—The mill product may be furnished as descaled or pickled, abrasive blasted, chemically milled, ground, machined, peeled, polished, or as specified by the purchaser.

## 5.4 Condition:

5.4.1 Flat mill products shall be supplied in the cold-worked, cold-worked and stress-relieved or annealed condition.

5.4.2 Bar and wire products shall be supplied in the annealed or cold worked cold-worked condition.

## 6. Chemical Requirements

6.1 The material shall conform to the chemical composition requirements in Table 1.

6.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to certify compliance with this specification.

<u>6.1.2</u> All commercial metals contain small amounts of elements other than those that are specified. It is neither practical nor necessary to specify limits for unspecified elements, whether residual elements or trace elements that can be present. The producer is permitted to analyze for unspecified elements and is permitted to report such analyses. The presence of an unspecified element and the reporting of an analysis for that element shall not be a basis for rejection.

6.1.3 Intentional elemental additions other than those specified in Table 1 are not permitted

6.2 The ingot analysis shall be considered the chemical analysis for products supplied under this specification.

6.3 When requested by the purchaser at the time of purchase, the supplier shall furnish a report certifying the values of carbon, oxygen, nitrogen, and hydrogen as specified in Table 2 for each lot of material supplied.

## **TABLE 1 Chemical Requirements**

_	Element	Compositions, max % mass/mass(mass/mass)	
		R05200 <sup>A</sup>	R05400 <sup>B</sup>
_	Carbon	0.010	0.010
	Oxygen	0.015	0.030
	Nitrogen	0.010	0.010
	Hydrogen	0.0015	0.0015
	Niobium	0.10	0.10
	Iron	0.010	0.010
	Titanium	0.010	0.010
	Tungsten	0.050	0.050
	Molybdenum	0.020	0.020
	Silicon	0.005	0.005
	Nickel	0.010	0.010
	Tantalum	balance <sup>C</sup>	balance <sup>C</sup>

<sup>A</sup> Electron-beam or vacuum-arc cast tantalum. Tantalum.

<sup>B</sup> Sintered tantalum. Tantalum.

<sup>C</sup> The percentage of tantalum is determined by difference and need not be determined or certified. Assumed equal to the difference of 100 % and the sum percentage of the other specified elements. The percentage of the Tantalum difference is not required to be reported.