



Designation: **D4313—12 D4313 – 17**

Standard Specification for General-Purpose, Heavy-Duty, and Extra-Heavy-Duty Crosslinked Chlorinated Polyethylene (CM) Jackets For Wire and Cable¹

This standard is issued under the fixed designation D4313; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope* Scope*

1.1 This specification covers crosslinked chlorinated polyethylene (CM) compounds suitable for use as outer coverings or jackets on electrical cables for general-purpose, heavy-duty, and extra-heavy-duty service.

1.2 These jacket materials are not recommended for use on cables which are to be installed at a temperature less than ~~than~~ -25°C .

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable

D1499 Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics

D1711 Terminology Relating to Electrical Insulation

G153 Practice for Operating Enclosed Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials

3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification refer to Terminology D1711. <https://standards.iteh.ai/astm-d4313-17>

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *aging (act of), n*—exposure of materials to air at a temperature of 121°C for 168 h and oil at 121°C for 18 h.

4. Physical Properties

4.1 Crosslinked jackets shall conform to the requirements for physical properties specified in Table 1.

4.2 *Tensile Strength and Percent Elongation at Rupture:*

4.2.1 The test is conducted in accordance with Standard Test Methods D470. The requirements for tensile strength and elongation are given in Table 1 of this Specification.

4.3 *Tensile Strength and Percent Elongation at Rupture After Oil Immersion:*

4.3.1 Fluid as specified in the product Standard shall be used.

4.3.2 The test is conducted in accordance with Test Methods D470. The requirements for tensile strength and elongation are given in Table 1 of this Specification.

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved Jan. 1, 2012; Nov. 1, 2017. Published February 2012; November 2017. Originally approved in 1987. Last previous edition approved in 2010 as D4313—03 (2010); D4313 – 12. DOI: [10.1520/D4313-17](https://doi.org/10.1520/D4313-17).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard