



Designation: D5627 – 17

# Standard Test Method for Water Extractable Residue from Particulate Ion-Exchange Resins<sup>1</sup>

This standard is issued under the fixed designation D5627; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the measurement of water soluble extractable residue from particulate ion-exchange resins based on elevated temperature extraction and gravimetric determination of residue.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D1129 Terminology Relating to Water](#)

[D1193 Specification for Reagent Water](#)

[D2187 Test Methods and Practices for Evaluating Physical and Chemical Properties of Particulate Ion-Exchange Resins](#)

[D2687 Practices for Sampling Particulate Ion-Exchange Materials](#)

[D2777 Practice for Determination of Precision and Bias of Applicable Test Methods of Committee D19 on Water](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D19 on Water and is the direct responsibility of Subcommittee D19.08 on Membranes and Ion Exchange Materials.

Current edition approved Nov. 1, 2017. Published November 2017. Originally approved in 1994. Last previous edition approved in 2009 as D5627 – 94 (2009) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/D5627-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this standard, refer to Terminology [D1129](#).

## 4. Summary of Test Method

4.1 A sample of particulate ion exchange material is contacted with water at an elevated temperature. After a specified contact time, the concentration of soluble material in the aqueous phase is measured gravimetrically after filtration.

## 5. Significance and Use

5.1 The presence of water extractables in ion-exchange resins can cause fouling of other materials downstream and contamination of process water. The quantity of water extractables is sometimes used as a specification to indicate resin quality, and typical values are 0.01 to 0.1 %.

5.2 It is recognized that this test method may not remove all potential sloughage products and does not measure volatile compounds. More extensive extraction and identification of compounds may be needed in specific cases.

## 6. Interferences

6.1 The hygroscopic nature of some extracted compounds can make it difficult to obtain a constant weight. Other extraction times and temperatures may give results that are not comparable to these.

## 7. Apparatus

7.1 *Funnel*, 60 mL with coarse frit.

7.2 *Filtration assembly*.

7.3 *Glass fiber filters*, without binder, pre-rinsed with water.<sup>3</sup>

7.4 *Weighing vessel*—Platinum, nickel, or aluminum may be used so long as there is no attack by the sample and constant weight can be achieved.

7.5 *Water bath*, for use at  $60 \pm 1^\circ\text{C}$ .

<sup>3</sup> Gelman Type A/E, Millipore Type AP40, Whatman GF/C, or equivalent, have been found suitable for this purpose.