



Designation: ~~A646/A646M – 06 (Reapproved 2016)~~ A646/A646M – 17

Standard Specification for Premium Quality Alloy Steel Blooms and Billets for Aircraft and Aerospace Forgings¹

This standard is issued under the fixed designation A646/A646M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers premium quality alloy steel semifinished rolled or forged blooms and billets for reforging into critical parts such as aircraft landing-gear forgings.

1.2 Blooms and billets, hereinafter referred to as blooms, are semifinished steel products, hot rolled or forged to approximate cross-sectional dimensions. Blooms may be square, round, hexagonal, octagonal, or rectangular in section. For the purposes of this specification, minimum bloom section size will be 16 in.² [103 cm²].

1.3 This specification covers two basic classifications of steel:

1.3.1 *Class I*—Vacuum-induction melted or consumable-electrode vacuum melted, or other suitable processes which will satisfy the quality requirements of this specification.

1.3.2 *Class II*—Air-melted vacuum degassed.

1.3.3 *Class III*—Air melted electric furnace ladle refined and vacuum degassed.

1.4 The values stated in either inch-pound or SI (metric) units are to be regarded separately as standards. Within the text and tables, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.5 Unless the order specifies the applicable “M” specification the material shall be furnished to the inch-pound units.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A255 Test Methods for Determining Hardenability of Steel](#)

[A388/A388M Practice for Ultrasonic Examination of Steel Forgings](#)

[A788/A788M Specification for Steel Forgings, General Requirements](#)

[A604/A604M Practice for Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets](#)

[E45 Test Methods for Determining the Inclusion Content of Steel](#)

[E114 Practice for Ultrasonic Pulse-Echo Straight-Beam Contact Testing](#)

~~[E127 Practice for Fabrication and Control of Aluminum Alloy Ultrasonic Standard Reference Blocks](#)~~

[E214 Practice for Immersed Ultrasonic Testing by the Reflection Method Using Pulsed Longitudinal Waves \(Withdrawn 2007\)](#)³

[E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)

[E428 Practice for Fabrication and Control of Metal, Other than Aluminum, Reference Blocks Used in Ultrasonic Testing](#)

2.2 *AMS Standards:*⁴

[AMS 2300 Steel Cleanliness, Premium-Quality](#)

[AMS 2301 Steel Cleanliness, Aircraft-Quality](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved March 1, 2016 Nov. 15, 2017, Published April 2016 December 2017. Originally approved in 1971. Last previous edition approved in 2011 2016 as A646/A646M – 06 (2011) (2016). DOI: ~~10.1520/A0646-A0646M-06R16~~ 10.1520/A0646_A0646M-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096, http://www.sae.org.

*A Summary of Changes section appears at the end of this standard

AMS 2304 Steel Cleanliness, Special Aircraft-Quality

3. Terminology

3.1 In addition to the terminology requirements of Specification **A788/A788M**, the following terms that are specific to this specification apply:

3.2 *Definitions:*

3.2.1 *air-melted vacuum-degassed steel*—arc- or induction-furnace-melted steel that is vacuum treated immediately prior to or during the operation of pouring the ingot.

3.2.2 *consumable-electrode vacuum-remelted steel*—metal that has been remelted into a crucible in vacuum from single or multiple electrodes.

3.2.3 *electroslag-melted steel*—metal that has been remelted into a crucible from single or multiple electrodes utilizing an electrical discharge through molten slag as a source of heat.

3.2.3.1 *Discussion*—

For the purposes of this specification the parent heat from which any electrode for remelting by the electroslag process has been produced shall have been either melted under vacuum or vacuum degassed immediately prior to or during pouring of the heat.

3.2.4 *vacuum induction melted steel*—metal that has been melted, refined, and poured from an induction furnace operating under vacuum.

4. Ordering Information and General Requirements

4.1 Material supplied to this specification shall conform to the requirements of Specification **A788/A788M**, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

4.1.1 If the requirements of this specification are in conflict with the requirements of Specification **A788/A788M**, the requirements of this specification shall prevail.

4.2 In addition to the ordering requirements of Specification **A788/A788M**, the following information should be supplied by the purchaser:

4.2.1 Class designation (see **1.3**),

4.2.2 Quality level (**Table 21**), grade designation (**Table 42**), or detailed chemistry for nonstandard grades,

4.2.3 Desired billet or bloom size,

4.2.4 Weight or quantity and length,

4.2.5 Minimum forging reduction required if ordered size exceeds 225 in.² [1450 cm²] (see **5.2.2**),

4.2.6 Annealing, if required (see **5.3.2**),

4.2.7 Macroetch standards of acceptance (see **7.1**),

4.2.8 Microcleanliness standards of acceptance (see **7.2**),

4.2.9 Specific ultrasonic examination requirements, such as transducer type and size, whether contact or immersion preferred, level of reportable discontinuities and any special surface finish requirements.

4.2.10 Hardenability standards of acceptance (see **8.1**), and

4.2.11 Any supplementary requirements desired.

5. Manufacture

5.1 *Melting Practice:*

5.1.1 The steel making provisions of Specification **A788/A788M** shall apply, except for the following modifications;

TABLE 1 Maximum Permissible Discontinuities in Ultrasonic Examination

Quality Level	Response, in. [mm]		Stringers, Length in. [mm]
	Single Discontinuities	Multiple Discontinuities	
AA	$\frac{3}{64}$ [1.0]	$\frac{2}{64}$ [0.8]	$\frac{2}{64}$ -1/2 [1.0-12.0]
A	$\frac{5}{64}$ [2.0]	$\frac{3}{64}$ [1.0]	$\frac{3}{64}$ -1 [1.0-25]
B	$\frac{8}{64}$ [3.0]	$\frac{5}{64}$ [2.0]	$\frac{5}{64}$ -1 [2.0-25]
C	$\frac{12}{64}$ [5.0]	$\frac{8}{64}$ [3.0]	$\frac{8}{64}$ -1 [3.0-25]