



Standard Specification for Temperature-Electromotive Force (emf) Tables for Standardized Thermocouples¹

This standard is issued under the fixed designation E230/E230M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification contains reference tables (Tables 8 to 25) that give temperature-electromotive force (emf) relationships for Types B, E, J, K, N, R, S, T, and C thermocouples.² These are the thermocouple types most commonly used in industry. The tables contain all of the temperature-emf data currently available for the thermocouple types covered by this standard and may include data outside of the recommended upper temperature limit of an included thermocouple type.

1.2 In addition, the specification includes standard and special tolerances on initial values of emf versus temperature for thermocouples (Table 1), thermocouple extension wires (Table 2), and compensating extension wires for thermocouples (Table 3). Users should note that the stated tolerances apply only to the temperature ranges specified for the thermocouple types as given in Tables 1, 2, and 3, and do not apply to the temperature ranges covered in Tables 8 to 25.

1.3 Tables 4 and 5 provide insulation color coding for thermocouple and thermocouple extension wires as customarily used in the United States.

1.4 Recommendations regarding upper temperature limits for the thermocouple types referred to in 1.1 are provided in Table 6.

1.5 Tables 26 to 45 give temperature-emf data for single-leg thermoelements referenced to platinum (NIST Pt-67). The tables include values for Types BP, BN, JP, JN, KP (same as EP), KN, NP, NN, TP, and TN (same as EN).

1.6 Tables for Types RP, RN, SP, and SN thermoelements are not included since, nominally, Tables 18 to 21 represent the thermoelectric properties of Type RP and SP thermoelements referenced to pure platinum. Tables for the individual thermoelements of Type C are not included because materials for Type C thermocouples are normally supplied as matched pairs only.

1.7 Polynomial coefficients which may be used for computation of thermocouple emf as a function of temperature are given in Table 7. Coefficients for the emf of each thermocouple pair as well as for the emf of most individual thermoelements versus platinum are included. Coefficients for type RP and SP thermoelements are not included since they are nominally the same as for types R and S thermocouples, and coefficients for type RN or SN relative to the nominally similar Pt-67 would be insignificant. Coefficients for the individual thermoelements of Type C thermocouples have not been established.

1.8 Coefficients for sets of inverse polynomials are given in Table 46. These may be used for computing a close approximation of temperature ($^{\circ}\text{C}$) as a function of thermocouple emf. Inverse functions are provided only for thermocouple pairs and are valid only over the emf ranges specified.

1.9 This specification is intended to define the thermoelectric properties of materials that conform to the relationships presented in the tables of this standard and bear the letter designations contained herein. Topics such as ordering information, physical and mechanical properties, workmanship, testing, and marking are not addressed in this specification. The user is referred to specific standards such as Specifications **E235**, **E574**, **E585/E585M**, **E608/E608M**, **E1159**, or **E2181/E2181M** for guidance in these areas.

1.10 The temperature-emf data in this specification are intended for industrial and laboratory use.

1.11 Thermocouple color codes per IEC 584–3 are given in **Appendix X1**.

1.12 The values stated in either SI units or inch-pound units are to be regarded separately as standard.

1.12.1 The values stated in brackets are not conversions to the values they succeed and therefore shall be used independently of the preceding values.

¹ This specification is under the jurisdiction of ASTM Committee E20 on Temperature Measurement and are the direct responsibility of Subcommittee E20.11 on Thermocouples - Calibration.

Current edition approved Nov. 1, 2012; Nov. 1, 2017. Published November 2012; November 2017. Originally approved in 1963. Last previous edition approved in 2011 as **E230 – 11**; **E230/E230M – 12**.² DOI: [10.1520/E0230_E0230M-12](https://doi.org/10.1520/E0230_E0230M-12); [10.1520/E0230_E0230M-17](https://doi.org/10.1520/E0230_E0230M-17).

² These temperature-emf relationships have been revised as required by the international adoption in 1989 of a revised International Temperature Scale (ITS-90).

1.12.2 The values given in parentheses are conversions of the values they succeed.

1.12.3 Combining values from the two systems may result in non-conformance with the standard.

1.13 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.14 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

E235 Specification for Thermocouples, Sheathed, Type K and Type N, for Nuclear or for Other High-Reliability Applications

E574 Specification for Duplex, Base Metal Thermocouple Wire With Glass Fiber or Silica Fiber Insulation

E585/E585M Specification for Compacted Mineral-Insulated, Metal-Sheathed, Base Metal Thermocouple Cable

E608/E608M Specification for Mineral-Insulated, Metal-Sheathed Base Metal Thermocouples

E1159 Specification for Thermocouple Materials, Platinum-Rhodium Alloys, and Platinum

E2181/E2181M Specification for Compacted Mineral-Insulated, Metal-Sheathed, Noble Metal Thermocouples and Thermocouple Cable

2.2 NIST Monograph:

NIST Monograph 175 Temperature-Electromotive Force Reference Functions and Tables for the Letter-Designated Thermocouple Types Based on the ITS-90⁴

2.3 IEC Standard:

IEC 584–3 Thermocouples – Part 3: Extension and Compensating Cables Tolerances and Identification System, 1989

3. Source of Data

3.1 The data in these tables are based upon the SI volt⁵ and the International Temperature Scale of 1990 (ITS-90).

3.2 The temperature-emf data in Tables 8 to 23 and 26 to 45, together with the corresponding equations in Tables 7 and 46 for all thermocouple types except Type C, have been extracted from NIST Monograph 175. Temperature-emf data in Tables 24 and 25 and the coefficients for Type C in Tables 7 and 46 have been developed from curves fitted to wire manufacturers' data.

NOTE 1—It is beyond the scope of this standard to discuss the origin of these tables. If further information is required, the reader should consult NIST Monograph 175.

3.3 These tables give emf values to three decimal places (1 μV) at temperature intervals of one degree. The tables are satisfactory for most industrial uses but may not be adequate for computer and similar applications. If greater precision is required, the reader should refer to NIST Monograph 175 which includes tables giving emf values to four decimal places (0.1 μV) for each type except Type C. Equations which permit easy and unique generation of the temperature-emf relationships can be found in Table 7. For convenience, coefficients of inverse polynomials that may be used to calculate approximate temperature ($^{\circ}\text{C}$) as a function of thermocouple emf are given in Table 46.

4. Thermocouple Types and Letter Designations

4.1 The letter symbols identifying each reference table are those which are in common use throughout industry and identify the following thermocouple calibrations:

4.1.1 *Type B*—Platinum-30 % rhodium (+) versus platinum-6 % rhodium (–).

4.1.2 *Type E*—Nickel-10 % chromium (+) versus copper-45 % nickel (constantan) (–).

4.1.3 *Type J*—Iron (+) versus copper-45 % nickel (constantan) (–).

4.1.4 *Type K*—Nickel-10 % chromium (+) versus nickel-5 % (aluminum, silicon) (–).

NOTE 2—Silicon, or aluminum and silicon, may be present in combination with other elements.

4.1.5 *Type N*—Nickel-14 % chromium, 1.5 % silicon (+) versus nickel-4.5 % silicon-0.1 % magnesium (–).

4.1.6 *Type R*—Platinum-13 % rhodium (+) versus platinum (–).

4.1.7 *Type S*—Platinum-10 % rhodium (+) versus platinum (–).

4.1.8 *Type T*—Copper (+) versus copper-45 % nickel (constantan) (–).

4.1.9 *Type C*—Tungsten-5 % Rhenium (+) versus Tungsten-26 % Rhenium (–).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899.

⁵ Discussed in NIST Technical Note 1263, Guidelines for Implementing the New Representations of the Volt and Ohm Effective January 1, 1990.

4.2 Each letter designation in 4.1 identifies a specific temperature-emf relationship (Tables 8 to 25) and may be applied to any thermocouple conforming thereto within stated tolerances on initial values of emf versus temperature, regardless of its composition.

4.3 The thermoelement identifying symbols in Tables 26 to 45 use the suffix letters P and N to denote, respectively, the positive and negative thermoelement of a given thermocouple type.

4.4 Tables 26 to 45 identify specific temperature-emf relationships of individual thermoelements with respect to platinum (NIST Pt-67). The appropriate letter designation may be applied to any thermoelement which, when combined with its mating thermoelement, will form a thermocouple conforming to the corresponding table within the stated tolerances.

4.5 An overall suffix letter “X” (for example KX, TX, EPX, JNX) denotes an “extension grade” material whose thermoelectric properties will match those of the corresponding thermocouple type within the stated extension grade tolerances over a limited temperature range. Most base metal extension wires have the same nominal composition as the thermocouple wires with which they are intended to be used, whereas the *compensating* extension wires for noble metal or refractory metal thermocouple types (S, R, B, or C) are usually of a different, more economical composition whose relative thermoelectric properties as a pair nonetheless closely approximate those of the noble metal or refractory metal thermocouples with which they are to be used over a limited temperature range.

5. Tolerances on Initial Values of Emf versus Temperature

5.1 In the United States, thermocouples and matched thermocouple wire pairs are normally supplied conforming to the tolerances on initial values of emf versus temperature provided in Table 1.

5.1.1 Tolerances on initial values of emf versus temperature for single-leg thermoelements referenced to platinum have been established only for Types KP and KN. These are supplied, by common practice, to a tolerance equivalent to one half the millivolt tolerance of the Type K thermocouple.

5.1.2 For all other thermocouple types, tolerances on initial values of emf versus temperature for single thermoelements should be established by agreement between the purchaser and the supplier.

5.1.3 In Tables 34, 35, 44, and 45, the thermoelements are identified by two thermoelement symbols indicating their applicability to two thermocouple types. This indicates that the temperature-electromotive force relationship of the table is typical of the referenced thermoelements over the temperature range given in Table 1 for the corresponding thermocouple type. It should not be assumed, however, that thermoelements used with one thermocouple type are interchangeable with those of the other, or that they have the same millivolt tolerances for the initial values of emf versus temperature.

5.2 Thermocouple extension wires and compensating extension wires are supplied to conform to the tolerances on initial values of emf versus temperature shown in Tables 2 and 3, respectively.

5.2.1 Initial tolerances of extension grade materials and compensating extension materials apply over a more limited range of temperature than the corresponding thermocouple grade materials. Applicable temperature ranges, consistent with typical usage, are given in Tables 2 and 3.

6. Color Coding

6.1 Color codes for insulation on thermocouple grade materials, along with corresponding thermocouple and thermoelement letter designations, are given in Table 4.

6.2 Extension wires for thermocouples are distinguished by having an identifying color in the outer jacket as shown in Table 5, where letter designations for the extension thermoelements and pairs are also presented.

6.3 Information presented in Tables 4 and 5 is based on customary practice in the United States.

NOTE 3—Other insulation color coding conventions may be found in use elsewhere in the world. Refer to [Appendix XI](#) for information.

7. List of Tables

7.1 Following is a list of the tables included in this standard:

7.1.1 General Tables:

Table Number	Title
1	Tolerances on Initial Values of Emf versus Temperature for Thermocouples
2	Tolerances on Initial Values of Emf versus Temperature for Extension Wires
3	Tolerances on Initial Values of Emf versus Temperature for Compensating Extension Wires
4	United States Color Codes for Single and Duplex Insulated Thermocouple Wire
5	United States Color Codes for Single and Duplex Insulated Extension Wire
6	Suggested Upper Temperature Limits for Protected Thermocouples
7	Polynomial Coefficients for Generating Thermocouple Emf as a Function of Temperature

7.1.2 Emf versus Temperature Tables for Thermocouples:

Table Number	Thermocouple Type	Temperature Range ^A
--------------	-------------------	--------------------------------



8	B	0 to 1820°C
9	B	0 °C to 1820 °C
10	B	-32 to 3308°F
11	B	32 °F to 3308 °F
12	E	-270 to 1000°C
13	E	-270 °C to 1000 °C
14	E	-454 to 1832°F
15	E	-454 °F to 1832 °F
16	J	-210 to 1200°C
17	J	-210 °C to 1200 °C
18	J	-346 to 2192°F
19	J	-346 °F to 2192 °F
20	K	-270 to 1372°C
21	K	-270 °C to 1372 °C
22	K	-454 to 2500°F
23	K	-454 °F to 2500 °F
24	N	-270 to 1300°C
25	N	-270 °C to 1300 °C
26	N	-454 to 2372°F
27	N	-454 °F to 2372 °F
28	R	-50 to 1768°C
29	R	-50 °C to 1768 °C
30	R	-58 to 3214°F
31	R	-58 °F to 3214 °F
32	S	-50 to 1768°C
33	S	-50 °C to 1768 °C
34	S	-58 to 3214°F
35	S	-58 °F to 3214 °F
36	T	-270 to 400°C
37	T	-270 °C to 400 °C
38	T	-454 to 752°F
39	T	-454 °F to 752 °F
40	G	0 to 2315°C
41	G	0 °C to 2315 °C
42	G	32 to 4200°F
43	G	32 °F to 4200 °F

7.1.3 Emf versus Temperature Tables for Thermoelements:

Table Number	Thermocouple Type	Thermoelement Type	Temperature Range ^A
26	B	BP	—0 to 1768°C
26	B	BP	0 °C to 1768 °C
27	B	BP	—32 to 3214°F
27	B	BP	32 °F to 3214 °F
28	B	BN	—0 to 1768°C
28	B	BN	0 °C to 1768 °C
29	B	BN	—32 to 3214°F
29	B	BN	32 °F to 3214 °F
30	J	JP	—210 to 760°C
30	J	JP	-210 °C to 760 °C
31	J	JP	—346 to 1400°F
31	J	JP	-346 °F to 1400 °F
32	J	JN	—210 to 760°C
32	J	JN	-210 °C to 760 °C
33	J	JN	—346 to 1400°F
33	J	JN	-346 °F to 1400 °F
34	K or E	KP or EP	—270 to 1372°C
34	K or E	KP or EP	-270 °C to 1372 °C
35	K or E	KP or EP	—454 to 2500°F
35	K or E	KP or EP	-454 °F to 2500 °F
36	K	KN	—270 to 1372°C
36	K	KN	-270 °C to 1372 °C
37	K	KN	—454 to 2500°F
37	K	KN	-454 °F to 2500 °F
38	N	NP	—200 to 1300°C
38	N	NP	-200 °C to 1300 °C
39	N	NP	—328 to 2372°F
39	N	NP	-328 °F to 2372 °F
40	N	NN	—200 to 1300°C
40	N	NN	-200 °C to 1300 °C
41	N	NN	—328 to 2372°F
41	N	NN	-328 °F to 2372 °F
42	T	TP	—270 to 400°C
42	T	TP	-270 °C to 400 °C
43	T	TP	—454 to 752°F
43	T	TP	-454 °F to 752 °F
44	T or E	TN or EN	—270 to 1000°C
44	T or E	TN or EN	-270 °C to 1000 °C



45
45

T or E
T or E

TN or EN
TN or EN

-454 to 1832°F
-454 °F to 1832 °F

[^] These temperature ranges represent the published temperature versus emf data for the thermocouple and thermoelement types listed. Refer to Table 6 for the recommended upper temperature limits for a specific thermocouple wire size and type.

7.1.4 *Supplementary Table:*

Table Number	Title
46	Coefficients of Inverse Polynomials for Computation of Approximate Temperature as a Function of Thermocouple Emf

8. Keywords

8.1 emf computation; compensating extension wire; inverse polynomial; polynomial coefficient; reference tables; thermocouple; thermocouple extension wire; thermoelement; upper temperature limit

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ASTM E230/E230M-17](#)

<https://standards.iteh.ai/catalog/standards/sist/9c1a2eb6-449a-4bb7-bda6-4260cc670310/astm-e230-e230m-17>

TABLE 1 Tolerances on Initial Values of Emf vs. Temperature for Thermocouples

NOTE 1—Tolerances in this table apply to new essentially homogeneous thermocouple wire, normally in the size range 0.25 to 3 mm in diameter (No. 30 to No. 8 AWG) and used at temperatures not exceeding the recommended limits of Table 6. If used at higher temperatures these tolerances may not apply.

NOTE 2—At a given temperature that is expressed in °C, the tolerance expressed in °F is 1.8 times larger than the tolerance expressed in °C. Where tolerances are given in percent, the percentage applies to the temperature being measured when expressed in degrees Celsius. To determine the tolerance in degrees Fahrenheit, multiply the tolerance in degrees Celsius by 9/5.

NOTE 3—**Caution:** Users should be aware that certain characteristics of thermocouple materials, including the emf-versus-temperature relationship may change with usage; consequently, test results and performance obtained at the time of manufacture may not necessarily apply throughout an extended period of use. Tolerances given in this table apply only to new wire as delivered to the user *and do not allow for changes in characteristics with use*. The magnitude of such changes will depend on such factors as wire size, temperature, time of exposure, and environment. It should be further noted that due to possible changes in homogeneity, attempting to recalibrate used thermocouples is likely to yield irrelevant results, and is not recommended. However, it may be appropriate to compare used thermocouples *in-situ* with new or known good ones to ascertain their suitability for further service under the conditions of the comparison.

Thermocouple Type	Temperature Range		Tolerances with Reference Junction 0°C [32°F] 0 °C [32 °F]			
	°C	°F	Standard Tolerances		Special Tolerances	
			°C	°F	°C	°F
T	0 to 370	32 to 700	The greater of ±1.0°C or ±0.75%	Note 2	The greater of ±0.5°C or ±0.4%	Note 2
T	0 to 370	32 to 700	The greater of ±1.0 °C or ±0.75 %	Note 2	The greater of ±0.5 °C or ±0.4 %	Note 2
J	0 to 760	32 to 1400	The greater of ±2.2°C or ±0.75%		The greater of ±1.1°C or ±0.4%	
J	0 to 760	32 to 1400	The greater of ±2.2 °C or ±0.75 %		The greater of ±1.1 °C or ±0.4 %	
*E	0 to 870	32 to 1600	The greater of ±1.7°C or ±0.5%		The greater of ±1.0°C or ±0.4%	
*E	0 to 870	32 to 1600	The greater of ±1.7 °C or ±0.5 %		The greater of ±1.0 °C or ±0.4 %	
K or N	0 to 1260	32 to 2300	The greater of ±2.2°C or ±0.75%		The greater of ±1.1°C or ±0.4%	
K or N	0 to 1260	32 to 2300	The greater of ±2.2 °C or ±0.75 %		The greater of ±1.1 °C or ±0.4 %	
R or S	0 to 1480	32 to 2700	The greater of ±1.5°C or ±0.25%		The greater of ±0.6°C or ±0.1%	
R or S	0 to 1480	32 to 2700	The greater of ±1.5 °C or ±0.25 %		The greater of ±0.6 °C or ±0.1 %	
B	870 to 1700	1600 to 3100	±0.5%		±0.25%	
G	0 to 2315	32 to 4200	The greater of ±4.4°C or 1%	Note 2	Not applicable	
C	0 to 2315	32 to 4200	The greater of ±4.4 °C or 1 %	Note 2	Not applicable	
T ^A	-200 to 0	-328 to 32	The greater of ±1.0°C or ±1.5%		B	
T ^A	-200 to 0	-328 to 32	The greater of ±1.0 °C or ±1.5 %		B	
*E ^A	-200 to 0	-328 to 32	The greater of ±1.7°C or ±1%		B	
*E ^A	-200 to 0	-328 to 32	The greater of ±1.7 °C or ±1 %		B	
K ^A	-200 to 0	-328 to 32	The greater of ±2.2°C or ±2%		B	
K ^A	-200 to 0	-328 to 32	The greater of ±2.2 °C or ±2 %		B	

*The standard tolerances shown do not apply to Type E mineral-insulated, metal-sheathed (MIMS) thermocouples and thermocouple cables as described in Specifications E608/E608M and E585/E585M. The standard tolerances for MIMS Type E constructions are the greater of ±2.2°C or ±0.75% from 0 to 870°C and the greater of ±2.2°C or ±2% from -200 to 0°C.

*The standard tolerances shown do not apply to Type E mineral-insulated, metal-sheathed (MIMS) thermocouples and thermocouple cables as described in Specifications E608/E608M and E585/E585M. The standard tolerances for MIMS Type E constructions are the greater of ±2.2 °C or ±0.75 % from 0 °C to 870 °C and the greater of ±2.2°C or ±2% from -200 °C to 0 °C.

^A Thermocouples and thermocouple materials are normally supplied to meet the tolerances specified in the table for temperatures above 0°C. The same materials, however, may not fall within the tolerances for temperatures below 0°C in the second section of the table. If materials are required to meet the tolerances stated for temperatures below 0°C the purchase order shall so state. Selection of materials usually will be required.

^B Special tolerances for temperatures below 0°C are difficult to justify due to limited available information. However, the following values for Types E and T thermocouples are suggested as a guide for discussion between the purchaser and supplier:

Type E, -200 to 0°C, ±1.0°C E, -200 °C to 0 °C, ±1.0 °C or ±0.5 % (whichever is greater)
 Type T, -200 to 0°C, ±0.5°C T, -200 °C to 0 °C, ±0.5 °C or ±0.8 % (whichever is greater)

Initial values of tolerance for Type J thermocouples at temperatures below 0°C and special tolerances for Type K thermocouples below 0°C are not given due to the characteristics of the materials. Data for type N thermocouples below 0°C are not currently available.

TABLE 2 Tolerances on Initial Values of Emf vs. Temperature for Extension Wires

NOTE 1—Tolerances in this table represent the maximum error contribution allowable from new and essentially homogeneous thermocouple extension wire when exposed to the full temperature range given in the table below. Extension grade materials are not intended for use outside the temperature range shown.

NOTE 2—Thermocouple extension wire makes a contribution to the total thermoelectric signal thermocouple circuit output that is dependent upon the temperature difference between the extreme ends of the extension wire length. The actual magnitude of any error introduced into a measuring circuit by homogeneous and correctly connected extension wires is equal to the algebraic difference of the deviations at its two end temperatures, as determined for that extension wire pair.

Thermocouple Type	Temperature Range		Tolerances—Reference Junction 0°C [32°F] 0 °C [32 °F]			
			Standard Tolerances		Special Tolerances	
	°C	[°F]	°C	[°F]	°C	[°F]
TX	-60 to 100	-75 to 200	±1.0	±1.8	±0.5	±0.9
TX	-60 to 100	-75 to 200	±1.0	±1.8	±0.5	±0.9
JX	0 to 200	32 to 400	±2.2	±4.0	±1.1	±2.0
EX	0 to 200	32 to 400	±1.7	±3.0	±1.0	±1.8
KX	0 to 200	32 to 400	±2.2	±4.0	±1.1	±2.0
NX	0 to 200	32 to 400	±2.2	±4.0	±1.1	±2.0

TABLE 3 Tolerances on Initial Values of Emf vs. Temperature for Compensating Extension Wires

NOTE 1—Tolerances in this table apply to new and essentially homogeneous thermocouple compensating extension wire when used at temperatures within the range given in the table below.

NOTE 2—Thermocouple compensating extension wire makes a contribution to the total thermoelectric signal thermocouple circuit output that is dependent upon the temperature difference between the extreme ends of the compensating extension wire length.

Thermocouple Type	Temperature Range		Tolerances—Reference Junction 0°C [32°F] 0 °C [32 °F]			
			Standard Tolerances		Special Tolerances	
	°C	[°F]	°C	[°F]	°C	[°F]
SX	0 to 200	32 to 400	±5	±9	A	
RX	0 to 200	32 to 400	±5	±9	A	
BX ^B	0 to 200	32 to 400	±4.2	±7.6	A	
B ^C	0 to 100	32 to 200	±3.7	±6.7	...	
CX	0 to 200	32 to 400	Initial Calibration Tolerance			
			±0.110 mV			

^A Special tolerance grade compensating extension wires are not available.

^B Proprietary alloy compensating extension wire is available for use over a wide temperature range.

^C Special compensating extension wires are not necessary with Type B over the limited temperature range 0 to 50°C [32 to 122°F], 0 °C to 50 °C [32 °F to 122 °F], where the use of non-compensated (copper/copper) conductors introduces no significant error. For a somewhat larger temperature gradient of 0 to 100°C [32 to 212°F], 0 °C to 100 °C [32 °F to 212 °F] across the extension portion of the circuit, the use of non-compensated (copper/copper) extension wires may result in small errors, the magnitude of which will not exceed the tolerances given for measurements above 1000°C [1800°F], 1000 °C [1800 °F].

TABLE 4 United States Color Codes for Single and Duplex Insulated Thermocouple Wire

NOTE 1—Data in this table represents customary practice in the United States of America. Different color code conventions may be in use in other parts of the world.

NOTE 2—For some types of insulations, colors may appear as a stripe or trace strand. High temperature braided insulations are normally supplied without color coding.

NOTE 3—The noble metal thermocouples are not normally supplied with colored insulations. However, if they were so furnished, the color codes for the corresponding single wire extensions would apply, with a brown overall jacket, where applicable.

Thermocouple Type	Thermoelement Designation	Individual Conductor Color	Overall Jacket Color
T	TP (+)	Blue	Brown
	TN (-)	Red	
J	JP (+)	White	Brown
	JN (-)	Red	
E	EP (+)	Purple	Brown
	EN (-)	Red	
K	KP (+)	Yellow	Brown
	KN (-)	Red	
N	NP (+)	Orange	Brown
	NN (-)	Red	

TABLE 5 United States Color Codes for Single and Duplex Insulated Extension Wire

NOTE 1—Data in this table represents customary practice in the United States of America. Different color code conventions may be in use in other parts of the world.

NOTE 2—For some types of insulations, colors may appear as a stripe or trace strand. High temperature braided insulations are normally supplied without color coding.

Thermocouple Type	Thermoelement Designation	Individual Conductor Color	Overall Jacket Color
TX	TPX (+)	Blue	Blue
	TNX (-)	Red, or Red/Blue Trace	
JX	JPX (+)	White	Black
	JNX (-)	Red, or Red/Black Trace	
EX	EPX (+)	Purple	Purple
	ENX (-)	Red, or Red/Purple Trace	
KX	KPX (+)	Yellow	Yellow
	KNX (-)	Red, or Red/Yellow Trace	
NX	NPX (+)	Orange	Orange
	NNX (-)	Red, or Red/Orange Trace	
RX or SX ^A	RPX/SPX (+)	Black	Green
	RNX/SNX (-)	Red, or Red/Black Trace	
BX ^B	BPX (+)	Gray	Gray
	BNX (-)	Red, or Red/Gray Trace	
CX	CPX (+)	Green	Red
	CNX (-)	Red	

^A Type R and S thermocouples utilize the same extension alloys.

^B Color code shown is applicable to constructions incorporating proprietary Type B compensating extension alloy wires. When uncompensated (copper/copper) extension materials are used with Type B thermocouples, the extension wire insulation is not normally color coded.

TABLE 6 Suggested Upper Temperature Limits for Protected Thermocouples

NOTE 1—This table provides the recommended upper temperature limits for the various thermocouple types and wire sizes. These limits apply to protected thermocouples, that is, thermocouples in conventional closed-end protecting tubes. They do not apply to compacted, mineral-insulated, metal-sheathed thermocouples.

NOTE 2—The temperature limits given here are intended only as a guide to the user and they should not be taken as absolute values nor as guarantees of satisfactory service life or performance. These types and sizes may be used at temperatures above the stated limits, but usually at the expense of stability or service life or both. In some instances, it may be necessary to reduce the temperature limits in order to achieve satisfactory performance in service. ASTM MNL-12^A and other literature sources should be consulted for additional applications information.

Thermo- couple Type	Upper Temperature limit for Various Wire Sizes, °C [°F]					
	No. 8 AWG (3.25 mm [0.128 in.])	No. 14 AWG (1.63 mm [0.064 in.])	No. 20 AWG (0.81 mm [0.032 in.])	No. 24 AWG (0.51 mm [0.020 in.])	No. 28 AWG (0.33 mm [0.013 in.])	No. 30 AWG (0.25 mm [0.010 in.])
T		370 [700]	260 [500]	200 [400]	200 [400]	150 [300]
J	760 [1400]	590 [1100]	480 [900]	370 [700]	370 [700]	320 [600]
E	870 [1600]	650 [1200]	540 [1000]	430 [800]	430 [800]	370 [700]
K and N	1260 [2300]	1090 [2000]	980 [1800]	870 [1600]	870 [1600]	760 [1400]
R and S				1480 [2700]		
B				1700 [3100]		
C ^B				2315 [4200] ^C		

^A Manual on the Use of Thermocouples in Temperature Measurement, ASTM MNL-12, 1993.

^B Type C thermoelements are not suitable for use in the presence of oxygen; therefore, protection for these thermocouples must provide an inert or non-oxidizing environment.

^C No. 24 AWG thermoelements are common for this thermocouple type, but other sizes are available and, with adequate protection, are generally useable over the same temperature range.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[ASTM E230/E230M-17](#)

<https://standards.iteh.ai/catalog/standards/sist/9c1a2eb6-449a-4bb7-bda6-4260cc670310/astm-e230-e230m-17>

TABLE 7 Polynomial Coefficients for Generating Thermocouple Emf as a Function of Temperature

NOTE 1—The following table contains sets of polynomial coefficients used to compute emfs for the various types of thermocouples and for their individual thermoelements paired with Pt–67, when reference junctions are at $\theta^{\circ}\text{C}$.

NOTE 2—The coefficients given are for an expression of the form: $E = c_0 + c_1t + c_2t^2 + c_3t^3 \dots + c_nt^n$. In this expression, E is in millivolts, t is in $^{\circ}\text{C}$, and $c_0, c_1, c_2, \dots, c_n$ are the coefficients given in the following table. For the Type K thermocouple and the Type KN thermoelement, coefficients b_0 and b_1 for an exponential term containing e, the natural logarithm base, also appear in the table. This term is of the form: $b_0e^{b_1(t-126.9686)^2}$ and, where given, it is to be evaluated and added to the polynomial result.

NOTE 3—If emf values on another temperature scale are desired, first convert the desired temperature to its equivalent in $^{\circ}\text{C}$, then evaluate the appropriate polynomial from the table below using the $^{\circ}\text{C}$ equivalent temperature.

Temperature Range		TYPE B Thermocouple	
		0 $^{\circ}\text{C}$ to 630.615 $^{\circ}\text{C}$	630.615 $^{\circ}\text{C}$ to 1820 $^{\circ}\text{C}$
	$c_0 =$	0.0	–3.893 816 862 1
	$c_1 =$	$-2.465\ 081\ 834\ 6 \times 10^{-4}$	$2.857\ 174\ 747\ 0 \times 10^{-2}$
	$c_2 =$	$5.904\ 042\ 117\ 1 \times 10^{-6}$	$-8.488\ 510\ 478\ 5 \times 10^{-5}$
	$c_3 =$	$-1.325\ 793\ 163\ 6 \times 10^{-9}$	$1.578\ 528\ 016\ 4 \times 10^{-7}$
	$c_4 =$	$1.566\ 829\ 190\ 1 \times 10^{-12}$	$-1.683\ 534\ 486\ 4 \times 10^{-10}$
	$c_5 =$	$-1.694\ 452\ 924\ 0 \times 10^{-15}$	$1.110\ 979\ 401\ 3 \times 10^{-13}$
	$c_6 =$	$6.299\ 034\ 709\ 4 \times 10^{-19}$	$-4.451\ 543\ 103\ 3 \times 10^{-17}$
	$c_7 =$		$9.897\ 564\ 082\ 1 \times 10^{-21}$
	$c_8 =$		$-9.379\ 133\ 028\ 9 \times 10^{-25}$
Temperature Range		TYPE E Thermocouple	
		–270 $^{\circ}\text{C}$ to 0 $^{\circ}\text{C}$	0 $^{\circ}\text{C}$ to 1000 $^{\circ}\text{C}$
	$c_0 =$	0.0	0.0
	$c_1 =$	$5.866\ 550\ 870\ 8 \times 10^{-2}$	$5.866\ 550\ 871\ 0 \times 10^{-2}$
	$c_2 =$	$4.541\ 097\ 712\ 4 \times 10^{-5}$	$4.503\ 227\ 558\ 2 \times 10^{-5}$
	$c_3 =$	$-7.799\ 804\ 868\ 6 \times 10^{-7}$	$2.890\ 840\ 721\ 2 \times 10^{-8}$
	$c_4 =$	$-2.580\ 016\ 084\ 3 \times 10^{-8}$	$-3.305\ 689\ 665\ 2 \times 10^{-10}$
	$c_5 =$	$-5.945\ 258\ 305\ 7 \times 10^{-10}$	$6.502\ 440\ 327\ 0 \times 10^{-13}$
	$c_6 =$	$-9.321\ 405\ 866\ 7 \times 10^{-12}$	$-1.919\ 749\ 550\ 4 \times 10^{-16}$
	$c_7 =$	$-1.028\ 760\ 553\ 4 \times 10^{-13}$	$-1.253\ 660\ 049\ 7 \times 10^{-18}$
	$c_8 =$	$-8.037\ 012\ 362\ 1 \times 10^{-16}$	$2.148\ 921\ 756\ 9 \times 10^{-21}$
	$c_9 =$	$-4.397\ 949\ 739\ 1 \times 10^{-18}$	$-1.438\ 804\ 178\ 2 \times 10^{-24}$
	$c_{10} =$	$-1.641\ 477\ 635\ 5 \times 10^{-20}$	$3.596\ 089\ 948\ 1 \times 10^{-28}$
	$c_{11} =$	$-3.967\ 361\ 951\ 6 \times 10^{-23}$	
	$c_{12} =$	$-5.582\ 732\ 872\ 1 \times 10^{-26}$	
	$c_{13} =$	$-3.465\ 784\ 201\ 3 \times 10^{-29}$	
Temperature Range		TYPE J Thermocouple	
		–210 $^{\circ}\text{C}$ to 760 $^{\circ}\text{C}$	760 $^{\circ}\text{C}$ to 1200 $^{\circ}\text{C}$
	$c_0 =$	0.0	$2.964\ 562\ 568\ 1 \times 10^{-2}$
	$c_1 =$	$5.038\ 118\ 781\ 5 \times 10^{-2}$	$-1.497\ 612\ 778\ 6$
	$c_2 =$	$3.047\ 583\ 693\ 0 \times 10^{-5}$	$3.178\ 710\ 392\ 4 \times 10^{-3}$
	$c_3 =$	$-8.568\ 106\ 572\ 0 \times 10^{-8}$	$-3.184\ 768\ 670\ 1 \times 10^{-6}$
	$c_4 =$	$1.322\ 819\ 529\ 5 \times 10^{-10}$	$1.572\ 081\ 900\ 4 \times 10^{-9}$
	$c_5 =$	$-1.705\ 295\ 833\ 7 \times 10^{-13}$	$-3.069\ 136\ 905\ 6 \times 10^{-13}$
	$c_6 =$	$2.094\ 809\ 069\ 7 \times 10^{-16}$	
	$c_7 =$	$-1.253\ 839\ 533\ 6 \times 10^{-19}$	
	$c_8 =$	$1.563\ 172\ 569\ 7 \times 10^{-23}$	
Temperature Range		TYPE K Thermocouple	
		–270 $^{\circ}\text{C}$ to 0 $^{\circ}\text{C}$	0 $^{\circ}\text{C}$ to 1372 $^{\circ}\text{C}$
	$c_0 =$	0.0	$-1.760\ 041\ 368\ 6 \times 10^{-2}$
	$c_1 =$	$3.945\ 012\ 802\ 5 \times 10^{-2}$	$3.892\ 120\ 497\ 5 \times 10^{-2}$
	$c_2 =$	$2.362\ 237\ 359\ 8 \times 10^{-5}$	$1.855\ 877\ 003\ 2 \times 10^{-5}$
	$c_3 =$	$-3.285\ 890\ 678\ 4 \times 10^{-7}$	$-9.945\ 759\ 287\ 4 \times 10^{-8}$
	$c_4 =$	$-4.990\ 482\ 877\ 7 \times 10^{-9}$	$3.184\ 094\ 571\ 9 \times 10^{-10}$
	$c_5 =$	$-6.750\ 905\ 917\ 3 \times 10^{-11}$	$-5.607\ 284\ 488\ 9 \times 10^{-13}$
	$c_6 =$	$-5.741\ 032\ 742\ 8 \times 10^{-13}$	$5.607\ 505\ 905\ 9 \times 10^{-16}$
	$c_7 =$	$-3.108\ 887\ 289\ 4 \times 10^{-15}$	$-3.202\ 072\ 000\ 3 \times 10^{-19}$
	$c_8 =$	$-1.045\ 160\ 936\ 5 \times 10^{-17}$	$9.715\ 114\ 715\ 2 \times 10^{-23}$
	$c_9 =$	$-1.988\ 926\ 687\ 8 \times 10^{-20}$	$-1.210\ 472\ 127\ 5 \times 10^{-26}$
	$c_{10} =$	$-1.632\ 269\ 748\ 6 \times 10^{-23}$	
Exponential Coefficients See Note 2	$b_0 =$		$1.185\ 976 \times 10^{-1}$
	$b_1 =$		$-1.183\ 432 \times 10^{-4}$
Temperature Range		TYPE N Thermocouple	
		–270 $^{\circ}\text{C}$ to 0 $^{\circ}\text{C}$	0 $^{\circ}\text{C}$ to 1300 $^{\circ}\text{C}$

TABLE 7 Continued

C_0	=	0.0	0.0
C_1	=	$2.615\ 910\ 596\ 2 \times 10^{-2}$	$2.592\ 939\ 460\ 1 \times 10^{-2}$
C_2	=	$1.095\ 748\ 422\ 8 \times 10^{-5}$	$1.571\ 014\ 188\ 0 \times 10^{-5}$
C_3	=	$-9.384\ 111\ 155\ 4 \times 10^{-8}$	$4.382\ 562\ 723\ 7 \times 10^{-8}$
C_4	=	$-4.641\ 203\ 975\ 9 \times 10^{-11}$	$-2.526\ 116\ 979\ 4 \times 10^{-10}$
C_5	=	$-2.630\ 335\ 771\ 6 \times 10^{-12}$	$6.431\ 181\ 933\ 9 \times 10^{-13}$
C_6	=	$-2.265\ 343\ 800\ 3 \times 10^{-14}$	$-1.006\ 347\ 151\ 9 \times 10^{-15}$
C_7	=	$-7.608\ 930\ 079\ 1 \times 10^{-17}$	$9.974\ 533\ 899\ 2 \times 10^{-19}$
C_8	=	$-9.341\ 966\ 783\ 5 \times 10^{-20}$	$-6.086\ 324\ 560\ 7 \times 10^{-22}$
C_9	=		$2.084\ 922\ 933\ 9 \times 10^{-25}$
C_{10}	=		$-3.068\ 219\ 615\ 1 \times 10^{-29}$

TYPE R Thermocouple

Temperature Range	-50 °C to 1064.18 °C		1064.18 °C to 1664.5 °C		1664.5 °C to 1768.1 °C	
	C_0	=	0.0	2.951 579 253 16	1.522 321 182 09	$1.522\ 321\ 182\ 09 \times 10^{-2}$
C_1	=	$5.289\ 617\ 297\ 65 \times 10^{-3}$	$-2.520\ 612\ 513\ 32 \times 10^{-3}$	$-2.688\ 198\ 885\ 45 \times 10^{-1}$	$-2.688\ 198\ 885\ 45 \times 10^{-1}$	
C_2	=	$1.391\ 665\ 897\ 82 \times 10^{-5}$	$1.595\ 645\ 018\ 65 \times 10^{-5}$	$1.712\ 802\ 804\ 71 \times 10^{-4}$	$1.712\ 802\ 804\ 71 \times 10^{-4}$	
C_3	=	$-2.388\ 556\ 930\ 17 \times 10^{-8}$	$-7.640\ 859\ 475\ 76 \times 10^{-9}$	$-3.458\ 957\ 064\ 53 \times 10^{-8}$	$-3.458\ 957\ 064\ 53 \times 10^{-8}$	
C_4	=	$3.569\ 160\ 010\ 63 \times 10^{-11}$	$2.053\ 052\ 910\ 24 \times 10^{-12}$	$-9.346\ 339\ 710\ 46 \times 10^{-15}$	$-9.346\ 339\ 710\ 46 \times 10^{-15}$	
C_5	=	$-4.623\ 476\ 662\ 98 \times 10^{-14}$	$-2.933\ 596\ 681\ 73 \times 10^{-16}$			
C_6	=	$5.007\ 774\ 410\ 34 \times 10^{-17}$				
C_7	=	$-3.731\ 058\ 861\ 91 \times 10^{-20}$				
C_8	=	$1.577\ 164\ 823\ 67 \times 10^{-23}$				
C_9	=	$-2.810\ 386\ 252\ 51 \times 10^{-27}$				

TYPE S Thermocouple

Temperature Range	-50 °C to 1064.18 °C		1064.18 °C to 1664.5 °C		1664.5 °C to 1768.1 °C	
	C_0	=	0.0	1.329 004 440 85	1.466 282 326 36	$1.466\ 282\ 326\ 36 \times 10^{-2}$
C_1	=	$5.403\ 133\ 086\ 31 \times 10^{-3}$	$3.345\ 093\ 113\ 44 \times 10^{-3}$	$-2.584\ 305\ 167\ 52 \times 10^{-1}$	$-2.584\ 305\ 167\ 52 \times 10^{-1}$	
C_2	=	$1.259\ 342\ 897\ 40 \times 10^{-5}$	$6.548\ 051\ 928\ 18 \times 10^{-6}$	$1.636\ 935\ 746\ 41 \times 10^{-4}$	$1.636\ 935\ 746\ 41 \times 10^{-4}$	
C_3	=	$-2.324\ 779\ 686\ 89 \times 10^{-8}$	$-1.648\ 562\ 592\ 09 \times 10^{-9}$	$-3.304\ 390\ 469\ 87 \times 10^{-8}$	$-3.304\ 390\ 469\ 87 \times 10^{-8}$	
C_4	=	$3.220\ 288\ 230\ 36 \times 10^{-11}$	$1.299\ 896\ 051\ 74 \times 10^{-14}$	$-9.432\ 236\ 906\ 12 \times 10^{-15}$	$-9.432\ 236\ 906\ 12 \times 10^{-15}$	
C_5	=	$-3.314\ 651\ 963\ 89 \times 10^{-14}$				
C_6	=	$2.557\ 442\ 517\ 86 \times 10^{-17}$				
C_7	=	$-1.250\ 688\ 713\ 93 \times 10^{-20}$				
C_8	=	$2.714\ 431\ 761\ 45 \times 10^{-24}$				

TYPE T Thermocouple

Temperature Range	-270 °C to 0 °C		0 °C to 400 °C	
	C_0	=	0.0	0.0
C_1	=	$3.874\ 810\ 636\ 4 \times 10^{-2}$	$3.874\ 810\ 636\ 4 \times 10^{-2}$	
C_2	=	$4.419\ 443\ 434\ 7 \times 10^{-5}$	$3.329\ 222\ 788\ 0 \times 10^{-5}$	
C_3	=	$1.184\ 432\ 310\ 5 \times 10^{-7}$	$2.061\ 824\ 340\ 4 \times 10^{-7}$	
C_4	=	$2.003\ 297\ 355\ 4 \times 10^{-8}$	$-2.188\ 225\ 684\ 6 \times 10^{-9}$	
C_5	=	$9.013\ 801\ 955\ 9 \times 10^{-10}$	$1.099\ 688\ 092\ 8 \times 10^{-11}$	
C_6	=	$2.265\ 115\ 659\ 3 \times 10^{-11}$	$-3.081\ 575\ 877\ 2 \times 10^{-14}$	
C_7	=	$3.607\ 115\ 420\ 5 \times 10^{-13}$	$4.547\ 913\ 529\ 0 \times 10^{-17}$	
C_8	=	$3.849\ 393\ 988\ 3 \times 10^{-15}$	$-2.751\ 290\ 167\ 3 \times 10^{-20}$	
C_9	=	$2.821\ 352\ 192\ 5 \times 10^{-17}$		
C_{10}	=	$1.425\ 159\ 477\ 9 \times 10^{-19}$		
C_{11}	=	$4.876\ 866\ 228\ 6 \times 10^{-22}$		
C_{12}	=	$1.079\ 553\ 927\ 0 \times 10^{-24}$		
C_{13}	=	$1.394\ 502\ 706\ 2 \times 10^{-27}$		
C_{14}	=	$7.979\ 515\ 392\ 7 \times 10^{-31}$		

TYPE C Coefficients

$t = 0\text{ °C to }2315\text{ °C}$

	0 °C to 630.615 °C		630.615 °C to 2315 °C	
	C_0	=	0.000000	4.0528823×10^{-1}
C_1	=	1.3406032×10^{-2}	1.1509355×10^{-2}	-2
C_2	=	1.1924992×10^{-5}	1.5696453×10^{-5}	-5
C_3	=	$-7.9806354 \times 10^{-9}$	$-1.3704412 \times 10^{-8}$	-8
C_4	=	$-5.0787515 \times 10^{-12}$	$5.2290873 \times 10^{-12}$	-12
C_5	=	$1.3164197 \times 10^{-14}$	$-9.2082758 \times 10^{-16}$	-16
C_6	=	$-7.9197332 \times 10^{-18}$	$4.5245112 \times 10^{-20}$	-20

TYPE BP Thermoelement vs. Platinum (NIST Pt-67)

TABLE 7 *Continued*

Temperature Range	0 °C to 630.615 °C	630.615 °C to 1768.1 °C
$C_0 =$	0.0	-7.968 043 228 2 .
$C_1 =$	4.822 787 568 7 × 10 ⁻³	6.394 111 021 3 × 10 ⁻²
$C_2 =$	1.565 116 570 9 × 10 ⁻⁵	-1.710 242 141 0 × 10 ⁻⁴
$C_3 =$	-2.223 379 788 2 × 10 ⁻⁸	3.055 578 252 7 × 10 ⁻⁷
$C_4 =$	2.833 324 407 4 × 10 ⁻¹¹	-3.210 574 449 2 × 10 ⁻¹⁰
$C_5 =$	-2.025 894 044 7 × 10 ⁻¹⁴	2.090 910 279 4 × 10 ⁻¹³
$C_6 =$	6.148 870 509 6 × 10 ⁻¹⁸	-8.233 582 542 6 × 10 ⁻¹⁷
$C_7 =$		1.782 284 151 5 × 10 ⁻²⁰
$C_8 =$		-1.618 707 418 7 × 10 ⁻²⁴

TYPE BN Thermoelement vs. Platinum (NIST Pt-67)

Temperature Range	0 °C to 630.615 °C	630.615 °C to 1768.1 °C
$C_0 =$	0.0	-4.074 226 366 2 .
$C_1 =$	5.069 295 752 2 × 10 ⁻³	3.536 936 274 3 × 10 ⁻²
$C_2 =$	9.747 123 592 0 × 10 ⁻⁶	-8.613 910 931 5 × 10 ⁻⁵
$C_3 =$	-2.090 800 471 8 × 10 ⁻⁸	1.477 050 236 2 × 10 ⁻⁷
$C_4 =$	2.676 641 488 3 × 10 ⁻¹¹	-1.527 039 962 9 × 10 ⁻¹⁰
$C_5 =$	-1.856 448 752 3 × 10 ⁻¹⁴	9.799 308 780 5 × 10 ⁻¹⁴
$C_6 =$	5.518 967 038 6 × 10 ⁻¹⁸	-3.782 039 439 3 × 10 ⁻¹⁷
$C_7 =$		7.925 277 432 8 × 10 ⁻²¹
$C_8 =$		-6.807 941 157 8 × 10 ⁻²⁵

TYPE JP Thermoelement vs. Platinum (NIST Pt-67)

Temperature Range	-210 °C to 760 °C
$C_0 =$	0.0
$C_1 =$	1.791 354 855 9 × 10 ⁻²
$C_2 =$	4.677 466 335 8 × 10 ⁻⁶
$C_3 =$	-7.122 599 299 1 × 10 ⁻⁸
$C_4 =$	1.335 212 501 6 × 10 ⁻¹⁰
$C_5 =$	-1.500 896 263 9 × 10 ⁻¹³
$C_6 =$	1.551 431 962 5 × 10 ⁻¹⁶
$C_7 =$	-7.950 357 212 5 × 10 ⁻²⁰
$C_8 =$	2.429 790 391 0 × 10 ⁻²⁴

Platinum (NIST Pt-67) vs. **TYPE JN** Thermoelement

Temperature Range	-210 °C to 760 °C
$C_0 =$	0.0
$C_1 =$	3.246 763 925 6 × 10 ⁻²
$C_2 =$	2.579 837 059 4 × 10 ⁻⁵
$C_3 =$	-1.445 507 273 0 × 10 ⁻⁸
$C_4 =$	-1.239 297 209 3 × 10 ⁻¹²
$C_5 =$	-2.043 995 698 0 × 10 ⁻¹⁴
$C_6 =$	5.433 771 071 8 × 10 ⁻¹⁷
$C_7 =$	-4.588 038 123 5 × 10 ⁻²⁰
$C_8 =$	1.320 193 530 6 × 10 ⁻²³

TYPE KP or EP Thermoelement vs. Platinum (NIST Pt-67)

Temperature Range	-270 °C to 0 °C	0 °C to 1372 °C
$C_0 =$	0.0	0.0
$C_1 =$	2.581 195 057 4 × 10 ⁻²	2.581 195 057 3 × 10 ⁻²
$C_2 =$	2.299 008 894 3 × 10 ⁻⁵	2.683 139 535 5 × 10 ⁻⁵
$C_3 =$	-6.157 475 446 0 × 10 ⁻⁷	-3.867 519 441 2 × 10 ⁻⁸
$C_4 =$	-2.327 184 376 5 × 10 ⁻⁸	3.030 555 323 4 × 10 ⁻¹¹
$C_5 =$	-5.457 033 359 6 × 10 ⁻¹⁰	-1.028 040 353 3 × 10 ⁻¹⁴
$C_6 =$	-7.845 394 226 4 × 10 ⁻¹²	-3.448 171 733 0 × 10 ⁻¹⁷
$C_7 =$	-7.251 284 060 8 × 10 ⁻¹⁴	8.251 289 448 0 × 10 ⁻²⁰
$C_8 =$	-4.356 917 479 1 × 10 ⁻¹⁶	-7.889 338 217 7 × 10 ⁻²³
$C_9 =$	-1.664 752 760 6 × 10 ⁻¹⁸	3.569 925 312 6 × 10 ⁻²⁶
$C_{10} =$	-3.737 720 750 1 × 10 ⁻²¹	-6.331 536 065 9 × 10 ⁻³⁰
$C_{11} =$	-3.774 144 269 5 × 10 ⁻²⁴	
$C_{12} =$	1.002 535 559 0 × 10 ⁻²⁷	
$C_{13} =$	3.893 531 072 5 × 10 ⁻³⁰	

Platinum (NIST Pt-67) vs. **TYPE KN** Thermoelement

Temperature Range	-270 °C to 0 °C	0 °C to 1372 °C
$C_0 =$	0.0	-1.760 041 368 6 × 10 ⁻²
$C_1 =$	1.363 817 745 2 × 10 ⁻²	1.310 925 440 3 × 10 ⁻²
$C_2 =$	6.322 846 542 6 × 10 ⁻⁷	-8.272 625 323 0 × 10 ⁻⁶

TABLE 7 Continued

	$c_3 =$	2.871 584 767 6 × 10 ⁻⁷	-6.078 239 846 2 × 10 ⁻⁸
	$c_4 =$	1.828 136 088 7 × 10 ⁻⁸	2.881 039 039 6 × 10 ⁻¹⁰
	$c_5 =$	4.781 942 767 9 × 10 ⁻¹⁰	-5.504 480 453 6 × 10 ⁻¹³
	$c_6 =$	7.271 290 952 1 × 10 ⁻¹²	5.952 323 079 2 × 10 ⁻¹⁶
	$c_7 =$	6.940 395 331 9 × 10 ⁻¹⁴	-4.027 200 945 1 × 10 ⁻¹⁹
	$c_8 =$	4.252 401 385 5 × 10 ⁻¹⁶	1.760 445 293 3 × 10 ⁻²²
	$c_9 =$	1.644 863 493 8 × 10 ⁻¹⁸	-4.780 397 440 1 × 10 ⁻²⁶
	$c_{10} =$	3.721 398 052 6 × 10 ⁻²¹	6.331 536 065 9 × 10 ⁻³⁰
	$c_{11} =$	3.774 144 269 5 × 10 ⁻²⁴	
	$c_{12} =$	-1.002 535 559 0 × 10 ⁻²⁷	
	$c_{13} =$	-3.893 531 072 5 × 10 ⁻³⁰	
Exponential Coefficients See Note 2	$b_0 =$		1.185 976 × 10 ⁻¹
	$b_1 =$		-1.183 432 × 10 ⁻⁴
TYPE NP Thermoelement vs. Platinum (NIST Pt-67)			
Temperature Range		-200 °C to 0 °C	0 °C to 1300 °C
	$c_0 =$	0.0	0.0
	$c_1 =$	1.541 798 843 0 × 10 ⁻²	1.544 538 594 7 × 10 ⁻²
	$c_2 =$	2.570 738 245 7 × 10 ⁻⁵	2.672 234 128 9 × 10 ⁻⁵
	$c_3 =$	-9.018 782 577 1 × 10 ⁻⁸	-2.559 531 305 2 × 10 ⁻⁸
	$c_4 =$	-5.365 479 300 5 × 10 ⁻¹⁰	-3.302 809 741 4 × 10 ⁻¹¹
	$c_5 =$	-3.352 621 597 6 × 10 ⁻¹²	2.007 532 297 1 × 10 ⁻¹³
	$c_6 =$	-7.272 344 767 0 × 10 ⁻¹⁵	-4.270 815 423 0 × 10 ⁻¹⁶
	$c_7 =$		5.181 347 352 2 × 10 ⁻¹⁹
	$c_8 =$		-3.688 712 493 1 × 10 ⁻²²
	$c_9 =$		1.426 873 470 8 × 10 ⁻²⁵
	$c_{10} =$		-2.312 130 215 4 × 10 ⁻²⁹
Platinum (NIST Pt-67) vs. TYPE NN Thermoelement			
Temperature Range		-200 °C to 0 °C	0 °C to 1300 °C
	$c_0 =$	0.0	0.0
	$c_1 =$	1.074 111 753 2 × 10 ⁻²	1.048 400 865 5 × 10 ⁻²
	$c_2 =$	-1.474 989 822 9 × 10 ⁻⁵	-1.101 219 940 9 × 10 ⁻⁵
	$c_3 =$	-3.653 285 783 2 × 10 ⁻⁹	6.942 094 028 9 × 10 ⁻⁸
	$c_4 =$	4.901 358 902 9 × 10 ⁻¹⁰	-2.195 836 005 3 × 10 ⁻¹⁰
	$c_5 =$	7.222 858 260 4 × 10 ⁻¹³	4.423 649 636 8 × 10 ⁻¹³
	$c_6 =$	-1.538 109 323 6 × 10 ⁻¹⁴	-5.792 656 096 4 × 10 ⁻¹⁶
	$c_7 =$	-7.608 930 079 1 × 10 ⁻¹⁷	4.793 186 547 0 × 10 ⁻¹⁹
	$c_8 =$	-9.341 966 783 5 × 10 ⁻²⁰	-2.397 612 067 6 × 10 ⁻²²
	$c_9 =$		6.580 494 631 8 × 10 ⁻²⁶
	$c_{10} =$		-7.560 893 996 5 × 10 ⁻³⁰
TYPE TP Thermoelement vs. Platinum (NIST Pt-67)			
Temperature Range		-270 °C to 0 °C	0 °C to 400 °C
	$c_0 =$	0.0	0.0
	$c_1 =$	5.894 548 229 7 × 10 ⁻³	5.894 548 226 5 × 10 ⁻³
	$c_2 =$	2.177 354 616 7 × 10 ⁻⁵	1.509 134 765 2 × 10 ⁻⁵
	$c_3 =$	2.826 761 733 1 × 10 ⁻⁷	1.385 988 324 2 × 10 ⁻⁷
	$c_4 =$	2.256 129 063 2 × 10 ⁻⁸	-1.827 351 164 9 × 10 ⁻⁹
	$c_5 =$	9.502 026 902 0 × 10 ⁻¹⁰	1.033 635 649 1 × 10 ⁻¹¹
	$c_6 =$	2.412 716 823 3 × 10 ⁻¹¹	-3.065 826 553 4 × 10 ⁻¹⁴
	$c_7 =$	3.910 747 567 8 × 10 ⁻¹³	4.681 530 823 5 × 10 ⁻¹⁷
	$c_8 =$	4.217 403 476 6 × 10 ⁻¹⁵	-2.974 071 681 2 × 10 ⁻²⁰
	$c_9 =$	3.094 671 890 4 × 10 ⁻¹⁷	1.474 503 431 3 × 10 ⁻²⁴
	$c_{10} =$	1.551 930 033 9 × 10 ⁻¹⁹	-3.659 405 308 7 × 10 ⁻²⁸
	$c_{11} =$	5.235 860 981 1 × 10 ⁻²²	
	$c_{12} =$	1.136 383 791 3 × 10 ⁻²⁴	
	$c_{13} =$	1.433 054 079 2 × 10 ⁻²⁷	
	$c_{14} =$	7.979 515 392 7 × 10 ⁻³¹	
Platinum (NIST Pt-67) vs. TYPE TN or EN Thermoelement			
Temperature Range		-270 °C to 0 °C	0 °C to 1000 °C
	$c_0 =$	0.0	0.0
	$c_1 =$	3.285 355 813 4 × 10 ⁻²	3.285 355 813 8 × 10 ⁻²
	$c_2 =$	2.242 088 818 1 × 10 ⁻⁵	1.820 088 022 7 × 10 ⁻⁵
	$c_3 =$	-1.642 329 422 6 × 10 ⁻⁷	6.758 360 162 4 × 10 ⁻⁸
	$c_4 =$	-2.528 317 078 0 × 10 ⁻⁹	-3.608 745 197 5 × 10 ⁻¹⁰
	$c_5 =$	-4.882 249 460 9 × 10 ⁻¹¹	6.605 244 362 3 × 10 ⁻¹³
	$c_6 =$	-1.476 011 640 4 × 10 ⁻¹²	-1.574 932 377 1 × 10 ⁻¹⁶
	$c_7 =$	-3.036 321 473 1 × 10 ⁻¹⁴	-1.336 172 944 2 × 10 ⁻¹⁸
	$c_8 =$	-3.680 094 883 0 × 10 ⁻¹⁶	2.227 815 139 1 × 10 ⁻²¹
	$c_9 =$	-2.733 196 978 5 × 10 ⁻¹⁸	-1.474 503 431 3 × 10 ⁻²⁴

TABLE 7 *Continued*

C_{10}	=	$-1.267\ 705\ 560\ 5 \times 10^{-20}$	$3.659\ 405\ 308\ 7 \times 10^{-28}$
C_{11}	=	$-3.589\ 947\ 524\ 7 \times 10^{-23}$	
C_{12}	=	$-5.682\ 986\ 428\ 0 \times 10^{-26}$	
C_{13}	=	$-3.855\ 137\ 308\ 5 \times 10^{-29}$	

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM E230/E230M-17](#)

<https://standards.itih.ai/catalog/standards/sist/9c1a2eb6-449a-4bb7-bda6-4260cc670310/astm-e230-e230m-17>