



Designation: D1633 – 17

Standard Test Methods for Compressive Strength of Molded Soil-Cement Cylinders¹

This standard is issued under the fixed designation D1633; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the compressive strength of soil-cement using molded cylinders as test specimens.

1.2 Two alternative procedures are provided as follows:

1.2.1 *Method A*—This procedure uses a test specimen prepared in a mold complying with Test Methods D698 (4.0 in. (101.6 mm) in diameter and 4.6 in. (116.8 mm) in height), sometimes referred to as a proctor mold, resulting in a height over diameter ratio of 1.15. This test method may be used only on materials with 30 % or less retained on the 19.0-mm ($\frac{3}{4}$ -in.) sieve. See Note 2.

1.2.2 *Method B*—This procedure uses a test specimen with a height over diameter ratio of 2.0 prepared in a cylindrical mold in accordance with Practice D1632 (2.8 in. (71.1 mm) in diameter and 9.0 in. (229 mm) in height). This test method is applicable to those materials that pass the 4.75-mm (No. 4) sieve.

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard, except as noted in below. The values given in parentheses are mathematical conversions to SI units, and are provided for information only and are not considered standard. Sieve sizes are identified by the standard designations in Specification E11. The alternative sieve size designation given in parentheses is for information only and does not represent a different standard sieve size.

1.3.1 The gravitational system of inch-pound units is used when dealing with inch-pound units. In this system, the pound (lbf) represents a unit of force (weight), while the unit for mass is slugs.

1.3.2 The slug unit of mass is almost never used in commercial practice, that is, density, balances, etc. Therefore, the standard unit for mass in this standard is either kilogram (kg) or gram (g), or both. Also, the equivalent inch-pound unit (slug) is not given/presented in parentheses.

1.3.3 It is common practice in the engineering/construction profession to concurrently use pounds to represent both a unit of mass (lbf) and of force (lbf). This implicitly combines two separate systems of units; that is, the absolute system and the gravitational system. It is scientifically undesirable to combine the use of two separate sets of inch-pound units within a single standard. As stated, this standard includes the gravitational system of inch-pound units and does not use/present the slug unit for mass. However, the use of balances or scales, recording pounds of mass (lbf) or recording density in lbf/ft³ shall not be regarded as nonconformance with this standard.

1.4 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice D6026 unless superseded by this test method.

1.4.1 The procedures used to specify how data are collected/recorded and calculated in the standard are regarded as the industry standard. In addition, they are representative of the significant digits that generally should be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of these test methods to consider significant digits used in analysis methods for engineering data.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.15 on Stabilization With Admixtures.

Current edition approved Nov. 1, 2017. Published November 2017. Originally approved in 1959. Last previous edition approved in 2007 as D1633 – 00(2007), which was withdrawn in July 2016 and reinstated in November 2017. DOI: 10.1520/D1633-17.

*A Summary of Changes section appears at the end of this standard

2. Referenced Documents

2.1 *ASTM Standards*:²

- C42/C42M** Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete
- D559** Test Methods for Wetting and Drying Compacted Soil-Cement Mixtures
- D560** Test Methods for Freezing and Thawing Compacted Soil-Cement Mixtures
- D653** Terminology Relating to Soil, Rock, and Contained Fluids
- D698** Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400 ft-lbf/ft³ (600 kN-m/m³))
- D1632** Practice for Making and Curing Soil-Cement Compression and Flexure Test Specimens in the Laboratory
- D2216** Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass
- D3740** Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction
- D4753** Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing
- D6026** Practice for Using Significant Digits in Geotechnical Data
- E4** Practices for Force Verification of Testing Machines
- E11** Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Terminology

3.1 *Definitions*:

3.1.1 For definitions of common technical terms in this standard, refer to Terminology **D653**.

4. Significance and Use

4.1 Method A makes use of the same compaction equipment and molds commonly available in soil laboratories and used for other soil-cement tests. It is considered that Method A gives a relative measure of strength rather than a rigorous determination of compressive strength. Because of the lesser height to diameter ratio (1.15) of the cylinders, the compressive strength determined by Method A will normally be greater than that for Method B.

4.2 Method B, because of the greater height to diameter ratio (2.00), gives a better measure of compressive strength from a technical viewpoint since it reduces complex stress conditions that may occur during the shearing of Method A specimens.

4.3 In practice, Method A has been more commonly used than Method B. As a result, it has been customary to evaluate or specify compressive strength values as determined by

Method A. A factor for converting compressive strength values based on height to diameter ratio is given in Section 8.³

NOTE 1—The quality of the result produced by this standard is dependent on the competence of the personnel performing it and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice **D3740** are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice **D3740** does not in itself ensure reliable results. Reliable results depend on many factors; Practice **D3740** provides a means of evaluating some of those factors.

5. Apparatus

5.1 *Compression Testing Machine*—This machine may be of any type having sufficient capacity and control to provide the rate of loading prescribed in 7.2. The testing machine shall be equipped with two steel bearing blocks with hardened faces, one of which is a spherically seated head block that normally will bear on the upper surface of the specimen, and the other a plain rigid block on which the specimen will rest. The bearing block surfaces intended for contact with the specimen shall have a Rockwell hardness of not less than HRC 60. The bearing faces shall be at least as large, and preferably slightly larger, than the surface of the specimen to which the load is applied. The bearing faces, when new, shall not depart from a plane by more than 0.0005 in. (0.013 mm) at any point, and they shall be maintained within a permissible variation limit of 0.001 in. (0.02 mm). In the spherically seated block, the diameter of the sphere shall not greatly exceed the diameter of the specimen and the center of the sphere shall coincide with the center of the bearing face. The movable portion of this block shall be held closely in the spherical seat, but the design shall be such that the bearing face can be rotated freely and tilted through small angles in any direction. The compression shall be verified in accordance with Practice **E4** at least annually to determine if indicated loads are accurate to $\pm 1.0\%$ in the applicable range of loading.

5.2 *Molds and Compaction Equipment*, in accordance with Test Methods **D559** or **D560** for Method A; Practice **D1632** for Method B.

5.3 *Balances*—A Class GP5 balance meeting the requirements of Guide **D4753** for a balance of 1-g readability and a Class GP2 balance meeting the requirements of Guide **D4753** for a balance of 0.1-g readability.

5.4 *Measuring Device*—A Measuring device suitable for measuring the heights and diameters of test specimens to the nearest 0.01 in. (0.25 mm).

6. Test Specimens

6.1 Prepare the test specimens as follows:

6.1.1 *Method A*—Specimens are prepared in accordance with Test Methods **D559** or **D560** using molds 4.0 in. (101.6 mm) in diameter and 4.584 in. (116.4 mm) in height.

6.1.2 *Method B*—Specimens are prepared in accordance with Practice **D1632** using molds 2.8 in. (71.1 mm) in diameter and 9.0 in. (299 mm) in height.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ For additional discussion on the significance and use of compressive strength results, see the *Soil-Cement Laboratory Handbook*, Chapter 4, Portland Cement Association, Skokie, IL, 1971, pp 31 and 32.