



Designation: **D1545 – 13 D1545 – 13 (Reapproved 2017)**

Standard Test Method for Viscosity of Transparent Liquids by Bubble Time Method¹

This standard is issued under the fixed designation D1545; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the viscosity in bubble seconds by timing. The bubble seconds are approximately equal to stokes for most liquids.

1.2 The test method is applicable to transparent liquids that are free from crystalline or gel particles.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Terminology

2.1 Definitions:

2.1.1 *viscosity, n*—the resistance experienced by one portion of a liquid moving over another portion of the liquid. The absolute unit of viscosity in the cgs, centimeter-gram-second, system is the poise which is expressed as dyne-seconds per square centimetre. Stokes are equal to poises divided by density. The absolute SI, International System of Units (metric system), viscosity unit is the pascal-second.

3. Apparatus

3.1 *Constant-Temperature Bath*—Any suitable bath capable of maintaining temperature at $25 \pm 0.1^\circ\text{C}$ with water as the bath medium.

3.2 *Standard Viscosity Tubes* of clear glass and with flat bottoms, 10.65 ± 0.025 mm in inside diameter; 114 ± 1 mm in outside length. Plainly legible lines shall be located as follows (**Note 1**):

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.24 on Physical Properties of Liquid Paints and Paint Materials.

Current edition approved Feb. 1, 2013; Dec. 1, 2017. Published March 2013; December 2017. Originally approved in 1958. Last previous edition approved in 2012 as D1545 – 07 (2012); D1545 – 13. DOI: 10.1520/D1545-13.10.1520/D1545-13R17.