



Designation: ~~D6762 – 02a (Reapproved 2009)~~<sup>ε1</sup> D6762 – 02a (Reapproved 2017)

## Standard Test Method for Determining the Hiding Power of Paint by Visual Evaluation of Spray Applied Coatings<sup>1</sup>

This standard is issued under the fixed designation D6762; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

---

<sup>ε1</sup> NOTE—Units statement in 1.3 was added editorially in July 2009.

---

### 1. Scope

1.1 This test method provides for the quantitative visual determination of the film thickness required to achieve full hiding. This film thickness is considered to be the hiding power of a test paint.

1.2 This method applies only to spray applied coatings but its concepts are valid for other methods of application as well.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**D16** Terminology for Paint, Related Coatings, Materials, and Applications

**D609** Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products

**D1005** Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers

**D1186** Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base (Withdrawn 2006)<sup>3</sup>

**D1400** Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base (Withdrawn 2006)<sup>3</sup>

**D1729** Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials

**D1730** Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting

**D2805** Test Method for Hiding Power of Paints by Reflectometry

**E691** Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

### 3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method, refer to Terminology **D16** and the *Paint/Coatings Dictionary*.<sup>4</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.26** on Optical Properties.

Current edition approved July 1, 2009Dec. 1, 2017. Published July 1, 2009December 2017. Originally approved in 2002. Last previous edition approved in 20022009 as ~~D6762 – 02a~~D6762 – 02a (2009)<sup>ε</sup>. DOI: ~~10.1520/D6762-02AR09E01~~10.1520/D6762-02AR17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Published by the Federation of Societies for Coatings Technology, 492 Norristown Rd., Blue Bell, PA 19422.

#### 4. Summary of Test Method

4.1 The test paint is applied by means of spray application in a wedge-shaped film over a black and white, black and gray or red and gray pattern so that a thickness variation is obtained, which provides excess hiding at one end of the pattern and partial hiding at the other end of the pattern.

4.2 The dry film is examined under standard illumination to select the point where the pattern just becomes obscured. The thickness of the film at this point is designated the hiding power of the paint.

#### 5. Significance and Use

5.1 This test method determines hiding power of a test paint by visual evaluation of a spray applied coating.

NOTE 1—Test Method **D2805** describes an instrumental method for determining hiding power. The paint film is applied at a uniform thickness (for example with a doctor blade), the film thickness is measured rigorously, and the opacity is determined photometrically. Hiding power is thereby determined with a high degree of precision.

5.2 Test Method **D6762** is less precise than Test Method **D2805**, but is commonly used since it is more closely related to the application characteristics of the paint and is simpler in concept and evaluation.

#### 6. Apparatus

6.1 *Test Surface*, a smooth-surfaced paper chart, approximately 2 by 11 in., with a test pattern having adjacent black and white, black and gray or red and gray areas and coated with a suitable varnish or lacquer so as to render the surface impervious to paint liquids.

NOTE 2—The red, gray, white and black areas should fall in the following colorimetric range:

	CIE-Y %	C <sup>A</sup>	h <sup>A</sup>
Red	4–7	10–18	26–38
Gray	28–34		
White	80–83		
Black	1 max		

<sup>A</sup> Valid for Illuminant D65<sup>10</sup> or C<sup>2</sup>, with 0°/45° geometry.

6.2 *Illumination*, a light source providing diffuse light of reasonable intensity, preferably northern sky light or an approximation of the same (see Practice **D1729**).

6.3 *Backer Panel*, 4 by 12 in. steel or aluminum panel. A larger panel may be used if desired.

6.4 *Film Thickness Measuring Device*, a film thickness measuring device in accordance with Test Methods **D1005**, **D1186**, and **D1400**.

6.5 *Spray Equipment*, either a hand spray gun or an automatic spray machine.

6.6 *Oven*, capable of maintaining the bake schedule for the product being evaluated.

6.7 *Tape*, masking or adhesive.

#### 7. Preparation of Wedge-shaped Paint Film (Hand Spray)

7.1 Prepare the backer panel in accordance with Practices **D609** or **D1730**.

7.2 Attach the desired test pattern to one side of the backer panel with masking tape or adhesive tape.

7.3 Reduce the material being tested to spray viscosity.

7.4 Attach spray gun to a suitable compressed air supply line and adjust air pressure for consistent fan spray.

7.5 Position the backer panel so that the long side is vertical. The panel should be placed so that the spray gun tip is approximately 12 in. from the face of the panel.

7.6 Prepare a wedge-shaped film. An example of a procedure for preparing a wedge-shaped film by means of hand spray is shown in **Appendix X1**.

NOTE 3—The film thickness should vary from partial hiding at one end to excess hiding at the other end, but the total variation from one end to the other should not exceed 50 μm.

7.7 Remove the panel and flash and bake per the recommended bake schedule.

#### 8. Preparation of Wedge-shaped Paint Film (Automatic Spray Machine)

8.1 Prepare the backer panel in accordance with Practices **D609** or **D1730**.

8.2 Attach the desired test pattern to the one side of the backer panel with masking tape or adhesive tape.

8.3 Reduce the material being tested to spray viscosity.