This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D4794 - 94 (Reapproved 2009) D4794 - 94 (Reapproved 2017)

Standard Test Method for Determination of Ethoxyl or Hydroxyethoxyl Substitution in Cellulose Ether Products by Gas Chromatography¹

This standard is issued under the fixed designation D4794; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is applicable to the determination of ethoxyl or hydroxyethoxyl substitution in cellulose ether products by a Zeisel gas chromatographic technique.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety safety, health, and health environmental practices and determine the applicability of regulatory limitations prior to use. For specific hazard statements, see Section 5 and Note 3.

<u>1.4 This international standard was developed in accordance with internationally recognized principles on standardization</u> established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Summary of Test Method

2.1 When a cellulose ether containing ethyl or hydroxyethyl substitutes is allowed to react with hydriodic acid, one mole of iodoethane is liberated for each mole of ethoxyl or hydroxyethoxyl ether substituted on the cellulose chain. The iodoethane is extracted in situ with σ -xylene o-xylene and quantitated by gas chromatography using an internal standard technique. It is recommended to run duplicate samples.

3. Apparatus

3.1 Gas Chromatograph with thermal conductivity detector and heated injection port.

3.2 *Electronic Integrator.*

3.3 *Column*—stainless steel, 1829 mm in length, 3.2 mm in outside diameter, packed with the reagent in 4.6, coiled to fit the chromatograph used; or equivalent column and packing as appropriate.

3.4 Syringe, 10 µL.

3.5 Reaction Vials, Caps, and Heating Block.²

3.6 Syringe, 100 µ L.

3.7 Cover, stainless steel, fabricated to cover the heating block.

4. Reagents and Materials


4.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

¹This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.36 on Cellulose and Cellulose Derivatives.

Current edition approved Feb. 1, 2009Dec. 1, 2017. Published February 2009December 2017. Originally approved in 1988. Last previous edition approved in 20032009 as D4794 – 94 (2003). (2009). DOI: 10.1520/D4794-94R09.10.1520/D4794-94R17.

² The sole source of supply of a heating block, Silli-Therm Heating Module, Reacti-Block 21, Reacti-Vials, and Minnert valve tops, known to the committee at this time is the Pierce Chemical Company P.O. Box 117, Rockford, IL 61105–9976. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

³ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see Analar Standards for Laboratory Chemicals, BDH Ltd., Poole, Dorset, U.K., and the United States Pharmacopeia and National Formulary, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.



4.2 Iodoethane, 99 % minimum.

4.3 O-xylene.

4.4 Toluene.

4.5 Hydriodic Acid, 57 % (sp gr 1.69 to 1.70).

4.6 *Column Packing*, 10 % methyl silicone stationary phase USP code [G1] coated on inert diatomite solid support USP code [S1A], 100/120 mesh.

5. Hazards

5.1 Safety precautions must be taken for handling of hydriodic acid.

5.2 During the reaction, the glass vials are under pressure. Exercise precaution in handling the hot vials.

6. Apparatus Preparation and Conditioning

6.1 *Column* (Note 1)—Columns are packed with reagent under vacuum and mechanical vibration using silanized glass wool to contain the packing. Install each in the gas chromatograph to facilitate on column injection. Condition the column at 200°C for 12 h, then allow it to come to equilibrium under the conditions described below:in the following table:

Oven temperature, °C	130 isothermal
Injection port temperature, °C	200
Detector temperature, °C	250
Detector current, ma	175 ma
Attenuation	1
Polarity	А
Carrier gas	helium
Column A, mL/min	30
Column B. mL/min	30

NOTE 1—The conditions used here were determined to be optimum for the column. Optimum conditions should be determined for each column on an individual basis.



NOTE 2—These settings were used with a Hewlett-Packard 3390A Integrator. Other units may require different settings.

6.2.2 Approximate Component Retention Times: /8e829681-239a-4931-ab09-183223712e6f/astm-d4794-942017

Relative Retention Time	Component
0.38	iodoethane
0.59	toluene (internal standard)
1.00	o-xylene

7. Preparation of Standard Solutions

- 7.1 Internal Standard Solution (25 mg toluene/mL o-xylene):
- 7.1.1 Weigh 25.00 \pm 0.01 g of toluene into a 1000-mL volumetric flask.
- 7.1.2 Dilute with o-xylene to 1000 mL.
- 7.2 Calibration Standard Solution:
- 7.2.1 Pipet 2.0 mL of 57 % hydriodic acid into a 5-mL vial.
- 7.2.2 Pipet 2.0 mL of the internal standard solution (prepared in 7.1) into the vial and seal with the mininert valve.
- 7.2.3 Weigh the vial and contents to the nearest 0.1 mg.
- 7.2.4 Add 50 µL of iodoethane to the vial with a syringe.
- 7.2.5 Weigh and record the amount of iodoethane added.

7.2.6 Shake for 30 s and allow to stand for 20 minutes.

8. Calibration of Electronic Integrator

8.1 Inject 1.0 μ L of the upper solvent layer of the standard solution prepared in 7.2 into the gas chromatograph and record the chromatogram.