



Designation: **D5869 – 07a (Reapproved 2013) D5869/D5869M – 07a (Reapproved 2018)^{ε1}**

Standard Practice for Dark Oven Heat Exposure of Roofing and Waterproofing Materials¹

This standard is issued under the fixed designation **D5869/D5869M**; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Units information was editorially corrected in January 2018.

1. Scope

1.1 This practice establishes a procedure and conditions of temperature and time for heat exposure of roofing and waterproofing materials and systems in the presence of air.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. The values given in parentheses are for information only. Values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D883 Terminology Relating to Plastics

D1079 Terminology Relating to Roofing and Waterproofing

D1566 Terminology Relating to Rubber

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

E230/E230M Specification and for Temperature-Electromotive Force (EMF)(emf) Tables for Standardized Thermocouples

E1137/E1137M Specification for Industrial Platinum Resistance Thermometers

E2251 Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids

3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice, refer to Terminologies D883, D1079, and D1566.

4. Summary of Practice

4.1 Specimens of roofing and waterproofing materials are exposed to heat in a dark forced-ventilation oven at a specified elevated temperature for a known period of time.

4.2 This practice specifies an exposure temperature of $70 \pm 3^\circ\text{C}$ ($158 \pm 5^\circ\text{F}$) in a forced-ventilation oven.

4.3 This practice permits the selection of the duration of heat exposure from three specified time periods, which are 35, 90, and 180 ± 0.25 consecutive days. The duration selected must be included in any report of results obtained by using this practice.

NOTE 1—The time period to be used should be specified in any standard that refers to this practice. European standards for polymer-modified

¹ This practice is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Steep Roofing Products and Assemblies.

Current edition approved May 1, 2013; Jan. 1, 2018. Published May 2013; January 2018. Originally approved in 1995. Last previous edition approved in 2007 as D5869 – 07a; D5869 – 07a (2013). DOI: 10.1520/D5869-07AR13; 10.1520/D5869_D5869M-07AR18E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.