



Designation: G 113 – 01

Standard Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials¹

This standard is issued under the fixed designation G 113; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology standard covers terms that relate to the durability testing of Nonmetallic Materials using natural and artificial weathering exposure techniques.

1.2 It is the intent of this terminology standard to include those weathering terms in wide use in ASTM for which standard definitions appear desirable.

2. Referenced Documents

2.1 ASTM Standards:

D 9 Terminology Relating to Wood²

E 41 Terminology Relating to Conditioning³

E 284 Terminology of Appearance⁴

E 349 Definitions of Terms Relating to Space Simulation⁵

E 456 Terminology Relating to Quality and Statistics⁶

E 772 Terminology Relating to Solar Energy Conversion⁷

E 973M Practice for the Determination of the Spectral Mismatch Parameter between a Photovoltaic Device and a Photovoltaic Reference Cell [Metric]⁷

G 84 Practice for Measurement of Time-of-Wetness on Surfaces Exposed to Wetting Conditions as in Atmospheric Corrosion Testing⁸

G 90 Practice for Performing Accelerated Outdoor Weathering of Nonmetallic Materials Using Concentrated Natural Sunlight³

2.2 AATCC Method:⁹

16 Colorfastness to Light

2.3 ANSI Standards:¹⁰

ANSI/NCSL Z540-2-1997 American National Standard for Expressing Uncertainty—U.S. Guide to the Expression of Uncertainty in Measurement

3. Significance and Use

3.1 This terminology is not intended to supersede the requirements of similar definitions in certain other documents, but is intended to provide a listing of terms that are in current widespread usage, and their context in relation to weathering.

4. Terminology

4.1 Definitions:

accelerated outdoor weathering, *n*—outdoor weathering using the sun as the source of irradiance, and where the rate of deterioration is accelerated over that of the in-service exposure position increasing one or more of the influencing parameters.

actinic radiation, *n*—the spectral region(s) of a light source responsible for the photodegradation of a particular material.

ambient temperature, *n*—the existing temperature of the air or of an object in thermal equilibrium with the surrounding atmosphere.

azimuth angle, *n*—an angle of a plane to the horizon measured clockwise to the object.

backed exposure, *n*—a technique of weathering in which the test specimens being exposed are mounted onto a solid backing material, of sufficient strength to hold the specimen. When the specimen and the backing are in direct contact the backing material must be of a type that will not contaminate the specimen. When two materials are intimately joined together to form one composite, the materials below the top surface are not considered as a backing.

DISCUSSION—The backing is typically plywood which has the effect of increasing specimen temperature and wet time during exposure, compared to exposure unbacked.

black box, *n*—a thin metal box painted flat black on the

¹ This guide is under the jurisdiction of ASTM Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.92 on Terminology.

Current edition approved July 10, 2001. Published September 2001. Originally published as G 113 – 92. Last previous edition G 113 – 94.

² Annual Book of ASTM Standards, Vol 04.10.

³ Annual Book of ASTM Standards, Vol 06.01.

⁴ Annual Book of ASTM Standards, Vol 14.04.

⁵ Annual Book of ASTM Standards, Vol 15.03.

⁶ Annual Book of ASTM Standards, Vol 14.02.

⁷ Annual Book of ASTM Standards, Vol 12.02.

⁸ Annual Book of ASTM Standards, Vol 03.02.

⁹ Available from American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709.

¹⁰ Available from National Conference of Standards Laboratories, 1800 30th St., Suite 305B, Boulder, CO 80301.



outside only exclusive of the bottom surface with an open top where the flat test specimens to be exposed constitute the top surface of the box; the box is equipped with mounting strips to hold the test specimens firmly in place; the top surface of the box must be completely filled at all times; any blank spaces on the top surface must be occupied by flat black “dummy” panels to maintain correct operating condition.

black box under glass, *n*—a glass covered enclosure or cabinet of any convenient size. It shall be constructed of corrosion resistant metal and be enclosed to prevent ambient air from circulating over the samples. Exterior non-glass surfaces shall be painted black. The interior shall remain unpainted.

black panel thermometer, *n*—a temperature measuring device consisting of a metal panel, having a black coating which absorbs all wavelengths uniformly, with a thermal sensitive element firmly attached to the center of the exposed surface. The black panel thermometer is used to control an artificial weathering device and to provide an estimate of the maximum temperature of samples exposed to a radiant energy source.

climatological types, *n*—major regions of significantly different recurring weather patterns. In weathering, several distinct climatological types are used to evaluate the atmospheric durability of materials. Within any single climatological variation, at a specific geographic location, short term weather patterns may fluctuate significantly. This may cause variability in short term exposures. Major climatic variations that are used for the study of weathering are:

warm, moist climate—subtropical climate distinguished as warm and humid year round, with frequent rain showers.

hot, dry climate—desert climate distinguished as sunny, hot, and dry year round, with rare scattered showers.

control, *n*—in weathering, the term control has three current widespread uses:

1. A material which is of similar composition and construction to the test material used for comparison, exposed at the same time.

DISCUSSION—A reference material can often be used as the control.

2. A portion of the material to be tested which is stored under conditions in which it is stable, and is used for comparison between exposed and original state.

DISCUSSION—This definition is deprecated in favor of “File Specimen.”

3. A portion of the exposed specimen which is protected from light exposure by masking.

DISCUSSION—This definition is deprecated in favor of “Masked Area.”

daylight, *n*—total (global) hemispherical solar radiation. See also **solar irradiance, global**

direct weathering, *n*—a technique of weathering in which the test specimens are exposed to all prevailing elements of the atmosphere.

dry-bulb temperature, *n*—the temperature of the ambient air; for example, the temperature that is measured by the dry-bulb thermometer of a psychrometer. **D 4023**

durability, *n*—in weathering, a measure of the retention of original condition and function of a material after exposure

to a specified set of conditions.

enclosed carbon arc, *n*—a light source in which an arc is produced across a pair of carbon rods by a high energy electrical source, such that a high intensity light is emitted. The carbons are enclosed in an inverted glass dome which acts to prolong the life of the carbons, and to modify the spectral power distribution received by the specimens.

exposure, *n*—the act of subjecting the test specimen to the test conditions.

exposure angle, *n*—the tilt from horizontal of the test specimen or any other exposed material, or both.

fading unit (AATCC), *n*—a specific amount of exposure made under the conditions specified in various test methods where one Fading Unit is one-twentieth ($\frac{1}{20}$ th) of the exposure required to produce a color change equal to Step No. 4 on the Gray Scale for Color Change or 1.7 ± 0.3 CIELAB units of color difference on Blue Wool Lightfastness Standard L 4 or 20 ± 1.7 CIELAB units of color difference on the Xenon Reference Fabric or combination thereof.

AATCC Technical Manual

file specimen, *n*—portion of the material to be tested which is stored under conditions in which it is stable, and is used for comparison between exposed and original state.

fluorescent ultraviolet lamp, *n*—a lamp in which the irradiance from a low pressure mercury arc is transformed to a longer wavelength UV radiation by a phosphor; the spectral power distribution of a fluorescent lamp is determined by the emission spectrum of the phosphor and the UV transmittance of the glass tube.

fresnel-reflector system, *n*—flat mirrors arranged in an array such that they reflect onto a target, the illuminated area of which simulates the size and shape of the flat mirror. Such an array simulates the ray-tracing of a parabolic trough of the same aperture angle. **G 90**

gray scale, *n*—the scale consists of nine pairs of standard gray chips each pair representing a difference in color or contrast (shade and strength) corresponding to a numerical fastness rating. The results of colorfastness tests are rated by visually comparing the difference in color represented by the scale.

AATCC Technical Manual

irradiance, *n*—the radiant power per unit area incident on a receiver, typically reported in watts per square metre, $W m^{-2}$

E 973

masked area, *n*—a portion of the exposed specimen which is protected from light exposure by masking. (See also **control**.)

DISCUSSION—The mask area is not protected from heat and moisture.

natural weathering, *n*—outdoor exposure of materials to unconcentrated sunlight, the purpose of which is to assess the effects of environmental factors on various functional and decorative parameters of interest.

open flame sunshine carbon arc, *n*—a light source in which an arc is produced across a pair of copper coated carbon rods filled with rare earth elements intended to produce a specific spectral power distribution. The carbons are open to the atmosphere and may be surrounded by a glass lantern