



Designation: ~~D2805 – 11~~ **D2805 – 11 (Reapproved 2018)**

Standard Test Method for Hiding Power of Paints by Reflectometry¹

This standard is issued under the fixed designation D2805; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

INTRODUCTION

Using equations derived from Kubelka-Munk turbid media theory (**1-4**)² (see **Annex A1**), the reflectance of a coating can be predicted for any film thickness from measurements made at only one. On this basis several rapid and accurate test methods (**5**, **6**) have been developed for determining hiding power. In the past such test methods have been considered difficult due to complexities, apparent and actual, in the treatment of data. The present test method has been simplified in this respect, primarily by adapting it fully for computer calculations.

Although the use of broad-band reflectometry makes this test method theoretically valid only for nonchromatic (white or gray) colors, good agreement has been obtained with chromatic paints as well. This is undoubtedly because the experimental measurements are made fairly close to the hiding power end point so that the Kubelka-Munk extrapolation and thus any associated error is relatively small.

This test method is therefore recommended without restriction as to color.

1. Scope

1.1 This test method covers the determination, without reference to a material paint standard, of the hiding power of air dry coatings with *Y tristimulus values greater than 15 %*. *With appropriate modification, it can also be used to test baking finishes.*

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*³

D344 Test Method for Relative Hiding Power of Paints by the Visual Evaluation of Brushouts

D1475 Test Method for Density of Liquid Coatings, Inks, and Related Products

D3924 Specification for Standard Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials (Withdrawn 2016)⁴

E284 Terminology of Appearance

E1247 Practice for Detecting Fluorescence in Object-Color Specimens by Spectrophotometry

E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry

E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

¹ This test method is under the jurisdiction of ASTM Committee **D01** on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee **D01.26** on Optical Properties.

Current edition approved ~~June 1, 2011~~ Feb. 1, 2018. Published ~~June 2011~~ February 2018. Originally approved in 1969. Last previous edition approved in ~~2003~~ 2011 as ~~D2805 – 96a (2003)~~ D2805 – 11. DOI: ~~10.1520/D2805-11~~ 10.1520/D2805-11R18.

² The boldface numbers in parentheses refer to the list of references at the end of this standard.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

E1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry

3. Terminology

3.1 *Definitions*—For definitions used in this test method, see Terminology **E284**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *contrast ratio, n*—the ratio of the reflectance of a film on a black substrate to that of an identical film on a white substrate.

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ASTM D2805-11\(2018\)](#)

<https://standards.itih.ai/catalog/standards/sist/4ba35a12-38d5-4260-bdaa-49bbcc6b096e/astm-d2805-112018>

3.2.1.1 C_w , n —the contrast ratio with a white substrate of reflectance W .

$$\text{Thus: } C_w = R_0/R_w$$

3.2.1.2 C , n —the contrast ratio with a white substrate for which $W = 0.80$.

$$\text{Thus: } C = R_0/R_{0.80}$$

3.2.2 *reflectance, n* —the daylight luminous diffuse reflectance factor (specular reflection excluded). Also referred to in this test method as the Y -tristimulus value. This value may be expressed as a percent or a decimal fraction, the latter being preferred and usually required for mathematical calculations.

3.2.2.1 *reflectivity, R_∞ , n* —the reflectance of film thick enough to have the same reflectance over both a black and a white substrate.

3.2.2.2 R_0 , n —the reflectance of a film on a black surface with a reflectance of 1 % or less, which is effectively zero for the purpose of this test.

3.2.2.3 W , n —the reflectance of a white substrate.

3.2.2.4 R_w , n —the reflectance of a film applied on a white substrate of reflectance W .

3.2.2.5 $R_{0.80}$, n —the reflectance of a film applied on a substrate having a reflectance of 80 %, which is the standard white-substrate reflectance in paint technology.

3.2.3 *scattering coefficient, S , n* —the ability of a material to internally scatter and thereby reflect light; expressed in this test method in the same units as spreading rate.

3.2.4 *spreading rate, H , n* —film area per unit volume of coating, in this test method expressed in square metres per litre (m^2/L).

3.2.4.1 *spreading rate, H_x , n* —an experimentally determined value of H .

3.2.4.2 *spreading rate, H_C , n* —value of H at a specified contrast ratio C .

3.2.4.3 *hiding power, $H_{0.98}$, n* —the spreading rate at the contrast ratio $C = 0.98$.

NOTE 1—It should be emphasized that a contrast ratio of 0.98 does not represent visually complete hiding, nor does it indicate that the same contrast ratio holds at every wavelength.

4. Summary of Test Method

4.1 The reflectivity R_∞ of the coating is determined from reflectance measurements on black and white hiding power charts.

4.2 The scattering coefficient S of the coating is determined from R_∞ , and the reflectance R_0 and spreading rate H_x of a film applied on black glass.

4.3 The hiding power, $H_{0.98}$ of the coating is calculated from the reflectivity R_∞ and the scattering coefficient S .

4.4 As an optional procedure the contrast ratio C at a specified spreading rate H_C is calculated from R_∞ and S .

5. Significance and Use

5.1 This is a precise instrumental method giving results having an absolute physical significance without reference to a comparison paint. It should be used when maximum precision and minimum subjectivity are required, as in testing specification coatings or evaluating the hiding efficiency of pigments.

5.2 Hiding power Test Method D344 is visual instead of instrumental, and gives results that are relative to a material standard instead of absolute. It is less precise than Test Method D2805 but more closely aligned with practical painting procedures.

6. Apparatus and Materials

6.1 *Substrates:*

6.1.1 *Black Glass Panels*, minimum size 200 by 200 mm, and approximately 6-mm thick.

6.1.2 *Black and White Paper Charts*—The surface shall be smooth and level, and impervious to paint liquids. The black area shall have a maximum reflectance of 1 % and the white area a minimum reflectance of 78 %. The white area shall be non-fluorescent, as observed visually under ultra-violet illumination, or determined in accordance with Practice E1247.

6.2 *Balance*, accurate to 0.1 mg.

6.3 *Glass Slides*—Round or square plates of thickness similar to that used for microscope specimen slides, with a minimum area of 40 cm^2 .

6.4 *Reflectance-Measuring Instrument*⁵—One that allows only diffusely reflected, radiant flux to be incident upon the measuring element. It shall employ a photometric system, including source, filters, and receptor, that provides a response closely similar to

⁵ Conforming with Test Methods E1331, E1347, or E1349. Other methods for measuring the CIE- Y tristimulus value (specular reflection excluded) are permissible.

the product of the spectral luminous efficiency function of the CIE standard observer and source *C*. It shall provide readings to at least the third decimal place and permit estimation to the fourth.

6.5 *Template*,⁶ with a film area approximately 100 cm² determined to the nearest tenth. Record the exact value on Line *C* of the worksheet shown in Fig. 1.

6.6 *Doctor Blade Film Applicators*, width 150 mm, clearances 50, 75, 100, 125, 150, 175, and 200 μm.

6.7 *Computer and Software*, for solving the relevant Kubelka-Munk equations.

7. Procedure

7.1 *General Instructions:*

7.1.1 *Film Application*—Make drawdowns manually with a smooth uniform motion, at the rate of about 6 cm/s. Hold paper charts flat by a vacuum plate or other suitable device while making drawdowns.

- A. Paint Density, *D*: _____ g/mL
- B. Nonvolatile Content, *N*: _____ (decimal fraction)
- C. Template Film Area, *A*: _____ cm²
- D. Drawdowns on Charts:

Chart	<i>R</i> ₀	<i>R</i> _w	<i>W</i>	<i>C</i> _w	<i>R</i> _∞
1					
2					
3					
4					
Mean	—	—	—		

$C_w = R_0/R_w$ $R_\infty = f(R_0, R_w, W)$ Eq A1.1 of Annex A1

- E. Drawdowns on Galss:

Panel	<i>R</i> ₀	<i>M</i> , g	<i>H</i> _x , m ² /L	<i>S</i> , m ² /L	<i>H</i> _{0.98} , m ² /L
1					
2					
3					
4					
Mean	—	—	—		

$H_x = \frac{AND}{10M} = \bar{M}$ $S = f(R_0, R_\infty, H_x)$ Eq A1.2 of Annex A1
 $H_{0.98} = f(S, C, R_\infty)$ where $C = 0.98$ Eq A1.3 of Annex A1

- G. Report

- (1) Hiding power *H*_{0.98} _____ m²/L _____ ft²/gal
- (2) Reflectivity, *R*_∞ _____
- (3) Scattering coefficient, *S* _____ m²/L
- (4) Applicator clearance _____ μm _____ mils
- (5) Contrast ratio, *C*_w _____
- (6) Sample identification
 - Type of paint _____ Color _____
 - Formula No. _____ Batch or sample No. _____
- (7) Reflectometer description
 - Manufacturer _____ Model name _____
 - Model No. _____ Type _____
 - Geometry _____ Aperture _____

- H. Alternative Hiding Power Report:

- Specified spreading rate, *H* _____ m²/L _____ ft²/gal
- Contrast ratio, *C* _____

FIG. 1 Work Sheet Form

⁶ The sole source of supply of the template known to the committee at this time is Paul Gardner Co., 316 N. E. First St., Pompano Beach, FL 33061. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.