



Designation: C478M – 18

Standard Specification for Circular Precast Reinforced Concrete Manhole Sections (Metric)¹

This standard is issued under the fixed designation C478M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

PART I—GENERAL

1. Scope

1.1 This specification covers the manufacture and purchase requirements of products used for the assembly and construction of circular vertical precast reinforced concrete manholes and structures used in sewer, drainage, and water works.

1.2 Part I, Sections 1 – 11, of this specification presents general requirements and requirements which are common to each precast concrete product covered by this specification.

1.3 Part II of this specification presents specific requirements for each manhole product in the following sections:

Product	Section
Grade Rings	12
Flat Slab Tops	13
Risers and Conical Tops	14
Base Sections	15
Steps and Ladders	16

NOTE 1—Future products will be included in Part II in a future revision of this specification.

1.4 This specification is the SI companion to C478.

NOTE 2—This specification is a manufacturing and purchase specification only, and does not include requirements for backfill, or the relationship between field load conditions and the strength requirements of the manhole products and appurtenances. Experience has shown, however, that the successful performance of this product depends upon the proper selection of the product strength, type of foundation and backfill, and care in the field installation of the manhole products and connecting pipes. The owner of the project for which these products are specified herein is cautioned to require inspection at the construction site.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.06 on Manholes and Specials.

Current edition approved Jan. 1, 2018. Published January 2018. Originally approved in 1980. Last previous edition approved in 2015 as C478M – 15a. DOI: 10.1520/C0478M-18.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement
- A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement
- A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete
- C33/C33M Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
- C150/C150M Specification for Portland Cement
- C260/C260M Specification for Air-Entraining Admixtures for Concrete
- C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete
- C494/C494M Specification for Chemical Admixtures for Concrete
- C497M Test Methods for Concrete Pipe, Manhole Sections, or Tile (Metric)
- C595/C595M Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C822 Terminology Relating to Concrete Pipe and Related Products
- C989/C989M Specification for Slag Cement for Use in Concrete and Mortars
- C1017/C1017M Specification for Chemical Admixtures for

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Use in Producing Flowing Concrete
C1116/C1116M Specification for Fiber-Reinforced Concrete
C1602/C1602M Specification for Mixing Water Used in the
 Production of Hydraulic Cement Concrete

2.2 *ACI Standard:*

ACI 318 Building Code, Requirements for Reinforced Concrete³

3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology **C822**.

4. Materials and Manufacture

4.1 General material requirements for precast reinforced concrete manhole products are presented in **4.1.1 – 4.1.9**. Other materials or additional requirements for a product, if any, are covered in the Part II section for that specific product.

4.1.1 *Reinforced Concrete*—Reinforced concrete shall consist of cementitious materials, mineral aggregates, admixtures, if used, and water, in which steel reinforcement has been embedded in such a manner so that the steel reinforcement and concrete act together.

4.1.2 *Cementitious Materials:*

4.1.2.1 *Cement*—Cement shall conform to the requirements for portland cement of Specification **C150/C150M**, or shall be portland blast-furnace slag cement, portland-limestone cement, or portland-pozzolan cement conforming to the requirements of Specification **C595/C595M**, except that the pozzolan constituent of the Type IP portland-pozzolan cement shall be fly ash.

4.1.2.2 *Fly Ash*—Fly ash shall conform to the requirements of Class F or Class C of Specification **C618**.

4.1.2.3 *Slag Cement*—Slag cement shall conform to the requirements of Grade 100 or 120 of Specification **C989/C989M**.

4.1.3 *Allowable Combinations of Cementitious Materials*—The combination of cementitious materials used in the concrete shall be one of the following:

- 4.1.3.1 Portland cement only,
- 4.1.3.2 Portland blast-furnace slag cement only,
- 4.1.3.3 Portland-pozzolan cement only,
- 4.1.3.4 Portland-limestone cement only,
- 4.1.3.5 A combination of portland cement or portland-limestone cement and slag cement,
- 4.1.3.6 A combination of portland cement or portland-limestone cement and fly ash,
- 4.1.3.7 A combination of portland cement or portland-limestone cement, slag cement, and fly ash, or
- 4.1.3.8 A combination of portland-pozzolan cement and fly ash.

4.1.4 *Aggregates*—Aggregates shall conform to Specification **C33/C33M**, except that the requirements for gradation shall not apply.

4.1.5 *Admixtures*—The following admixtures and blends are allowable:

4.1.5.1 Air-entraining admixture conforming to Specification **C260/C260M**;

4.1.5.2 Chemical admixture conforming to Specification **C494/C494M**;

4.1.5.3 Chemical admixture for use in producing flowing concrete conforming to Specification **C1017/C1017M**;

4.1.5.4 Chemical admixture or blend approved by the owner.

4.1.6 *Steel Reinforcement*—Reinforcement shall consist of wire and welded wire conforming to Specification **A1064/A1064M**; or of bars conforming to Specification **A615/A615M**, Grade 280 or 420, or Specification **A706/A706M**, Grade 420.

4.1.7 *Water*—Water used in the production of concrete shall be potable or non-potable water that meets the requirements of Specification **C1602/C1602M**.

4.1.8 *Fiber*—Synthetic fibers and nonsynthetic fibers shall be allowed to be used, at the manufacturer's option, in concrete manholes as a nonstructural manufacturing material. Synthetic fibers (Type II and Type III) and nonsynthetic fiber (Type 1) designed and manufactured specifically for use in concrete and conforming to the requirements of Specification **C1116/C1116M** shall be accepted.

4.1.9 *Other Materials*—Other materials required for a product and not covered in Section 4 will be covered in the Part II section for that specific product.

5. Design

5.1 Design requirements for a product are prescribed in the specific Part II section for that product.

5.1.1 The minimum compressive strength of concrete manhole products covered by this specification shall be 27.6 MPa unless specified otherwise in Part II of this specification.

5.2 Modified or Special Design:

5.2.1 Manufacturers are not prohibited from submitting to the owner, for approval prior to manufacture, designs other than those prescribed in the specific section for a product. If such approval is obtained, then the product shall meet all the tests and performance requirements specified by the owner in accordance with the appropriate sections on manufacture and physical requirements.

5.2.2 If permitted by the owner, the manufacturer is not prohibited from requesting approval of designs of special sections, such as reducers, tees, and bases.

6. Reinforcement

6.1 This section presents requirements for reinforcement cover, continuity, laps, welds and splices. Other reinforcement requirements are presented in Section 4 and any additional requirements are given in the Part II section for a specific product.

6.2 *Cover*—The exposure of the ends of reinforcement, stirrups or spacers used to position the reinforcement during placement of the concrete shall not be cause for rejection.

6.3 *Continuity*—The continuity of the circumferential reinforcement shall not be destroyed during the manufacture of the product, except when lift holes or pipe openings are provided in the product.

³ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.aci-int.org>.

6.4 *Welded Steel Cage Laps, Welds, and Splices:*

6.4.1 If splices are not welded, the reinforcement shall be lapped not less than 20 diameters for deformed bars, and 40 diameters for plain bars and cold-drawn wire. In addition, where lapped cages of welded wire fabric are used without welding, the lap shall contain a longitudinal wire.

6.4.2 When splices are welded and are not lapped to the minimum requirements in 6.4.1, there shall be a minimum lap of 50 mm and a weld of sufficient length such that pull tests of representative specimens shall develop at least 50 % of the minimum specified tensile strength of the steel. For butt welded splices in bars or wire, permitted only with helically wound cages, pull tests of representative specimens shall develop at least 75 % of the minimum specified tensile strength of the steel.

6.5 *Steel Hoop Splices*—When splices are welded and not lapped to the minimum requirements in 6.4.1, there shall be a minimum lap of 50 mm and a weld of sufficient length such that pull tests from representative specimens shall develop at least 50 % of the minimum specified tensile strength of the steel. For butt welded splices, pull tests from representative specimens shall develop at least 75 % of the minimum specified tensile strength of the steel.

7. Precast Concrete Manufacture

7.1 *Mixture*—The aggregates shall be sized, graded, proportioned, and mixed with such proportions of cementitious materials and water as will produce a thoroughly-mixed concrete of such quality that the products will conform to the test and design requirements of this specification. All concrete shall have a water-cementitious ratio not exceeding 0.53 by mass. Cementitious materials shall be as specified in 4.1.2 and shall be added to the mix in a proportion not less than 280 kg/m³, unless mix designs with a lower cementitious materials content demonstrate that the quality and performance of the product meet the requirements of this specification.

7.2 *Curing*—Concrete products shall be subjected to any one of the methods of curing prescribed in 7.2.1 – 7.2.4 or to any other method or combination of methods approved by the owner that will give satisfactory results.

7.2.1 *Steam Curing*—Concrete products are placed in a curing chamber, free of outside drafts, and cured in a moist atmosphere maintained by the injection of steam for such time and such temperatures as may be needed to enable the products to meet the strength requirements. The curing chamber shall be so constructed as to allow full circulation of the steam around the entire product.

7.2.2 *Water Curing*—Concrete products are water-cured by covering with water-saturated material, or by a system of perforated pipes, mechanical sprinklers, porous hose, or by any other approved method that will keep the products moist during the curing period.

7.2.3 *Sealing Membrane*—A sealing membrane conforming to the requirements of Specification C309 is applied and shall be left intact until the required concrete strength requirements are met. The concrete at the time of application of the membrane shall be within 6°C of the atmospheric temperature.

All concrete surfaces shall be kept moist prior to the application of the membrane and shall be damp when the membrane is applied.

7.2.4 The manufacturer is not prohibited from combining methods prescribed in 7.2.1 – 7.2.3 provided the required concrete compressive strength is attained.

8. Acceptance

8.1 *Acceptance Procedures:*

8.1.1 Unless otherwise designated by the owner at the time of, or before, placing an order, acceptance procedures for precast reinforced concrete manhole products shall be as specified in the Part II section for a particular product, and shall not be prohibited from consisting of one or more of the following:

8.1.1.1 Acceptance of a product on the basis of tests of materials, including concrete compressive strength and absorption.

8.1.1.2 Acceptance of a product on the basis of inspection of the finished product, including amount and placement of reinforcement to determine conformance with the design prescribed under this specification, and freedom from defects.

8.2 *Test Methods:*

8.2.1 *Concrete Compressive Strength Test:*

8.2.1.1 *Type of Specimen*—Compression tests for satisfying the minimum specified concrete strength requirement shall be made on either concrete cylinders or, at the option of the manufacturer, on cores cut from the concrete manhole product.

8.2.1.2 *Compression Testing of Cylinders*—Cylinders shall be made in accordance with Test Methods C497M, and shall be tested in accordance with Test Method C39/C39M. For manhole products, an owner shall not be prohibited from requiring concrete compressive tests on cylinder specimens numbering in the amount of 5 % of the total order of a manhole product, but not to exceed two cylinders for each day's production. The average compressive strength of all cylinders tested shall be equal to or greater than the specified strength of the concrete. Not more than 10 % of the cylinders tested shall fall below the specified strength of the concrete. In no case shall any cylinder tested fall below 80 % of the specified strength of the concrete.

8.2.1.3 *Compression Testing of Cores*—Cores shall be cut from the concrete manhole product and tested in accordance with Test Methods C497M, except that the requirements for moisture conditioning shall not apply. One core shall be taken from a manhole product selected at random from each day's production run of a single concrete strength. When the concrete compressive strength of the core is equal to or greater than 80 % of the specified strength of the concrete, the concrete strength of the production run is acceptable. If the core does not meet the preceding concrete strength requirement, another core from the same manhole product may be taken and tested.

8.2.1.4 If the concrete compressive strength of the recore is equal to or greater than 80 % of the specified strength of the concrete, the concrete strength of the production run is acceptable. If the recore does not meet the preceding concrete strength requirement, that manhole product shall be rejected. Two manhole products from the remainder of the day's production run shall be selected at random and one core taken

from each manhole product and tested. When the average concrete strength of the two cores is equal to or greater than 80 % of the specified strength of the concrete with no core below 75 % of the specified strength of the concrete, the concrete strength of the day's production run shall be acceptable.

8.2.1.5 If the concrete strength of the two cores does not meet the preceding concrete strength requirement, then the remainder of the day's production run shall be either rejected, or, at the option of the manufacturer, each manhole product of the remainder of the day's production run is not prohibited from being cored and accepted individually.

8.2.1.6 *Plugging Core Holes*—Core holes on accepted manhole sections shall be plugged and sealed by the manufacturer in a manner such that the manhole products will meet all of the requirements of this specification. Manhole sections so sealed shall be considered as satisfactory for use.

8.2.2 *Absorption Test:*

8.2.2.1 The absorption of a specimen from a concrete product, as determined in Test Methods C497M, shall not exceed 9 % of the dry mass for Test Method A procedure or 8.5 % for Test Method B procedure. All specimens shall be free of visible cracks and shall represent the full thickness of the product.

8.2.2.2 Specimens for Test Method B shall meet the requirements of Test Methods C497M.

8.2.2.3 Each specimen tested by Test Method A shall have a minimum mass of 1.0 kg.

8.2.2.4 When the initial absorption specimen from a concrete product fails to conform to this specification, the absorption test shall be made on another specimen from the same product and the results of the retest shall be substituted for the original test results.

8.2.3 *Retests*—When not more than 20 % of the concrete test specimens tested under either 8.2.2.1 or 8.2.2.2 fail to pass the requirements of this specification, the manufacturer is not prohibited from culling his stock and eliminating whatever quantity of product he desires and shall so mark the culled product that they will not be shipped for the order. The required tests shall be made on the balance of the order and the products shall be accepted if in conformance with the requirements of this specification.

8.3 *Test Equipment*—Every manufacturer furnishing manhole products under this specification shall furnish all facilities and personnel necessary to carry out the tests required for acceptance.

9. Repairs

9.1 Repair of manhole products shall not be prohibited, if necessary, because of imperfections in manufacture or damage during handling, and will be acceptable if, in the opinion of the owner, the repaired products conform to the requirements of this specification.

10. Inspection

10.1 The quality of materials, the process of manufacture, and the finished manhole products shall be subject to inspection and approval by the owner.

11. Product Marking

11.1 The following information shall be legibly marked on each precast concrete product:

11.1.1 Specification and product designation: MH for manhole base, riser, conical tops, and grade rings,

11.1.2 Date of manufacture, and

11.1.3 Name or trademark of the manufacturer.

11.2 Marking shall be indented into the concrete or shall be painted thereon with waterproof paint.

PART II—PRODUCTS

12. Grade Rings

12.1 *Scope*—This section covers precast reinforced concrete grade rings used for final adjustment of manholes to grade.

12.2 *Acceptance*—Acceptability of grade rings covered by this specification shall be determined by the results of such tests of materials as are required by Section 4; by compressive strength tests on concrete cores or concrete cylinders required by Section 8; and by inspection of the finished product, including amount and placement of reinforcement as prescribed by 12.4, 12.5 and 12.6, to determine its conformance with the design prescribed under this specification and its freedom from defects.

12.3 *Design*—The minimum wall thickness shall be one twelfth of the internal diameter of the grade ring or 100 mm, whichever is greater.

12.3.1 *Joints*—Grade rings are not required to have the joint formed with male and female ends.

12.4 *Circumferential Reinforcement:*

12.4.1 The circumferential reinforcement shall have an equivalent area of not less than 150 mm²/vertical m, but not less than 15 mm² in any one grade ring.

12.4.2 The circumferential reinforcement shall be one line in the center third of the wall of the grade ring.

12.5 *Permissible Variations:*

12.5.1 *Internal Diameter*—The internal diameter of grade rings shall not vary more than ± 1 %.

12.5.2 *Wall Thickness*—The wall thickness of grade rings shall be not less than that prescribed in the design by more than 5 % or ± 5 mm, whichever is greater. A wall thickness greater than that prescribed in the design shall not be cause for rejection.

12.5.3 *Height of Two Opposite Sides*—Variations in laying heights of two opposite sides of grade rings shall be not more than 6 mm.

12.5.4 *Height of Grade Ring*—The underrun in height of a grade ring shall be not more than 20 mm/m of height.

12.5.5 *Position of Reinforcement*—For grade rings with a 100-mm wall thickness, the maximum variation in the design position of circumferential reinforcement from that described in 12.4.1 shall be ± 10 % of the wall thickness or ± 6 mm, whichever is greater. For grade rings with a wall thickness greater than 100-mm, the maximum variation from the design position of reinforcement shall be ± 10 % of the wall thickness or ± 16 mm, whichever is the lesser. In no case, however, shall the cover over the reinforcement be less than 19 mm. The