



Designation: ~~A288 – 91 (Reapproved 2013)~~ A288 – 91 (Reapproved 2018)

Standard Specification for Carbon and Alloy Steel Forgings for Magnetic Retaining Rings for Turbine Generators¹

This standard is issued under the fixed designation A288; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers quenched and tempered carbon and alloy steel forgings for magnetic retaining rings for turbine generators.

1.2 Supplementary requirements of an optional nature are provided. These shall apply only when specified by the purchaser.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A275/A275M Practice for Magnetic Particle Examination of Steel Forgings](#)

[A531/A531M Practice for Ultrasonic Examination of Turbine-Generator Steel Retaining Rings](#)

[A788/A788M Specification for Steel Forgings, General Requirements](#)

3. Ordering Information

3.1 In addition to the ordering information required by Specification [A788/A788M](#), the purchaser shall include with the inquiry and order a detailed drawing, sketch, or written description of the forging, including the number and location of mechanical test specimens.

4. Manufacture

4.1 The melting processes of Specification [A788/A788M](#) shall be applicable except that the basic electric furnace process shall be used if separate refining or remelting is not employed.

4.2 *Vacuum Degassing*—For Class 3 machined forgings over 2½ in. (63.5 mm) wall thickness, and Classes 4 to 8, the molten steel shall be vacuum treated immediately prior to or during the operation of pouring the ingot in order to remove objectionable gases, especially hydrogen.

4.3 *Discard*—Sufficient discard shall be made from each ingot to secure freedom from piping and undue segregation.

4.4 *Heat Treatment:*

4.4.1 *Heat Treatment for Mechanical Properties*—Heat treatment for properties shall be by quenching and tempering.

4.4.2 *Tempering Temperature*—The final tempering temperature shall be not less than ~~400°F (595°C)~~ 1100 °F (595 °C).

4.5 *Machining:*

4.5.1 *Preliminary Machining*—Forgings shall be machined all over prior to quenching and tempering for mechanical properties.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved ~~June 1, 2013~~ March 1, 2018. Published ~~June 2013~~ March 2018. Originally approved in 1946. Last previous edition approved in ~~2008~~ 2013 as A288 – 91(2008)(2013). DOI: ~~10.1520/A0288-91R13~~ 10.1520/A0288-91R18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.