



Designation: F1314 – 18

# Standard Specification for Wrought Nitrogen Strengthened 22 Chromium–13 Nickel–5 Manganese–2.5 Molybdenum Stainless Steel Alloy Bar and Wire for Surgical Implants (UNS S20910)<sup>1</sup>

This standard is issued under the fixed designation F1314; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought nitrogen strengthened 22 chromium – 13 nickel – 5 manganese – 2.5 molybdenum stainless steel alloy bar and wire for surgical implants.

1.2 The SI units in this standard are the primary units. The values stated in either primary SI units or secondary inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of each other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

- [A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)
- [A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings](#)
- [A555/A555M Specification for General Requirements for Stainless Steel Wire and Wire Rods](#)
- [A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)
- [E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Feb. 1, 2018. Published March 2018. Originally approved in 1990. Last previous edition approved in 2013 as F1314 – 13a<sup>ε1</sup>. DOI: 10.1520/F1314-18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [E10 Test Method for Brinell Hardness of Metallic Materials](#)
- [E18 Test Methods for Rockwell Hardness of Metallic Materials](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- [E45 Test Methods for Determining the Inclusion Content of Steel](#)
- [E112 Test Methods for Determining Average Grain Size](#)
- [E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys](#)
- [E407 Practice for Microetching Metals and Alloys](#)
- [F138 Specification for Wrought 18Chromium-14Nickel-2.5Molybdenum Stainless Steel Bar and Wire for Surgical Implants \(UNS S31673\)](#)
- [F746 Test Method for Pitting or Crevice Corrosion of Metallic Surgical Implant Materials](#)
- [IEEE/ASTM SI 10 American National Standard for Metric Practice](#)
- 2.2 *Aerospace Materials Specification:*<sup>3</sup>
  - [AMS 2248 Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys](#)
  - [AMS 2630 Inspection, Ultrasonic Product Over 0.5 inch \(12.7 mm\) Thick](#)
  - [AMS 2632 Ultrasonic Inspection of Thin Materials](#)
- 2.3 *ISO Standards:*<sup>4</sup>
  - [ISO 6892 Metallic Materials Tensile Testing at Ambient Temperature](#)
  - [ISO 9001 Quality Management Systems—Requirements](#)

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *bar, n*—round bars and flats from 4.75 mm [0.1875 in.] to 101.60 mm [4.00 in.] in diameter or thickness (other sizes and shapes by special order).

<sup>3</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

3.1.2 *forging bar, n*—as described in 3.1.2 used for production of forgings, may be furnished in the hot rolled condition.

3.1.3 *lot, n*—the total number mill products produced under the same melt heat under the same conditions at essentially the same time.

3.1.4 *wire, n*—rounds less than 4.75 mm [0.1875 in.] in diameter.

**4. Ordering Information**

4.1 Inquiries and orders for material under this specification shall include the following information:

- 4.1.1 Quantity;
- 4.1.2 ASTM designation and date of issue;
- 4.1.3 Mechanical properties (if applicable for special conditions);
- 4.1.4 Form (bar or wire);
- 4.1.5 Applicable dimensions including size, thickness, width, and length (exact, random, or multiples) or drawing number;
- 4.1.6 Tolerances—unless otherwise specified by purchaser, tolerances must meet the requirements of Specification A484/A484M, A555/A555M, or both, as applicable;
- 4.1.7 Condition (see 5.1);
- 4.1.8 Finish (see 5.2);
- 4.1.9 Special tests (if any); and
- 4.1.10 Other requirements.

**5. Materials and Manufacture**

5.1 *Condition*—Bar and wire shall be furnished in the hot-worked, annealed, or cold-worked condition, as specified.

5.2 *Finish*—Bar and wire shall be furnished bright annealed, cold drawn, pickled, ground, or ground and polished, as specified by the purchaser.

**6. Chemical Requirements**

6.1 The supplier’s heat analysis shall conform to the chemical requirements prescribed in Table 1. The supplier shall not ship material with chemistry outside the requirements specified in Table 1.

**TABLE 1 Chemical Composition**

Element	Composition, % (Mass/Mass)
Carbon	0.030 max
Manganese	4.00 to 6.00
Phosphorus	0.025 max
Sulfur	0.010 max
Silicon	0.75 max
Chromium	20.50 to 23.50
Nickel	11.50 to 13.50
Molybdenum	2.00 to 3.00
Nitrogen	0.20 to 0.40
Niobium	0.10 to 0.30
Vanadium	0.10 to 0.30
Copper	0.50 max
Iron	balance <sup>A</sup>

<sup>A</sup> Approximately equal to the difference of 100 % and the sum percentage of the other specified elements. Reporting of the iron difference is not required.

6.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.

6.1.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods A751.

6.2 *Product Analysis*—The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

6.2.1 Acceptance or rejection of a heat or lot of material may be made by the purchaser on the basis of this product analysis.

6.2.2 Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. Product analysis limits shall be as specified in Table 2.

6.2.3 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods E354.

**7. Metallurgical Requirements**

7.1 The material shall contain no delta ferrite, chi, or sigma phases when it is examined metallographically at 100× magnification in accordance with Practice E407.

7.2 The microcleanliness of the material, as determined by Practice E45, Method A, except using Plate Ir, on representative billet or bar samples from the heat shall not exceed the following:

Inclusion Type	A (Sulfide)	B (Alumina)	C (Silicate)	D (Globular Oxide)
Thin	1.5	2.5	2.5	2.5
Heavy	1.5	1.5	1.5	1.5

**8. Mechanical Requirements**

8.1 *Tensile Properties:*

**TABLE 2 Product Analysis Tolerances<sup>A</sup>**

Element	Permissible Variation Under the Minimum Limit or Over the Maximum Limit, % (Mass/Mass) <sup>B</sup>
Carbon	0.005
Manganese <sup>C</sup>	0.05
Phosphorus	0.005
Sulfur	0.005
Silicon	0.05
Chromium	0.25
Nickel	0.15
Molybdenum	0.10
Nitrogen <sup>C</sup>	0.02 under min; 0.04 over max
Niobium	0.05
Vanadium	0.03
Copper	0.03

<sup>A</sup>Refer to AMS 2248 for chemical check analysis limits (except nitrogen).

<sup>B</sup>For elements in which only a maximum percentage is indicated, the “under minimum limit” is not applicable.

<sup>C</sup>The specified range for this element is not covered by AMS 2248 and permissible variation has been established through industrial practice.