



Designation: **B176—17 B176 – 18**

Standard Specification for Copper-Alloy Die Castings¹

This standard is issued under the fixed designation B176; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for copper-alloy die castings. The alloys specified are Copper Alloy UNS Nos. C85470, C85700, C85800, C86500, C87800, C99700, and C99750.²

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:³

[B824 Specification for General Requirements for Copper Alloy Castings](#)

[B846 Terminology for Copper and Copper Alloys](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E23 Test Methods for Notched Bar Impact Testing of Metallic Materials](#)

[E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

2.2 ADCI/NADCA Standards:⁴

[“E” Series Product Standards](#)

2.3 Federal Standard:⁵

[Fed. Std. No. 123 Marking for Shipment \(Civil Agencies\)](#)

2.4 Military Standards:⁵

[MIL-STD-129 Marking for Shipment and Storage \(Military Agencies\)](#)

[MIL-P-116 Methods of Preservation](#)

3. General Requirements

3.1 The following sections of Specification [B824](#) constitute a part of this specification.

3.1.1 Terminology (Section 3),

3.1.2 Number of Tests and Retests (Section 11) (Note to users: Paragraph 10.3 of Specification [B824](#) applies only when mechanical requirements are specified in the purchase order.),

3.1.3 Test Methods (Section 13),

¹ This specification is under the jurisdiction of ASTM Committee [B05](#) on Copper and Copper Alloys and is the direct responsibility of Subcommittee [B05.05](#) on Castings and Ingots for Remelting.

Current edition approved ~~April 1, 2017~~ March 1, 2018. Published ~~May 2017~~ March 2018. Originally approved in 1942. Last previous edition approved in ~~2014~~ 2017 as [B176-14-17](#). DOI: [10.1520/B0176-17.10.1520/B0176-18](#).

² The UNS system for copper and copper alloys (see Practice [E527](#)) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from North American Die Casting Association (NADCA), 3250 Arlington Heights Rd., Suite 101, Arlington Heights, IL 60004, [http://www.diecasting.org](#)—[http://www.diecasting.org](#).

⁵ Available from DLA Document Services, Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, [http://quicksearch.dla.mil/](#)—[http://quicksearch.dla.mil/](#).

*A Summary of Changes section appears at the end of this standard

- 3.1.4 Significance of Numerical Limits (Section 14),
- 3.1.5 Inspection (Section 15),
- 3.1.6 Rejection and Rehearing (Section 16),
- 3.1.7 Certification (Section 17),
- 3.1.8 Test Report (Section 18),
- 3.1.9 Product Marking (Section 19), and
- 3.1.10 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in 3.1, above, appears in this specification, it contains additional requirements which supplement those appearing in Specification B824.

4. Terminology

4.1 For general terms related to copper and copper alloys, refer to Terminology B846.

5. Ordering Information

5.1 Include the following information when placing orders for die castings under this specification as applicable:

- 5.1.1 Specification title, number, and year of issue,
- 5.1.2 Part name and number,
- 5.1.3 Copper Alloy UNS Number,
- 5.1.4 Quantity and delivery schedule, as required,

5.1.5 Engineering drawing of die casting, when required, giving all necessary dimensions and tolerances and showing latest revisions and allowances for machining, if any. Location of ejector pin marks or parting lines shall be at the option of the manufacturer unless specifically designated on the drawing.

5.1.6 When die castings are purchased for agencies of the U.S. Government the Supplementary Requirements of Specification B824 may be specified.

5.2 The following requirements are optional and should be specified in the purchase order when required.

- 5.2.1 Inspection lot sampling (Section 9),
- 5.2.2 Soundness requirements (10.1),
- 5.2.3 Mechanical requirements (Section 7),
- 5.2.4 Special requirements (Section 10),
- 5.2.5 Certification (Specification B824),
- 5.2.6 Foundry test report (Specification B824),
- 5.2.7 Witness inspection (Specification B824),

TABLE 1 Chemical Requirements

Copper Alloy UNS No.	Composition, % max (unless shown as a range or min)											
	Copper	Tin	Lead	Zinc	Iron	Nickel including Cobalt	Aluminum	Manganese	Antimony	Sulfur	Phosphorus	Silicon
C85470	60.0–65.0	1.0–4.0	0.09	Rem	0.20	...	0.10–1.0	0.02–0.25	...
C85700	58.0–64.0	0.50–1.5	0.8–1.5	32.0–40.0	0.7	1.0	0.8	0.05
C85800	57.0 min ^A	1.5	1.5	31.0–41.0	0.50	0.50	0.55	0.25	0.05	0.05	0.01	0.25 ^B
C86500	55.0–60.0 ^A	1.0	0.40	36.0–42.0	0.40–2.0	1.0	0.50–1.5	0.10–1.5
C87800	80.0 min ^A	0.25	0.09	12.0–16.0	0.15	0.20	0.15	0.15	0.05	0.05	0.01	3.8–4.2 ^{B,C}
C99700	54.0 min ^A	1.0	2.0	19.0–25.0	1.0	4.0–6.0	0.50–3.0	11.0–15.0
C99750	55.0–61.0	...	0.50–2.5	17.0–23.0	1.0 ^D	5.0	0.25–3.0	17.0–23.0

TABLE 1 Chemical Requirements

Copper Alloy UNS No.	Composition, % max (unless shown as a range or min)													
	Copper	Tin	Lead	Zinc	Iron	Nickel	Aluminum	Manganese	Magnesium	Antimony	Sulfur	Phosphorus	Silicon	Arsenic
C85470	60.0–65.0	1.0–4.0	0.09	Rem	0.20	...	0.10–1.0	0.02–0.25
C85700	58.0–64.0	0.50–1.5	0.8–1.5	32.0–40.0	0.7	1.0	0.8	0.05	...
C85800	57.0 min ^A	1.5	1.5	31.0–41.0	0.50	0.50 ^B	0.55	0.25	...	0.05	0.05	0.01	0.25	0.05
C86500	55.0–60.0 ^A	1.0	0.40	36.0–42.0	0.40–2.0	1.0 ^B	0.50–1.5	0.10–1.5
C87800	80.0 min	0.25	0.09	12.0–16.0	0.15	0.20 ^B	0.15	0.15	0.01	0.05	0.05	0.01	3.8–4.2	0.05
C99700	54.0 min	1.0	2.0	19.0–25.0	1.0	4.0–6.0	0.50–3.0	11.0–15.0
C99750	55.0–61.0	...	0.50–2.5	17.0–23.0	1.0	5.0	0.25–3.0	17.0–23.0

^A In determining copper min, copper may be determined as copper plus nickel.

^B Arsenic 0.05 max. Nickel value includes Cobalt.

^C Magnesium 0.01 max.

^D Iron content above the nickel content may cause hard spots resulting in decreased machinability.