



Designation: C954 – 18

Standard Specification for Steel Drill Screws for the Application of Gypsum Panel Products or Metal Plaster Bases to Steel Studs from 0.033 in. (0.84 mm) to 0.112 in. (2.84 mm) in Thickness¹

This standard is issued under the fixed designation C954; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers minimum requirements for steel drill screws for use in fastening gypsum panel products or metal plaster bases to steel members from 0.033 in. (0.84 mm) to 0.112 in. (2.84 mm) in thickness.

1.2 This specification also covers physical properties and test methods for determining performance requirements.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following safety hazards caveat pertains only to the test methods described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.02 on Specifications and Test Methods for Accessories and Related Products.

Current edition approved April 1, 2018. Published April 2018. Originally approved in 1981. Last previous edition approved in 2015 as C954 – 15. DOI: 10.1520/C0954-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [A510/A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel](#)
- [A1040 Guide for Specifying Harmonized Standard Grade Compositions for Wrought Carbon, Low-Alloy, and Alloy Steels](#)
- [C11 Terminology Relating to Gypsum and Related Building Materials and Systems](#)
- [C847 Specification for Metal Lath](#)
- [C955 Specification for Cold-Formed Steel Structural Framing Members](#)
- [C1396/C1396M Specification for Gypsum Board](#)
- [C1513 Specification for Steel Tapping Screws for Cold-Formed Steel Framing Connections](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions relating to gypsum and related building materials and systems, see Terminology C11.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *steel drill screw, n*—self-drilling tapping screw with the ability to drill its own hole, form or cut mating threads without deforming its own threads or breaking during assembly.

4. Materials

4.1 Screws shall be made from steel wire manufactured in accordance with Specification A510/A510M.

4.1.1 Chemical composition shall be in accordance with Guide A1040, Grade 1018 to 1022.

5. Physical Properties

5.1 *Metallurgical Requirements:*

5.1.1 The surface of the screw shall be carbonitrided to a depth of 0.004 to 0.008 in. (0.10 to 0.20 mm).

5.1.2 The core hardness shall be 32 to 40 HRC after being drawn at a minimum temperature of 625°F (330°C).

5.1.3 The screw shall have no band of free ferrite between the case and core nor shall the case contain appreciable amounts of retained austenite or other soft constituents.

*A Summary of Changes section appears at the end of this standard

5.1.4 Surface hardness shall be determined by a micro hardness instrument at “the root of the thread profile,” as exposed by removal of enough material to form a flat surface along the length of the screw.

5.1.5 *Ductility*—Screws shall have sufficient ductility to be able to withstand a 5° bend without visible signs of fracture when tested as specified in paragraph 8.2.1 of Specification **C1513**.

5.2 *Dimensions and Permissible Variations:*

5.2.1 *General:*

5.2.1.1 *Head Diameter*—The head of the screw shall not be out of round more than 0.021 in. (0.51 mm) and have the following shape and dimensions:

5.2.1.2 *Screw Diameter*—Screws shall have a major diameter not less than 0.136 in. (3.45 mm).

5.2.1.3 *Points*, shall provide for self-drilling into steel studs from 0.333 in. (0.84 mm) to 0.112 in. (2.84 mm) in thickness and meet the performance tests in Section 6.

5.2.1.4 *Driving Recess*, shall be a No. 2 “Phillips” design with a minimum depth of 0.104 in. (2.64 mm) as determined with a “Phillips” penetration depth gage or a recess of equal performance.

5.2.1.5 *Length*—Nominal lengths shall be minimum length.

5.2.2 *Screws for Fastening Gypsum Board:*

5.2.2.1 Screw-head minimum diameter shall be 0.3145 in. (8.00 mm).

5.2.2.2 The top of the head shall be flat. The outer flange thickness shall be 0.025 ± 0.005 in. (0.64 ± 0.13 mm). The contour beneath the flange head shall be such that the screw head shall be able to be driven so that the head of the screw rests immediately below the surface of the gypsum panel products.

5.2.2.3 For screws less than 1½ in. (38 mm) overall length, the threads shall extend to the lower edge of the head contour.

5.2.3 *Screws for Fastening Metal Plaster Bases:*

5.2.3.1 Screw head minimum diameter shall be 0.437 in. (11.1 mm).

5.2.3.2 The top of the head shall be flat or contoured. The underside of the head shall be flat.

5.2.3.3 The threads shall extend to the underside of the head.

6. Performance Requirements

6.1 *Spin-Out:*

6.1.1 Screws shall self-drill and drive into a stud 0.0538 in. (1.4 mm) thick with an approximate hardness of 65 HRB without spin-out.

6.1.2 Screws shall self drill and drive into a stud 0.0966 in. (2.5 mm) thick, with a hardness of 80 HRB without spin-out.

6.2 *Performance:*

6.2.1 When tested in accordance with Section 10 and 11, screws shall meet the requirements as follows:

6.2.1.1 *Gypsum Panel Products*—When tested in accordance with Section 11, screw threads shall be capable of pulling the head of the screw below the surface of the gypsum board

6.2.1.2 *Metal Plaster Bases*—When tested in accordance with Section 10, screw threads shall be adequate to pull metal

lath tight against the flange of a steel stud 0.033 in. (0.84 mm) thick so that when subjected to a steady pull, the lath will tear and not slip out from under the screw head when tested in accordance with 10.5.1.

7. Finish and Appearance

7.1 Screws shall be corrosion-resistant treated with a material which will not inhibit adhesion to joint compounds or plaster and will not bleed through decorative finishes.

7.2 Screws shall be straight, clean, smooth, neatly formed, and free of defects such as burrs and deformations.

8. Sampling

8.1 Obtain not less than 90 screws from not less than five containers.

9. Number of Tests and Retests

9.1 Test a minimum of five screws for each test. If any of the first lot fails, test 25 more screws.

9.2 If two or more of the second lot fail the second test, then the represented lot fails to meet the specified requirements.

10. Metal Lath Test Method

10.1 *Summary of Test Method:*

10.1.1 This test method utilizes steel screws designed for use to hold metal plaster base materials applied with power-driven screw guns of 2500 rpm maximum to steel studs.

10.2 *Significance and Use:*

10.2.1 This test method evaluates the ability of steel drill screws used to secure metal plaster bases to certain steel framing members.

10.2.2 The test shall be conducted in a laboratory or on-site.

10.3 *Apparatus:*

10.3.1 *Power-Driven Drill Screw Gun*, capable of 2500 rpm (free spindle speed) with a depth-sensitive nose piece, supplied with a screw driving bit to fit the screw used in the test.

10.3.2 *Vice*, or similar device, to support the stud during the test.

10.3.3 *Clamp*—Locking pliers (for example, Vise-Grips), 6 in. (152 mm).

10.4 *Materials:*

10.4.1 *Steel Stud*—Specification **C955**, one section of 0.033-in. thick stud (0.84 mm).

10.4.2 *Gypsum Wallboard*—Specification **C1396/C1396M**, Type X, ⅝ in. (16 mm) thick.

10.4.3 *Screw Specimens*, to be tested.

10.4.4 *Diamond Mesh Metal Lath*, Specification **C847**, diamond mesh, weight 2.5 lb/yd² (1.4 kg/m²).

10.5 *Procedure for Performance Tests:*

10.5.1 Using the screw specimen, attach metal lath to center of a flange of a steel stud which has been securely and rigidly supported.

10.5.1.1 Grasp the metal lath with locking pliers and pull steadily in a plane parallel to the plane of the lath. Observe whether the lath tears before it slips out from under the screw head.