



Designation: E534 – 18

# Standard Test Methods for Chemical Analysis of Sodium Chloride<sup>1</sup>

This standard is issued under the fixed designation E534; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 These test methods cover the chemical analyses usually required for sodium chloride.

1.2 The analytical procedures appear in the following sections:

	Section
Sample Preparation	5 to 9
Moisture	10 to 17
Water Insolubles	18 to 26
Calcium and Magnesium	27 to 34
Sulfate	35 to 42
Reporting of Analyses	43 to 45

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 Review the current safety data sheets (SDS) for detailed information concerning toxicity, first-aid procedures, handling, and safety precautions.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D1193 Specification for Reagent Water

D6809 Guide for Quality Control and Quality Assurance

<sup>1</sup> These test methods are under the jurisdiction of ASTM Committee D16 on Aromatic, Industrial, Specialty and Related Chemicals and are under the direct responsibility of Subcommittee D16.13 on Chlorine.

Current edition approved Feb. 1, 2018. Published April 2018. Originally approved in 1975. Last previous edition approved in 2013 as E534 – 13. DOI: 10.1520/E0534-18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Procedures for Aromatic Hydrocarbons and Related Materials

E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals (Withdrawn 2009)<sup>3</sup>

E200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis

## 3. Significance and Use

3.1 Sodium chloride occurs in nature. It is a necessary article of diet as well as the source for production of many sodium compounds and chlorine. The methods listed in 1.2 provide procedures for analyzing sodium chloride to determine if it is suitable for its intended use.

## 4. Reagents

4.1 *Purity of Reagents*—Unless otherwise indicated, it is intended that all reagents should conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>4</sup>

4.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean Type II or III reagent water conforming to Specification D1193.

## SAMPLE PREPARATION

## 5. Scope

5.1 This test method covers preparation of a sample that will be as representative as possible of the entire bulk quantity. The results of any analysis pertain only to the sample used.

## 6. Apparatus

6.1 *Coarse Grinder.*

6.2 *High-Speed Blender.*

6.3 *Oven.*

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Precision for Moisture Method**

Level, %	Repeatability			Laboratory Precision			Reproducibility		
	Standard Deviation, %	Degrees of Freedom	95 % Limit, %	Standard Deviation, %	Degrees of Freedom	95 % Limit, %	Standard Deviation, %	Degrees of Freedom	95 % Limit, %
0.003 to 0.004	0.0014	36	0.004	0.00223	18	0.006	0.00322	8	0.009
0.025 to 0.035	0.0071	60	0.02	0.00428	30	0.01	0.0138	9	0.04

6.4 *Riffle Sampler.*

6.5 *Scale.*

## 7. Reagents

7.1 *Hydrochloric Acid, Standard (1 meq/mL HCl)*—Prepare and standardize in accordance with Practice E200.

## 8. Rock and Solar Salt Stock Solutions

8.1 Mix and split sample to 500 g, using the riffle sampler.

8.2 If sample appears wet, dry at 110°C for 2 h.

8.3 Grind the sample to –8 mesh in the coarse grinder.

8.4 Mix ground sample well and weigh out a 25.0-g representative portion for rock salt or 50.0 g for solar salt.

8.5 Place 200 mL of water in the high-speed blender and start at low speed.

8.6 Slowly add the salt sample to the high-speed blender and blend for 5 min.

8.7 Test for water insolubles as described in Sections 18 – 26.

8.8 Save filtrate from water insolubles test and dilute in a volumetric flask to 1 L with water as a stock solution for subsequent analyses.

## 9. Evaporated and Purified Salt Stock Solutions

9.1 Mix and split the sample to 100 g for evaporated salt, or 200 g for purified evaporated salt.

9.2 Transfer to a 1-L volumetric flask.

9.3 Add 800 mL of water and allow the salt to dissolve.

9.4 Add 2 mL of concentrated HCl to dissolve any water insoluble calcium salts, particularly calcium carbonate.

9.5 Dilute to volume with water and use as a stock solution for subsequent analyses.

# MOISTURE

## 10. Scope

10.1 This test method determines free moisture in the salt over a concentration range from 0.00 to 0.04 %. It does not determine occluded moisture trapped within the salt crystals. The procedure is based on weight loss after a sample is heated to volatilize moisture.

## 11. Apparatus

11.1 *Analytical Balance* capable of weighing to  $\pm 0.001$  g.

11.2 *Desiccator.*

11.3 *Oven.*

## 12. Procedure, Rock and Solar Salt

12.1 Weigh 100 g of salt to the nearest 0.05 g into a previously dried and tared moisture dish.

12.2 Dry at 110°C for 2 h.

12.3 Cool in a desiccator and weigh.

## 13. Procedure, Evaporated and Purified Evaporated Salt

13.1 Weigh 20 g of salt to the nearest 0.001 g into a previously dried and weighed glass weighing bottle and cover.

13.2 Dry at 110°C for 2 h.

13.3 Cool in a desiccator, replace cover, and weigh.

## 14. Calculation

14.1 Calculate the percentage of moisture as follows:

$$\text{moisture, mass (m/m) \%} = \frac{A}{B} \times 100 \quad (1)$$

where:

$A$  = loss of mass on drying, g, and

$B$  = mass of sample, g.

## 15. Report

15.1 Report the moisture content to the nearest 0.001 %.

## 16. Precision and Bias<sup>5</sup>

16.1 Ten laboratories analyzed five samples in duplicate on two different days. Practice E180 was followed for the design and analysis of the data; the details are given in ASTM Research Report RR:E15-1052.

16.1.1 *Intermediate Precision, formerly called Repeatability (Single Analyst)*—The standard deviation for a single determination has been estimated to be the percent absolute values shown in Table 1 at the indicated degrees of freedom. The 95 % limit for the difference between two such runs is the percent absolute values in Table 1.

16.1.2 *Laboratory Precision (Within-Laboratory, Between-Days Variability)*—The standard deviation of results (each the average of duplicates), obtained by the same analyst on different days, has been estimated to be the percent absolute values shown in Table 1 at the indicated degrees of freedom. The 95 % limit for the difference between two such averages is the percent absolute values in Table 1.

<sup>5</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:E15-1052. Contact ASTM Customer Service at service@astm.org.

16.1.3 *Reproducibility (Multilaboratory)*—The standard deviation of results (each the average of duplicates), obtained by analysts in different laboratories, has been estimated to be percent absolute values shown in [Table 1](#). The 95 % limit for the difference between two such averages is the percent absolute values in [Table 1](#).

16.2 *Bias*—The bias of this test method has not been determined due to the unavailability of suitable reference materials.

## 17. Quality Guidelines

17.1 Laboratories shall have a quality control system in place.

17.1.1 Confirm the performance of the test instrument or test method by analyzing a quality control sample following the guidelines of standard statistical quality control practices.

17.1.2 A quality control sample is a stable material isolated from the production process and representative of the sample being analyzed.

17.1.3 When QA/QC protocols are already established in the testing facility, these protocols are acceptable when they confirm the validity of test results.

17.1.4 When there are no QA/QC protocols established in the testing facility, use the guidelines described in [Guide D6809](#) or similar statistical quality control practices.

## WATER INSOLUBLES

## 18. Scope

18.1 This gravimetric method determines only the amount of insolubles present in sodium chloride which will not dissolve in water.

## 19. Apparatus

19.1 *Analytical Balance.*

19.2 *Desiccator.*

19.3 *Magnetic Stirrer with Stirring Bar.*

19.4 *Parabella Filter Funnel Assembly*, 1000-mL, or its equivalent with 0.3- $\mu$ m glass fiber filter disk.

## 20. Reagents

20.1 *Silver Nitrate, Standard Solution*, 0.1 meq/mL  $\text{AgNO}_3$ —Prepare and standardize in accordance with [Practice E200](#).

## 21. Procedure, Rock and Solar Salts

21.1 Transfer a sample prepared in accordance with [8.1](#) to [8.6](#) to a 1-L Erlenmeyer flask, washing out the blender with 100 mL of water. Add 300 mL of water to give a total of 600 mL of water added.

21.2 Stir on a magnetic stirrer for 1 h. Adjust the stirrer speed to give maximum agitation without danger of losing any sample due to splashing. Place a beaker or watch glass over top of the flask while stirring.

21.3 Filter the solution by vacuum through a previously dried (110°C for 1 h) and accurately weighed filter disk using

the Parabella funnel. Transfer all insolubles to the paper and wash free of chlorides with water until the filtrate shows no turbidity when tested with 0.1 meq/mL  $\text{AgNO}_3$  solution.

21.4 Dilute filtrate and washings to 1 L with water in volumetric flask.

21.5 Dry the filter disk at 110°C for 1 h.

21.6 Cool in a desiccator and weigh the disk on an analytical balance.

21.7 Save the filtrate for subsequent analyses.

## 22. Procedure, Evaporated and Purified Evaporated Salts

22.1 Place a well mixed sample in a 2-L beaker. Use 100-g sample for evaporated or 200 g for purified evaporated salt.

22.2 Add 750 mL of water.

22.3 Mix with a mechanical stirrer until solution is complete.

22.4 Filter the solution by vacuum through a previously dried (110°C for 1 h) and accurately weighed filter disk using the Parabella funnel. Transfer all insolubles to the paper and wash free of chlorides with water until the filtrate shows no turbidity when tested with 0.1 meq/mL  $\text{AgNO}_3$  solution.

22.5 Dry the filter disk at 110°C for 1 h.

22.6 Cool in a desiccator and weigh on an analytical balance.

22.7 Dilute the filtration and washings to 1 L with water in a volumetric flask and reserve for subsequent analyses.

## 23. Calculation

23.1 Calculate the percentage of water insolubles as follows:

$$\text{insolubles, \% mass (m/m)} = \frac{A}{B} \times 100 \quad (2)$$

where:

A = increase in mass of filter disk, g, and

B = sample mass, g.

## 24. Report

24.1 Report the percentage of water insolubles to the nearest percentage shown as follows:

Range, %	Report to, %
0.002 to 0.005	0.001
0.01 to 0.04	0.01
0.15 to 0.35	0.01

## 25. Precision and Bias<sup>5</sup>

25.1 Ten laboratories analyzed six samples in duplicate on two different days. [Practice E180](#) was followed for the design and analysis of the data; the details are given in [ASTM Research Report RR:E15-1052](#).

25.1.1 *Intermediate Precision, formerly called Repeatability (Single Analyst)*—The coefficient of variation for a single determination has been estimated to be the percent relative values shown in [Table 2](#) at the indicated degrees of freedom. The 95 % limit for the difference between two such runs is percent relative values shown in [Table 2](#).