



Designation: C76 – 18

# Standard Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe<sup>1</sup>

This standard is issued under the fixed designation C76; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification covers reinforced concrete pipe intended to be used for the conveyance of sewage, industrial wastes, and storm water, and for the construction of culverts.

1.2 This specification is the inch-pound companion to Specification C76M; therefore, no SI equivalents are presented in this specification. Reinforced concrete pipe that conform to the requirements of C76M, are acceptable under this Specification C76 unless prohibited by the Owner.

NOTE 1—This specification is a manufacturing and purchase specification only, and does not include requirements for bedding, backfill, or the relationship between field load condition and the strength classification of pipe. However, experience has shown that the successful performance of this product depends upon the proper selection of the class of pipe, type of bedding and backfill, and care that installation conforms to the construction specifications. The owner of the reinforced concrete pipe specified herein is cautioned that he must correlate the field requirements with the class of pipe specified and provide inspection at the construction site.

NOTE 2—Attention is called to the specification for reinforced concrete D-load culvert, storm drain, and sewer pipe (Specification C655).

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

A36/A36M Specification for Carbon Structural Steel

A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

A1064/A1064M Specification for Carbon-Steel Wire and Welded Wire Reinforcement, Plain and Deformed, for Concrete

C33/C33M Specification for Concrete Aggregates

C76M Specification for Reinforced Concrete Culvert, Storm Drain, and Sewer Pipe (Metric)

C150/C150M Specification for Portland Cement

C260/C260M Specification for Air-Entraining Admixtures for Concrete

C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete

C443 Specification for Joints for Concrete Pipe and Manholes, Using Rubber Gaskets

C494/C494M Specification for Chemical Admixtures for Concrete

C497 Test Methods for Concrete Pipe, Manhole Sections, or Tile

C595/C595M Specification for Blended Hydraulic Cements

C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete

C655 Specification for Reinforced Concrete D-Load Culvert, Storm Drain, and Sewer Pipe

C822 Terminology Relating to Concrete Pipe and Related Products

C989/C989M Specification for Slag Cement for Use in Concrete and Mortars

C990 Specification for Joints for Concrete Pipe, Manholes, and Precast Box Sections Using Preformed Flexible Joint Sealants

C1017/C1017M Specification for Chemical Admixtures for Use in Producing Flowing Concrete

C1116/C1116M Specification for Fiber-Reinforced Concrete

C1602/C1602M Specification for Mixing Water Used in the Production of Hydraulic Cement Concrete

C1628 Specification for Joints for Concrete Gravity Flow Sewer Pipe, Using Rubber Gaskets

## 3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology C822.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.02 on Reinforced Sewer and Culvert Pipe.

Current edition approved April 1, 2018. Published April 2018. Originally approved in 1930. Last previous edition approved in 2016 as C76 - 16. DOI: 10.1520/C0076-18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard



TABLE 2 Design Requirements for Class II Reinforced Concrete Pipe<sup>A</sup>

NOTE 1—See Section 5 for basis of acceptance specified by the owner. The strength test requirements in pounds-force per linear foot of pipe under the three-edge-bearing method shall be either the D-load (test load expressed in pounds-force per linear foot per foot of diameter) to produce a 0.01-in. crack, or the D-loads to produce the 0.01-in. crack and the ultimate load as specified below, multiplied by the internal diameter of the pipe in feet.

D-load to produce a 0.01-in. crack 1000  
 D-load to produce the ultimate load 1500

Internal Designated Diameter, in.	Reinforcement, in. <sup>2</sup> /linear ft of pipe wall														
	Wall A				Wall B				Wall C						
	Wall Thickness, in.	Concrete Strength, 4000 psi			Wall Thickness, in.	Concrete Strength, 4000 psi			Wall Thickness, in.	Concrete Strength, 4000 psi					
		Circular Reinforcement <sup>C</sup>		Elliptical Reinforcement <sup>D</sup>		Circular Reinforcement <sup>C</sup>		Elliptical Reinforcement <sup>D</sup>		Circular Reinforcement <sup>C</sup>		Elliptical Reinforcement <sup>D</sup>			
Inner Cage	Outer Cage	Inner Cage	Outer Cage		Inner Cage	Outer Cage	Inner Cage		Outer Cage						
12	1¾	0.07 <sup>B</sup>	...	...	2	0.07 <sup>B</sup>	...	...	2¾	0.07 <sup>B</sup>	...	...			
15	1⅞	0.07 <sup>B</sup>	...	...	2¼	0.07 <sup>B</sup>	...	...	3	0.07 <sup>B</sup>	...	...			
18	2	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>	2½	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>	3¼	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
21	2¼	0.12	...	0.10	2¾	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>	3½	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
24	2½	0.12	...	0.11	3	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>	3¾	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
27	2⅝	0.15	...	0.12	3¼	0.12	...	0.11	4	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
30	2¾	0.15	...	0.14	3½	0.14	...	0.12	4¼	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
33	2⅞	0.16	...	0.15	3¾	0.15	...	0.12	4½	0.07 <sup>B</sup>	...	0.07 <sup>B</sup>			
36	3	0.14	0.08	0.15	4 <sup>E</sup>	0.12	0.07	0.12	4¾ <sup>E</sup>	0.07	0.07	0.08			
42	3½	0.16	0.10	0.18	4½	0.15	0.09	0.17	5¼	0.10	0.07	0.11			
48	4	0.21	0.12	0.23	5	0.18	0.11	0.20	5¾	0.14	0.08	0.15			
54	4½	0.24	0.15	0.27	5½	0.21	0.12	0.24	6¼	0.17	0.10	0.19			
60	5	0.30	0.18	0.33	6	0.24	0.15	0.27	6¾	0.21	0.12	0.24			
66	5½	0.35	0.21	0.39	6½	0.31	0.19	0.34	7¼	0.24	0.15	0.27			
72	6	0.41	0.24	0.45	7	0.35	0.21	0.39	7¾	0.30	0.18	0.33			
78	6½	0.45	0.27	0.51	7½	0.40	0.24	0.44	8¼	0.35	0.21	0.39			
84	7	0.51	0.31	0.57	8	0.45	0.27	0.51	8¾	0.41	0.24	0.45			
90	7½	0.57	0.34	0.63	8½	0.51	0.31	0.57	9¼	0.48	0.29	0.53			
96	8	0.62	0.36	0.69	9	0.57	0.34	0.63	9¾	0.55	0.33	0.60			
Concrete Strength, 5000 psi															
102	8½	0.76	0.45	Inner Circular Plus Elliptical	0.30	9½	0.68	0.41	Inner Circular Plus Elliptical	0.27	10¼	0.62	0.36	Inner Circular Plus Elliptical	0.24
108	9	0.85	0.51	Inner Circular Plus Elliptical	0.34	10	0.76	0.45	Inner Circular Plus Elliptical	0.30	10¾	0.70	0.42	Inner Circular Plus Elliptical	0.27
114	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...
120	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...
126	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...
132	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...
138	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...
144	A	...	...	...	A	...	...	...	A	...	...	...	...	...	...

<sup>A</sup>For modified or special designs see 7.2 or with the permission of the owner utilize the provisions of Specification C655. Steel areas may be interpolated between those shown for variations in diameter, loading, or wall thickness. Pipe over 96 in. in diameter shall have two circular cages or an inner circular plus one elliptical cage.

<sup>B</sup>For these classes and sizes, the minimum practical steel reinforcement is specified. The specified ultimate strength of non-reinforced pipe is greater than the minimum specified strength for the equivalent diameters.

<sup>C</sup>As an alternative to designs requiring both inner and outer circular cages the reinforcement may be positioned and proportioned in either of the following manners:

An inner circular cage plus an elliptical cage such that the area of the elliptical cage shall not be less than that specified for the outer cage in the table and the total area of the inner circular cage plus the elliptical cage shall not be less than that specified for the inner cage in the table,

An inner and outer cage plus quadrant mats in accordance with Fig. 1, or

An inner and outer cage plus an elliptical cage in accordance with Fig. 2.

<sup>D</sup>Elliptical and quadrant steel must be held in place by means of holding rods, chairs, or other positive means throughout the entire casting operation.

<sup>E</sup>As an alternative, single cage reinforcement may be used. The reinforcement area in square in. per linear foot shall be 0.20 for wall B and 0.16 for wall C.

6. Materials

6.1 Reinforced Concrete—The reinforced concrete shall consist of cementitious materials; mineral aggregates; admixtures, if used; and water in which steel has been embedded in such a manner that the steel and concrete act together.

6.2 Cementitious materials:

6.2.1 Cement—Cement shall conform to the requirements of Specification C150/C150M, or shall be portland blast-furnace slag cement, portland-limestone cement, or portland-pozzolan

cement conforming to the requirements of Specification C595/C595M, except that the pozzolan constituent in the Type IP portland-pozzolan cement shall be fly ash.

6.2.2 Slag Cement—Slag cement shall conform to the requirements of Grade 100 or 120 of Specification C989/C989M.

6.2.3 Fly Ash—Fly ash shall conform to the requirements of Class F or Class C of Specification C618.

6.2.4 Allowable Combinations of Cementitious Materials—The combination of cementitious materials used in the concrete shall be one of the following:

**TABLE 3 Design Requirements for Class III Reinforced Concrete Pipe<sup>A</sup>**

NOTE 1—See Section 5 for basis of acceptance specified by the owner. The strength test requirements in pounds-force per linear foot of pipe under the three-edge-bearing method shall be either the D-load (test load expressed in pounds-force per linear foot per foot of diameter) to produce a 0.01-in. crack, or the D-loads to produce the 0.01-in. crack and the ultimate load as specified below, multiplied by the internal diameter of the pipe in feet.

		Reinforcement, in. <sup>2</sup> /linear ft of pipe wall											
		Wall A			Wall B				Wall C				
Internal Designated Diameter, in.	Wall Thicknesses, in.	Concrete Strength, 4000 psi			Concrete Strength, 4000 psi				Concrete Strength, 4000 psi				
		Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	Wall Thicknesses, in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	Wall Thicknesses, in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	
		Inner Cage	Outer Cage			Inner Cage	Outer Cage			Inner Cage	Outer Cage		
12	1 3/4	0.07 <sup>D</sup>	...	...	2	0.07 <sup>D</sup>	...	...	2 3/4	0.07 <sup>D</sup>	...	...	
15	1 7/8	0.07 <sup>D</sup>	...	...	2 1/4	0.07 <sup>D</sup>	...	...	3	0.07 <sup>D</sup>	...	...	
18	2	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	2 1/2	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	3 1/4	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	
21	2 1/4	0.14	...	0.11	2 3/4	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	3 1/2	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	
24	2 1/2	0.17	...	0.14	3	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>	3 3/4	0.07	...	0.07 <sup>D</sup>	
27	2 5/8	0.18	...	0.16	3 1/4	0.16	...	0.14	4	0.08	...	0.07 <sup>D</sup>	
30	2 3/4	0.19	...	0.18	3 1/2	0.18	...	0.15	4 1/4	0.10	...	0.08	
33	2 7/8	0.21	...	0.20	3 3/4	0.20	...	0.17	4 1/2	0.12	...	0.10	
36	3	0.21	0.12	0.23	4 <sup>E</sup>	0.17	0.10	0.19	4 3/4 <sup>E</sup>	0.08	0.07	0.09	
42	3 1/2	0.24	0.15	0.27	4 1/2	0.21	0.12	0.23	5 1/4	0.12	0.07	0.12	
48	4	0.32	0.19	0.35	5	0.24	0.14	0.27	5 3/4	0.16	0.10	0.18	
54	4 1/2	0.38	0.23	0.42	5 1/2	0.29	0.17	0.32	6 1/4	0.21	0.12	0.23	
60	5	0.44	0.26	0.49	6	0.34	0.20	0.38	6 3/4	0.24	0.15	0.27	
66	5 1/2	0.50	0.30	0.55	6 1/2	0.41	0.24	0.45	7 1/4	0.31	0.19	0.34	
72	6	0.57	0.34	0.63	7	0.49	0.29	0.54	7 3/4	0.36	0.21	0.40	
Concrete Strength, 5000 psi													
78	6 1/2	0.64	0.38	0.71	7 1/2	0.57	0.34	0.63	8 1/4	0.42	0.24	0.47	
84	7	0.72	0.43	0.80	8	0.64	0.38	0.71	8 3/4	0.50	0.30	0.56	
Concrete Strength, 5000 psi													
90	7 1/2	0.81	0.49	0.90	8 1/2	0.69	0.41	0.77	9 1/4	0.59	0.35	0.66	
96	8	0.93	0.56	1.03	9	0.76	0.45	0.84	9 3/4	0.70	0.42	Inner Circular Plus Elliptical 0.27	
102	8 1/2	1.03	0.62	Inner Circular Plus Elliptical 0.62	9 1/2	0.90	0.54	Inner Circular Plus Elliptical 0.54	10 1/4	0.83	0.50	Inner Circular Plus Elliptical 0.33	
108	9	1.22	0.73	Inner Circular Plus Elliptical 0.73	10	1.08	0.65	Inner Circular Plus Elliptical 0.65	10 3/4	0.99	0.59	Inner Circular Plus Elliptical 0.40	
114	A	...	...	...	A	...	...	...	A	...	...	...	
120	A	...	...	...	A	...	...	...	A	...	...	...	
126	A	...	...	...	A	...	...	...	A	...	...	...	
132	A	...	...	...	A	...	...	...	A	...	...	...	
138	A	...	...	...	A	...	...	...	A	...	...	...	
144	A	...	...	...	A	...	...	...	A	...	...	...	

<sup>A</sup>For modified or special designs see 7.2 or with the permission of the owner utilize the provisions of Specification C655. Steel areas may be interpolated between those shown for variations in diameter, loading, or wall thickness. Pipe over 96 in. in diameter shall have two circular cages or an inner circular plus one elliptical cage.

<sup>B</sup>As an alternative to designs requiring both inner and outer circular cages the reinforcement may be positioned and proportioned in either of the following manners: An inner circular cage plus an elliptical cage such that the area of the elliptical cage shall not be less than that specified for the outer cage in the table and the total area of the inner circular cage plus the elliptical cage shall not be less than that specified for the inner cage in the table,

An inner and outer cage plus quadrant mats in accordance with Fig. 1, or

An inner and outer cage plus an elliptical cage in accordance with Fig. 2.

<sup>C</sup>Elliptical and quadrant steel must be held in place by means of holding rods, chairs, or other positive means throughout the entire casting operation.

<sup>D</sup>For these classes and sizes, the minimum practical steel reinforcement is specified. The specified ultimate strength of non-reinforced pipe is greater than the minimum specified strength for the equivalent diameters.

<sup>E</sup>As an alternative, single cage reinforcement may be used. The reinforcement area in square in. per linear foot shall be 0.30 for wall B and 0.20 for wall C.

- 6.2.4.1 Portland cement only,
- 6.2.4.2 Portland blast-furnace slag cement only,
- 6.2.4.3 Portland-pozzolan cement only,
- 6.2.4.4 Portland-limestone cement only,
- 6.2.4.5 A combination of portland cement or portland-limestone cement and slag cement,

- 6.2.4.6 A combination of portland cement or portland-limestone cement and fly ash,
- 6.2.4.7 A combination of portland cement or portland-limestone cement, slag cement and fly ash, or
- 6.2.4.8 A combination of portland-pozzolan cement and fly ash.

TABLE 4 Design Requirements for Class IV Reinforced Concrete Pipe<sup>A</sup>

NOTE 1—See Section 5 for basis of acceptance specified by the owner.

The strength test requirements in pounds-force per linear foot of pipe under the three-edge-bearing method shall be either the D-load (test load expressed in pounds-force per linear foot per foot of diameter) to produce a 0.01-in. crack, or the D-loads to produce the 0.01-in. crack and the ultimate load as specified below, multiplied by the internal diameter of the pipe in feet.

		D-load to produce a 0.01-in. crack			D-load to produce the ultimate load							
		2000			3000							
		Reinforcement, in. <sup>2</sup> /linear ft of pipe wall										
Internal Designated Diameter, in.	Wall Thickness, in.	Wall A			Wall B			Wall C				
		Concrete Strength, 5000 psi			Concrete Strength, 4000 psi			Concrete Strength, 4000 psi				
		Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	Wall Thickness, in.	Circular Reinforcement <sup>B</sup>		Elliptical Wall Reinforcement <sup>C</sup> in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	
Inner Cage	Outer Cage	Inner Cage	Outer Cage			Inner Cage	Outer Cage					
12	1¾	0.15	...	...	2	0.07	...	...	2¾	0.07 <sup>D</sup>	...	...
15	1⅞	0.16	...	...	2¼	0.10	...	...	3	0.07 <sup>D</sup>	...	...
18	2	0.17	...	0.15	2½	0.14	...	0.11	3¼	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>
21	2¼	0.23	...	0.21	2¾	0.20	...	0.17	3½	0.07 <sup>D</sup>	...	0.07 <sup>D</sup>
24	2½	0.29	...	0.27	3	0.27	...	0.23	3¾	0.07	0.07	0.08
27	2⅝	0.33	...	0.31	3¼	0.31	...	0.24	4	0.08	0.07	0.09
30	2¾	0.38	...	0.35	3½	0.35	...	0.27	4¼	0.09	0.07	0.10
33	A	...	...	...	3¾	0.27	0.16	0.30	4½	0.11	0.07	0.12
36	A	...	...	...	4	0.30	0.18	0.33	4¾	0.14	0.08	0.15
42	A	...	...	...	4½	0.35	0.21	0.39	5¼	0.20	0.12	0.21
48	A	...	...	...	5	0.42	0.24	0.47	5¾	0.26	0.16	0.29
54	A	...	...	...	5½	0.50	0.30	0.55	6¼	0.34	0.20	0.38
Concrete Strength, 5000 psi												
60	A	...	...	...	6	0.59	0.35	0.66	6¾	0.41	0.24	0.45
66	A	...	...	...	6½	0.69	0.41	0.77	7¼	0.51	0.31	0.57
Concrete Strength, 5000 psi												
72	A	...	...	...	7	0.79	0.47	0.88	7¾	0.60	0.36	0.68
78	A	...	...	...	A	...	...	...	8¼	0.71	0.43	0.79
84	A	...	...	...	A	...	...	...	8¾	0.85	0.51	0.94
90	A	...	...	...	A	...	...	...	A	...	...	...
96	A	...	...	...	A	...	...	...	A	...	...	...
102	A	...	...	...	A	...	...	...	A	...	...	...
108	A	...	...	...	A	...	...	...	A	...	...	...
114	A	...	...	...	A	...	...	...	A	...	...	...
120	A	...	...	...	A	...	...	...	A	...	...	...
126	A	...	...	...	A	...	...	...	A	...	...	...
132	A	...	...	...	A	...	...	...	A	...	...	...
138	A	...	...	...	A	...	...	...	A	...	...	...
144	A	...	...	...	A	...	...	...	A	...	...	...

<sup>A</sup>For modified or special designs see 7.2 or with the permission of the owner utilize the provisions of Specification C655. Steel areas may be interpolated between those shown for variations in diameter, loading, or wall thickness. Pipe over 96 in. in diameter shall have two circular cages or an inner circular plus one elliptical cage.

<sup>B</sup>As an alternative to designs requiring both inner and outer circular cages the reinforcement may be positioned and proportioned in either of the following manners:  
 An inner circular cage plus an elliptical cage such that the area of the elliptical cage shall not be less than that specified for the outer cage in the table and the total area of the inner circular cage plus the elliptical cage shall not be less than that specified for the inner cage in the table,  
 An inner and outer cage plus quadrant mats in accordance with Fig. 1, or  
 An inner and outer cage plus an elliptical cage in accordance with Fig. 2.

For Wall C, in sizes 24 to 33 in., a single circular cage with an area not less than the sum of the specified inner and outer circular reinforcement areas.

<sup>C</sup>Elliptical and quadrant steel must be held in place by means of holding rods, chairs, or other positive means throughout the entire casting operation.

<sup>D</sup>For these classes and sizes, the minimum practical steel reinforcement is specified.

6.3 *Aggregates*—Aggregates shall conform to Specification C33/C33M except that the requirement for gradation shall not apply.

6.4 *Admixtures*—The following admixtures and blends are allowable:

6.4.1 Air-entraining admixture conforming to Specification C260/C260M;

6.4.2 Chemical admixture conforming to Specification C494/C494M;

6.4.3 Chemical admixture for use in producing flowing concrete conforming to Specification C1017/C1017M; and

6.4.4 Chemical admixture or blend approved by the owner.

6.5 *Steel Reinforcement*—Reinforcement shall consist of wire and welded wire conforming to Specification A1064/A1064M, or of bars conforming to Specification A36/A36M, Specification A615/A615M, Grade 40 or 60, or Specification A706/A706M, Grade 60. For helically wound cages only, weld shear tests are not required.

6.6 *Fibers*—Synthetic fibers and nonsynthetic fibers shall be allowed to be used, at the manufacturer's option, in concrete pipe as a nonstructural manufacturing material. Synthetic fibers



TABLE 5 Design Requirements for Class V Reinforced Concrete Pipe<sup>A</sup>

NOTE 1—See Section 5 for basis of acceptance specified by the owner.

The strength test requirements in pounds-force per linear foot of pipe under the three-edge-bearing method shall be either the D-load (test load expressed in pounds-force per linear foot per foot of diameter) to produce a 0.01-in. crack, or the D-loads to produce the 0.01-in. crack and the ultimate load as specified below, multiplied by the internal diameter of the pipe in feet.

D-load to produce a 0.01-in. crack	3000
D-load to produce the ultimate load	3750

Internal Designated Diameter, in.	Reinforcement, in. <sup>2</sup> /linear ft of pipe wall											
	Wall A				Wall B				Wall C			
	Concrete Strength, 6000 psi				Concrete Strength, 6000 psi				Concrete Strength, 6000 psi			
	Wall Thickness, in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	Wall Thickness, in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>	Wall Thickness, in.	Circular Reinforcement <sup>B</sup>		Elliptical Reinforcement <sup>C</sup>
Inner Cage		Outer Cage	Inner Cage			Outer Cage	Inner Cage			Outer Cage		
12	A	...	...	...	2	0.10	...	...	2¾	0.07 <sup>D</sup>	...	...
15	A	...	...	...	2¼	0.14	...	...	3	0.07 <sup>D</sup>	...	...
18	A	...	...	...	2½	0.19	...	0.16	3¼	0.10	...	...
21	A	...	...	...	2¾	0.24	...	0.21	3½	0.10	...	...
24	A	...	...	...	3	0.30	...	0.24	3¾	0.12	0.07	0.12
27	A	...	...	...	3¼	0.38	0.23	0.42	4	0.14	0.08	0.16
30	A	...	...	...	3½	0.41	0.24	0.45	4¼	0.18	0.11	0.20
33	A	...	...	...	3¾	0.45	0.27	0.51	4½	0.23	0.14	0.24
36	A	...	...	...	4	0.50	0.30	0.56	4¾	0.27	0.16	0.30
42	A	...	...	...	4½	0.60	0.36	0.67	5¼	0.36	0.21	0.40
48	A	...	...	...	5	0.73	0.44	0.81	5¾	0.47	0.27	0.52
54	A	...	...	...	A	...	...	...	6¼	0.58	0.35	0.64
60	A	...	...	...	A	...	...	...	6¾	0.70	0.42	0.78
66	A	...	...	...	A	...	...	...	7¼	0.84	0.50	0.93
72	A	...	...	...	A	...	...	...	7¾	0.99	0.59	1.10
78	A	...	...	...	A	...	...	...	A	...	...	...
84	A	...	...	...	A	...	...	...	A	...	...	...
90	A	...	...	...	A	...	...	...	A	...	...	...
96	A	...	...	...	A	...	...	...	A	...	...	...
102	A	...	...	...	A	...	...	...	A	...	...	...
108	A	...	...	...	A	...	...	...	A	...	...	...
114	A	...	...	...	A	...	...	...	A	...	...	...
120	A	...	...	...	A	...	...	...	A	...	...	...
126	A	...	...	...	A	...	...	...	A	...	...	...
132	A	...	...	...	A	...	...	...	A	...	...	...
138	A	...	...	...	A	...	...	...	A	...	...	...
144	A	...	...	...	A	...	...	...	A	...	...	...

<sup>A</sup>For modified or special designs see 7.2 or with the permission of the owner utilize the provisions of Specification C655. Steel areas may be interpolated between those shown for variations in diameter, loading, or wall thickness. Pipe over 96 in. in diameter shall have two circular cages or an inner circular plus one elliptical cage.

<sup>B</sup>As an alternative to designs requiring both inner and outer circular cages the reinforcement may be positioned and proportioned in either of the following manners:  
 An inner circular cage plus an elliptical cage such that the area of the elliptical cage shall not be less than that specified for the outer cage in the table and the total area of the inner circular cage plus the elliptical cage shall not be less than that specified for the inner cage in the table,

An inner and outer cage plus quadrant mats in accordance with Fig. 1, or

An inner and outer cage plus an elliptical cage in accordance with Fig. 2.

<sup>C</sup>Elliptical and quadrant steel must be held in place by means of holding rods, chairs, or other positive means throughout the entire casting operation.

<sup>D</sup>For these classes and sizes, the minimum practical steel reinforcement is specified.

(Type II and Type III) and nonsynthetic fiber (Type I) designed and manufactured specifically for use in concrete and conforming to the requirements of Specification C1116/C1116M shall be accepted.

6.7 Water—Water used in the production of concrete shall be potable or nonpotable water that meets the requirements of Specification C1602/C1602M.

7. Design

7.1 Design Tables—The diameter, wall thickness, compressive strength of the concrete, and the area of the circumferential reinforcement shall be as prescribed for Classes I to V in Tables 1-5, except as provided in 7.2.

7.1.1 The reinforcement as presented in the tables herein allows single circular cage reinforcement, or separate inner and

outer circular cage reinforcement or a combination thereof. Footnotes to the tables are intended to clarify tabulated requirements or provide acceptable alternative reinforcement designs, either of which are applicable and binding as if they were contained in the body of the specification.

7.2 Modified and Special Designs:

7.2.1 If permitted by the owner the manufacturer may request approval by the owner of modified designs that differ from the designs in 7.1; or special designs for sizes and loads beyond those shown in Tables 1-5, 7.1, or special designs for pipe sizes that do not have steel reinforcement areas shown in Tables 1-5 of 7.1.

7.2.2 Such modified or special designs shall be based on rational or empirical evaluations of the ultimate strength and cracking behavior of the pipe and shall fully describe to the