



Designation: E1477 – 98a (Reapproved 2017)^{ε1}

Standard Test Method for Luminous Reflectance Factor of Acoustical Materials by Use of Integrating-Sphere Reflectometers¹

This standard is issued under the fixed designation E1477; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—A typo in Section 6.1 was editorially corrected in April 2018.

1. Scope

1.1 This test method covers the measurement of the luminous reflectance factor of acoustical materials for use in predicting the levels of room illumination.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E284 Terminology of Appearance

E308 Practice for Computing the Colors of Objects by Using the CIE System

E1164 Practice for Obtaining Spectrometric Data for Object-Color Evaluation

E1264 Classification for Acoustical Ceiling Products

E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry

E1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements

E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

3. Terminology

3.1 *Definitions:*

3.1.1 Definitions of appearance terms in Terminology E284 are applicable to this test method.

3.1.2 *integrating sphere, n*—an optical device used either to collect flux reflected or transmitted from a specimen into a hemisphere or to provide isotropic irradiation of a specimen from a complete hemisphere, consisting of an approximately spherical cavity with apertures (ports) for admitting and detecting flux, and usually having additional apertures over which sample and reference specimens are placed and for including or excluding the specularly reflected components. (E284)

3.1.3 *luminous, adj*—weighted according to the spectral luminous efficiency function $V(\lambda)$ of the CIE. (E284)

3.1.4 *reflectance factor, R, n*—ratio of the flux reflected from the specimen to the flux reflected from the perfect reflecting diffuser under the same geometric and spectral conditions of measurement. (E284)

3.1.5 *perfect reflecting diffuser*—ideal reflecting surface that neither absorbs nor transmits light, but reflects light in a diffused manner with the radiance of the reflecting surface being the same for all reflecting angles, regardless of the angular distribution of the incident light. (E284)

4. Summary of Test Method

4.1 Test specimens are measured for (total) luminous reflectance factor by standard color-measurement techniques using a spectrophotometer, tristimulus (filter) colorimeter, or other reflectometer having a hemispherical optical measuring system, such as an integrating sphere. The specular component is included to provide the total reflectance factor condition. The instrument standard is referenced to the perfect reflecting diffuser. Luminous reflectance factor is calculated as CIE tristimulus value Y for the CIE 1964 (10°) standard observer and CIE standard illuminant D65 (daylight) or F2 (cool white fluorescent).

¹ This test method is under the jurisdiction of ASTM Committee E12 on Color and Appearance and is the direct responsibility of Subcommittee E12.02 on Spectrophotometry and Colorimetry.

Current edition approved June 1, 2017. Published June 2017. Originally approved in 1992. Last previous edition approved in 2013 as E1477 – 98a (2013). DOI: 10.1520/E1477-98AR17E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.