



Designation: **F1700–18** **F1700 – 18a**

## Standard Specification for Solid Vinyl Floor Tile<sup>1</sup>

This standard is issued under the fixed designation F1700; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope

1.1 This specification covers solid vinyl<sup>2</sup> floor tiles that are monolithic, surface decorated or printed, and protected by a clear wear layer.

1.2 This type of floor covering is intended for use in commercial, light commercial, and residential buildings. General information and performance characteristics which determine serviceability and recommended use are included in this specification.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>3</sup>

[F137 Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus](#)

[F141 Terminology Relating to Resilient Floor Coverings](#)

[F373 Test Method for Embossed Depth of Resilient Floor Coverings](#)

[F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces](#)

[F410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement](#) [86/astm-fl700-18a](#)

[F925 Test Method for Resistance to Chemicals of Resilient Flooring](#)

[F1514 Test Method for Measuring Heat Stability of Resilient Flooring by Color Change](#)

[F1515 Test Method for Measuring Light Stability of Resilient Flooring by Color Change](#)

[F1914 Test Methods for Short-Term Indentation and Residual Indentation of Resilient Floor Covering](#)

[F2055 Test Method for Size and Squareness of Resilient Floor Tile by Dial Gage Method](#)

[F2199 Test Method for Determining Dimensional Stability of Resilient Floor Tile after Exposure to Heat](#)

#### 2.2 Other Standards:

[ANSI/ASQC Z1.4–1993 Sampling Procedures and Tables for Inspection by Attributes](#)<sup>4</sup>

### 3. Classification

3.1 The vinyl floor tiles covered by this specification shall be classified as follows:

3.1.1 *Class I*—Monolithic Vinyl Tile.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [F06](#) on Resilient Floor Coverings and is the direct responsibility of Subcommittee [F06.80](#) on Specifications.

Current edition approved ~~Jan. 1, 2018~~ March 1, 2018, Published ~~February 2018~~ April 2018. Originally approved in 1996. Last previous edition approved in ~~2013~~ 2018 as ~~F1700–13a~~ [F1700 – 18](#). DOI: ~~10.1520/F1700-18~~ [10.1520/F1700-18A](#).

<sup>2</sup> For solid vinyl definition, refer to Terminology [F141](#).

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> Available from American National Standards Institute, 11 West 42nd St., New York, NY 10036.

- 3.1.1.1 *Type A*—Smooth Surface.
- 3.1.1.2 *Type B*—Embossed Surface.
- 3.1.2 *Class II*—Surface-Decorated Vinyl Tile.
  - 3.1.2.1 *Type A*—Smooth Surface.
  - 3.1.2.2 *Type B*—Embossed Surface.
- 3.1.3 *Class III*—Printed Film Vinyl Tile.
  - 3.1.3.1 *Type A*—Smooth Surface.
  - 3.1.3.2 *Type B*—Embossed Surface.

3.2 The embossed surfaces may or may not be grouted with ink.

#### 4. Ordering Information

4.1 The purchaser shall state whether this specification is to be used, select the preferred options permitted herein, and include the following contract requirements on the purchase order:

- 4.1.1 Title, number, and date of this specification,
- 4.1.2 Class, type, and pattern number (Section 3),
- 4.1.3 Quantity in square feet, pieces, or cartons,
- 4.1.4 Size required (Section 6),
- 4.1.5 Thickness required (Section 6),
- 4.1.6 Lot formation if other than as specified in ANSI/ASQC Z1.4–1993 (see Sections 8 and 10),
- 4.1.7 Sampling if other than as specified in ANSI/ASQC Z1.4–1993 (see Sections 8 and 10),
- 4.1.8 Packing requirement if other than as specified (Section 12),
- 4.1.9 Palletization if required (agreement between the manufacturer and the purchaser),
- 4.1.10 Marking required if other than specified (Section 13) (agreement between the manufacturer and the purchaser),
- 4.1.11 Chemical resistance (see 6.8). The basic chemicals used in the test are those likely to be found in domestic, commercial and institutional use. Many proprietary compounds contain one or more of these basic chemicals. Should the flooring for unusual application need to be resistant to a specific chemical, this additional requirement should become part of the procurement document.
- 4.1.12 Other requirements (agreement between the manufacturer and the purchaser).

#### 5. Material and Manufacture

5.1 *Material*—The tile shall be composed of binder, filler, and pigments compounded with suitable lubricants and processing aids. The binder consists of one or more polymers or copolymers of vinyl chloride, other modifying resins, plasticizers, and stabilizers which comprise at least the following minimum percent weight: see Table 1. The polymers or copolymers of vinyl chloride comprise at least 60 % of the weight of the binder. Any copolymer of vinyl chloride used shall contain at least 85 % vinyl chloride.

5.2 *Class, Type, and Pattern Number*—The class, type, and pattern number, as applicable shall be as specified in the contract or order (see 4.1).

NOTE 1—The patterns that are available are indicated in individual manufacturer’s current catalogs.

5.3 *Monolithic Vinyl Tile*—The tile shall be uniform, with respect to color, pattern effect, and composition, throughout the thickness of the tile.

5.4 *Surface Decorated*—In surface-decorated tiles, the pattern and color need not extend through the entire thickness of the tile. The composition of each layer shall be according to Table 1.

5.4.1 The appearance of the surface decorated tile, when the wearing layer is removed by any suitable means, to a depth of 0.010 in. (0.25 mm) shall compare favorably for decoration with the tile’s original appearance.

5.5 *Printed Film Vinyl Tile*—The structure of printed solid vinyl tiles is formed of vinyl wear layer which may be transparent or translucent. The pattern and colors are created by a print between the wear layer and the intermediate colored layer or base layer. Other base layers may be added. Products will comply with Table 1 for binder content.

5.5.1 For commercial applications, the wear layer shall be a minimum of 0.020 in. (0.50 mm) thick.

**TABLE 1 Minimum Binder Content**

	Class I	Class II	Class III
Each ply or layer	34 %	34 %	...
Clear wear layer	...	...	90 %
Base/Inter layer(s)	...	...	30 % <sup>A</sup>

<sup>A</sup>Single composite average of binder content for layers, other than clear wear layer.