

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Conductors of insulated cables

Ames des câbles isolés

Without a doubt, the most common way to get full document from standards.iteh.ai



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2004 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Conductors of insulated cables

Ames des câbles isolés

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

R

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Terms and definitions	6
3 Classification	6
4 Materials	7
4.1 Introduction	7
4.2 Solid aluminium conductors	7
4.3 Circular and shaped stranded aluminium conductors.....	7
5 Solid conductors and stranded conductors.....	7
5.1 Solid conductors (class 1).....	7
5.1.1 Construction	7
5.1.2 Resistance.....	8
5.2 Stranded circular non-compacted conductors (class 2).....	8
5.2.1 Construction	8
5.2.2 Resistance.....	8
5.3 Stranded compacted circular conductors and stranded shaped conductors (class 2)	8
5.3.1 Construction	8
5.3.2 Resistance.....	8
6 Flexible conductors (classes 5 and 6).....	8
6.1 Construction.....	8
6.2 Resistance	9
7 Check of compliance with Clauses 5 and 6.....	9
Annex A (normative) Measurement of resistance	13
Annex B (informative) Exact formulae for the temperature correction factors.....	15
Annex C (informative) Guide to the dimensional limits of circular conductors	16

INTERNATIONAL ELECTROTECHNICAL COMMISSION

CONDUCTORS OF INSULATED CABLES**FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60228 has been prepared by IEC technical committee 20: Electric cables.

This third edition cancels and replaces the IEC 60228 (1978), its Amendment 1 (1993) and its first supplement, IEC 60228A (1982).

The principal changes with respect to the previous edition are as follows:

- a) the consolidation of material from IEC 60228A;
- b) addition of a definition for nominal cross-sectional area;
- c) an increase in the range of conductor sizes in Tables 1 and 2;
- d) addition of a note that solid aluminum alloy conductors, having the same dimensions as aluminum conductors, will have a higher resistance;
- e) strengthening of the recommendations for dimensional limits of compacted stranded copper conductors.

The text of this standard is based on the following documents:

FDIS	Report on voting
20/718/FDIS	20/737/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Conductors described in IEC 60228 are specified in metric sizes. Canada at present uses conductor sizes and characteristics according to the American Wire Gauge (AWG) system and kcmil for larger sizes as shown below. The use of these sizes is currently prescribed uniformly across Canada for installations by sub-national regulations. IEC TC 20 cable product standards do not prescribe cables with AWG/kcmil conductors.

AWG				kcmil			
Conductor size	Nominal cross-sectional area mm ²	Conductor size	Nominal cross-sectional area mm ²	Conductor size	Nominal cross-sectional area mm ²	Conductor size	Nominal cross-sectional area mm ²
-	-	-	-	250	127	750	380
-	-	-	-	300	152	800	405
20	0,519	4	21,2	350	177	900	456
18	0,823	3	26,7	400	203	1000	507
16	1,31	2	33,6	450	228	1200	608
14	2,08	1	42,4	500	253	1250	633
12	3,31	1/0	53,5	550	279	1500	760
10	5,26	2/0	67,4	600	304	1750	887
8	8,37	3/0	85,0	650	329	2000	1010
6	13,3	4/0	107	700	355	-	-

INTRODUCTION

IEC 60228 is intended as a fundamental reference standard for IEC Technical Committees and National Committees in drafting standards for electric cables, and to the National Committees in drafting specifications for use in their own countries. These committees should select from the tables of this general standard the conductors appropriate to the particular applications with which they are concerned and either include the applicable details in their cable specifications or make appropriate references to this standard.

In preparing this edition the main objects have been to incorporate IEC 60228A into it and maintain a simplified yet informative standard so far as is compatible with technical and economic considerations.

Sample Document

get full document from standards.iteh.ai

CONDUCTORS OF INSULATED CABLES

1 Scope

This International Standard specifies the nominal cross-sectional areas, in the range 0,5 mm² to 2 500 mm², for conductors in electric power cables and cords of a wide range of types. Requirements for numbers and sizes of wires and resistance values are also included. These conductors include solid and stranded copper, aluminium and aluminium alloy conductors in cables for fixed installations and flexible copper conductors.

The standard does not apply to conductors for telecommunication purposes.

The applicability of this standard to a particular type of cable is as specified in the standard for the type of cable.

Unless indicated to the contrary in a particular clause, this standard relates to the conductors in the finished cable and not to the conductor as made or supplied for inclusion into a cable.

Informative annexes are included giving supplementary information covering temperature correction factors for resistance measurement (Annex B) and dimensional limits of circular conductors (Annex C).

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

metal-coated

coated with a thin layer of suitable metal, such as tin or tin alloy

2.2

nominal cross-sectional area

value that identifies a particular size of conductor but is not subject to direct measurement

NOTE Each particular size of conductor in this standard is required to meet a maximum resistance value.

3 Classification

The conductors have been divided into four classes, 1, 2, 5 and 6. Those in classes 1 and 2 are intended for use in cables for fixed installations. Classes 5 and 6 are intended for use in flexible cables and cords but may also be used for fixed installations.

- Class 1: solid conductors.
- Class 2: stranded conductors.
- Class 5: flexible conductors.
- Class 6: flexible conductors which are more flexible than class 5.

4 Materials

4.1 Introduction

The conductors shall consist of one of the following:

- plain or metal-coated annealed copper;
- aluminium or aluminium alloy.

4.2 Solid aluminium conductors

Circular and shaped solid aluminium conductors shall be made from aluminium such that the tensile strength of the completed conductor is within the following limits:

Nominal cross-sectional area mm ²	Tensile strength N/mm ²
10 and 16	110 to 165
25 and 35	60 to 130
50	60 to 110
70 and above	60 to 90

NOTE The values given above are not applicable to aluminium alloy conductors.

4.3 Circular and shaped stranded aluminium conductors

Stranded aluminium conductors shall be made from aluminium such that the tensile strength of the individual wires is within the following limits:

Nominal cross-sectional area mm ²	Tensile strength N/mm ²
10	up to 200
16 and above	125 to 205

NOTE 1 The values given above are not applicable to aluminium alloy conductors.

NOTE 2 This data can only be checked on wires taken before stranding and not on wires taken from a stranded conductor.

5 Solid conductors and stranded conductors

5.1 Solid conductors (class 1)

5.1.1 Construction

- a) Solid conductors (class 1) shall consist of one of the materials specified in Clause 4.
- b) Solid copper conductors shall be of circular cross-section.

NOTE Solid copper conductors having nominal cross-sectional areas of 25 mm² and above are for particular types of cable, e.g. mineral insulated, and not for general purposes.

- c) Solid aluminium and solid aluminium alloy conductors of sizes 10 mm² to 35 mm² shall be of circular cross-section. Larger sizes shall be of circular cross-section for single-core cables and may be of either circular or shaped cross-section for multi-core cables.

5.1.2 Resistance

The resistance of each conductor at 20 °C, when determined in accordance with Clause 7, shall not exceed the appropriate maximum value given in Table 1.

NOTE For solid aluminium alloy conductors, having the same nominal cross-sectional area as an aluminium conductor the resistance value given in Table 1 should be multiplied by a factor of 1,162 unless otherwise agreed between the manufacturer and the purchaser.

5.2 Stranded circular non-compacted conductors (class 2)

5.2.1 Construction

- a) Stranded circular non-compacted conductors (class 2) shall consist of one of the materials specified in Clause 4.
- b) Stranded aluminium or aluminium alloy conductors shall have a cross-sectional area not less than 10 mm².
- c) The wires in each conductor shall all have the same nominal diameter.
- d) The number of wires in each conductor shall be not less than the appropriate minimum number given in Table 2.

5.2.2 Resistance

The resistance of each conductor at 20 °C, when determined in accordance with Clause 7, shall not exceed the appropriate maximum value given in Table 2.

5.3 Stranded compacted circular conductors and stranded shaped conductors (class 2)

5.3.1 Construction

- a) Stranded compacted circular conductors and stranded shaped conductors (class 2) shall consist of one of the materials specified in Clause 4. Stranded compacted circular aluminium or aluminium alloy conductors shall have a nominal cross-sectional area not less than 10 mm². Stranded shaped copper, aluminium or aluminium alloy conductors shall have a nominal cross-sectional area of not less than 25 mm².
- b) The ratio of the diameters of two different wires in the same conductor shall not exceed 2.
- c) The number of wires in each conductor shall be not less than the appropriate minimum number given in Table 2.

NOTE This requirement applies to conductors made with wires of circular cross-section before compaction and not to conductors made with pre-shaped wires.

5.3.2 Resistance

The resistance of each conductor at 20 °C, when determined in accordance with Clause 7, shall not exceed the appropriate value given in Table 2.

6 Flexible conductors (classes 5 and 6)

6.1 Construction

- a) Flexible conductors (classes 5 and 6) shall consist of plain or metal-coated annealed copper.
- b) The wires in each conductor shall have the same nominal diameter.
- c) The diameter of the wires in each conductor shall not exceed the appropriate maximum value given in Tables 3 or 4.

6.2 Resistance

The resistance of each conductor at 20 °C, when determined in accordance with Clause 7, shall not exceed the appropriate maximum value given in Tables 3 or 4.

7 Check of compliance with Clauses 5 and 6

Compliance with the requirements of 5.1.1, 5.2.1, 5.3.1 and 6.1 shall be checked on the completed cable by inspection and measurement where practicable.

Compliance with the requirements for resistance given in 5.1.2, 5.2.2, 5.3.2 and 6.2 shall be checked by measurement in accordance with Annex A and corrected for temperature by the factors in Table A.1.

Table 1 – Class 1 solid conductors for single-core and multicore cables

1	2	3	4
Nominal cross-sectional area mm ²	Maximum resistance of conductor at 20 °C		
	Circular, annealed copper conductors		Aluminium and aluminium alloy conductors, circular or shaped ^c
	Plain	Metal-Coated	
	Ω/km	Ω/km	Ω/km
0,5	36,0	36,7	-
0,75	24,5	24,8	-
1,0	18,1	18,2	-
1,5	12,1	12,2	-
2,5	7,41	7,56	-
4	4,61	4,70	-
6	3,08	3,11	-
10	1,83	1,84	3,08 ^a
16	1,15	1,16	1,91 ^a
25	0,727 ^b	-	1,20 ^a
35	0,524 ^b	-	0,868 ^a
50	0,387 ^b	-	0,641
70	0,268 ^b	-	0,443
95	0,193 ^b	-	0,320 ^d
120	0,153 ^b	-	0,253 ^d
150	0,124 ^b	-	0,206 ^d
185	0,101 ^b	-	0,164 ^d
240	0,0775 ^b	-	0,125 ^d
300	0,0620 ^b	-	0,100 ^d
400	0,0465 ^b	-	0,0778
500	-	-	0,0605
630	-	-	0,0469
800	-	-	0,0367
1 000	-	-	0,0291
1 200	-	-	0,0247

^a Aluminium conductors 10 mm² to 35 mm² circular only; see 5.1.1 c).

^b See note to 5.1.1 b).

^c See note to 5.1.2.

^d For single core cables, four sectoral shaped conductors may be assembled into a single circular conductor. The maximum resistance of the assembled conductor shall be 25 % of that of the individual component conductors.

Table 2 – Class 2 stranded conductors for single-core and multi-core cables

1	2	3	4	5	6	7	8	9	10
Nominal cross-sectional area mm ²	Minimum number of wires in the conductor						Maximum resistance of conductor at 20°C		
	Circular		Circular compacted		Shaped		Annealed copper conductor		Aluminium or aluminium alloy conductor ^c Ω/km
	Cu	Al	Cu	Al	Cu	Al	Plain wires Ω/km	Metal-coated wires Ω/km	
0,5	7	-	-	-	-	-	36,0	36,7	-
0,75	7	-	-	-	-	-	24,5	24,8	-
1,0	7	-	-	-	-	-	18,1	18,2	-
1,5	7	-	6	-	-	-	12,1	12,2	-
2,5	7	-	6	-	-	-	7,41	7,56	-
4	7	-	6	-	-	-	4,61	4,70	-
6	7	-	6	-	-	-	3,08	3,11	-
10	7	7	6	6	-	-	1,83	1,84	3,08
16	7	7	6	6	-	-	1,15	1,16	1,91
25	7	7	6	6	6	6	0,727	0,734	1,20
35	7	7	6	6	6	6	0,524	0,529	0,868
50	19	19	6	6	6	6	0,387	0,391	0,641
70	19	19	12	12	12	12	0,268	0,270	0,443
95	19	19	15	15	15	15	0,193	0,195	0,320
120	37	37	18	15	18	15	0,153	0,154	0,253
150	37	37	18	15	18	15	0,124	0,126	0,206
185	37	37	30	30	30	30	0,0991	0,100	0,164
240	37	37	34	30	34	30	0,0754	0,0762	0,125
300	61	61	34	30	34	30	0,0601	0,0607	0,100
400	61	61	53	53	53	53	0,0470	0,0475	0,0778
500	61	61	53	53	53	53	0,0366	0,0369	0,0605
630	91	91	53	53	53	53	0,0283	0,0286	0,0469
800	91	91	53	53	-	-	0,0221	0,0224	0,0367
1 000	91	91	53	53	-	-	0,0176	0,0177	0,0291
1 200	b						0,0151	0,0151	0,0247
1 400 ^a	b						0,0129	0,0129	0,0212
1 600	b						0,0113	0,0113	0,0186
1 800 ^a	b						0,0101	0,0101	0,0165
2 000	b						0,0090	0,0090	0,0149
2 500	b						0,0072	0,0072	0,0127

^a These sizes are non-preferred. Other non-preferred sizes are recognized for some specialized applications but are not within the scope of this standard.

^b The minimum number of wires for these sizes is not specified. These sizes may be constructed from 4, 5 or 6 equal segments (Milliken).

^c For stranded aluminium alloy conductors having the same nominal cross-sectional area as an aluminium conductor the resistance value should be agreed between the manufacturer and the purchaser.