

INTERNATIONAL STANDARD

CONSOLIDATED VERSION

**Specifications for particular types of winding wires -
Part 0-1: General requirements - Enamelled round copper wire**

Sample Document

get full document from standards.iteh.ai



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2026 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search -

webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope	6
2 Normative references	6
3 Terms, definitions, general notes and appearance	6
3.1 Terms and definitions.....	6
3.2 General notes	7
3.2.1 Methods of test.....	7
3.2.2 Winding wire.....	8
3.3 Appearance	8
4 Dimensions	8
4.1 Conductor diameter	8
4.2 Out of roundness of conductor (nominal conductor diameters over 0,063 mm)	12
4.3 Minimum increase in diameter due to the insulation and the bonding layer (nominal conductor diameters over 0,063 mm).....	12
4.3.1 Enamelled wires without a bonding layer	12
4.3.2 Enamelled wires with a bonding layer	12
4.3.3 Intermediate nominal conductor diameters.....	12
4.4 Maximum overall diameter	12
4.4.1 Enamelled wires without a bonding layer	12
4.4.2 Enamelled wires with a bonding layer	13
5 Electrical resistance	13
6 Elongation	14
7 Springiness	14
7.1 Nominal conductor diameters from 0,080 mm up to and including 1,600 mm.....	14
7.2 Nominal conductor diameters over 1,600 mm.....	14
8 Flexibility and adherence	16
8.1 Mandrel winding test (nominal conductor diameters up to and including 1,600 mm)	16
8.2 Stretching test (nominal conductor diameters over 1,600 mm)	16
8.3 Jerk test (nominal conductor diameters up to and including 1,000 mm).....	16
8.4 Peel test (nominal conductor diameters over 1,000 mm)	16
9 Heat shock	17
9.1 Nominal conductor diameters up to and including 1,600 mm	17
9.2 Nominal conductor diameters over 1,600 mm.....	17
10 Cut-through	18
11 Resistance to abrasion	18
12 Resistance to solvents.....	18
13 Breakdown voltage	18
13.1 General.....	18
13.2 Nominal conductor diameters up to and including 0,100 0,500 mm	18
13.3 Nominal conductor diameters over 0,100 mm up to and including 2,500 mm	20
13.4 Nominal conductor diameters over 2,500 mm.....	22

14	Continuity of insulation (nominal conductor diameters up to and including 1,600 mm)	23
15	Temperature index	23
16	Resistance to refrigerants.....	23
17	Solderability	23
18	Heat or solvent bonding.....	23
19	Dielectric dissipation factor.....	23
20	Resistance to transformer oil	23
21	Loss of mass	23
23	Pin hole test	24
30	Packaging	24
	Annex A (informative) Dimensions for intermediate nominal conductor diameters (R 40).....	25
	Annex B (informative normative) Method for the calculation of linear resistance	29
	Annex C (informative) Resistance	31
	Bibliography.....	34
	 Table 1 – Dimensions of enamelled wires (R 20) – Preferred nominal conductor diameters (1 of 2)	9
	Table 2 – Dimensions of enamelled wires with a bonding layer (R 20) – Preferred nominal conductor diameters (1 of 2)	11
	Table 3 – Electrical resistance	13
	Table 4 – Elongation	14
	Table 5 – Springiness	15
	Table 6 – Mandrel winding	16
	Table 7 – Heat shock	17
	Table 8 – Breakdown voltage – Preferred nominal conductor diameters (R 20) (0,018 mm up to and including 0,100 0,500 mm).....	19
	Table 9 – Breakdown voltage – Intermediate nominal conductor diameters (R 40) (0,019 mm up to and including 0,095 0,475 mm).....	20
	Table 10 – Breakdown voltage – Preferred nominal conductor diameters (R 20) (0,112 mm up to and including 2,500 mm)	21
	Table 11 – Breakdown voltage – Intermediate nominal conductor diameters (R 40) (0,106 mm up to and including 0,950 mm)	22
	Table 12 – Breakdown voltage – Nominal conductor diameters over 2,500 mm.....	22
	Table 13 – Continuity of insulation	23
	Table 14 – Maximum number of pin holes	24
	Table A.1 – Dimensions of enamelled wires (R 40) – Intermediate nominal conductor diameters (1 of 2)	25
	Table A.2 – Dimensions of enamelled wires with a bonding layer (R 40) – Intermediate nominal conductor diameters (1 of 2)	27
	Table B.1 – Ratios	30
	Table C.1 – Electrical resistances – Nominal conductor diameters over 0,063 0,280 mm up to and including 1,000 5,000 mm	33

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-1: General requirements – Enamelled round copper wire

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendments has been prepared for user convenience.

IEC 60317-0-1 edition 4.2 contains the fourth edition (2023-10) [documents 55/1409/FDIS and 55/1430/RVD], its amendment 1 (2019-08) [documents 55/1782/FDIS and 55/1799/RVD] and its amendment 2 (2026-08) [documents 55/2088/FDIS and 55/2115/RVD].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendments 1 and 2. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 60317-0-1 has been prepared by IEC technical committee 55: Winding wires.

This fourth edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- revision to the definition of nominal conductor dimension;
- new subclause containing general notes on winding wire, formerly a part of the scope;
- revision to elongation requirements in Table 4;
- revisions to Clause 13, Breakdown voltage, to include new requirements for intermediate wire diameters;
- revision to continuity of insulation requirements in Table 13;
- revision to the introduction of Annex A;
- revision to B.2 of Annex B;
- revision to Table C.1 of Annex C.

This standard is to be read in conjunction with the IEC 60851 series. The clause numbers used in this part of IEC 60317 are identical with the respective test numbers of the IEC 60851 series.

In case of inconsistencies between IEC 60851 and this part of IEC 60317, the latter prevails.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

Sample Document

get full document from standards.iteh.ai

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-1: General requirements – Enamelled round copper wire

1 Scope

This part of IEC 60317 specifies general requirements of enamelled round copper winding wires with or without bonding layer.

The range of nominal conductor diameters is given in the relevant specification sheet.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60172, *Test procedure for the determination of the temperature index of enamelled winding wires*

IEC 60851 (all parts), *Winding wires – Test methods*

ISO 3, *Preferred numbers – Series of preferred numbers*

ISO 1190-1, *Copper and copper alloys – Code of designation – Part 1: Designation of materials*

ASTM B49-17, *Standard Specification for Copper Rod for Electrical Purposes*

EN 1977:2013, *Copper and copper alloys – Copper drawing stock (wire rod)*

3 Terms, definitions, general notes and appearance

For the purposes of this document, the following terms and definitions apply.

3.1 Terms and definitions

3.1.1

bonding layer

material which is deposited on an enamelled wire and which has the specific function of bonding wires together

3.1.2

class

thermal performance of a wire expressed by the temperature index and the heat shock temperature

3.1.3

coating

material which is deposited on a conductor or wire by a suitable means and then dried and/or cured

3.1.4

conductor

bare metal after removal of the insulation

3.1.5

crack

opening in the insulation which exposes the conductor to view at the stated magnification

3.1.6

dual coating

insulation composed of two different materials, an underlying and a superimposed coating

3.1.7

enamelled wire

wire coated with an insulation of cured resin

3.1.8

grade

range of thickness of the insulation of a wire

3.1.9

insulation

coating or covering on the conductor with the specific function of withstanding voltage

3.1.10

nominal conductor dimension

designation of the conductor size in accordance with the IEC 60317 series

3.1.11

normal vision

20/20 vision, with corrective lenses, if necessary

3.1.12

sole coating

insulation composed of one material

3.1.13

winding wire

wire used for winding a coil to provide a magnetic field

3.1.14

wire

conductor coated or covered with an insulation

3.2 General notes

3.2.1 Methods of test

All methods of test to be used for this part of IEC 60317 are given in the IEC 60851 series.

The clause numbers used in this standard are identical to the corresponding test numbers in the IEC 60851 series of standards.

In case of inconsistencies between the publication on methods of test and this standard, IEC 60317-0-1 shall prevail.

Where no specific range of nominal conductor diameters is given for a test, the test applies to all nominal conductor diameters covered by the specification sheet.

Unless otherwise specified, all tests shall be carried out at a temperature from 15 °C to ~~35~~ 40 °C and a relative humidity ~~from 45 of 25~~ % to 75 %. Before measurements are made, the specimens shall be preconditioned under these atmospheric conditions for a time sufficient to allow the specimens to reach stability.

The wire to be tested shall be removed from the packaging in such a way that the wire will not be subjected to tension or unnecessary bends. Before each test, sufficient wire should be discarded to ensure that any damaged wire is not included in the test specimens.

3.2.2 Winding wire

See the relevant specification sheet.

In addition, when reference is made to a winding wire according to a standard of the IEC 60317 series mentioned under Clause 2, the following information is given in the description:

- reference to IEC specification;
- nominal conductor diameter in millimetres;
- grade.

EXAMPLE IEC 60317-1 – 0,500 Grade 2

3.3 Appearance

The film coating shall be essentially smooth and continuous, free from streaks, blisters and foreign material when examined with normal vision, as wound on the original spool or reel.

When agreed upon between the user and supplier, examination using 6× to 10× magnification shall be used for wires with a nominal diameter less than 0,1 mm.

4 Dimensions

4.1 Conductor diameter

The series of preferred nominal conductor diameters shall correspond to series R 20 according to ISO 3. The actual values and their tolerances are given in Tables 1 and 2.

The series of intermediate diameters from which the user may select intermediate nominal conductor diameters, when required for technical reasons, shall correspond to series R 40 according to ISO 3. The actual values and their tolerances are given in Annex A.

The conductor diameter shall not differ from the nominal diameter by more than the limit given in Tables 1 or 2.

**Table 1 – Dimensions of enamelled wires (R 20) –
Preferred nominal conductor diameters (1 of 2)**

Nominal conductor diameter mm	Conductor tolerance $\pm$ mm	Minimum increase due to the insulation mm			Maximum overall diameter mm		
		Grade 1	Grade 2	Grade 3	Grade 1	Grade 2	Grade 3
0,018		0,002	0,004	0,006	0,022	0,024	0,026
0,020		0,002	0,004	0,007	0,024	0,027	0,030
0,022		0,002	0,005	0,008	0,027	0,030	0,033
0,025		0,003	0,005	0,008	0,031	0,034	0,037
0,028		0,003	0,006	0,009	0,034	0,038	0,042
0,032		0,003	0,007	0,010	0,039	0,043	0,047
0,036		0,004	0,008	0,011	0,044	0,049	0,053
0,040		0,004	0,008	0,012	0,049	0,054	0,058
0,045		0,005	0,009	0,013	0,055	0,061	0,066
0,050		0,005	0,010	0,014	0,060	0,066	0,072
0,056		0,006	0,011	0,015	0,067	0,074	0,081
0,063		0,006	0,012	0,017	0,076	0,083	0,090
0,071	0,003	0,007	0,012	0,018	0,084	0,091	0,098
0,080	0,003	0,007	0,014	0,020	0,094	0,101	0,108
0,090	0,003	0,008	0,015	0,022	0,105	0,113	0,120
0,100	0,003	0,008	0,016	0,023	0,117	0,125	0,132
0,112	0,003	0,009	0,017	0,026	0,130	0,139	0,147
0,125	0,003	0,010	0,019	0,028	0,144	0,154	0,163
0,140	0,003	0,011	0,021	0,030	0,160	0,171	0,181
0,160	0,003	0,012	0,023	0,033	0,182	0,194	0,205
0,180	0,003	0,013	0,025	0,036	0,204	0,217	0,229
0,200	0,003	0,014	0,027	0,039	0,226	0,239	0,252
0,224	0,003	0,015	0,029	0,043	0,252	0,266	0,280
0,250	0,004	0,017	0,032	0,048	0,281	0,297	0,312
0,280	0,004	0,018	0,033	0,050	0,312	0,329	0,345
0,315	0,004	0,019	0,035	0,053	0,349	0,367	0,384
0,355	0,004	0,020	0,038	0,057	0,392	0,411	0,428
0,400	0,005	0,021	0,040	0,060	0,439	0,459	0,478
0,450	0,005	0,022	0,042	0,064	0,491	0,513	0,533
0,500	0,005	0,024	0,045	0,067	0,544	0,566	0,587

Table 1 (2 of 2)

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase due to the insulation mm			Maximum overall diameter mm		
		Grade 1	Grade 2	Grade 3	Grade 1	Grade 2	Grade 3
0,560	0,006	0,025	0,047	0,071	0,606	0,630	0,653
0,630	0,006	0,027	0,050	0,075	0,679	0,704	0,728
0,710	0,007	0,028	0,053	0,080	0,762	0,789	0,814
0,800	0,008	0,030	0,056	0,085	0,855	0,884	0,911
0,900	0,009	0,032	0,060	0,090	0,959	0,989	1,018
1,000	0,010	0,034	0,063	0,095	1,062	1,094	1,124
1,120	0,011	0,034	0,065	0,098	1,184	1,217	1,248
1,250	0,013	0,035	0,067	0,100	1,316	1,349	1,381
1,400	0,014	0,036	0,069	0,103	1,468	1,502	1,535
1,600	0,016	0,038	0,071	0,107	1,670	1,706	1,740
1,800	0,018	0,039	0,073	0,110	1,872	1,909	1,944
2,000	0,020	0,040	0,075	0,113	2,074	2,112	2,148
2,240	0,022	0,041	0,077	0,116	2,316	2,355	2,392
2,500	0,025	0,042	0,079	0,119	2,578	2,618	2,656
2,800	0,028	0,043	0,081	0,123	2,880	2,922	2,961
3,150	0,032	0,045	0,084	0,127	3,233	3,276	3,316
3,550	0,036	0,046	0,086	0,130	3,635	3,679	3,721
4,000	0,040	0,047	0,089	0,134	4,088	4,133	4,176
4,500	0,045	0,049	0,092	0,138	4,591	4,637	4,681
5,000	0,050	0,050	0,094	0,142	5,093	5,141	5,186

NOTE Minimum overall diameter up to and inclusive of 0,060 mm is calculated from the maximum resistance value for each corresponding diameter of Table 3, then adding the minimum increase due to the insulation.

Table 2 – Dimensions of enamelled wires with a bonding layer (R 20) – Preferred nominal conductor diameters (1 of 2)

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase underlying coating mm		Minimum increase bonding layer mm	Maximum overall diameter mm	
		Grade 1B	Grade 2B		Grade 1B	Grade 2B
0,020		0,002	0,004	0,002	0,026	0,029
0,022		0,002	0,005	0,002	0,030	0,033
0,025		0,003	0,005	0,002	0,034	0,037
0,028		0,003	0,006	0,003	0,038	0,042
0,032		0,003	0,007	0,003	0,044	0,048
0,036		0,004	0,008	0,003	0,050	0,055
0,040		0,004	0,008	0,003	0,055	0,060
0,045		0,005	0,009	0,003	0,062	0,068
0,050		0,005	0,010	0,003	0,068	0,074
0,056		0,006	0,011	0,003	0,075	0,082
0,063		0,006	0,012	0,005	0,085	0,092
0,071	0,003	0,007	0,012	0,005	0,094	0,101
0,080	0,003	0,007	0,014	0,005	0,105	0,112
0,090	0,003	0,008	0,015	0,005	0,117	0,125
0,100	0,003	0,008	0,016	0,005	0,129	0,137
0,112	0,003	0,009	0,017	0,008	0,143	0,152
0,125	0,003	0,010	0,019	0,009	0,158	0,168
0,140	0,003	0,011	0,021	0,010	0,175	0,186
0,160	0,003	0,012	0,023	0,010	0,197	0,209
0,180	0,003	0,013	0,025	0,010	0,220	0,233
0,200	0,003	0,014	0,027	0,011	0,243	0,256
0,224	0,003	0,015	0,029	0,012	0,270	0,284
0,250	0,004	0,017	0,032	0,013	0,300	0,316
0,280	0,004	0,018	0,033	0,013	0,331	0,348
0,315	0,004	0,019	0,035	0,014	0,369	0,387
0,355	0,004	0,020	0,038	0,015	0,413	0,432
0,400	0,005	0,021	0,040	0,016	0,461	0,481
0,450	0,005	0,022	0,042	0,016	0,514	0,536
0,500	0,005	0,024	0,045	0,017	0,568	0,590
0,560	0,006	0,025	0,047	0,017	0,630	0,654

Table 2 (2 of 2)

Nominal conductor diameter mm	Conductor tolerance ± mm	Minimum increase underlying coating mm		Minimum increase bonding layer mm	Maximum overall diameter mm	
		Grade 1B	Grade 2B		Grade 1B	Grade 2B
0,630	0,006	0,027	0,050	0,018	0,704	0,729
0,710	0,007	0,028	0,053	0,019	0,788	0,815
0,800	0,008	0,030	0,056	0,020	0,882	0,911
0,900	0,009	0,032	0,060	0,020	0,987	1,017
1,000	0,010	0,034	0,063	0,021	1,091	1,123
1,120	0,011	0,034	0,065	0,022	1,214	1,247
1,250	0,013	0,035	0,067	0,022	1,346	1,379
1,400	0,014	0,036	0,069	0,023	1,499	1,533
1,600	0,016	0,038	0,071	0,023	1,702	1,738
1,800	0,018	0,039	0,073	0,024	1,905	1,942
2,000	0,020	0,040	0,075	0,025	2,108	2,146

NOTE Minimum overall diameter up to and inclusive of 0,060 mm is calculated from the maximum resistance value for each corresponding diameter of Table 3, then adding the minimum increase due to the insulation, plus minimum increase due to the bonding layer.

4.2 Out of roundness of conductor (nominal conductor diameters over 0,063 mm)

The difference between the minimum and maximum diameter, at any one point, shall not be more than the figure given in column 2 of Table 1 or Table 2.

4.3 Minimum increase in diameter due to the insulation and the bonding layer (nominal conductor diameters over 0,063 mm)

4.3.1 Enamelled wires without a bonding layer

The minimum increase in diameter due to the insulation shall not be less than the values given in Table 1.

4.3.2 Enamelled wires with a bonding layer

The minimum increase in diameter due to the insulation including the bonding layer shall not be less than the values given in Table 2.

4.3.3 Intermediate nominal conductor diameters

For intermediate nominal conductor diameters, the minimum increase figure corresponding to the next larger nominal conductor diameter in Table 1 or Table 2 shall apply.

4.4 Maximum overall diameter

4.4.1 Enamelled wires without a bonding layer

The maximum overall diameter shall not exceed the values given in Table 1.

4.4.2 Enamelled wires with a bonding layer

The maximum overall diameter shall not exceed the values given in Table 2.

5 Electrical resistance

The copper rod being used shall comply with at least one of the following: EN 1977, ISO 1190-1 or ASTM B49-17.

For nominal conductor diameters up to and including 0,280 mm the resistance at 20 °C shall be within the limits given in Table 3.

By agreement between purchaser and supplier, resistance measurements may be made for nominal conductor diameters over ~~0,0280~~ 0,280 mm. In case of such an agreement, the resistance at 20 °C shall be within the limits given in Annex C.

Table 3 – Electrical resistance

Nominal conductor diameter mm	Resistance Ω/m		
	Minimum	Nominal	Maximum
0,018	60,46	67,18	73,89
0,020	48,97	54,41	59,85
0,022	40,47	44,97	49,47
0,025	31,34	34,82	38,31
0,028	24,99	27,76	30,54
0,032	19,13	21,25	23,38
0,036	15,282	16,79	18,305
0,040	12,379	13,60	14,827
0,045	9,781	10,75	11,715
0,050	7,922	8,706	9,489
0,056	6,316	6,940	7,565
0,063	4,990	5,484	5,977
0,071	3,929	4,318	4,706
0,080	3,133	3,401	3,703
0,090	2,495	2,687	2,900
0,100	2,034	2,176	2,333
0,112	1,632	1,735	1,848
0,125	1,317	1,393	1,475
0,140	1,055	1,110	1,170
0,160	0,812 2	0,850 2	0,890 6
0,180	0,644 4	0,671 8	0,700 7
0,200	0,523 7	0,544 1	0,565 7
0,224	0,418 8	0,433 8	0,449 5
0,250	0,334 5	0,348 2	0,362 8
0,280	0,267 6	0,277 6	0,288 2
NOTE 1 Values for nominal conductor diameter up to and including 0,071 mm are calculated according to B.1 of Annex B.			
NOTE 2 Values for nominal conductor diameters above 0,071 mm are calculated according to B.2 of Annex B.			
NOTE 3 Nominal resistance values are provided for information only and are calculated according to Annex C.			