

INTERNATIONAL STANDARD

CONSOLIDATED VERSION

Magnetic materials -

**Part 8-5: Specifications for individual materials - Electrical steel strip and sheet
with specified mechanical properties and magnetic polarization**

get full document from standards.iteh.ai



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2026 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search -

webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Classification.....	7
5 Designation	7
6 General requirements	8
6.1 Production process	8
6.2 Form of supply.....	8
6.3 Delivery condition	8
6.4 Surface condition.....	9
6.5 Suitability for cutting	9
6.6 Suitability for welding.....	9
7 Technical requirements	9
7.1 Mechanical properties.....	9
7.2 Magnetic polarization.....	9
7.3 Geometrical characteristics and tolerances	11
7.3.1 Thickness	11
7.3.2 Width.....	13
7.3.3 Length	13
7.3.4 Edge wave (wave factor)	14
7.3.5 Residual curvature.....	14
7.3.6 Edge camber	15
7.4 Technological characteristics	15
7.4.1 Density	15
8 Inspection and testing.....	15
8.1 General.....	15
8.2 Selection of test samples	16
8.3 Preparation of test specimens.....	16
8.3.1 Mechanical properties.....	16
8.3.2 Magnetic polarization.....	16
8.3.3 Geometrical characteristics and tolerances.....	17
8.4 Test methods	17
8.4.1 General	17
8.4.2 Mechanical properties.....	17
8.4.3 Magnetic polarization.....	17
8.4.4 Geometrical characteristics and tolerances.....	17
8.5 Retests	18
9 Marking, labelling and packaging.....	18
10 Complaints	18
11 Information to be supplied by the purchaser	18
Annex A (informative) Number of test strips for magnetic property testing.....	19
Table 1 – Mechanical and magnetic characteristics for hot-rolled grades	10

Table 2 – Mechanical and magnetic characteristics for cold-rolled grades.....	11
Table 3 – Tolerance on nominal thickness for hot-rolled grades	12
Table 4 – Tolerance on nominal thickness for cold-rolled grades	12
Table 5 – Maximum difference in thickness in a direction perpendicular to the direction of rolling for hot-rolled grades	12
Table 6 – Maximum difference in thickness in a direction perpendicular to the direction of rolling for cold-rolled grades	13
Table 7 – Tolerance on nominal width of products supplied with trimmed edges	13
Table 8 – Tolerance on nominal length of sheets	14
Table 9 – Maximum distance between the lower face of a test specimen and the flat surface table for hot-rolled grades	14
Table 10 – Maximum distance between the lower face of a test specimen and the flat surface table for cold-rolled grades	15
Table 11 – Minimum number of Epstein test strips	16
Table A.1 – Number of test strips for magnetic property testing	19

Sample Document

get full document from standards.iteh.ai

INTERNATIONAL ELECTROTECHNICAL COMMISSION

Magnetic materials - Part 8-5: Specifications for individual materials - Electrical steel strip and sheet with specified properties and magnetic polarization

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of a patent, which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60404-8-5 edition 2.1 contains the second edition (2020-08) [documents 68/648/CDV and 68/662/RVC] and its amendment 1 (2026-06) [documents 68/794/CDV and 68/804/RVC].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 60404-8-5 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

This second edition cancels and replaces the first edition published in 1989. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) extension of the range of products to include the improved grades;
- b) division of "flatness" into "edge wave (wave factor)" and "residual curvature" in consistent with IEC 60404-9;
- c) change length of test specimen for determinations of geometrical characters from 2 m to 1 m.

The text of this International Standard is based on the following documents:

CDV	Report on voting
68/648/CDV	68/662/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60404 series, published under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this document and its amendment will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

INTRODUCTION

The first edition of IEC 60404-8-5, "*Magnetic materials – Part 8: Specifications for individual materials – Section Five – Specification for steel sheet and strip with specified mechanical properties and magnetic permeability*", was published in April 1989 and has not been revised for more than 30 years. Since then, new grades of cold-rolled material of minimum proof strength $R_{p0,2}$ greater than 400 MPa were developed and widely used. Thus, IEC TC 68 decided in 2017 at their meeting in Paris to revise this document. This revision also includes corrections to the first edition in order to improve consistency with the other parts of the IEC 60404-8 subseries.

Sample Document

get full document from standards.iteh.ai

1 Scope

This part of IEC 60404 defines the grades of electrical steel strip and sheet with specified mechanical properties and magnetic polarization. In particular, it gives general requirements, mechanical properties, magnetic polarization, geometric characteristics, tolerances and technological characteristics, as well as inspection procedures.

This document applies to electrical steel strip and sheet intended for the construction of poles and rims of rotating electrical machines.

The grades are grouped into two classes according to their manufacturing process:

- hot-rolled grades;
- cold-rolled grades.

They correspond to Class D21 of IEC 60404-1.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-121, *International Electrotechnical Vocabulary – Part 121: Electromagnetism*

IEC 60050-221, *International Electrotechnical Vocabulary – Chapter 221: Magnetic materials and components*

IEC 60404-1, *Magnetic materials – Part 1: Classification*

IEC 60404-2, *Magnetic materials – Part 2: Methods of measurement of the magnetic properties of electrical steel strip and sheet by means of an Epstein frame*

IEC 60404-4, *Magnetic materials – Part 4: Methods of measurement of d.c. magnetic properties of iron and steel*

IEC 60404-9, *Magnetic materials – Part 9: Methods of determination of the geometrical characteristics of electrical steel strip and sheet*

ISO 404, *Steel and steel products – General technical delivery requirements*

ISO 2566-1, *Steel – Conversion of elongation values – Part 1: Carbon and low alloy steels*

ISO 6892-1, *Metallic materials – Tensile testing – Part 1: Method of test at room temperature*

ISO 10474, *Steel and steel products – Inspection documents*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-121, IEC 60050-221, IEC 60404-9 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

edge wave

wave factor

variations of flatness of a length of strip or a sheet taking a form of waves at the slit edge of the product

Note 1 to entry: Edge wave is characterized by the wave factor which is the relation of the height of the wave to its length, expressed as a percentage.

[SOURCE: IEC 60404-9: 2018, 3.1]

3.2

residual curvature

variations of flatness of a length of strip or a sheet taking a permanent curvature in the rolling direction of the product

[SOURCE: IEC 60404-9: 2018, 3.2]

3.3

edge camber

greatest distance between a longitudinal edge of a length of strip or a sheet and the line joining the two extremities of the measured length of this edge

[SOURCE: IEC 60404-9: 2018, 3.3]

4 Classification

The grades covered by this document are classified according to the specified value of minimum proof strength $R_{p0.2}$, in MPa¹, according to the specified value of minimum magnetic polarization at a DC magnetic field strength of 15 000 A/m, in T, and according to the nominal thickness of the product², in mm.

5 Designation

The steel name comprises the following in the order given:

- the characteristic letters
 - "TG" for hot-rolled grades;
 - "TF" for cold-rolled grades;
- the specified value of minimum proof strength $R_{p0.2}$, in MPa;
- one hundred times the nominal thickness of the product, in mm;
- one hundred times the specified value of minimum magnetic polarization at a DC magnetic field strength of 15 000 A/m, in T.

¹ 1 MPa = 1 N/mm².

² In the rest of the document, the word "product" is used to mean "strip and sheet".

EXAMPLE: TF350-100-181 for cold-rolled electrical steel strip and sheet with a minimum proof strength $R_{p0,2}$ of 350 MPa, a nominal thickness of 1,0 mm, and a minimum magnetic polarization of 1,81 T at a DC magnetic field strength of 15 000 A/m.

6 General requirements

6.1 Production process

The production process of the steel and its chemical composition are left to the discretion of the manufacturer.

6.2 Form of supply

The product is supplied in coils in the case of strip and in bundles in the case of sheets.

The mass of the coils or bundles of sheets shall be agreed between the manufacturer and the purchaser at the time of enquiry and order.

The internal diameter of coils shall be agreed between the manufacturer and the purchaser at the time of enquiry and order. The recommended value for the internal diameter of coils is approximately 610 mm for hot-rolled grades, and approximately 508 mm for cold-rolled grades.

Strip shall be of constant width and wound in such a manner that the edges are superimposed in a regular manner and the side faces of the coil are substantially flat.

Coils shall be sufficiently tightly wound in order that they do not collapse under their own weight.

Strip may exhibit welds or interleaves resulting from the removal of defective zones or from the joining of several lengths to obtain the sizes of the coils required by the purchaser, if agreed between the manufacturer and the purchaser at the time of enquiry and order. If necessary, the marking of welds or interleaves may be agreed between the manufacturer and the purchaser at the time of enquiry and order.

For coils containing repair welds or interleaves, each part of the strip shall be of the same grade.

The edges of parts welded together shall not be so much out of alignment as to affect the further processing of the product.

Sheets which make up each bundle shall be stacked so that the side faces are substantially flat and approximately perpendicular to the top face.

Products supplied in sheets shall not contain any welds.

6.3 Delivery condition

The product is normally supplied without insulation. By agreement between the manufacturer and the purchaser at the time of enquiry and order, the product may be supplied with insulation on one or both sides. If the product is supplied with insulation, the nature of the insulation, its properties and their verification shall be agreed between the manufacturer and the purchaser at the time of enquiry and order.

Hot-rolled grades are normally supplied with an oxide scale layer unless they have been ordered pickled.

The product may be supplied lightly coated with oil by agreement between the manufacturer and the purchaser at the time of enquiry and order.

Coils supplied with trimmed edges and sheets shall not contain excessive burrs or cutting distortions which are prejudicial to the method of working of the product.

6.4 Surface condition

The surfaces shall be smooth and clean, free from grease and rust³. Dispersed defects such as scratches, blisters, cracks, etc. are only permitted if they are within the limits of the tolerances on thickness and if they are not detrimental to the correct use of the supplied product.

6.5 Suitability for cutting

The product shall be able to be cut or punched without causing premature wear of tools. The product shall be suitable for cutting or punching accurately into the usual shapes at any point when appropriate cutting or punching tools and technologies are used.

A special requirement concerning suitability for cutting or punching of the product may be specified by agreement between the manufacturer and the purchaser at the time of enquiry and order.

6.6 Suitability for welding

A special requirement concerning suitability for welding of the product may be specified by agreement between the manufacturer and the purchaser at the time of enquiry and order.

7 Technical requirements

7.1 Mechanical properties

The specified values of minimum proof strength $R_{p0.2}$, minimum tensile strength R_m and minimum percentage elongation after fracture A shall be as given in Table 1 and Table 2.

7.2 Magnetic polarization

The specific values of minimum magnetic polarization at DC magnetic field strengths of 5 000 A/m and 15 000 A/m shall be as given in Table 1 and Table 2.

The values of peak magnetic polarization at AC magnetic field strengths of 5 000 A/m and 15 000 A/m (expressed as peak values) and at frequencies of 50 Hz or 60 Hz may be used instead, provided the specified values of minimum magnetic polarization given in Table 1 and Table 2 are satisfied.

Other values at a magnetic field strength lower than 15 000 A/m may be specified by agreement between the manufacturer and the purchaser at the time of enquiry and order, instead of the values at a magnetic field strength of 15 000 A/m.

³ This should not be confused with some coloration of the insulation coating inherent to the manufacturing process.

Table 1 – Mechanical and magnetic characteristics for hot-rolled grades

Steel name ^a	Minimum proof strength $R_{p0,2}$ MPa	Minimum tensile strength R_m MPa	Minimum percentage elongation after fracture for an original gauge length L_0 A %		Minimum magnetic polarization ^c at a DC magnetic field strength J T	
			$L_0 = 80 \text{ mm}$	$L_0 = 5,65 \sqrt{S_0}$	5 000 A/m	15 000 A/m ^d
TG250-...-180	250	350	22	26	1,60	1,80
TG300-...-180	300	400	20	24	1,60	1,80
TG350-...-179	350	450	18	22	1,55	1,79
TG400-...-179	400	500	16	19	1,55	1,79
TG450-...-179	450	550	14	17	1,54	1,79
TG500-...-179	500	600	12	14	1,53	1,79
TG550-...-178	550	650	12	14	1,52	1,78
TG600-...-178	600	700	10	12	1,50	1,78
TG650-...-178	650	750	10	12	1,48	1,78
TG700-...-178	700	800	10	12	1,46	1,78

^a is one hundred times the nominal thickness of the product, in millimetres. Other steel names may be agreed between the manufacturer and the purchaser at the time of enquiry and order.

^b These values shall be obtained on a tensile test specimen of type 2, $L_0 = 80 \text{ mm}$, for products with thickness less than 3 mm and on a proportional test specimen, $L_0 = 5,65\sqrt{S_0}$, for products with thickness equal to or greater than 3 mm, the values may be converted each other in accordance with ISO 2566-1. Where L_0 is the original gauge length marked on the test specimen, in mm, and S_0 is the original cross-sectional area of the test specimen, in mm^2 (See 8.3.1).

^c It has been common practice for many years to give values of magnetic flux density. In fact the Epstein frame is used to determine magnetic polarization (intrinsic flux density) which is defined as follows in accordance with IEC 60050-121:

$$J = B - \mu_0 H$$

where

J is the magnetic polarization;

B is the magnetic flux density;

μ_0 is the magnetic constant: $4 \pi \times 10^{-7} \text{ H} \cdot \text{m}^{-1}$;

H is the magnetic field strength.

^d Other values at a magnetic field strength lower than 15 000 A/m may be agreed between the manufacturer and the purchaser at the time of enquiry and order, instead of the values at a magnetic field strength of 15 000 A/m.