

INTERNATIONAL STANDARD

COMMENTED VERSION

**Secondary cells and batteries containing alkaline or other non-acid electrolytes -
Safety requirements for portable sealed secondary cells, and for batteries made
from them, for use in portable applications -
Part 1: Nickel systems**

get full document from standards.iteh.ai



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2026 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search -

webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews, graphical symbols and the glossary. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 500 terminological entries in English and French, with equivalent terms in 25 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Parameter measurement tolerances	7
5 General safety considerations	8
5.1 General.....	8
5.2 Insulation and wiring	8
5.3 Venting	8
5.4 Temperature, voltage and current management	8
5.5 Terminal contacts	9
5.6 Assembly of cells into batteries	9
5.7 Quality plan	9
6 Type test and sample size	9
7 Specific requirements and tests	10
7.1 Charging procedure for test purposes	10
7.2 Intended use	10
7.2.1 Continuous low-rate charging (cells).....	10
7.2.2 Vibration	10
7.2.3 Case stress at high ambient temperature (batteries).....	11
7.2.4 Temperature cycling	11
7.3 Reasonably foreseeable misuse.....	12
7.3.1 Incorrect installation (cells).....	12
7.3.2 External short circuit.....	12
7.3.3 Free fall	13
7.3.4 Mechanical shock (crash hazard).....	13
7.3.5 Thermal abuse (cells)	13
7.3.6 Crushing of Crush (cells)	13
7.3.7 Low pressure (cells)	14
7.3.8 Overcharge.....	14
7.3.9 Forced discharge (cells)	14
8 Information for safety.....	14
8.1 General.....	14
8.2 Small cell and battery safety information	15
9 Marking	15
9.1 Cell marking.....	15
9.2 Battery marking	16
9.3 Caution for ingestion of small cells and batteries	16
9.4 Other information	16
10 Packaging	16
Annex A (informative) Recommendations to equipment manufacturers and battery assemblers	17
Annex B (informative) Recommendations to the end-users	18
Annex C (informative) Packaging	19
Bibliography.....	20

List of comments.....	21
Figure 1 – Temperature profile for 7.2.4 – Temperature cycling test.....	12
Figure 2 – Ingestion gauge	15
Table 1 – Sample size for type tests	10
Table 2 – Conditions for vibration test.....	11

Sample Document

get full document from standards.iteh.ai

INTERNATIONAL ELECTROTECHNICAL COMMISSION

Secondary cells and batteries containing alkaline or other non-acid electrolytes - Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications - Part 1: Nickel systems

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC [had/had not] received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This commented version (CMV) of the official standard IEC 62133-1:2026 edition 2.0 allows the user to identify the changes made to the previous IEC 62133-1:2017 edition 1.0. Furthermore, comments from IEC SC 21A experts are provided to explain the reasons of the most relevant changes, or to clarify any part of the content.

A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text. Experts' comments are identified by a blue-background number. Mouse over a number to display a pop-up note with the comment.

This publication contains the CMV and the official standard. The full list of comments is available at the end of the CMV.

IEC 62133-1 has been prepared by subcommittee 21A: Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC technical committee 21: Secondary cells and batteries. It is an International Standard.

This second edition cancels and replaces the first edition of IEC 62133-1 published in 2017. It constitutes a technical revision.

This edition includes the following significant technical changes with respect to IEC 62133-1:2017:

- a) removal of the definition "secondary battery";
- b) removal of the definition "portable battery";
- c) "removal of the definition "portable cell";
- d) replacement of the single term "room temperature" with $20\text{ °C} \pm 5\text{ °C}$ in 7.2.3;
- e) modification of Figure 1.

The text of this International Standard is based on the following documents:

Draft	Report on voting
21A/946/FDIS	21A/969/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts of the IEC 62133 series, published under the general title *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

1 Scope

This part of IEC 62133 specifies requirements and tests for the safe operation of portable sealed secondary nickel cells and batteries containing alkaline electrolyte, under intended use and reasonably foreseeable misuse.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-482:2004, *International Electrotechnical Vocabulary (IEV) - Part 482: Primary and secondary cells and batteries*

IEC 61951-1, *Secondary cells and batteries containing alkaline or other non-acid electrolytes - ~~Portable sealed rechargeable single cells~~ Secondary sealed cells and batteries for portable applications* 1 - Part 1: Nickel-Cadmium

IEC 61951-2, *Secondary cells and batteries containing alkaline or other non-acid electrolytes - ~~Portable sealed rechargeable single cells~~ Secondary sealed cells and batteries for portable applications* 1 - Part 2: Nickel-metal hydride

ISO/IEC Guide 51, *Safety aspects - Guidelines for their inclusion in standards*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-482, ISO/IEC Guide 51 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

safety

freedom from unacceptable risk

3.2

risk

combination of the probability of occurrence of harm and the severity of that harm

3.3

harm

physical injury or damage to the health of people or damage to property or to the environment

3.4

hazard

potential source of harm

3.5

intended use

use of a product, process or service in accordance with specifications, instructions and information provided by the supplier

3.6

reasonably foreseeable misuse

use of a product, process or service in a way which is not intended by the supplier, but which may result from readily predictable human behaviour

3.7

secondary cell

basic manufactured unit providing a source of electrical energy by direct conversion of chemical energy, that consists of electrodes, separators, electrolyte, container and terminals, and that is designed to be charged electrically

~~3.8~~

~~**secondary battery 2**~~

~~assembly of secondary cell(s) ready for use as a source of electrical energy characterized by its voltage, size, terminal arrangement, capacity and rate capability~~

~~Note 1 to entry:—Includes single cell batteries.~~

3.8

leakage

unplanned, visible escape of liquid electrolyte

3.9

venting

release of excessive internal pressure from a cell or battery in a manner intended by design to preclude rupture or explosion

3.10

rupture

mechanical failure of a cell container or battery case induced by an internal or external cause, resulting in exposure or spillage but not ejection of materials

3.11

explosion

failure that occurs when a cell container or battery case opens violently and major components are forcibly expelled

3.12

fire

emission of flames from a cell or battery

~~3.14~~

~~**portable battery 2**~~

~~battery for use in a device or appliance which is conveniently hand-carried~~

~~3.15~~

~~**portable cell 2**~~

~~cell intended for assembly in a portable battery~~

3.13

rated capacity

capacity value of a cell or battery determined under specified conditions and declared by the manufacturer

Note 1 to entry: The rated capacity is the quantity of electricity C_5 Ah (ampere-hours) declared by the manufacturer which a single cell can deliver when discharged at the reference test current of $0,2 I_t$ A to a specified final voltage, after charging, storing and discharging under specified conditions.

[SOURCE: IEC 60050-482:2004, 482-03-15, modified – In the definition, "battery" replaced with "cell or battery", Note 1 to entry added]

3.14

reference test current

I_t

charge or discharge current, expressed as a multiple of I_t A, where I_t A = C_5 Ah/1 h, as defined in IEC 61434, and based on the rated capacity (C_5 Ah) of the cell or battery

3.15

button cell

coin cell

cell with a cylindrical shape in which the overall height is less than the diameter, e.g. in the shape of a button or a coin

Note 1 to entry: In practice, the term coin is used exclusively for non-aqueous lithium cells.

[SOURCE: IEC 60050-482:2004, 482-02-40]

3.16

cylindrical cell

cell with a cylindrical shape in which the overall height is equal to or greater than the diameter

[SOURCE: IEC 60050-482:2004, 482-02-39]

3.17

prismatic cell

cell having the shape of a parallelepiped whose faces are rectangular

[SOURCE: IEC 60050-482:2004, 482-02-38, modified – Source term is "prismatic" (adj.). In the definition, "qualifies a cell or a battery" replaced with "cell"]

4 Parameter measurement tolerances

The overall accuracy of controlled or measured values, relative to the specified or actual parameters, shall be within these tolerances:

- a) ± 1 % for voltage;
- b) ± 1 % for current;
- c) ± 2 °C for temperature;
- d) $\pm 0,1$ % for time;
- e) ± 1 % for dimension;
- f) ± 1 % for capacity.

These tolerances comprise the combined accuracy of the measuring instruments, the measurement techniques used, and all other sources of error in the test procedure.

The details of the instrumentation used shall be provided in any report of results.

5 General safety considerations

5.1 General

The safety of secondary cells and batteries requires the consideration of two sets of applied conditions:

- a) intended use;
- b) reasonably foreseeable misuse.

Cells and batteries shall be so designed and constructed that they are safe under conditions of both intended use and reasonably foreseeable misuse. It is expected that cells or batteries subjected to misuse may fail to function following such experience. They shall not however present significant hazards. It may also be expected that cells and batteries subjected to intended use shall not only be safe but shall continue to be functional in all respects.

Potential hazards which are the subject of this document are:

- fire;
- burst/explosion;
- leakage of cell electrolyte;
- venting with continuous emission of flammable and/or toxic gas, and/or smoke; **3**
- burns from excessively high external temperatures;
- rupture of battery case with exposure of internal components.

Conformity with 5.2 to 5.7 for cells and batteries other than button cells is checked by inspection, by the tests of Clauses 7, and in accordance with the appropriate standard (see Clause 2 and Table 1).

5.2 Insulation and wiring

The insulation resistance between the positive terminal and externally exposed metal surfaces of the battery excluding electrical contact surfaces shall be not less than 5 MΩ at 500 V DC when measured 60 s after applying the voltage.

Internal wiring and insulation should be sufficient to withstand the maximum anticipated current, voltage and temperature requirements. The orientation of wiring should be such that adequate clearances and creepage distances are maintained between conductors. The mechanical integrity of internal connections should be sufficient to accommodate conditions of reasonably foreseeable misuse (i.e. solder alone is not considered a reliable means of connection).

5.3 Venting

Battery cases and cells shall incorporate a pressure relief mechanism or shall be so constructed that they will relieve excessive internal pressure at a value and rate that will preclude rupture, explosion and self-ignition. If encapsulation is used to support cells within an outer case, the type of encapsulant and the method of encapsulation shall neither cause the battery to overheat during normal operation nor inhibit pressure relief.

5.4 Temperature, voltage and current management

The design of batteries shall be such that abnormal temperature-rise conditions are prevented. Batteries shall be designed to be within temperature, voltage and current limits specified by the cell manufacturer. Batteries shall be provided with specifications and charging instructions for equipment manufacturers so that associated chargers are designed to maintain charging within the temperature, voltage and current limits specified.

Where necessary, applicable means can be provided to limit current to safe levels during charge and discharge.

5.5 Terminal contacts

The size and shape of the terminal contacts shall ensure that they can carry the maximum anticipated current. External terminal contact surfaces shall be formed from conductive materials with good mechanical strength and corrosion resistance. Terminal contacts shall be arranged so as to minimize the risk of short circuits.

5.6 Assembly of cells into batteries

If there is more than one battery housed in a single battery case, cells used in the assembly of each battery shall have closely matched capacities, be of the same design, be of the same chemistry and be from the same manufacturer. The battery shall have some type of safety device or feature for charging (example: keyed connector). 4

Manufacturers of cells shall specify current, voltage and temperature limits so that the battery manufacturer/designer may ensure proper design and assembly.

Batteries that are designed for the selective discharge of a portion of their series-connected cells shall incorporate circuitry to prevent operation of cells outside the limits specified by the cell manufacturer.

Protective circuit components should be added as appropriate and consideration given to the end-device application. When testing a battery, the manufacturer of the battery should provide a test report confirming its compliance according to this document.

5.7 Quality plan

The manufacturer shall prepare and implement a quality plan that defines procedures for the inspection of materials, components, cells and batteries and which covers the whole process of producing each type of cell or battery. Manufacturers should understand their process capabilities and should institute the necessary process controls as they relate to product safety.

6 Type test and sample size

Tests are made with the number of cells or batteries specified in Table 1 using cells or batteries that are not more than six months old. Unless otherwise specified in the relevant subclause of this document 5, tests are carried out in an ambient temperature of $20\text{ °C} \pm 5\text{ °C}$.

NOTE Test conditions are for type tests only and do not imply that intended use includes operation under these conditions. Similarly, the limit of six months is introduced for consistency and does not imply that the cell or battery safety is reduced after six months.

Table 1 – Sample size for type tests

Test	Cell ^a	Battery
7.2.1 Continuous low rate charging (cells)	5	–
7.2.2 Vibration	5	5
7.2.3 Case stress at high ambient temperature (batteries)	–	3
7.2.4 Temperature cycling	5	5
7.3.1 Incorrect installation (cells)	5 sets of 4	–
7.3.2 External short circuit	5 per temperature	5 per temperature
7.3.3 Free fall	3	3
7.3.4 Mechanical shock (crash hazard)	5	5
7.3.5 Thermal abuse (cells)	5	–
7.3.6 Crush (cells)	5 (10 for prismatic)	–
7.3.7 Low pressure (cells)	3	–
7.3.8 Overcharge	5	5
7.3.9 Forced discharge (cells)	5	–
^a – not applicable to button cells		

7 Specific requirements and tests

7.1 Charging procedure for test purposes

Unless otherwise stated in this document, the charging procedure for test purposes is carried out in an ambient temperature of 20 °C ± 5 °C, using the method declared by the manufacturer.

Prior to charging, the cell or battery shall have been discharged at 20 °C ± 5 °C at a constant current of 0,2 I_t A down to a specified final voltage.

WARNING: These tests use procedures which may result in harm if adequate precautions are not taken. Tests should only be performed by qualified and experienced technicians using adequate protection. To prevent burns, caution should be taken for those cells or batteries whose casings may exceed 75 °C as a result of testing.

7.2 Intended use

7.2.1 Continuous low-rate charging (cells)

a) Requirement

A continuous low-rate charge shall not cause fire or explosion.

b) Test

Fully charged cells are subjected for 28 days to a charge as specified by the manufacturer.

c) Acceptance criteria

No fire, no explosion.

7.2.2 Vibration

a) Requirements

Vibration encountered during transportation shall not cause leakage, fire or explosion.

b) Test

Fully charged cells or batteries are vibration-tested under the following test conditions and the sequence in Table 2. A simple harmonic motion is applied to the cells or batteries with an amplitude of 0,76 mm, and a total maximum excursion of 1,52 mm. The frequency is