

TECHNICAL SPECIFICATION

SPÉCIFICATION TECHNIQUE

BASIC SAFETY PUBLICATION

PUBLICATION FONDAMENTALE DE SÉCURITÉ

Fire hazard testing –

Part 6-31: Smoke obscuration – Small-scale static test – Materials

Essais relatifs aux risques du feu –

Partie 6-31: Opacité des fumées – Méthode statique à petite échelle – Matériaux



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2013 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente. un corrigendum ou amendement peut avoir été publié.

Liens utiles:

Recherche de publications CEI - www.iec.ch/searchpub

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

TECHNICAL SPECIFICATION

SPÉCIFICATION TECHNIQUE

BASIC SAFETY PUBLICATION

PUBLICATION FONDAMENTALE DE SÉCURITÉ

Fire hazard testing –

Part 6-31: Smoke obscuration – Small-scale static test – Materials

Essais relatifs aux risques du feu –

Partie 6-31: Opacité des fumées – Méthode statique à petite échelle – Matériaux

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

R

ICS 13.220.99; 29.020

ISBN 978-2-83220-671-3

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Relevance of test data and special observations	9
5 Test specimens	10
5.1 General	10
5.2 Number of test specimens	10
5.3 Size of test specimens	10
5.4 Conditioning of test specimens	10
6 Test procedure	10
6.1 Preparation and calibration of the test chamber.....	10
6.2 Preparation of test specimens.....	10
6.3 Test conditions	10
6.4 Determination of smoke opacity – running a test.....	11
6.5 Abnormal behaviour during a test.....	12
7 Expression of results	12
7.1 General.....	12
7.2 Specific optical density	12
8 Repeatability and reproducibility.....	13
9 Test report.....	14
Annex A (informative) Evaluation of the repeatability and the reproducibility from inter-laboratory tests	15
Annex B (informative) Example of test report – Determination of smoke opacity without air-change.....	18
Bibliography	20
Table A.1 – Measurement of D_m	15
Table A.2 – Measurement of VOF_4	16
Table A.3 – Coefficients of variation and relative precision of maximum specific optical density (D_m) in tests with application of pilot flames	16
Table A.4 – Coefficients of variation and relative precision of maximum specific optical density (D_m) in tests without application of pilot flames.....	17

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FIRE HAZARD TESTING –

**Part 6-31: Smoke obscuration –
Small-scale static test – Materials**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 60695-6-31, which is a technical specification, has been prepared by IEC technical committee 89: Fire hazard testing.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
89/1055/DTS	89/1093/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This second edition of IEC/TS 60695-6-31 cancels and replaces the first edition published in 1999. It constitutes a technical revision.

It has the status of a basic safety publication in accordance with IEC Guide 104 and ISO/IEC Guide 51.

This technical specification is to be used in conjunction with IEC/TS 60695-6-30.

The main changes with respect to the previous edition are listed below:

- The Foreword has been revised and updated.
- The Introduction has been updated.
- The Scope has been updated.
- The Normative references have been updated.
- Minor technical changes have been made throughout the document.
- Detailed editorial updates have been added throughout the document.

A list of all parts of the IEC 60695 series, under the general title *Fire hazard testing*, can be found on the IEC website.

Part 6 consists of the following parts:

- Part 6-1: Smoke obscuration – General guidance
- Part 6-2: Smoke obscuration – Summary and relevance of test methods
- Part 6-30: Smoke obscuration – Small scale static method – Apparatus
- Part 6-31: Smoke obscuration – Small-scale static test – Materials

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- transformed into an International Standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

The risk of fire needs to be considered in any electrical circuit, and the objective of component, circuit and equipment design, and the choice of materials, is to reduce the likelihood of fire, even in the event of foreseeable abnormal use, malfunction or failure.

Electrotechnical products, primarily as victims of fire, may nevertheless contribute to the fire. One of the contributing hazards is the release of smoke, which may cause a reduction of visibility and/or orientation which could impede escape from the building, or could impede fire fighting.

Consequently, a reduction in the amount and the rate of generation of smoke produced by materials/products during a fire reduces damage to equipment, facilitates evacuation of people and facilitates the intervention of emergency services.

Sample Document

get full document from standards.iteh.ai

FIRE HAZARD TESTING –

Part 6-31: Smoke obscuration – Small-scale static test – Materials

1 Scope

This part of IEC 60695 describes the test methods for the determination of the specific optical density of smoke produced by materials used in electrotechnical products using the apparatus described in technical specification IEC/TS 60695-6-30. Test specimens are exposed vertically to a radiant heat source with or without the application of a pilot flame in a closed chamber (i.e. without air-change).

The test methods are only applicable to flat, solid, non-metallic test specimens of materials used in electrotechnical products.

This technical specification does not provide a classification system for the behaviour of materials.

The test methods are not applicable to materials which melt and flow away from the direct impingement of heat flux.

The test methods are not recommended for further development for electrotechnical products, nor are they recommended as the basis for regulation or other controls on smoke release due to the limitations of the physical fire model and the test specimen geometry – see Clause 4.

WARNING: Appropriate safety measures are to be taken as toxic and harmful fire effluents may be produced by pyrolysis or combustion of test specimens.

This basic safety publication is intended for use by technical committees in the preparation of standards in accordance with the principles laid down in IEC Guide 104 and ISO/IEC Guide 51.

One of the responsibilities of a technical committee is, wherever applicable, to make use of basic safety publications in the preparation of its publications. The requirements, test methods or test conditions of this basic safety publication will not apply unless specifically referred to or included in the relevant publications.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60695-6-1, *Fire hazard testing – Part 6-1: Smoke obscuration – General guidance*

IEC/TS 60695-6-30:2012, *Fire hazard testing – Part 6: Guidance and test methods on the assessment of obscuration hazards of vision caused by smoke opacity from electrotechnical products involved in fires – Section 30: Small scale static method. Determination of smoke opacity. Description of the apparatus*

IEC Guide 104:2010, *The preparation of safety publications and the use of basic safety publications and group safety publications*

ISO 5659-2:2012, *Plastics – Smoke generation – Part 2: Determination of optical density by a single-chamber test*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply:

3.1

fire effluent

totality of gases and aerosols, including suspended particles, created by combustion or pyrolysis in a fire

[SOURCE: ISO/IEC 13943, definition 4.105]

3.2

fire hazard assessment

evaluation of the possible causes of fire, the possibility and nature of subsequent fire growth, and the possible consequences of fire

3.3

fire-safety engineering

application of engineering methods based on scientific principles to the development or assessment of designs in the built environment through the analysis of specific fire scenarios or through the quantification of risk for a group of fire scenarios

[SOURCE: ISO/IEC 13943:2008, definition 4.126]

3.4

fire scenario

qualitative description of the course of a fire with respect to time, identifying key events that characterise the studied fire and differentiate it from other possible fires

Note 1 to entry: It typically defines the ignition and fire growth processes, the fully developed fire stage, the fire decay stage, and the environment and systems that impact on the course of the fire.

[SOURCE: ISO/IEC 13943:2008, definition 4.129]

3.5

heat flux

amount of thermal energy emitted, transmitted or received per unit area and per unit time

Note 1 to entry: The typical units are watts per square metre ($\text{W} \times \text{m}^{-2}$).

[SOURCE: ISO/IEC 13943:2008, definition 4.173]

3.6

obscuration of smoke

reduction in the intensity of light due to its passage through smoke

Note 1 to entry: In practice, obscuration of smoke is usually measured as the transmittance, which is normally expressed as a percentage.

Note 2 to entry: Obscuration of smoke causes a reduction in visibility.

[SOURCE: ISO/IEC 13943:2008, definition 4.242]

3.7

opacity of smoke

ratio of incident light intensity to transmitted light intensity through smoke, under specified conditions

Note 1 to entry: Opacity of smoke is the reciprocal of transmittance.

Note 2 to entry: The opacity of smoke is dimensionless.

[SOURCE: ISO/IEC 13943:2008, definition 4.243]

3.8

optical density of smoke

measure of the attenuation of a light beam passing through smoke expressed as the logarithm to the base 10 of the opacity of smoke

cf. **specific optical density**, D_s (3.13)

Note 1 to entry: The optical density of smoke is dimensionless.

[SOURCE: ISO/IEC 13943:2008, definition 4.244]

3.9

physical fire model

laboratory process, including the apparatus, the environment and the fire test procedure intended to represent a certain phase of a fire

[SOURCE: ISO/IEC 13943:2008, definition 4.251]

3.10

real-scale fire test

fire test that simulates a given application, taking into account the real scale, the real way the item is installed and used, and the environment

Note 1 to entry: Such a fire test normally assumes that the products are used in accordance with the conditions laid down by the specifier and/or in accordance with normal practice.

[SOURCE: ISO/IEC 13943:2008, definition 4.273]

3.11

small-scale fire test

fire test performed on a test specimen of small dimensions

Note 1 to entry: A fire test performed on a test specimen of which the maximum dimension is less than 1 m is usually called a small-scale fire test.

[SOURCE: ISO/IEC 13943:2008, definition 4.292]

3.12

smoke

visible part of **fire effluent**

[SOURCE: ISO/IEC 13943:2008, definition 4.293]

3.13

specific optical density, D_s

optical density of smoke multiplied by a geometric factor, plus a filter factor

Note 1 to entry: The geometric factor is $V/(A \times L)$, where V is the volume of the test chamber, A is the area of the exposed surface of the test specimen, and L is the light path length.

Note 2 to entry: The use of the term “specific” does not denote “per unit mass” but rather denotes a quantity associated with a particular test apparatus and area of the exposed surface of the test specimen.

Note 3 to entry: The filter factor is a number which is calculated from the optical density of a moveable neutral density filter (see 7.2).

Note 4 to entry: The specific optical density of smoke is dimensionless.

3.14

transmittance

⟨smoke⟩ ratio of transmitted light intensity through smoke to incident light intensity, under specified conditions

cf. obscuration of smoke (3.6)

Note 1 to entry: Transmittance through smoke is the reciprocal of opacity of smoke.

Note 2 to entry: It is dimensionless and is usually expressed as a percentage.

[SOURCE: ISO/IEC 13943:2008 definition 4.346]

4 Relevance of test data and special observations

This small-scale fire test apparatus has been in worldwide use since about 1970, primarily for material evaluation purposes. In the early 1990s, ISO/TC 61 developed a similar apparatus that was designed, in part, to overcome a number of limitations of the IEC apparatus, and in 1994 the first edition of ISO 5659-2 was published. It is now recognised that ISO 5659-2 overcomes the following significant limitations:

- a) The heat flux is relatively low; consequently the method is only able to replicate conditions found in ISO 19706 fire stage 1b and, possibly, fire stage 2.
- b) The test specimen is vertically mounted, which excludes liquids and some thermoplastics. Test specimens which swell towards the furnace also give problems, as the incident heat flux experienced by the front of the test specimen increases significantly, and the pilot flames can be extinguished, rendering the test invalid.
- c) The limitations of the low heat flux and test specimen geometry mean that it is difficult to establish a link between data from the apparatus and real fire scenarios.
- d) There are no means of monitoring the test specimen mass during the test

Further limitations include the following:

- e) There is little or no correlation between data from this apparatus, and the behaviour of products in fires or real-scale fire tests.
- f) The air supply is limited and the test specimen ceases to burn if the oxygen concentration falls below approximately 14 %.
- g) The deposition of smoke on the walls is significant.

The test methods do however offer the useful option to evaluate smoke production from both flaming and non-flaming combustion, albeit at a low heat flux.

The data generated are not suitable for use as input to fire hazard assessment or for fire safety engineering.

Overall, these test methods are not recommended for further development for electrotechnical products. Neither are they recommended as the basis for regulation or other controls on smoke release for electrotechnical products, due to the limitations of the physical fire model and the test specimen geometry.

5 Test specimens

5.1 General

These test methods are sensitive to small variations in geometry, surface orientation, thickness, mass, composition and method of preparation; results obtained by these test methods are therefore dependent on the above parameters.

5.2 Number of test specimens

For each test on a given material, at least three test specimens shall be tested under the same conditions.

Under certain circumstances, it may be necessary to test three additional test specimens (see 6.5).

5.3 Size of test specimens

This method is applicable only to essentially flat solid materials.

The test specimens shall be square with sides $76^{+0,2}_{-0,6}$ mm. The thickness shall be a maximum of 25,4 mm and, when practicable, shall be that of the end-use application of the material.

For comparative testing, materials shall be tested at the same thickness as there is no known correlation between the specific optical density and thickness.

5.4 Conditioning of test specimens

Before the test, the test specimens shall be conditioned for at least 24 h at $23\text{ °C} \pm 3\text{ °C}$ and at a relative humidity of $50\% \pm 10\%$. The test specimen shall be tested within 30 min of being conditioned.

6 Test procedure

6.1 Preparation and calibration of the test chamber

Preparation and calibration of the test chamber shall be carried out as described in Clause 7 of IEC/TS 60695-6-30:2012.

6.2 Preparation of test specimens

Each test specimen shall be wrapped in a single layer of aluminium foil (about 0,04 mm thick), with the bright face outside, taking care to avoid unnecessary wrinkles or perforations.

It is then mounted in the test specimen holder ensuring that it is retained close against the front window by a backing board, rod and a spring arrangement behind the test specimen.

Excess aluminium foil along the side and top edges should be trimmed off after mounting. The excess foil on the bottom edge shall be folded in such a way as to minimize losses of any melted material at the bottom of the holder.

6.3 Test conditions

The test specimen is exposed to the radiant heat flux emitted by the furnace. The average heat flux at the surface of the test specimen shall be $25\text{ kW/m}^2 \pm 0,5\text{ kW/m}^2$.