

TECHNICAL SPECIFICATION

**Fuel cell technologies –
Part 7-1: Single cell test methods for polymer electrolyte fuel cell (PEFC)**

get full document from standards.iteh.ai



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2010 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00

TECHNICAL SPECIFICATION

**Fuel cell technologies –
Part 7-1: Single cell test methods for polymer electrolyte fuel cell (PEFC)**

get full document from standards.iteh.ai

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE



ICS 27.070

ISBN 978-2-88910-984-5

CONTENTS

FOREWORD.....	5
INTRODUCTION.....	7
1 Scope.....	8
2 Normative references	8
3 Terms and definitions	8
4 General safety considerations	11
5 Cell components.....	11
5.1 General.....	11
5.2 Sizing the membrane electrode assembly (MEA).....	11
5.3 Gas diffusion layer (GDL)	12
5.4 Gasket	12
5.5 Flow plate	12
5.6 Current collector.....	12
5.7 Clamping plate (or pressure plates).....	12
5.8 Clamping hardware	12
5.9 Temperature-control device.....	13
6 Cell assembly.....	13
6.1 Assembly procedure.....	13
6.2 Cell orientation and gas connections.....	13
6.3 Leak check.....	13
7 Test station setup.....	14
7.1 Minimum equipment requirement.....	14
7.2 Schematic diagram.....	14
7.3 Maximum variation in test station controls (inputs to test).....	15
8 Measurement.....	16
8.1 Instrument uncertainty.....	16
8.2 Measuring instruments and measuring methods	16
8.3 Measurement units.....	18
9 Gas composition.....	18
9.1 Fuel composition.....	18
9.2 Oxidant composition.....	18
10 Test preparation.....	19
10.1 Standard test conditions	19
10.2 Ambient conditions	19
10.3 Frequency of measurement	19
10.4 Repeatability and reproducibility.....	19
10.5 Maximum permissible variation in measured values	20
10.6 Number of test samples	20
10.7 Leak check of gas circuit with inert or test gas	20
10.8 Initial conditioning and stable state check.....	20
10.9 Shutdown	20
10.10 Re-conditioning	20
11 Performance tests	21
11.1 Steady test	21
11.2 I-V characteristics tests	21

11.3	IR measurement	22
11.4	Limiting current test	22
11.5	Gain tests	23
11.6	Gas stoichiometry tests	24
11.7	Temperature effect test	24
11.8	Pressure effect test	25
11.9	Humidity effect tests	25
11.10	Fuel composition test	26
11.11	Overload test	26
11.12	Long-term operation test	26
11.13	Start/stop cycling test	27
11.14	Load cycling test	27
11.15	Impurity influence tests	28
12	Test report	29
12.1	General	29
12.2	Report items	30
12.3	Test data description	30
12.4	Measurement condition description	30
12.5	Test cell data description	30
Annex A (informative)	Flow plate	31
Annex B (informative)	Cell component alignment	33
Annex C (informative)	Leak test	34
Annex D (informative)	Initial conditioning	35
Annex E (informative)	Shutdown	36
Annex F (informative)	Reconditioning	37
Annex G (informative)	I-V characteristic test	38
Annex H (informative)	Start/stop cycling test	40
Annex I (informative)	Load cycling test	41
Annex J (informative)	Test report	43
Bibliography		48
Figure 1	– Test station schematic diagram for single cell testing	15
Figure 2	– Typical testing flowchart	19
Figure A.1	– Design for flow plate (single serpentine flow channel)	32
Figure A.2	– Design for flow plate (triple serpentine flow channel)	32
Figure B.1	– Single cell assembly using typical components	33
Figure I.1	– First load cycling profile	41
Figure I.2	– Second load cycling profile	42
Table 1	– Parameters and units	18
Table G.1	– Current density increments if maximum current density is known	38
Table G.2	– Current density increments if maximum current density is unknown	39
Table J.1	– Test input parameters	45
Table J.2	– Test output parameters	46

Table J.3 – Functional performance before the measurement step (start up and conditioning)	46
Table J.4 – Functional performance during the polarization step	47

Sample Document

get full document from standards.iteh.ai

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FUEL CELL TECHNOLOGIES –

**Part 7-1: Single cell test methods
for polymer electrolyte fuel cell (PEFC)**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 62282-7-1, which is a technical specification, has been prepared by IEC technical committee 105: Fuel cell technologies.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
105/241/DTS	105/253A/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 62282 series, under the general title: *Fuel cell technologies*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

This Technical Specification describes standard single-cell test methods for polymer electrolyte fuel cells (PEFCs); it provides consistent and repeatable methods to test the performance of single cells. This Technical Specification is to be used by component manufacturers or stack manufacturers who assemble components in order to evaluate the performance of cell components, including membrane-electrode assemblies (MEAs) and flow plates. This Technical Specification is also available for fuel suppliers to determine the maximum allowable impurities in fuels.

Users of this Technical Specification may selectively execute test items suitable for their purposes from those described in this technical specification. This document is not intended to exclude any other methods.

Sample Document

get full document from standards.iteh.ai

FUEL CELL TECHNOLOGIES –

Part 7-1: Single cell test methods for polymer electrolyte fuel cell (PEFC)

1 Scope

This part of IEC 62282 covers cell assemblies, test apparatus, measuring instruments and measuring methods, performance test methods, and test reports for PEFC single cells.

This Technical Specification is used for evaluating:

- a) the performance of membrane electrode assemblies (MEAs) for PEFCs,
- b) materials or structures of other components of PEFCs, or
- c) the influence of impurities in fuel and/or in air on the fuel cell performance.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC/TS 62282-1:2010, *Fuel cell technologies – Part 1: Terminology*

ISO/TS 14687-2:2008, *Hydrogen fuel – Product specification – Part 2: Proton exchange membrane (PEM) fuel cell applications for road vehicles*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply:

3.1

anode

the electrode at which fuel oxidation takes place by the removal of electrons from the fuel to the external electric load, concurrent with the release of protons (H^+) to the polymer electrolyte

3.2

catalyst

substance that accelerates (increases the rate of) a reaction without being consumed itself

The catalyst lowers the activation energy of the reaction, allowing for an increase in the reaction rate. This is also referred to as an electrocatalyst, as defined in IEC/TS 62282-1.

3.3

catalyst-coated membrane

CCM

term used to describe a membrane (in a PEFC) whose surfaces are coated with a layer of catalyst to form the reaction zone of the electrode

3.4**cathode**

the electrode at which oxidant reduction takes place, facilitated by the donation of electrons from the external circuit and protons (H^+) from the polymer electrolyte, followed by the release of reduced oxidant products (water)

3.5**clamping plate (or pressure plate)**

frame used to compress the cell components together to maintain electrical conductivity and sealing

3.6**current collector**

conductive material, which can consist of metals, graphite or composite materials, that collects electrons from an anode or discharges electrons to a cathode

3.7**electrode**

catalytic layer that facilitates either an oxidation or reduction reaction, and has both electronic and ionic conduction.

3.8**flow plate**

conductive plate made of metals, a material such as graphite, or a conductive polymer that may be a carbon-filled composite, which is incorporated with flow channels for fuel or oxidant gas feed and has electrical contact with an electrode

3.9**fuel**

hydrogen or hydrogen-containing gas that reacts at the anode

3.10**fuel cell**

electrochemical device that converts the chemical energy of a fuel and an oxidant to electrical energy (DC power), heat and reaction products

The fuel and oxidant are typically stored outside of the fuel cell and transferred into the fuel cell as the reactants are consumed.

3.11**gas diffusion electrode****GDE**

component on the anode or cathode side comprising all electronic conductive elements of the electrode, i.e. gas diffusion layer and catalyst layer

3.12**gas diffusion layer****GDL**

porous conductive component placed between an electrode and a flow plate, to serve as electric contact and allow access of reactants to the electrode and the removal of reaction products

3.13**gasket**

sealing component which prevents the reaction gas from leaking out of a cell

3.14

limiting current density

the current density where the cell voltage sharply decreases to near zero

3.15

maximum current density

the highest current density specified by the manufacturer allowed for a short time

3.16

membrane electrode assembly

MEA

component of a fuel cell (3.10) consisting of an electrolyte membrane with gas diffusion electrodes (3.11) on either side

3.17

minimum cell voltage

the lowest cell voltage specified by the manufacturer

3.18

open circuit voltage

OCV

the cell voltage at zero current density with the cell under operating conditions

3.19

oxidant

oxygen or oxygen-containing gas (e.g., air) that reacts at the cathode

3.20

polymer electrolyte

polymer resin membrane having proton exchange capability in which current is carried by the movement of such ions from an anode to a cathode

3.21

polymer electrolyte fuel cell

PEFC

fuel cell that employs a polymer electrolyte membrane as an electrolyte, which is also called a proton exchange membrane fuel cell (PEMFC)

3.22

power

measure calculated from the voltage multiplied by the current at a steady state ($P = V \times I$)

3.23

power density

measure calculated by dividing the power by the geometric, electrode area

3.24

rated current density

maximum current density specified by the manufacturer of the MEA or single cell for continuous operation

3.25

rated power density

maximum power density specified by the manufacturer of the MEA or single cell for continuous operation

3.26**rated voltage**

minimum cell voltage specified by the manufacturer of the MEA or single cell for continuous operation

3.27**single cell**

cell typically consisting of an anode flow plate, MEA, cathode flow plate and sealing gaskets (see Annex B for additional information)

3.28**single cell test**

test of the fuel cell performance based on a single cell

3.29**stoichiometry**

molar ratio of the fuel (or oxidant) gases supplied to the cell to that required by the chemical reaction, as calculated from the current

4 General safety considerations

An operating fuel cell uses oxidizing and reducing gases. Typically, these gases are stored in high-pressure containers. The fuel cell itself may or may not be operated at pressures greater than atmospheric pressure.

Those who carry out single cell testing shall be trained and experienced in the operation of single cell test systems and specifically in safety procedures involving electrical equipment and reactive, compressed gases. Safely operating a single cell test station requires appropriate technical training and experience as well as safe facilities and equipment, all of which are outside the scope of this technical specification.

5 Cell components**5.1 General**

A single cell of a PEFC shall be composed of all or some of the following components:

- a) an MEA,
- b) gaskets,
- c) an anode-side flow plate and a cathode-side flow plate,
- d) an anode-side current collector and a cathode-side current collector,
- e) an anode-side clamping plate and a cathode-side clamping plate,
- f) electrically insulating sheets,
- g) clamping or axial load hardware which may include bolts, washers, springs, etc.,
- h) temperature-control devices,
- i) other miscellaneous parts.

5.2 Sizing the membrane electrode assembly (MEA)

The electrode area shall be as large as needed to measure desired parameters. A suggested electrode size should be approximately 25 cm², though larger cells having larger electrodes may give more relevant data for practical applications. The active electrode area shall be reported and shall be the smaller of the two electrode active areas. The approximate uncertainty in the area measurement shall be reported also.

5.3 Gas diffusion layer (GDL)

A gas diffusion layer shall be made of highly gas-diffusible, electrically conductive and corrosion-resistant materials.

5.4 Gasket

The gasket material shall be compatible with fuel cell reactants, components and reaction products, and cell operating temperature. It shall prevent gas leakage.

5.5 Flow plate

Flow plates shall be made of materials that have negligible gas permeability, but high electric conductivity. Resin-impregnated, high-density, synthetic graphite, polymer/carbon composites, or corrosion-resistant metal, such as titanium or stainless steel, is recommended. If metal is used, the plate surface may be coated/plated (e.g., with gold) in order to reduce contact resistance. The flow plate should be corrosion-resistant and should provide a suitable seal.

A serpentine flow channel is suggested. Further information about a suggested design is given in Annex A. The flow field configuration shall be documented in the test report.

The flow plates for testing shall allow the accurate measurement of cell operating temperature. For example, flow plates may have a small hole on an edgewise face in order to accommodate a temperature sensor. In this case, the hole shall reach the centre of the flow plate.

NOTE If the objective of testing is to evaluate the design of a particular flow channel, it is not necessary to use the suggested flow plate design.

5.6 Current collector

Current collectors shall be made of materials that have high electric conductivity, such as metal. Metal collectors may be plated with contact-resistance-reducing materials, such as gold or silver; however care must be taken in choosing the coating material. It must be compatible with the cell components and reactants and products.

They should be thick enough to minimize voltage drop over their surface area. They should provide an output terminal for wire connection.

If metal flow plates act as current collectors, independent current collectors are not required.

5.7 Clamping plate (or pressure plates)

Clamping plates (or pressure plates) shall be flat and smooth-surfaced, with their mechanical properties strong enough to withstand the bending force being applied when clamped with bolts.

If the clamping plates are conductive, they shall be insulated from the current collectors in order to prevent short-circuiting.

5.8 Clamping hardware

Clamping hardware shall have high mechanical strength in order to withstand the stresses generated during installation and operation. Washers and springs may be used to maintain constant, uniform pressure on the single cell. A torque wrench or other measuring device shall be used to set exact pressure on the cell.

It is recommended to electrically insulate the clamping hardware.

5.9 Temperature-control device

The single cell shall be provided with a temperature-control device (for heating/cooling) in order to maintain it at a constant temperature and with a uniform temperature profile along the flow plate and across the cell. The temperature-control device may be programmable to follow a fixed temperature profile. The temperature-control device shall have means to prevent over-temperature.

There are multiple ways of achieving this requirement.

One simple way is to convectively cool and electrically heat the clamping (pressure) plates. The heating can be achieved by attaching a skin resistance heater to the external surface of the plate. An alternate method is to insert a cartridge heater into a hole in the plate.

In either case, care is required to maintain isolation for electrical safety.

6 Cell assembly

6.1 Assembly procedure

Cell assembly procedures have large impact on the repeatability of fuel cell data. Specific procedures shall be documented for the following assembly operations.

- a) membrane alignment, including identification of anode and cathode sides,
- b) diffusion media (i.e., GDL) alignment, including identification of anode and cathode parts, as well as the sides to be placed facing the membrane and flowfield,
- c) gasket/seal placement,
- d) alignment fixtures or jigs to be used, if any,
- e) compression procedures and specifications, such as diffusion media compression values, bolt tightening order, compression springs, and final torque specifications.

NOTE Pressure may be checked by pressure-sensitive paper/film.

Typical alignment of cell component is shown in Annex B.

After assembling, the isolation between the clamping plates and current collectors shall be checked.

6.2 Cell orientation and gas connections

A cell shall be operated in an orientation which facilitates product water removal. The cell orientation shall be documented.

Many flow patterns can be used; the flow pattern shall be documented. Examples are given in Annex A.

6.3 Leak check

The differential pressure on the membrane is the most critical. The maximum differential pressure specified by the manufacturer should not be exceeded.

The cell must have minimal external and internal leakage. Examples leak-check procedures are given in Annex C. In principle, the leak-check procedure consists of injecting an inert or test gas into both the anode and cathode sides. By using a suitable pressure difference, the nature and direction of the leak can be ascertained. The maximum pressures, the nature of the test gas and leakage rates shall be documented. If a leak is detected, other tests, such as bubble test, may be performed to further delineate type and nature of leak.