
**Plastics piping systems for pressure
and non-pressure drainage and
sewerage — Glass-reinforced
thermosetting plastics (GRP) systems
based on unsaturated polyester (UP)
resin**

*iTeh Standards
(https://standards.iteh.ai/catalog/standards/iso/70a3f242-8c6f-40be-9a01-43789dd6bec7/iso-10467-2018)
Document Preview*

*Systèmes de canalisation en matières plastiques pour les
branchements et les collecteurs d'assainissement avec ou sans
pression — Systèmes en plastiques thermodurcissables renforcés de
verre (PRV) à base de résine de polyester non saturé (UP)*

ISO 10467:2018

<https://standards.iteh.ai/catalog/standards/iso/70a3f242-8c6f-40be-9a01-43789dd6bec7/iso-10467-2018>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 10467:2018](https://standards.iteh.ai/catalog/standards/iso/70a3f242-8c6f-40be-9a01-43789dd6bec7/iso-10467-2018)

<https://standards.iteh.ai/catalog/standards/iso/70a3f242-8c6f-40be-9a01-43789dd6bec7/iso-10467-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	3
4 General	12
4.1 Classification	12
4.1.1 Categories	12
4.1.2 Nominal size	12
4.1.3 Nominal stiffness	12
4.1.4 Nominal pressure	12
4.2 Materials	13
4.2.1 General	13
4.2.2 Reinforcement	13
4.2.3 Resin	13
4.2.4 Aggregates and fillers	14
4.2.5 Thermoplastics liners	14
4.2.6 Elastomers	14
4.2.7 Metals	14
4.3 Wall construction	14
4.3.1 Inner layer	14
4.3.2 Structural layer	14
4.3.3 Outer layer	14
4.4 Appearance	14
4.5 Reference conditions for testing	15
4.5.1 Temperature	15
4.5.2 Properties of water for testing	15
4.5.3 Loading conditions	15
4.5.4 Conditioning	15
4.5.5 Measurement of dimensions	15
4.6 Elapsed time, x, for determination of long-term properties	15
4.7 Joints	15
4.7.1 General	15
4.7.2 Types of joint	16
4.7.3 Flexibility of the joint	16
4.7.4 Sealing ring	16
4.7.5 Adhesives	16
4.8 Effect on water quality	16
4.9 Assessment of conformity	17
5 Pipes	17
5.1 Type of pipes	17
5.2 Geometrical characteristics	17
5.2.1 Diameter	17
5.2.2 Wall thickness	23
5.2.3 Length	23
5.3 Mechanical characteristics	23
5.3.1 Initial specific ring stiffness	23
5.3.2 Long-term specific ring stiffness under wet conditions	24
5.3.3 Initial resistance to failure in a deflected condition	25
5.3.4 Ultimate long-term resistance to failure in a deflected condition	27
5.3.5 Initial specific longitudinal tensile strength	28
5.3.6 Initial design and failure pressures for pressure pipes	30
5.3.7 Long-term failure pressure	32
5.4 Resistance to strain corrosion	32

5.4.1	General.....	32
5.4.2	Procedure using failure points.....	32
5.4.3	Procedure using specified levels of strain.....	33
5.4.4	Test piece length.....	35
5.4.5	Test solution.....	35
5.5	Marking.....	35
6	Fittings.....	35
6.1	All types.....	35
6.1.1	General.....	35
6.1.2	Diameter series.....	35
6.1.3	Nominal pressure (PN).....	35
6.1.4	Nominal stiffness (SN).....	36
6.1.5	Fitting type.....	36
6.1.6	Mechanical characteristics of fittings.....	36
6.1.7	Installed leaktightness of fittings.....	36
6.1.8	Dimensions.....	37
6.2	Bends.....	37
6.2.1	Classification of bends.....	37
6.2.2	Dimensions and tolerances of bends.....	37
6.3	Branches.....	40
6.3.1	Classification of branches.....	40
6.3.2	Dimensions and tolerances of branches.....	40
6.4	Reducers.....	43
6.4.1	Classification of reducers.....	43
6.4.2	Dimensions and tolerances of reducers.....	43
6.5	Non pressure saddles.....	45
6.5.1	Classification of saddles.....	45
6.5.2	Dimensions of saddles and associated tolerances.....	46
6.6	Flanges.....	46
6.6.1	Classification of flanges.....	46
6.6.2	Dimensions and tolerances for adaptors.....	47
6.7	Marking.....	48
7	Joint performance.....	49
7.1	General.....	49
7.1.1	Interchangeability.....	49
7.1.2	Requirements.....	49
7.1.3	Test temperature.....	50
7.1.4	Non-pressure piping and joints.....	50
7.1.5	Dimensions.....	50
7.2	Flexible joints.....	50
7.2.1	General.....	50
7.2.2	Maximum allowable draw.....	50
7.2.3	Maximum allowable angular deflection.....	50
7.2.4	Flexible non-end-load-bearing joints with elastomeric sealing rings.....	50
7.2.5	Flexible end-load-bearing joints with elastomeric sealing rings.....	51
7.3	Rigid joints.....	51
7.3.1	Wrapped or cemented.....	51
7.3.2	Bolted flange joints.....	52
7.4	Marking.....	52
	Annex A (normative) Principles used to establish the design requirements based on regression testing and consideration of the variability of the product.....	54
	Bibliography.....	59

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 6, *Reinforced plastics pipes and fittings for all applications*.

This second edition cancels and replaces the first edition (ISO 10467:2004), which has been technically revised. It also incorporates the Amendment ISO 10467:2004/Amd. 1:2012.

The main changes compared to the previous edition are as follows:

- inclusion of a guidance for the harmonization of design practices which are based on a partial safety factor concept and risk management engineering, as well as inclusion of the probability of failure and possible consequences of failures;
- addition of references to the general principle for the reliability of structures detailed in ISO 2394 and EN 1990;
- addition of a new safety factor concept for the hydrostatic pressure design;
- addition of a clear reference for assessment of conformity;
- changes in [Clause 6](#), including pressure tests requirements for fittings;
- changes in [Clause 7](#);
- changes in [Annex A](#) for the establishment of the design requirements.

Plastics piping systems for pressure and non-pressure drainage and sewerage — Glass-reinforced thermosetting plastics (GRP) systems based on unsaturated polyester (UP) resin

1 Scope

This document specifies the properties of piping system components made from glass-reinforced thermosetting plastics (GRP) based on unsaturated polyester resin (UP). It is suited for all types of drainage and sewerage with or without pressure. This document is applicable to GRP UP piping systems, with flexible or rigid joints with or without end thrust load-bearing capability, primarily intended for use in direct buried installations.

NOTE 1 For the purpose of this document, the term polyester resin (UP) also includes vinyl-ester resins (VE).

NOTE 2 Piping systems conforming to this document can also be used for non-buried applications, provided the influence of the environment and the supports are considered in the design of the pipes, fittings and joints.

NOTE 3 This document can also apply for other installations, such as slip-lining rehabilitation of existing pipes.

NOTE 4 This document is also referenced in ISO 25780, which specifies requirements for GRP-pipes used for jacking installation.

The requirements for the hydrostatic pressure design of pipes referring to this document meet the requirements of ISO/TS 20656-1 and the general principle for the reliability of structures detailed in ISO 2394 and in EN 1990. These International Standards provide procedures for the harmonization of design practices and address the probability of failure, as well as possible consequences of failures. The design practices are based on a partial safety factor concept, as well as on risk management engineering.

This document is applicable to pipes, fittings and their joints of nominal sizes from DN 50 to DN 4000 which are intended to be used for the conveyance of water at temperatures up to 50 °C, with or without pressure. In a pipework system, pipes and fittings of different nominal pressure and stiffness ratings may be used together. [Clause 4](#) specifies the general aspects of GRP UP piping systems intended to be used in the field of drainage or sewerage with or without pressure.

[Clause 5](#) specifies the characteristics of pipes made from GRP UP with or without aggregates and/or fillers. The pipes may have a thermoplastics or thermosetting resin liner. [Clause 5](#) also specifies the test parameters for the test methods referred to in this document.

[Clause 6](#) specifies the characteristics of fittings made from GRP UP, with or without a thermoplastics or thermosetting resin liner, intended to be used in the field of drainage and sewerage. [Clause 6](#) specifies the dimensional and performance requirements for bends, branches, reducers, saddles and flanged adaptors. [Clause 6](#) covers requirements to prove the structural design of fittings. It is applicable to fittings made using any of the following techniques:

- fabrication from straight pipes;
- moulding by
 - 1) filament winding,
 - 2) tape winding,
 - 3) contact moulding, and
 - 4) hot or cold compression moulding.