



**International
Standard**

ISO 1158

**Plastics — Vinyl chloride
homopolymers and copolymers —
Determination of chlorine content**

*Plastiques — Homopolymères et copolymères de chlorure de
vinyle — Dosage du chlore*

**Fourth edition
2026-03**

Sample Document

get full document from ecommerce.sist.si

Sample Document

get full document from ecommerce.sist.si



COPYRIGHT PROTECTED DOCUMENT

© ISO 2026

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Test sample	4
8 Procedure	5
8.1 Method A — Combustion bomb.....	5
8.2 Method B — Oxygen flask.....	5
9 Expression of results	7
10 Precision	7
11 Test report	7

Sample Document

get full document from ecommerce.sist.si

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastics materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 1158:1998), which has been technically revised.

The main changes are as follows:

- the mandatory normative references clause has been added (see [Clause 2](#));
- the mandatory terms and definitions clauses has been added (see [Clause 3](#));
- the unit of concentration of nitric acid solution has been changed, and a preparation method has been added (see [5.3](#));
- a method for determining the endpoint of titration by potentiometric titration has been added (see [8.1.6](#), [8.2.5](#));
- the preparation method of potassium hydroxide solution has been added (see [5.5.3](#));
- the requirements of filter paper have been changed (see [6.5.2](#));
- the test procedure for collecting the combustion-based liquid and the amount of liquid collected in method B have been changed (see [8.2.5](#));
- the tolerances of the method have been changed (see [9.2](#)).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Vinyl chloride homopolymers and copolymers — Determination of chlorine content

WARNING — All precautions in this document shall be taken to protect operators from risks presented by both methods.

1 Scope

This document specifies two methods for the determination of the chlorine content of homopolymers and copolymers of vinyl chloride, free from plasticizers or additives, namely:

- method A (combustion in a bomb);
- method B (combustion in a flask).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 6353-1, *Reagents for chemical analysis — Part 1: General test methods*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

A test portion is oxidised with sodium peroxide (method A) or gaseous oxygen (method B) followed by potentiometric or volumetric titration of the resulting chlorides.

5 Reagents

During the analysis, use only reagents of analytical grade as specified in ISO 6353-1, and grade 3 or better purity water as specified in ISO 3696, as well as the following.

5.1 Silver nitrate, standard volumetric solution $c(\text{AgNO}_3) = 0,1 \text{ mol/l}$ or $0,05 \text{ mol/l}$.

5.2 Nitric acid, mass concentration of approximately 68 %.

5.3 Nitric acid solution, $c(\text{HNO}_3) = 125 \text{ g/l}$, measure 135 ml of concentrated nitric acid (5.2) and dilute to 1 000 ml.