
**Hard coal and coke — Mechanical
sampling —**

**Part 2:
Coal — Sampling from moving streams**

Houille et coke — Échantillonnage mécanique —

Partie 2: Charbon — Échantillonnage en continu

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 13909-2:2016(E)

© ISO 2016

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Establishing a sampling scheme	1
4.1 General	1
4.2 Design of the sampling scheme	2
4.2.1 Material to be sampled	2
4.2.2 Division of lots	2
4.2.3 Basis of sampling	2
4.2.4 Precision of sampling	2
4.2.5 Bias of sampling	3
4.3 Precision of results	3
4.3.1 Precision and total variance	3
4.3.2 Primary increment variance	4
4.3.3 Preparation and testing variance	4
4.3.4 Number of sub-lots and number of increments per sub-lot	4
4.4 Minimum mass of sample	7
4.5 Mass of primary increment	9
4.6 Size analysis	9
5 Methods of sampling	10
5.1 General	10
5.2 Time-basis sampling	11
5.2.1 Method of taking primary increments	11
5.2.2 Sampling interval	11
5.2.3 Mass of increment	11
5.3 Mass-basis sampling	11
5.3.1 Method of taking primary increments	11
5.3.2 Sampling interval	12
5.3.3 Mass of increment	12
5.4 Stratified random sampling	12
5.4.1 General	12
5.4.2 Time-basis stratified random sampling	13
5.4.3 Mass-basis stratified random sampling	13
5.5 Reference sampling	13
6 Design of mechanical samplers	13
6.1 Safety	13
6.2 Information	13
6.3 Basic requirements	13
6.4 Location of sampling equipment	14
6.5 Provision for checking precision	14
6.6 Provision for testing for bias	14
6.7 General requirements for designing mechanical samplers	14
6.8 Design of falling-stream-type samplers	14
6.8.1 General	14
6.8.2 Cutter velocity	15
6.9 Cross-belt-type primary samplers	17
6.9.1 Operation	17
6.9.2 Design of cross-belt samplers	20
6.10 Maintenance and checking of sampling equipment	21
7 Handling and storage of samples	22
8 Sample preparation	23

9	Bias	23
9.1	Minimization of bias.....	23
9.2	Checking for precision and bias.....	24
10	Verification	24
Annex A (normative) Evaluation of sampling equipment for mass-basis sampling		25
Bibliography		30

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 4, *Sampling*.

This second edition cancels and replaces the first edition (ISO 13909-2:2001), which has been technically revised.

ISO 13909 consists of the following parts, under the general title *Hard coal and coke — Mechanical sampling*:

- *Part 1: General introduction*
- *Part 2: Coal — Sampling from moving streams*
- *Part 3: Coal — Sampling from stationary lots*
- *Part 4: Coal — Preparation of test samples*
- *Part 5: Coke — Sampling from moving streams*
- *Part 6: Coke — Preparation of test samples*
- *Part 7: Methods for determining the precision of sampling, sample preparation and testing*
- *Part 8: Methods of testing for bias*

Annex B forms a normative part of this part of ISO 13909. Annex A of this part of ISO 13909 is for information only.

Sample Document

get full document from standards.iteh.ai

Hard coal and coke — Mechanical sampling —

Part 2:

Coal — Sampling from moving streams

1 Scope

This part of ISO 13909 specifies procedures and requirements for the design and establishment of mechanical samplers for the sampling of coal from moving streams and describes the methods of sampling used.

It does not cover mechanical sampling from stationary lots which is dealt with in ISO 13909-3^[1].

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 13909-1:2016, *Hard coal and coke — Mechanical sampling — Part 1: General introduction*

ISO 13909-4, *Hard coal and coke — Mechanical sampling — Part 4: Coal — Preparation of test samples*

ISO 13909-7, *Hard coal and coke — Mechanical sampling — Part 7: Methods for determining the precision of sampling, sample preparation and testing*

ISO 13909-8, *Hard coal and coke — Mechanical sampling — Part 8: Methods of testing for bias*

ISO 21398, *Hard coal and coke — Guidance to the inspection of mechanical sampling systems*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13909-1 apply.

4 Establishing a sampling scheme

4.1 General

The general procedure for establishing a sampling scheme is as follows.

- a) Define the quality parameters to be determined and the types of samples required.
- b) Define the lot.
- c) Define or assume the precision required (see 4.3.1).
- d) Determine the method of combining the increments into samples and the method of sample preparation (see ISO 13909-4).
- e) Determine or assume the variability of the coal (see 4.3.2) and the variance of preparation and testing (see 4.3.3). Methods for determining variability and the variance of preparation and testing are given in ISO 13909-7.

- f) Establish the number of sub-lots and the number of increments per sub-lot required to attain the desired precision (see [4.3.4](#)).
- g) Decide whether to use time-basis or mass-basis sampling (see [Clause 5](#)) and define the sampling intervals in minutes for time-basis sampling or in tonnes for mass-basis sampling.
- h) Ascertain the nominal top size of coal for the purpose of determining the minimum mass of sample (see [4.4](#) and [Table 1](#)).

NOTE The nominal top size may initially be ascertained by consulting the consignment details, or by visual estimation, and may be verified, if necessary, by preliminary test work.

- i) Determine the minimum average increment mass (see [4.5](#)).

4.2 Design of the sampling scheme

4.2.1 Material to be sampled

The first stage in the design of the scheme is to identify the coal to be sampled. Samples may be required for technical evaluation, process control, quality control and for commercial reasons by both the producer and the customer. It is essential to ascertain exactly at what stage in the coal-handling process the sample is required and, as far as practicable, to design the scheme accordingly. In some instances, however, it may prove impracticable to obtain samples at the preferred points and, in such cases, a more practicable alternative is required.

4.2.2 Division of lots

A lot may be sampled as a whole or as a series of sub-lots, e.g. coal dispatched or delivered over a period of time, a ship load, a train load, a wagon load or coal produced in a certain period, e.g. a shift.

It may be necessary to divide a lot into a number of sub-lots in order to improve the precision of the results. For lots sampled over long periods, it may be expedient to divide the lot into a series of sub-lots, obtaining a sample for each.

4.2.3 Basis of sampling

Sampling may be carried out on either a time-basis or a mass-basis. In time-basis sampling, the sampling interval is defined in minutes and seconds and the increment mass is proportional to the flow rate at the time of taking the increment. In mass-basis sampling, the sampling interval is defined in tonnes and the mass of increments constituting the sample is uniform. Of these two alternatives, time-basis sampling is easier to implement and verify, because only a fixed speed cutter and a timing device are required. On the other hand, for mass-basis sampling, a conveyor belt weightometer is required as well as a device that is controlled sufficiently to adjust the primary cutter speed increment by increment to achieve uniform increment mass.

4.2.4 Precision of sampling

After the desired sampling precision has been selected, the number of sub-lots and the minimum number of increments per sub-lot collected shall be determined as described in [4.3.4](#), and the average mass of the primary increments shall be determined as described in [4.5](#).

For single lots, the quality variation shall be assumed as the worst case (see [4.3.2](#)). The precision of sampling achieved may be measured using the procedure of replicate sampling (see ISO 13909-7).

At the start of regular sampling of unknown coals, the worst-case quality variation shall be assumed, in accordance with [4.3.2](#). When sampling is in operation, a check may be carried out to confirm that the desired precision has been achieved, using the procedures described in ISO 13909-7.

If any subsequent change in precision is required, the number of sub-lots and of increments shall be changed as determined in 4.3.4 and the precision attained shall be rechecked. The precision shall also be checked if there is any reason to suppose that the variability of the coal being sampled has increased. The number of increments determined in 4.3.4 applies to the precision of the result when the sampling errors are large relative to the testing errors, e.g. for moisture content.

4.2.5 Bias of sampling

It is of particular importance in sampling to ensure, as far as possible, that the parameter to be measured is not altered by the sampling and sample preparation process or by subsequent storage prior to testing. This may require, in some circumstances, a limit on the minimum mass of primary increment (see 4.5).

When collecting samples for moisture determination from lots over an extended period, it may be necessary to limit the standing time of samples by dividing the lot into a number of sub-lots (see 4.3.4).

Sampling systems shall be tested for bias in accordance with the methods given in ISO 13909-8.

4.3 Precision of results

4.3.1 Precision and total variance

In all methods of sampling, sample preparation and analysis, errors are incurred and the experimental results obtained from such methods for any given parameter will deviate from the true value of that parameter. While the absolute deviation of a single result from the “true” value cannot be determined, it is possible to make an estimate of the precision of the experimental results. This is the closeness with which the results of a series of measurements made on the same coal agree among themselves, and the deviation of the mean of the results from an accepted reference value, i.e. the bias of the results (see ISO 13909-8).

It is possible to design a sampling scheme by which, in principle, an arbitrary level of precision can be achieved.

The desired overall precision for a lot is normally agreed between the parties concerned. In the absence of such agreement, a value of one tenth of the ash content may be assumed up to 10 % ash, subject to a maximum of 1 % absolute for ash contents above 10 %.

The theory of the estimation of precision is discussed in ISO 13909-7. The following formula is derived:

$$P_L = 2\sqrt{\frac{\frac{V_I}{n} + V_{PT}}{m}} \quad (1)$$

where

P_L is the estimated index of overall precision of sampling, sample preparation and testing for the lot, expressed as a percentage absolute;

V_I is the primary increment variance;

n is the number of increments per sub-lot;

m is the number of sub-lots in the lot;

V_{PT} is the preparation and testing variance.

If the quality of a coal of a type not previously sampled is required, then in order to devise a sampling scheme, assumptions have to be made about the variability (see 4.3.2). The precision actually achieved for a particular lot by the scheme devised can be measured by the procedures given in ISO 13909-7.