
**Paints and varnishes — Friction-
reduction coatings for the interior of
on- and offshore steel pipelines for
non-corrosive gases**

*Peintures et vernis — Revêtements réduisant le frottement pour
l'intérieur de gazoducs en acier enterrés et immergés pour le
transport de gaz non corrosifs*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Coating material	2
4.1 General	2
4.2 Particular requirements for qualification of the coating material	3
4.2.1 General	3
4.2.2 Non-volatile matter (by mass)	3
4.2.3 Non-volatile matter (by volume)	3
4.2.4 Viscosity	3
4.2.5 Density	3
4.2.6 Ash (residue on ignition)	3
4.2.7 Pot life	4
4.2.8 Infrared spectrograms	4
4.2.9 Appearance	4
4.3 Particular requirements for qualification of the cured paint film	4
4.3.1 Preparation of test panels	4
4.3.2 Conditioning of test panels	4
4.3.3 Dry film thickness	5
4.3.4 Adhesion	5
4.3.5 Buchholz hardness	5
4.3.6 Resistance to neutral salt spray	5
4.3.7 Resistance to artificial ageing	5
4.3.8 Bend test (conical mandrel)	5
4.3.9 Resistance to gas pressure variations	5
4.3.10 Resistance to water immersion	6
4.3.11 Resistance to chemicals	6
4.3.12 Resistance to hydraulic blistering	6
4.4 Packaging, labelling and storing	6
4.5 Quality assurance	6
4.6 Product data sheet	6
4.7 Qualification certificate	7
4.8 Batch test certificate	8
5 Application of the coating material	9
5.1 General	9
5.2 Surface preparation	10
5.3 Paint preparation	10
5.4 Paint application	10
6 Production control	11
6.1 Assessment of the coating on the pipes	11
6.1.1 Appearance	11
6.1.2 Dry film thickness	11
6.2 Assessment of the coating on steel panels	11
6.2.1 Preparation of test panels	11
6.2.2 Adhesion	11
6.2.3 Buchholz hardness	11
6.2.4 Bend test	11
6.2.5 Curing test	11
6.2.6 Porosity test	11
7 Repairs	12

8	Handling, transportation and storage	12
8.1	Handling.....	12
8.2	Transportation to the storage area.....	12
8.3	Storage.....	12
8.4	Loading coated pipes for transportation.....	12
Annex A	(normative) Determination of ash (refer to 4.2.5)	13
Annex B	(normative) Dry film thickness (refer to 6.1.2)	14
Annex C	(normative) Resistance to gas pressure variations (refer to 4.3.9)	15
Annex D	(normative) Hydraulic-pressure blistering (refer to 4.3.12)	18
Annex E	(normative) Porosity of a film of the coating material on a glass panel (refer to 6.2.6)	20
Annex F	(normative) Curing test (refer to 6.2.5)	21
Annex G	(normative) Wet-sponge test (refer to 6.2.6)	22
Bibliography		23

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 14, *Protective paint systems for steel structures*.

This second edition cancels and replaces the first edition (ISO 15741:2001), which has been technically revised.

Introduction

Internal coating of pipelines is used to reduce friction and improve the flow conditions when conveying non-corrosive gases, and to offer sufficient corrosion protection during storage and transport of the pipes. The reduction in friction depends on various parameters like the pressure and temperature of the gas, and the diameter of the pipe. Therefore, it is not possible to give a single figure for this reduction in friction.

In order to establish sufficient corrosion protection and to ensure optimum performance of the internal coating in the steel pipes, it is necessary for owners of pipelines, planners, consultants, companies carrying out the work, inspectors of protective coatings and manufacturers of coating materials to have at their disposal state-of-the-art information in concise form including requirements for the coating. Such information has to be as complete as possible, unambiguous and easily understandable to avoid difficulties and misunderstandings between the parties concerned.

Sample Document

get full document from standards.iteh.ai

Paints and varnishes — Friction-reduction coatings for the interior of on- and offshore steel pipelines for non-corrosive gases

1 Scope

This document specifies requirements and methods of test for liquid epoxy paints and internal coatings of such paints in steel pipes and fittings for the conveyance of non-corrosive gas. It also deals with the application of the paint. Other paints or paint systems are not excluded provided they comply with the requirements given in this document. The coating consists of one layer, which is normally shop-applied on blast-cleaned steel by airless spray or other suitable spraying techniques. The applied and cured paint film must be smooth to give the desired reduction in friction. Brush application is only used for small repair jobs.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2409, *Paints and varnishes — Cross-cut test*

ISO 2811 (all parts), *Paints and varnishes — Determination of density*

ISO 2812-1:2007, *Paints and varnishes — Determination of resistance to liquids — Part 1: Immersion in liquids other than water*

ISO 2812-2, *Paints and varnishes — Determination of resistance to liquids — Part 2: Water immersion method*

ISO 2815, *Paints and varnishes — Buchholz indentation test*

ISO 3233-1, *Paints and varnishes — Determination of the percentage volume of non-volatile matter — Part 1: Method using a coated test panel to determine non-volatile matter and to determine dry film density by the Archimedes principle*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*

ISO 6860, *Paints and varnishes — Bend test (conical mandrel)*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8503-1, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 1: Specifications and definitions for ISO surface profile comparators for the assessment of abrasive blast-cleaned surfaces*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 19840:2012, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

coater

company which is responsible for application of the coating material in accordance with the provisions of this document

3.2

coating material manufacturer

supplier of the coating material

3.3

dry film thickness

DFT

thickness of a coating remaining on the surface when the coating has hardened/cured

[SOURCE: ISO 12944-5:2007, 3.10]

3.4

natural gas

complex gaseous mixture of hydrocarbons, primarily methane, but generally also including ethane, propane and higher hydrocarbons in much smaller amounts and some non-combustible gases, such as nitrogen and carbon dioxide

[SOURCE: ISO 14532:2014, 2.1.1.1]

3.5

nominal dry film thickness

NDFT

dry film thickness specified for each coat or for the whole paint system

[SOURCE: ISO 12944-5:2007, 3.11]

3.6

pinhole

film defect characterized by small pore-like flaws in a coating which extend entirely through the applied film and have the general appearance of pinpricks when viewed by reflected light

3.7

purchaser

organization or individual that buys the coated pipes and fittings

4 Coating material

4.1 General

The coating material shall typically be a two-pack epoxy paint. It shall not contain any substances which will be released from the paint film after it has cured and are proven to be detrimental to the operation of the pipeline and the quality of the gas.

Unless otherwise agreed, the coating material shall be qualified in accordance with [4.2](#) and [4.3](#) and shall not be changed after qualification.

The manufacturer of the coating material shall provide on request infrared spectrograms of the base component and the curing agent component (see [4.2.8](#)).

In addition, the manufacturer shall provide a product data sheet (see [4.6](#)), a health and safety data sheet and a certificate stating the test results obtained in accordance with [4.2](#) and [4.3](#), respectively, and, if applicable, deviating test conditions.

The manufacturer shall also provide with every batch of the coating material a batch test certificate stating the information as given in [4.8](#).

Unless otherwise agreed, the applied coating shall provide corrosion protection during storage and transport for a minimum period of one year without significant breakdown of the coating.

The typical operating-temperature range for this type of coating is between $-20\text{ }^{\circ}\text{C}$ and $110\text{ }^{\circ}\text{C}$.

Where, subsequently, external coatings have to be applied, care shall be taken not to allow the internal coating to be damaged by the elevated temperatures which may occur.

4.2 Particular requirements for qualification of the coating material

4.2.1 General

The following subclauses describe the laboratory test methods which are required for qualification of the coating material.

4.2.2 Non-volatile matter (by mass)

When determined in accordance with ISO 3251, the non-volatile matter (by mass) of the coating material shall comply with the value specified by the coating material manufacturer in the qualification certificate ([Table 2](#)).

4.2.3 Non-volatile matter (by volume)

When determined in accordance with ISO 3233-1, the non-volatile matter (by volume) of the coating material shall comply with the value specified by the coating material manufacturer in the product data sheet ([Table 1](#)).

4.2.4 Viscosity

When determined by the method specified by the manufacturer, the viscosity of the ready-mixed coating material shall comply with the value specified by the coating material manufacturer in the qualification certificate ([Table 2](#)).

4.2.5 Density

When determined in accordance with one of the parts of the ISO 2811 series, the density of the coating material shall comply with the value specified by the coating material manufacturer in the product data sheet ([Table 1](#)).

4.2.6 Ash (residue on ignition)

When determined in accordance with the method described in [Annex A](#), the ash (residue on ignition) of the coating material shall comply with the value specified by the coating material manufacturer in the qualification certificate ([Table 2](#)).