
**Space systems — Space environment —
Simulation guidelines for radiation
exposure of non-metallic materials**

*Systèmes spatiaux — Environnement spatial — Lignes directrices de
simulation pour l'exposition aux radiations des matériaux non
métalliques*

Sample Document

get full document from standards.iteh.ai



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	2
3 Terms, definitions, abbreviated terms and acronyms	2
3.1 Terms and definitions	2
3.2 Abbreviated terms and acronyms	4
4 Space environment radiation characteristics.....	5
4.1 Sources of radiation in space	5
4.2 Radiation levels for Earth orbits	5
4.3 Methods for charged particle and photon irradiation.....	6
5 Properties of spacecraft materials	6
5.1 General	6
5.2 Surface properties	6
5.3 Volume (bulk) properties	7
5.4 Measure of radiation action.....	7
6 Requirements for simulation of space radiation.....	7
6.1 Objective.....	7
6.2 Methodology (test)	7
6.3 Methodology for simulation that involves simulation of the type of radiation, its spectrum, and intensity	8
7 Radiation sources for simulation	10
7.1 Sources.....	10
7.2 Low-energy protons	10
7.3 Low-energy electrons	10
7.4 High-energy proton accelerators.....	10
7.5 High-energy electron accelerators	10
7.6 Ultraviolet radiation.....	10
8 Alternate simulation method	11
8.1 Methodology	11
8.2 Standard spacecraft orbits	11
Annex A (informative) Additional information	13
Annex B (informative) Depth dose	15
Annex C (informative) Accelerated tests	21
Bibliography.....	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15856 was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 14, *Space systems and operations*.

Sample Document

get full document from standards.iteh.ai

Introduction

The purpose of this International Standard is to establish guidelines for designing space systems that are highly reliable and will have long mission life spans. It is impossible to reproduce the space environment for ground testing of space system elements because of the variety and complexity of the environments and the effects on materials. The reliability of the test results depends on simulating the critical effects of the space environments for a particular mission. The main objectives of the simulation are to get test results that are satisfactory for the material behaviour in a space environment and to use existing radiation sources and methods available in the test laboratory.

Non-metallic materials used in space systems are affected by electrons and protons in a broad energy interval, electromagnetic solar radiation (both the near and the far ultraviolet radiation) and X-ray radiation. The response of non-metallic materials to radiation depends on the type of radiation and energy that defines the ionization losses density, and the radiation response of materials depends on these losses. The radiation spectrum and chemical composition of materials define the absorbed dose distribution, especially in the near-the-surface layers.

During the design of the space system, it is necessary to simulate long mission time in reasonable ground time. For this reason, it is necessary to perform accelerated radiation tests requiring the use of dose rates that may be of an order of magnitude greater than in the natural space environment. These high dose rates can influence the effects on the properties of materials. Therefore, the main requirement for the correct simulation in radiation tests involves simulating the correct effects of materials in space by considering the type, spectrum (energy), and absorbed dose rate of the radiation. Simulation is complex because the various properties of materials may respond differently to the approximations of the natural space environment used for testing. In addition, various materials may respond differently to the same simulated space radiation environment. This is valid for different classes of materials such as polymeric and semiconductor materials.

The space engineering materials in space environment are exposed not only to charged particles and electromagnetic solar radiation but also to a number of other environmental factors, e.g. atomic oxygen, deep vacuum, thermocycling, etc. Synergistic interactions can significantly increase the material degradation, i.e. decrease the time of operation, but in certain cases (like solar absorptance variation under UV and protons) synergistic interaction can decrease the degradation. These effects are not well understood and have to be simulated as far as possible. Space environment simulation at the combined exposure is a much more complicated procedure than the simulation of each factor separately. Development of corresponding standards, both for different factors and different classes of materials, will be provided in the following stages of the standard set preparation for space environment simulation at on-ground tests of materials.

This International Standard contains normative statements, recommended practices and informative parts. The term “shall” indicates a normative statement.

Sample Document

get full document from standards.iteh.ai

Space systems — Space environment — Simulation guidelines for radiation exposure of non-metallic materials

IMPORTANT — The electronic file of this document contains colours which are considered to be useful for the correct understanding of the document. Users should therefore consider printing this document using a colour printer.

1 Scope

This International Standard is the first part of a series on space environment simulation for on-ground tests of materials used in space. This International Standard covers the testing of non-metallic materials exposed to simulated space radiation. Non-metallic materials include glasses, ceramics and polymer-metal composite materials such as metal matrix composites and laminated materials. This International Standard does not cover semiconductor materials used for electronic components. The types of simulated radiation include charged particles (electrons and protons), solar ultraviolet radiation and soft X-radiation of solar flares. Synergistic interactions of the radiation environment are covered only for these natural, and some induced, environmental effects.

This International Standard outlines the recommended methodology and practices for the simulation of space radiation effects on materials. Simulation methods are used to reproduce the effects of the space radiation environment on materials that are located on surfaces of space vehicles and behind shielding.

This methodology involves:

- a) the definition of the environment to be simulated using commonly accepted space environment models;
- b) the definition of the material properties under test or of concern in accordance with the specificity of degradation in the space environment, satellite-specific constraints determination, temperature conditions (constant values or cycled temperature mode), mechanical stress, charging, contamination, etc.;
- c) the selection of laboratory radiation simulation sources, energies and fluences that will be used to reproduce the kind of orbital radiation and mimic the orbital dose profiles;
- d) the exposure techniques and procedures used to perform the laboratory simulation including contamination control, acceleration factors (dose rates), temperature control, vacuum levels and atmospheric effects.

An alternative method using standard spacecraft orbits and environments is included.

This International Standard does not specify the design of material specimens, methods of measuring the properties of materials and characteristics of radiation sources, the design of vacuum systems and the preparation of test reports. The user should select designs and measurement methods based on the state of the art and the requirements of specific space systems and contracts.

This International Standard does not include a list of hazards and safety precautions. The users are responsible for providing safe conditions based on national and local regulations.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60544-2, *Guide for determining the effects of ionizing radiation on insulating materials — Part 2: Procedures for irradiation and test*

ASTM E490, *Standard Solar Constant and Zero Air Mass Solar Spectral Irradiance Tables*

ASTM E512, *Standard Practice for Combined, Simulated Space Environment Testing of Thermal Control Materials with Electromagnetic and Particulate Radiation*

3 Terms, definitions, abbreviated terms and acronyms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

absorbed dose

D

amount of energy imparted by ionizing radiation per unit mass of irradiated matter

NOTE 1 The quotient of $d\bar{\epsilon}$ by dm , where $d\bar{\epsilon}$ is the mean energy imparted by ionizing radiation to matter of mass dm , is

$$D = \frac{d\bar{\epsilon}}{dm}$$

NOTE 2 The special name of the unit for absorbed dose is the gray (Gy). 1 Gy = 1 J·kg⁻¹.

3.1.2

acceleration factor

ratio of dose rate between simulation and expectation at space application for the same type of radiation

3.1.3

bremstrahlung

brake radiation

photon radiation, continuously distributed in energy up to the energy of the incident particle radiation, emitted from a material due to deceleration of incident particle radiation within the material, mainly due to electrons

3.1.4

depth distribution criterion of absorbed dose

ratio of the exponent index, μ , of the absorbed dose depth profile curve to the material density, ρ

NOTE The depth distribution criterion of absorbed dose is measured in square centimetres per gram.

3.1.5

depth dose profile

distribution of the absorbed dose through the depth of material

3.1.6

energy fluence

total energy of ionizing radiation per unit area of the irradiated surface

NOTE Energy fluence is measured in joules per square metre.

3.1.7**galactic cosmic rays****GCR**

high-energy-charged particle fluxes penetrating the heliosphere from local interstellar space

[ISO 15390, definition 2.1]

3.1.8**heliosphere**

region surrounding the sun where the solar wind dominates the interstellar medium

NOTE Also known as solar cavity.

3.1.9**ionizing radiation**

any type of radiation consisting of charged particles or uncharged particles or both, that, as a result of physical interaction, creates ions of opposite signs by either primary or secondary processes

NOTE Charged particles could be positive or negative electrons, protons or other heavy ions, and uncharged particles could be X-rays, gamma rays, or neutrons.

3.1.10**linear energy transfer****LET**

energy delivered by a charged particle passing through a substance and locally absorbed per unit length of path

NOTE It is measured in joules per metre. Other dimensions are $\text{keV}\cdot\mu\text{m}^{-1}$, $\text{J}\cdot\text{m}^{-2}\cdot\text{kg}^{-1}$, $\text{MeV}\cdot\text{cm}^{-2}\cdot\text{g}^{-1}$, $\text{MeV}\cdot\text{cm}^{-2}\cdot\text{mg}^{-1}$.

3.1.11**mean free path**

average distance that a subatomic particle, ion, atom or molecule travels between successive collisions with ions, atoms or molecules

3.1.12**natural space environment**

environment that exists in space without a spacecraft system present

NOTE This includes radiation, vacuum, residual atmosphere, plasmas, magnetic fields and meteoroids.

3.1.13**near ultraviolet radiation****NUV radiation**

solar electromagnetic radiation with a wavelength in the range of 300 nm to 400 nm

3.1.14**radiation action measure**

energetic characteristic of radiation action on a material

NOTE The radiation action measure for non-metallic materials is an absorbed dose or energy fluence.

3.1.15**radiation belt**

electrons and protons trapped by the geomagnetic (planetary magnetic) field

3.1.16**radiation scale effect**

dependence of the material degradation on the thickness ratio of irradiated and unirradiated layers