
Dentistry — Refractory investment and die material

*Médecine bucco-dentaire — Revêtements et matériaux pour
modèles réfractaires*

Sample Document

get full document from standards.iteh.ai



Reference number
ISO 15912:2016(E)

© ISO 2016

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	3
5 Requirements	3
5.1 General	3
5.2 Material consistency and freedom from contamination	3
5.3 Fluidity	3
5.4 Initial setting time	4
5.5 Compressive strength	4
5.6 Linear thermal dimensional change	4
5.7 Adequacy of expansion of Type 1 and Type 2 materials	4
6 Sampling, test conditions and mixing	4
6.1 Sampling	4
6.2 Test conditions	4
6.3 Mixing	5
6.3.1 Apparatus	5
6.3.2 Procedure	5
7 Test methods	5
7.1 Material consistency and freedom from contamination	5
7.1.1 Test procedure	5
7.1.2 Test report	5
7.2 Fluidity	5
7.2.1 Apparatus	5
7.2.2 Number of test-pieces	6
7.2.3 Test procedure	6
7.2.4 Evaluation of results	6
7.2.5 Test report	6
7.3 Initial setting time	7
7.3.1 Apparatus	7
7.3.2 Procedure	9
7.3.3 Number of determinations	9
7.3.4 Evaluation of results	10
7.3.5 Test report	10
7.4 Compressive strength	10
7.4.1 Apparatus	10
7.4.2 Number of test-pieces	10
7.4.3 Preparation of test-pieces	11
7.4.4 Test procedure	11
7.4.5 Evaluation of results	12
7.4.6 Test report	12
7.5 Linear thermal dimensional change	12
7.5.1 Apparatus	12
7.5.2 Number of test-pieces	13
7.5.3 Preparation of the test-piece	13
7.5.4 Test procedure for the measurement of linear thermal expansion of Types 1, 2 and 3 products	14
7.5.5 Test procedure for the measurement of linear thermal dimensional changes of a Type 4 product	15
7.5.6 Evaluation of results	15
7.5.7 Test report	16

7.6	Adequacy of expansion of Type 1 and Type 2 products	16
7.6.1	General	16
7.6.2	Type 1 and Type 2 products intended for casting of dental metallic materials	17
7.6.3	Type 1 products intended for dental pressable-ceramic products	18
7.6.4	Evaluation of results	20
7.6.5	Test report	20
8	Manufacturer's instructions	20
8.1	General	20
8.2	Information for use	20
8.3	Physical properties	21
8.4	Safety labelling and instructions for a product containing silica	22
9	Marking	22
9.1	General	22
9.2	Powder container	22
9.2.1	Outer container	22
9.2.2	Individual packets	23
9.3	Liquid container	23
10	Packaging	23
10.1	Powder	23
10.2	Liquid	24
	Bibliography	25

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 106 *Dentistry*, Subcommittee SC2, *Prosthodontic Materials*.

This second edition cancels and replaces the first edition (ISO 15912:2006), which has been technically revised. It also incorporates the Amendment ISO 15912-1:2006/Amd 1:2011.

In this edition, dental pressable-ceramic investment materials are included in the Scope for the first time. These products are intended for the production of ceramic crowns and inlays and, as such, the same requirements as those for an investment product intended for the production of metallic crowns and inlays by casting are relevant (Type 1, according to the classification in this standard).

The previous edition contained requirements and test methods that had been developed for discontinued composition specific standards. In recent years products have been introduced that have other chemistries (for the binder and the refractory phase), specifically to minimize chemical reaction between the mould and the molten casting metallic material. A number of technical changes have been made to enable all dental casting investment products, regardless of their composition, to seek compliance with this International Standard and maintains the agreed philosophy that this International Standard should be inclusive, application-driven and not be limited by composition considerations.

Where appropriate, aspects of the test procedures have been changed to follow the manufacturer's instructions for use. The requirement for thermal dimensional change now takes into account the cooling of some products (after burn-out) to a lower casting temperature. The specification for the dilatometer has been changed for it to be compatible with the heating — and where relevant, the cooling after burn-out — of the product to the casting temperature.

The procedure for determining the initial setting time has been revised to harmonize with that present in the latest edition of the standard for dental gypsum products, ISO 6873:2013.^[1] Although substantially editorial, there are technical changes.

Information for use now requires a statement of the type of refractory phase(s) that is (are) present.

Labelling requirements for products that contain silica have been revised to comply with the current United Nations Globally Harmonized System for Classification and Labelling of Chemicals (UN GHS)^[2] and recommendations for silica as a hazardous material.

Containers of liquid must be marked to indicate the use to which the liquid is put.

Sample Document

get full document from standards.iteh.ai

Dentistry — Refractory investment and die material

1 Scope

This International Standard gives requirements and test methods for determining the compliance of dental casting investment, dental brazing investment, dental pressable-ceramic investment and dental refractory die materials used in the dental laboratory, regardless of the composition of the refractory powder, the composition of the binder, or the particular application.

This International Standard classifies such products into types and classes, according to their intended use and the burn-out procedure recommended by the manufacturer.

It also gives requirements for marking, labelling and manufacturer's instructions.

It specifies requirements for the essential physical and mechanical properties of the products and the test methods to be used for determining them.

NOTE 1 Compliance with all of the requirements presented in [Clause 5](#) may not be necessary for some products, and a requirement might not be applicable to a product with a particular binder chemistry or be intended for an application in which that requirement is irrelevant. When this is the case, a clear statement to this effect is given according to [Clause 5](#).

NOTE 2 A specific quantitative requirement for setting expansion is not included in this International Standard. If the setting expansion of gypsum-bonded investment is measured, then the procedure given in ISO 6873[1] can be considered — a procedure not recommended, however, for investment materials with other binders.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 286-2, *Geometrical product specifications (GPS) — ISO code system for tolerances on linear sizes — Part 2: Tables of standard tolerance classes and limit deviations for holes and shafts*

ISO 1942, *Dentistry — Vocabulary*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 6872, *Dentistry — Ceramic materials*

ISO 8601, *Data elements and interchange formats — Information interchange — Representation of dates and times*

ISO 15854, *Dentistry — Casting and baseplate waxes*

ISO 22674, *Dentistry — Metallic materials for fixed and removable restorations and appliances*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1942 and the following apply.

3.1

dental casting investment material

powdered particulate refractory and binder system that is mixed with a specified liquid to produce a pourable fluid that sets around a pattern to form the mould for casting a dental metallic prosthesis

Note 1 to entry: In some products, the binder may be dispersed in the refractory powder and the product is supplied as a mixed powder. Alternatively, the chemistry of the binder may lead to it being present in a solution (to be used with the powder that is supplied) with part or none of it being dispersed in the refractory powder, as received.

Note 2 to entry: The specified liquid may be pure water, an aqueous binder solution, or an aqueous solution to enhance expansion.

3.2

dental refractory die material

powdered particulate refractory and binder system that is mixed with a specified liquid to produce a fluid that sets (and is designed specifically) to form of a hard die, suitable for the production of a dental ceramic prosthesis using the sintering technique

3.3

dental brazing investment material

powdered particulate refractory and binder system that is mixed with a specified liquid to produce a fluid that sets (and is designed specifically) to form a cast upon which metallic components are held, or are partly embedded, accurately in place while they are joined by brazing

Note 1 to entry: The cast may be referred to as the model, though that is a deprecated term.

3.4

dental pressable ceramic investment

powdered particulate refractory and binder system that is mixed with a specified liquid to produce a pourable fluid that sets around a pattern to form a mould into which a dental pressable-ceramic, softened by heating, can be forced under pressure

3.5

special liquid

liquid, other than water, supplied by the manufacturer for mixing with the dental casting investment powder for the purpose of increasing the expansion of the mould

3.6

slow- or step-heating method

heating method in which (at a time after setting that is recommended by the manufacturer) the dental casting investment mould, or dental pressable-ceramic mould, or dental brazing investment cast or dental refractory die is placed in a burn-out furnace set at room temperature, after which the temperature of the furnace is increased to the end temperature in a series of stages and at a programmed rate recommended by the manufacturer

3.7

quick-heating method

heating method in which (at a time after setting that is recommended by the manufacturer) the dental casting investment mould, or dental pressable-ceramic mould, or dental brazing investment cast, or dental refractory die is placed directly into the hot burn-out furnace that is set and held at the burn-out temperature recommended by the manufacturer

3.8

burn-out temperature

<Types 1 and 2 materials> temperature to which the mould is heated to burn off the pattern material and expand the mould

3.9

burn-out temperature

<Type 3 material> temperature to which the cast is heated to burn off any material used for shielding and accurately locating the components to be brazed, and to expand the cast

3.10**burn-out temperature**

<Type 4 material> temperature to which the die is heated initially to burn off the pattern material

3.11**casting temperature**

<Types 1 and 2 materials intended for casting a dental metallic material> temperature of the mould at which the molten metallic material is forced into the mould

3.12**ceramic pressing temperature**

<Type 1 investment materials intended for use with dental pressable-ceramics> temperature at which the mould and ceramic ingot are taken and at which the ceramic is pressed into the mould

Note 1 to entry: The mould is placed in a burn-out furnace at a lower temperature and held at this temperature before the pressable-ceramic ingot is placed in the crucible of the mould, after which both are transferred to the pressing furnace, that is at, or is raised to, a higher temperature to soften the ceramic ingot

3.13**green state**

condition of the material immediately after setting before structural changes are brought about by aging or burn-out, changes that produce increased strength or further dimensional changes

4 Classification

For the purposes of this International Standard, dental casting investment, dental brazing investment, dental pressable-ceramic investment and dental refractory die materials are classified into the following types, according to the intended application:

- Type 1, for the construction of inlays, crowns and other fixed prostheses;
- Type 2, for the construction of complete or partial dentures or other removable appliances;
- Type 3, for the construction of casts used in brazing procedures;
- Type 4, for the construction of refractory dies.

In addition, the materials are divided into two classes: Class 1 is recommended for burn-out by a slow- or step-heating method; Class 2 is recommended for burn-out by a quick-heating method.

5 Requirements**5.1 General**

If a manufacturer claims suitability for both classes, then the material shall satisfy the requirements when it is subjected to both heating techniques. This applies to requirements [5.5](#) and [5.6](#) and, if appropriate, requirement [5.7](#).

5.2 Material consistency and freedom from contamination

When examined in accordance with [7.1](#), the powder shall be uniform and free of lumps and foreign matter. If a special liquid is supplied, it shall be free of sediment.

5.3 Fluidity

When measured in accordance with [7.2](#), the fluidity shall not vary by more than 30 % from the value stated by the manufacturer [according to [8.3 a](#)].