
**Non-alloy steel wire rod for
conversion to wire —**

**Part 1:
General requirements**

*Fil-machine en acier non allié destiné à la fabrication de fils —
Partie 1: Exigences générales*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	3
5 Ordering information to be supplied by the purchaser	3
6 Production process	4
7 Requirements	4
7.1 General.....	4
7.2 Quality system.....	4
7.3 Method of delivery.....	4
7.4 Delivery condition.....	5
8 Dimensions, mass and tolerances	5
9 Inspection	5
9.1 Inspection and inspection documents.....	5
9.2 Extension of inspection.....	5
9.3 Acceptance unit, number of samples and test pieces.....	5
9.4 Sampling and preparation of samples and test pieces.....	6
9.4.1 Chemical composition.....	6
9.4.2 Tensile strength.....	6
9.4.3 Decarburization, surface discontinuities, non-metallic inclusions, core segregation and microstructure.....	6
9.5 Test methods.....	6
9.5.1 Chemical composition.....	6
9.5.2 Tensile strength.....	6
9.5.3 Surface discontinuities.....	6
9.5.4 Decarburization.....	7
9.5.5 Non-metallic inclusions.....	7
9.5.6 Core segregation.....	7
9.5.7 Microstructure.....	7
9.5.8 Determination of cementite network in high-carbon steel wire rod.....	7
9.6 Retest.....	7
10 Marking	7
11 Disputes	7
Annex A (normative) Determination of core segregation	8
Annex B (informative) Measurement of surface discontinuities	11
Annex C (informative) Mechanical damage	14
Annex D (normative) Determination of percentage of resolvable pearlite in high-carbon steel wire rod	18
Annex E (normative) Determination of cementite network in high-carbon steel wire rod	22
Bibliography	27

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 17, *Steel wire rod and wire products*.

This third edition cancels and replaces the second edition (ISO 16120-1:2011), which has been technically revised.

The main changes compared to the previous edition are:

- core segregation, surface discontinuity and mechanical damage have been added to the terms and definitions;
- determination of cementite network in high-carbon steel wire rod ([9.5.8](#) and [Annex E](#)) added.

A list of all parts in the ISO 16120 series can be found on the ISO website.

Non-alloy steel wire rod for conversion to wire —

Part 1: General requirements

1 Scope

The ISO 16120 series is applicable to wire rod of non-alloy steel intended for wire drawing and/or cold rolling. The cross-section can be circular, oval, square, rectangular, hexagonal, octagonal, half-round or another shape, generally with at least 5 mm nominal dimension, and with a smooth surface.

This document specifies general requirements for non-alloy steel wire rod for conversion to wire. It is not applicable to products for which standards exist or are in development, for example:

- steel wire rod intended for heat treatment;
- free-cutting steel wire rod;
- steel wire rod for cold heading and cold extrusion;
- steel wire rod intended for the production of electrodes and products for welding;
- steel wire rod for welded fabric for reinforcement for concrete;
- steel wire rod for ball and roller bearings (see ISO 683-17);
- steel wire rod for wire for high fatigue strength mechanical springs, such as valve springs.

In addition to the requirements of this document, the general technical delivery requirements specified in ISO 404 apply.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404:2013, *Steel and steel products — General technical delivery requirements*

ISO 3887, *Steels — Determination of depth of decarburization*

ISO 4885, *Ferrous products — Heat treatments — Vocabulary*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6929, *Steel products — Vocabulary*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO 16120-2:2017, *Non-alloy steel wire rod for conversion to wire — Part 2: Specific requirements for general-purpose wire rod*

ISO 16120-3:2011, *Non-alloy steel wire rod for conversion to wire — Part 3: Specific requirements for rimmed and rimmed substitute, low-carbon steel wire rod*

ISO 16120-4:2017, *Non-alloy steel wire rod for conversion to wire — Part 4: Specific requirements for wire rod for special applications*

ISO 16124, *Steel wire rod — Dimensions and tolerances*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 377, ISO 404, ISO 4885, ISO 4948-1, ISO 4948-2 and ISO 6929 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 rod

hot-rolled finished product hot-wound into irregular coils

Note 1 to entry: Rod used for wire-drawing purposes in coil form is generally termed wire rod.

3.2 heat analysis

chemical analysis representative of the heat, by a method determined at the steelmaker's discretion

[SOURCE: ISO 404:2013, 3.11, modified.]

3.3 product analysis

chemical analysis carried out on a sample of the product taken after the final hot rolling operation

[SOURCE: ISO 404:2013, 3.12, modified.]

3.4 resolvable pearlite

two-phased structure in which ferrite and iron carbide lamellae can be clearly observed under optical microscopy in certain conditions

3.5 core segregation

local variation in chemical composition that is noticeable over a cross-section of wire rod (3.1) by macrographic examination and that concerns primarily the segregation resulting from a solidification process in continuous casting

Note 1 to entry: It is for this reason that an examination, specifically for carbon core segregation, will reveal the presence of segregation.

Note 2 to entry: A different technique is used to assess grain boundary cementite (which may be detrimental to further processing), the formation of which is related to carbon segregation and the cooling rate after wire rod rolling. However, grain boundary cementite should not be confused with core segregation.

3.6**surface discontinuity**

measurable discontinuity in the surface of the wire *rod* (3.1), introduced at some point during the manufacturing process

3.7**mechanical damage**

discernible contact which the wire *rod* (3.1) encounters after the rolling and coiling operation, i.e. during subsequent handling of the coil, and which marks the surface

Note 1 to entry: The contact can be introduced by abrasion or impact and can occur between coils or between the coil and any other material capable of inducing damage (concrete, steel or other materials).

Note 2 to entry: See [Annex C](#).

4 Classification

The classification of the steel grades covered by this document is indicated in ISO 16120-2, ISO 16120-3 and ISO 16120-4 for the corresponding steel grades.

5 Ordering information to be supplied by the purchaser

The following information shall be supplied by the purchaser at the time of enquiry and order, to enable the supplier to comply satisfactorily with the requirements of the ISO 16120 series:

- a) quantity to be delivered;
- b) cross-section and product type (e.g. round wire rod, square wire rod, hexagonal wire rod, etc.);
- c) nominal dimensions of the wire rod and tolerance class in accordance with ISO 16124 (if another tolerance class such as T1 is required);
- d) reference to the relevant part of ISO 16120, i.e. ISO 16120-2;
- e) steel grade, including any variations, and/or the addition of other elements, as permitted by ISO 16120-2 and ISO 16120-4;

(For steels according to ISO 16120-2 and ISO 16120-4, wire rod can also be ordered by the mean tensile strength; see ISO 16120-2:2017, Clause 3 and 4.6 and ISO 16120-4:2017, Clause 3 and 4.8. When ordering to tensile strength, it is necessary also to indicate the required tolerances on tensile strength ranges — Option A or Option B.)

- f) type of inspection and inspection document in accordance with ISO 10474 (or in accordance with other regional standards, e.g. EN 10204);
- g) surface condition (where different from the as-rolled condition);
- h) dimensions and mass of coils;
- i) where applicable, indication of the type of descaling (chemical cleaning or mechanical);
- j) where applicable, the amount of microalloying elements (see ISO 16120-2 and ISO 16120-4);
- k) where applicable, class B for the depth of decarburization (see ISO 16120-4);

NOTE If nothing is mentioned in the order, class A will be delivered;

- l) where applicable, the microstructure (see ISO 16120-4:2017, 4.11);
- m) where applicable, suitability for galvanizing;
- n) where applicable, suitability for direct drawing;

- o) where applicable, the quality system (see [7.2](#));
- p) where applicable, the method of binding and labelling.

Items g) to p) are options. If the purchaser does not indicate a wish to implement any of these options, the supplier shall supply the product in accordance with the basic specifications of items a) to f).

Examples 1 and 2 provide two ordering examples.

EXAMPLE 1 For grades ordered according to chemical composition, 100 tonnes of round wire rod, nominal diameter of 12 mm with dimensional tolerances according to ISO 16124, class T1, steel grades ISO 16120-2 – C52D in the as-rolled condition with an inspection document 3.1 according to ISO 10474.

100 t round wire rod ISO 16124-12,0T1

ISO 16120-2 – C52D

ISO 10474 inspection document [3.1](#)

EXAMPLE 2 For grades ordered according to tensile strength, 200 tonnes of round wire rod, nominal diameter of 5,5 mm with dimensional tolerances according to ISO 16124, class T1, steel grades ISO 16120-4 – C##D2 with tensile strength 1 020 MPa, tensile strength tolerance Option A, in the as-rolled condition with an inspection document 3.1 according to ISO 10474.

200 t round wire rod ISO 16124-5, 5T1

ISO 16120-4 – C##D2-1020A

ISO 10474 inspection document [3.1](#)

NOTE The symbol “##” means “to be left blank” since the carbon content is at the discretion of the supplying mill, and the supplying mill indicates the exact number of ## based on the grade designation until shipment. See ISO 16120-2:2017, Table 1 and ISO 16120-4:2017, Table 1, respectively, for the grade designation.

6 Production process

At the request of the purchaser at the time of enquiry and ordering, the steel making and manufacturing process shall be made known to the purchaser. Those processes that are specifically agreed upon shall not be changed without the prior agreement of the purchaser.

7 Requirements

7.1 General

Suppliers are responsible, using the means they think fit, for inspecting their product in accordance with various quality criteria specified. In view of the practical difficulties in inspecting a coil of wire rod along its entire length, it cannot be proved that no value greater than the specified limits is to be found in the coil as a whole. Statistical evaluation of performances applicable to all coils may be agreed between the purchaser and the manufacturer at the time of ordering.

7.2 Quality system

If agreed between the supplier and purchaser at the time of enquiry and order, the wire rod supplied shall be produced under a mutually acceptable quality system.

7.3 Method of delivery

Wire rod shall be delivered by heat or part of a heat. Unless otherwise specified, the number of heats per delivery should be minimized as far as possible.

7.4 Delivery condition

Wire rod shall be supplied in the as-rolled state, in coils of one continuous length with non-aligned turns, but capable of being unwound in a regular manner during subsequent processing.

The coils shall be cut back at both ends to provide a product of uniform shape and properties.

8 Dimensions, mass and tolerances

The dimensions, mass and tolerances of the wire rod shall be in accordance with the requirements of ISO 16124.

9 Inspection

9.1 Inspection and inspection documents

Inspection and inspection documents shall be in accordance with ISO 404 and ISO 10474.

9.2 Extension of inspection

If the order is accompanied by a request for an inspection certificate or an inspection report, the inspection shall be carried out in accordance with [Table 1](#). If the order requires an inspection document [3.1](#) or [3.2](#), the purchaser shall supply to the manufacturer the name and address of the organization or person nominated to carry out the inspection.

Table 1 — Extension of inspection

Subject of test	General-purpose wire rod (ISO 16120-2)	Rimmed and rimmed substitute, low-carbon wire rod (ISO 16120-3)	Wire rod for special applications (ISO 16120-4)
Surface discontinuities	0	0	0
Decarburization	—	—	0
Non-metallic inclusions	—	0	0
Core segregation	0	—	0
Product analysis	0	0	0
Tensile strength	0	0	0
Microstructure	—	—	0 ^a
^a See Annex D . — is not carried out. 0 is carried out only if part of the options agreed at the time of ordering.			

9.3 Acceptance unit, number of samples and test pieces

Unless otherwise agreed, the acceptance unit is composed of wire rod of the same cross-sectional dimension, originating from the same heat, and rolled in the same continuous lot.

If specific inspection is required, the number of samples and test pieces given in [Table 2](#) shall apply. For wire rod for special applications, a higher frequency of sampling may be agreed. If non-specific inspection is required, the performance statistics or suitable data may be used.