
**Plastics piping systems for drainage
and sewerage without pressure —
Non-circular pipes and joints made
of glass-reinforced thermosetting
plastics (GRP) based on unsaturated
polyester resins (UP) — Dimensions,
requirements and tests**

*Systèmes de canalisation en plastiques pour réseaux d'assainissement
sans pression — Tuyaux non-circulaires, assemblages de tuyaux et
raccords en plastiques thermodurcissables renforcés de verre (PRV) à
base de résines de polyester non saturé (UP) — Dimensions, exigences
et essais*



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General requirements	8
4.1 Classification	8
4.1.1 Categories	8
4.1.2 Nominal size	8
4.2 Materials	8
4.2.1 General	8
4.2.2 Reinforcement	8
4.2.3 Resin	8
4.2.4 Aggregates and fillers	9
4.2.5 Elastomers	9
4.2.6 Metals	9
4.3 Wall construction	9
4.3.1 Inner layer	9
4.3.2 Structural layer	9
4.3.3 Outer layer	9
4.3.4 Appearance	9
4.4 Reference conditions for testing	10
4.4.1 Temperature	10
4.4.2 Properties of water for testing	10
4.4.3 Loading conditions	10
4.4.4 Conditioning	10
4.4.5 Measurement of dimensions	10
4.4.6 Elapsed time for determination of long-term properties, (x)	10
4.5 Joints	10
4.5.1 General	10
4.5.2 Types of joint	10
4.5.3 Flexibility of the jointing system	10
4.5.4 Sealing ring	11
4.5.5 Adhesives	11
5 Pipes	11
5.1 Geometrical characteristics	11
5.1.1 Dimensions	11
5.2 Mechanical characteristics	12
5.2.1 General	12
5.2.2 Short-term bending modulus	13
5.2.3 Long-term creep bending modulus	14
5.2.4 Short-term bending strength	14
5.2.5 Long-term bending strength	15
5.2.6 Resistance to strain corrosion	16
5.2.7 Minimum initial longitudinal tensile strength	17
5.3 Marking	18
6 Fittings	19
6.1 All types	19
6.1.1 General	19
6.1.2 Diameter series	19
6.1.3 Mechanical characteristics of fittings	19
6.1.4 Installed leak tightness of fittings	19

6.1.5	Dimensions	19
6.2	Marking	19
7	Joint performance	20
7.1	General	20
7.1.1	Requirements	20
7.1.2	Test temperature	20
7.1.3	Dimensions	20
7.2	Flexible joints	20
7.2.1	General	20
7.2.2	Maximum allowable draw	20
7.2.3	Maximum allowable angular deflection	20
7.2.4	Maximum allowable misalignment	20
7.2.5	Flexible non-end-load-bearing joints with elastomeric sealing rings	20
7.3	Rigid joints	22
7.3.1	Wrapped or cemented	22
Annex A (informative) Examples for static calculation		24
Bibliography		25

Sample Document

get full document from standards.iteh.ai

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 6, *Reinforced plastics pipes and fittings for all applications*.

get full document from standards.iteh.ai

Introduction

The goal to establish this product standard is to standardize the requirements for non-circular GRP pipes.

This document specifies the requirements for non-circular GRP pipe systems, designed to be used for the renovation of existing channels or open cut installation.

This document specifies dimensions, requirements and tests of non-circular pipes including short and long-term properties. To establish long-term properties, it is recommended to use the circular pipes samples.

[Annex A](#) shows commonly used calculation methods but only as information. The calculation method is selected by the designer.

This document does not include the recommended practice for installation as this should be a separate document.

Sample Document

get full document from standards.iteh.ai

Plastics piping systems for drainage and sewerage without pressure — Non-circular pipes and joints made of glass-reinforced thermosetting plastics (GRP) based on unsaturated polyester resins (UP) — Dimensions, requirements and tests

1 Scope

This document specifies the required properties of the piping system and its components made from glass-reinforced thermosetting plastics (GRP) based on unsaturated polyester resin (UP) intended to be used for drainage or sewerage without pressure including culverts.

It is the responsibility of the purchaser or specifier to make the appropriate selections taking into account their particular requirements and any relevant national regulations and installation practices or codes.

This document is applicable to non-circular GRP-UP pipes, with flexible or rigid joints, primarily intended for use in buried installations but may also be used to reline existing non-circular pipe lines.

NOTE 1 GRP-UP includes pipes with vinyl ester liners or made entirely from vinyl ester.

NOTE 2 Piping systems conforming to this document can be used also for non-buried applications provided the influence of the environment, e.g. from UV-radiation, and the supports are considered in the design of the pipes, fittings and joints.

This document is applicable to pipes, fittings and their joints of nominal sizes from DN 150 to DN 4000, which are intended to be used for the conveyance of surface water or sewage at temperatures up to 50 °C.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 75-2:2013, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 178, *Plastics — Determination of flexural properties*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

ISO 4633, *Rubber seals — Joint rings for water supply, drainage and sewerage pipelines — Specification for materials*

ISO 8513:2016, *Plastics piping systems — Glass-reinforced thermosetting plastics (GRP) pipes — Test methods for the determination of the initial longitudinal tensile strength*

ISO 8533, *Plastics piping systems for pressure and non-pressure drainage and sewerage — Glass-reinforced thermosetting plastics (GRP) systems based on unsaturated polyester (UP) resin — Test methods to prove the design of cemented or wrapped joints*

ISO 8639, *Glass-reinforced thermosetting plastics (GRP) pipes and fittings — Test methods for leaktightness and proof of structural design of flexible joints*

ISO 10468, *Glass-reinforced thermosetting plastics (GRP) pipes — Determination of the long-term specific ring creep stiffness under wet conditions and calculation of the wet creep factor*

ISO 10928, *Plastics piping systems — Glass-reinforced thermosetting plastics (GRP) pipes and fittings — Methods for regression analysis and their use*

ISO 10952, *Plastics piping systems — Glass-reinforced thermosetting plastics (GRP) pipes and fittings — Determination of the resistance to chemical attack for the inside of a section in a deflected condition*

EN 681-1, *Elastomeric seals — Material requirements for pipe joint seals used in water and drainage applications — Part 1: Vulcanized rubber*

EN/TS 14632, *Plastics piping systems for drainage, sewerage and water supply, pressure and non-pressure — Glass-reinforced thermosetting plastics (GRP) based on unsaturated polyester resin (UP) — Guidance for the assessment of conformity*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 nominal size

$BN \times HN$

alphanumerical designation of size, which is common to all components in a piping system, it is a convenient pair of numbers for reference purposes that is related to the maximum internal breadth (B) and the maximum internal height (H)

Note 1 to entry: The designation for reference or marking purposes consists of the letters $BN(B) \times HN(H)$ and the numerical values for (B) and (H), when expressed in millimetres.

3.2 declared dimensions

dimensions which a manufacturer states to be the internal breadth (B) and height (H) produced in respect of a particular nominal size $BN \times HN$

3.3 specific ring stiffness

S

physical characteristic of a circular pipe which is a measure of the resistance to ring deflection per metre length under external load

Note 1 to entry: Specific ring stiffness is determined using formula below and is expressed in Newtons per square metre (N/m^2):

$$S = \frac{E \cdot I}{d_m^3}$$

where

E is the apparent modulus of elasticity, which can be derived from the result of the ring stiffness test, i.e. ISO 7685, expressed in Newtons per square metre (N/m^2);

d_m is the mean diameter of the pipe, in metres (m) (see 3.5);

I is the second moment of area in the longitudinal direction per metre length, in metres to the fourth power per metre, (m^4/m):

$$I = \frac{e^3}{12}$$

where

e is the wall thickness, in metres.

3.4 initial specific ring stiffness

S_0
value of S obtained when a circular pipe is tested in accordance with ISO 7685

Note 1 to entry: Initial specific ring stiffness is expressed in newtons per square metre (N/m^2).

3.5 mean diameter

d_m
diameter of the circle corresponding with the middle of a circular pipe wall cross section

Note 1 to entry: Mean diameter is derived using the formula with the inside diameter and wall thickness expressed in metres (m):

$$d_m = ID + e$$

where

e is the pipe's wall thickness.

3.6 wet creep factor

$\alpha_{x,\text{creep,wet}}$
ratio of the long-term specific ring stiffness, $S_{x,\text{wet}}$ to the initial specific ring stiffness, S_0 at x years

Note 1 to entry: See 4.4.6 for value of x .

Note 2 to entry: Determined using circular test-pieces under sustained diametrical loading in wet conditions when tested in accordance with ISO 10468.

Note 3 to entry: Wet creep factor is a dimensionless number given by the formula:

$$\alpha_{x,\text{creep,wet}} = \frac{S_{x,\text{wet}}}{S_0}$$

3.7 long-term specific ring stiffness

$S_{x,\text{wet}}$
determined value of specific ring stiffness S at x years for circular pipe

3.8 rerating factor

R_{RF}
multiplication factor that quantifies the relationship of a product's mechanical, physical and chemical properties under service conditions above 35 °C [*design service temperature* (3.16)] to those applicable at a standard test temperature of 23 °C