
**Routine method for analysis of high alloy
steel by X-ray fluorescence spectrometry
(XRF) by using a near-by technique**

*Méthode de routine pour l'analyse des aciers fortement alliés par
spectrométrie de fluorescence de rayons X (FRX) à l'aide d'une
méthode de correction*

Sample Document

get full document from standards.iteh.ai



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17054 was prepared by the European Committee for Standardization (CEN) (as EN 10315:2006) and was adopted by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*.

Sample Document

get full document from standards.iteh.ai

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Principle.....	5
4 Reagents.....	5
5 Apparatus	6
6 Safety precautions.....	7
7 Sampling.....	7
8 Final sample preparation	7
9 Procedure	7
10 Calibration	8
11 Standardization	9
12 Statistical Process Control (SPC) parameters.....	9
13 "Near by technique" method.....	10
14 Test report	10
Annex A (normative) Precision	12
Annex B (normative) Graphical representation of precision data.....	17
Bibliography.....	28

Foreword

This document (EN 10315:2006) has been prepared by Technical Committee ECISS/TC 20 “Methods of chemical analysis of ferrous products”, the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2006, and conflicting national standards shall be withdrawn at the latest by December 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

EN 10315:2006 (E)

1 Scope

This European Standard specifies a procedure on how to improve the performance of a routine XRF method, already in use for analysis of high alloy steels, by using a "near by technique".

The "near by technique" requires at least one target sample (preferable a CRM) of a similar composition as the unknown sample.

The method is applicable to elements within the concentration ranges according to Table 1:

Table 1 — Concentration ranges

Element	Concentration range, % (m/m) ^a
Si	0,05 to 1,5
Mn	0,05 to 5,0
P	0,005 to 0,035
Cr	10 to 25
Ni	0,1 to 30
Mo	0,1 to 6,5
Cu	0,02 to 1,5
Co	0,015 to 0,30
V	0,015 to 0,15
Ti	0,015 to 0,50
Nb	0,05 to 1,0
^a The concentration ranges specified, represents those ranges studied during the precision test. The procedure has the potential to be used outside those ranges <u>but</u> it needs to be validated by each laboratory in every case.	

The method is applicable to analysis of either chill-cast or wrought samples having a diameter of at least 25 mm and with a carbon concentration of less than 0,3 % (see NOTE). Other elements should have a concentration below 0,2 %.

NOTE High carbon concentrations, in combination with high Mo and Cr concentrations, could have undesirable structural effects on the sample and could affect the determination of phosphorus and chromium, in particular.

Matrix effects exist between the elements listed. To compensate for those inter-element effects, mathematical corrections shall be applied. A variety of computer programs for corrections is commonly used and included in the software package from the manufacturers.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 10280, *Steel and iron — Determination of titanium content — Diantipyrylmethane spectrophotometric method (ISO 10280:1991)*

EN ISO 10700, *Steel and iron — Determination of manganese content — Flame atomic spectrometric method (ISO 10700:1994)*

EN ISO 10714, *Steel and iron — Determination of phosphorus content — Phosphovanadomolybdate spectrophotometric method (ISO 10714:1992)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996)*

CR 10299, *Guidelines for the preparation of standard routine methods with wavelength-dispersive X-ray fluorescence spectrometry*

ISO 4829-1, *Steel and cast iron — Determination of total silicon content — Reduced molybdosilicate spectrophotometric method — Part 1: Silicon contents between 0,05 and 1,0 %*

ISO 4829-2, *Steel and iron — Determination of total silicon content — Reduced molybdosilicate spectrophotometric method — Part 2: Silicon contents between 0,01 and 0,05 %*

ISO 4937, *Steel and iron — Determination of chromium content — Potentiometric or visual titration method*

ISO 4938, *Steel and iron — Determination of nickel content — Gravimetric or titrimetric method*

ISO 4942, *Steel and iron — Determination of vanadium content — N-BPHA spectrophotometric method*

ISO 4946, *Steel and cast iron — Determination of copper content — 2,2'-DiquinolyI spectrophotometric method*

ISO 9441, *Steel — Determination of niobium content — PAR spectrophotometric method*

ISO 11652, *Steel and iron — Determination of cobalt content — Flame atomic absorption spectrometric method*

ISO/TS 13899-1, *Steel — Determination of Mo, Nb and W contents in alloyed steel — Inductively coupled plasma atomic emission spectrometric method — Part 1: Determination of Mo content*

3 Principle

The sample is finished to a clean uniform surface and then irradiated by an X-ray beam of high energy. The secondary X-rays produced are dispersed by means of crystals and the intensities are measured by detectors at selected characteristic wavelengths. The measuring time is set to reach below a specified counting statistical error. Preliminary concentrations of the elements are determined by relating the measured intensities of unknown samples to analytical curves prepared from reference materials, CRM or RM, of known compositions. The final concentrations are calculated by using the results obtained by measuring a CRM of the same grade. The correction is made for the elements of interest by using the difference between the certified value and the value obtained during the measurement of the CRM (the "near by technique"). A fixed channel or a sequential system may be used to provide simultaneous or sequential determinations of element concentrations.

4 Reagents

4.1 P10 gas (90 % argon mixed with 10 % methane) for the gas-flow proportional detector.

4.2 A set of Certified Reference Materials (CRM). All reference material used for calibration or calibration verification shall be certified by internationally recognized bodies (see NOTE).

EN 10315:2006 (E)

NOTE A complete set of internationally recognised CRMs to cover all elements at all concentration levels may not be available. Other CRMs could be used if the material is certified by referee procedures based on SI units.

4.3 Reference materials used for standardization or for statistical process control (SPC samples) of the method need not to be certified, but adequate homogeneity data shall be available. Select the standardization samples in such a way that they cover at least the low and top end of the concentration range for each element.

4.4 Pure ethanol.

5 Apparatus**5.1 Sample preparation equipment**

For the final preparation, use a surface grinder with 180-grit or finer **aluminium oxide** (see NOTE) belts or discs. Other preparation procedures are also possible (turning, for example). But in each case, the surfaces of CRMs, RMs and samples shall be prepared under the same conditions.

NOTE Paper made of silicon carbide will disable Si determinations and paper made of zirconium oxide will disable Zr determinations, and aluminium determinations also sometimes as zirconium oxide is often contaminated by aluminium oxide.

5.2 X-ray fluorescence spectrometer

A simultaneous or sequential wavelength dispersive spectrometer. This test method is written for use with commercially available instruments.

5.3 X-ray tube

Tube with a high-purity element target. Rhodium is recommended for analysis of steel.

5.4 Analysing crystals

To cover all elements specified in this method, flat or curved crystals made of LiF(200) and PE (for light elements, atom no. approximately < 22) are required. Crystals made of LiF(220) and Ge or other crystals optimized for individual elements may also be used.

5.5 Collimators

For sequential instruments, a two collimator system is necessary: a coarse collimator for light elements (atom no. approximately < 22) and a fine collimator for heavy elements.

5.6 Detectors

One scintillation detector for heavy elements and one gas-flow proportional detector for light elements (atom no. approximately < 22). Sealed proportional detectors may also be used. The combination of detectors and how to use them, in single or dual mode, depends on the equipment used. See the operation manual for the equipment in question.

5.7 Vacuum system

A vacuum system capable of keeping the pressure at a constant level below at least 40 Pa during the measurement.