
**Reaction to fire tests for products —
Determination of the gross heat of
combustion (calorific value)**

*Essais de réaction au feu de produits — Détermination du pouvoir
calorifique supérieur (valeur calorifique)*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 1716:2018

<https://standards.iteh.ai/catalog/standards/iso/2373a99d-a9c2-4ace-9340-43c519f1fac8/iso-1716-2018>



iTeh Standards
(<https://standards.itih.ai>)
Document Preview

ISO 1716:2018

<https://standards.itih.ai/catalog/standards/iso/2373a99d-a9c2-4ace-9340-43c519f1fac8/iso-1716-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	3
5 Test apparatus	3
6 Reagents and materials	8
7 Test specimens	8
7.1 General	8
7.2 Sampling	9
7.2.1 General	9
7.2.2 Loose-fill material	9
7.2.3 Liquid-applied products	9
7.2.4 Thin film products	9
7.3 Determination of surface density	9
7.4 Grinding	10
7.5 Type of specimen	10
7.6 Conditioning	10
7.7 Number of test specimens	10
7.8 Determination of mass	10
7.9 Crucible method	11
7.10 "Cigarette" method	11
8 Test procedure	12
8.1 General	12
8.2 Calibration procedure	12
8.2.1 Determination of the water equivalent	12
8.2.2 Conditions for recalibration	12
8.3 Standard test procedure	12
9 Expression of results	14
9.1 Corrections for manual apparatus	14
9.2 Corrections for isothermal calorimeter (see Annex C)	14
9.3 Calculation of the gross heat of combustion of the specimen	15
9.4 Calculation of the gross heat of combustion of the product	16
9.4.1 General	16
9.4.2 Homogeneous product	17
9.4.3 Non-homogeneous product	17
10 Test report	18
11 Validity of test results	18
Annex A (normative) Calculation of net heat of combustion	20
Annex B (informative) Precision of test method	21
Annex C (informative) Calculation by graph of the corrective term, c, necessary because of the cooling of the calorimeter	24
Annex D (informative) Example of determination of the gross heat of combustion of a non-homogeneous product	25
Bibliography	30

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Fire initiation and growth*.

This fourth edition cancels and replaces the third edition (ISO 1716:2010), which has been technically revised.

ISO 1716:2018

<https://standards.iteh.ai/catalog/standards/iso/2373a99d-a9c2-4ace-9340-43c519f1fac8/iso-1716-2018>

Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value)

WARNING — The attention of all persons concerned with managing and carrying out this test is drawn to the fact that fire testing may be hazardous and that there is a possibility that toxic and/or harmful gases may be evolved during the test. Operational hazards may also arise during the testing of specimens, such as the possibility of an explosion, and during the disposal of test residues.

WARNING — An assessment of all the potential hazards and risks to health should be made and safety precautions should be identified and provided. Written safety instructions should be issued. Appropriate training should be given to relevant personnel. Laboratory personnel should ensure that they follow written instructions at all times.

1 Scope

This document specifies a method for the determination of the gross heat of combustion (Q_{PCS}) of products at constant volume in a bomb calorimeter.

This method is intended to be applied to solid products.

NOTE Liquids can be tested with similar equipment and using conditions described in ASTM D2401^[1], as described in IEC 61039^[2] using ISO 1928^[3] test equipment.

[Annex A](#) specifies the calculation of the net heat of combustion, Q_{PCI} , when required.

Information on the precision of the test method is given in [Annex B](#).

2 Normative references

ISO 1716:2018

<https://standards.iteh.ai/catalog/standards/iso/2373a99d-a9c2-4ace-9340-43c519f1fac8/iso-1716-2018>

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

EN 13238, *Reaction to fire tests for building products — Conditioning procedures and general rules for selection of substrates*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

product

material, element or component about which information is required