
**Welding consumables — Tubular
cored electrodes for gas shielded
metal arc welding of creep-resisting
steels — Classification**

*Produits consommables pour le soudage — Fils-électrodes fourrés
pour le soudage à l'arc avec gaz de protection des aciers résistant au
fluage — Classification*

Sample Document

get full document from standards.iteh.ai



Sample Document

get full document from standards.iteh.ai



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Classification	2
4 Symbols and requirements	3
4.1 Symbol for the product/process.....	3
4.2 Symbol for the chemical composition of all-weld metal.....	3
4.3 Symbol for the mechanical properties of all-weld metal.....	3
4.4 Symbol for type of electrode core or the usability characteristics of the electrodes.....	10
4.5 Symbol for shielding gas.....	10
4.6 Symbol for welding position.....	11
4.7 Symbol for hydrogen content of deposited metal.....	11
5 Mechanical tests	11
5.1 Tensile and impact tests.....	11
5.2 Preheating and interpass temperatures.....	12
5.3 Pass sequence.....	12
6 Chemical analysis	12
7 Rounding procedure	12
8 Fillet weld test	13
9 Retests	14
10 Technical delivery conditions	14
11 Example of designation	14
Annex A (informative) Classification systems	17
Annex B (informative) Description of composition designations of electrode in the classification system based upon tensile strength and chemical composition	19
Annex C (informative) Description of types of electrode core in the classification system based upon chemical composition	20
Annex D (informative) Description of types of usability characteristics in the classification system based upon tensile strength and chemical composition	21
Annex E (informative) Notes on hydrogen content	22
Bibliography	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

This second edition cancels and replaces the first edition (ISO 17634:2004), which has been technically revised.

Introduction

This International Standard provides a classification system for tubular cored electrodes in terms of chemical composition of the all-weld metal, type of electrode core, type of shielding gas, and welding position or in terms of the tensile properties, chemical composition of the all-weld metal, usability characteristics of the electrodes, shielding gas, and welding position. The ratio of proof to tensile strength of weld metal is generally higher than that of parent metal. Matching weld metal proof strength to parent metal proof strength will not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Where the application requires matching tensile strength, therefore, selection of consumables is made by reference to column 4 of [Table 2](#).

Of note is that the mechanical properties of all-weld metal test specimens used to classify the tubular cored electrodes will vary from those obtained in production joints because of differences in welding procedure such as electrode size, width of weave, welding position, and parent metal composition.

The classification according to system A is mainly based on EN 12071:1999. The classification according to system B is mainly based upon standards used around the Pacific Rim.

Sample Document

get full document from standards.iteh.ai

Sample Document

get full document from standards.iteh.ai

Welding consumables — Tubular cored electrodes for gas shielded metal arc welding of creep-resisting steels — Classification

1 Scope

This International Standard specifies requirements for classification of tubular cored electrodes used in the post-weld heat-treated condition for gas shielded metal arc welding of creep-resisting and low alloy elevated temperature steels. One tubular cored electrode can be tested and classified with different shielding gases.

This International Standard is a combined specification providing for classification utilizing a system based upon the chemical composition of all-weld metal or utilizing a system based upon the tensile strength and the chemical composition of all-weld metal.

- 1) Paragraphs and tables which carry the suffix letter “A” are applicable only to tubular cored electrodes classified to the system based upon chemical composition with requirements for the yield strength and the average impact energy of 47 J of all-weld metal in accordance with this International Standard.
- 2) Paragraphs and tables which carry the suffix letter “B” are applicable only to tubular cored electrodes classified to the system based upon the tensile strength and chemical composition of all-weld metal in accordance with this International Standard.
- 3) Paragraphs and tables which have neither the suffix letter “A” nor the suffix letter “B” are applicable to all tubular cored electrodes classified in accordance with this International Standard.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current, but for the purposes of this International Standard, pulsed current is not used for determining the electrode classification.

2 Normative references

The following referenced documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6947, *Welding and allied processes — Welding positions*

ISO 14175, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000/Amd 1:2011, *Welding Consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Classification

Classification designations are based upon two approaches to indicate the chemical composition, the tensile properties, and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all as will be clear from the following sections. In most cases, a given commercial product can be classified in both systems. Then, either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a tubular cored electrode and appropriate shielding gas combination as given below. With the exception of the symbol for welding position which is based on ISO 15792-3, the classification is based on the tubular cored electrode size 1,2 mm or if this is not manufactured, the next larger diameter manufactured.

3.1A Classification by chemical composition

The classification is divided into six parts:

- 1) The first part (T) indicates a tubular cored electrode.
- 2) The second part gives a symbol indicating the chemical composition of all-weld metal (see [Table 1](#)).
- 3) The third part gives a symbol indicating the type of electrode core (see Table 3A).
- 4) The fourth part gives a symbol indicating the shielding gas (see [4.5](#)).
- 5) The fifth part gives a symbol indicating the welding position (see Table 4A).
- 6) The sixth part gives a symbol indicating the hydrogen content of deposited metal (see [Table 5](#)).

3.1B Classification by tensile strength and chemical composition

The classification is divided into seven parts:

- 1) The first part (T) indicates a tubular cored electrode.
- 2) The second part gives a symbol indicating the strength and elongation of all-weld metal in the post-weld heat-treated condition (see [Table 2](#)).
- 3) The third part gives a symbol indicating the usability characteristics of the electrode. (see [Table 3B](#));
- 4) The fourth part gives a symbol indicating the welding position (see Table 4B).
- 5) The fifth part gives a symbol indicating the shielding gas (see [4.5](#)).
- 6) The sixth part gives a symbol indicating the chemical composition of all-weld metal (see [Table 1](#));
- 7) The seventh part gives a symbol indicating the hydrogen content of deposited metal (see [Table 5](#)).

In both systems, the electrode classification shall include all compulsory sections and may include an optional section as outlined below.

3.2A Compulsory and optional section in the classification by chemical composition

a) Compulsory section

This section includes the symbols for the type of product, the chemical composition, the type of electrode core, and the shielding gas, i.e. the symbols defined in [4.1](#), [4.2](#), [4.4A](#), and [4.5](#).

b) Optional section

This section includes the symbols for the welding positions for which the electrode is suitable and the symbol for hydrogen content, i.e. the symbols defined in [4.6](#) and [4.7](#).

The full designation shall comprise the compulsory symbols and may include optional symbols chosen by the manufacturer. The full designation (see [Clause 10](#)) shall be used on packages and in the manufacturer's literature and data sheets.

3.2B Compulsory and optional section in the classification by tensile strength and chemical composition

a) Compulsory section

This section includes the symbols for the type of product, the strength, and elongation in the post-weld heat-treated condition, the welding positions for which the electrode is suitable, the usability characteristics, the shielding gas, the impact properties, and the chemical composition, i.e. the symbols defined in [4.1](#), [4.2](#), [4.3B](#), [4.4B](#), [4.5](#), and [4.6](#).

b) Optional section

This section includes the symbol for hydrogen content, i.e. the symbol defined in [4.7](#).

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol for the tubular cored electrode used in the gas shielded metal arc welding process is the letter T.

4.2 Symbol for the chemical composition of all-weld metal

The symbol in [Table 1](#) indicates the chemical composition of all-weld metal determined in accordance with [Clause 6](#).

4.3 Symbol for the mechanical properties of all-weld metal

4.3A Classification by chemical composition

No symbol shall be used for the mechanical properties of the all-weld metal. The all-weld metal obtained with the tubular cored electrodes in [Table 1](#) under conditions given in [Clause 5](#) shall also fulfil the mechanical property requirements specified in [Table 2](#).

4.3B Classification by tensile strength and chemical composition

The symbol for tensile strength shall be the following:

- 49 for 490 MPa to 660 MPa tensile strength;
- 55 for 550 MPa to 690 MPa tensile strength;
- 62 for 620 MPa to 760 MPa tensile strength;
- 69 for 690 MPa to 830 MPa tensile strength.

The complete mechanical property requirements that shall be fulfilled by the various compositions are specified in [Table 2](#).